

# A STUDY OF THE FORMATION AND SELF-LUBRICANT MECHANISMS OF BORIC ACID FILMS ON BORIC OXIDE COATINGS

A. ERDEMIR, G. R. FENSKE and R. A. ERCK

Argonne National Laboratory, Tribology Section, Materials and Components Technology Division,  
Argonne, IL 60439 (U.S.A.)

## Abstract

An investigation was made of the formation and self-lubrication mechanisms of boric acid films on boric oxide coatings prepared by vacuum evaporation. Measured friction coefficients of a steel ball sliding on a boric-oxide-coated steel disk and a sapphire ball sliding on a boric-oxide-coated alumina disk were 0.025-0.05 at steady state, depending on load and substrate material. This low friction was correlated with the formation of a lubricious boric acid film on boric oxide coatings exposed to open air. For the mechanism of self-lubrication, the layered triclinic crystal structure of boric acid was proposed. The atoms constituting each boric acid molecule are arrayed in closely packed and strongly bonded layers that are 0.318 nm apart and held together by weak forces, such as van der Waal's. It is hypothesized that, during sliding, these layers can align themselves parallel to the direction of relative motion and, once so aligned, can slide over one another with relative ease to provide low friction. Structural and chemical findings were included to substantiate the proposed solid lubrication mechanism.

## 1. Introduction

Solid lubricants continue as prominent choices for triboapplications involving high vacuum and temperatures where liquid counterparts cannot operate efficiently. Molybdenum disulfide (MoS<sub>2</sub>), because of its ultralow friction coefficient in vacuum and inert gas environments, has been of particular importance for spacecraft mechanisms [1-3]. With the use of advanced sputtering and ion beam technologies, great strides have been made in both the application and use of this lubricant where precision control of mechanical motion is of utmost concern [3,4]. Recent experimental studies indicate that sputtered and/or ion-beam-deposited MoS<sub>2</sub> coating can achieve friction coefficients as low as 0.01 and functional lifetimes of hundreds of thousands of cycles [1,4,5]. A major drawback of MoS<sub>2</sub> is its inability to provide low friction where moisture and O<sub>2</sub> are present [6,7].

In this paper we describe a new solid lubricant that can result from chemical reaction between moisture in open air and boric oxide (B<sub>2</sub>O<sub>3</sub>) coatings on steel and ceramic substrates. The lubricious film is boric acid (H<sub>3</sub>BO<sub>3</sub>). On the basis of thermodynamics data and crystal chemical knowledge, the self-formation and self-lubrication mechanisms of boric acid films are elucidated.

Both boric oxide and its hydrated form, boric acid, attracted some attention in previous years, mainly for lubrication at high temperatures. Peterson et al. observed that, at temperatures above the glass transition point of vitreous boric oxide (e.g. about 450°C), viscosity decreases sharply [8], and dramatic reductions in friction coefficients occur in tribosystems lubricated with boric oxide [8,9]. For example, Johnson and Sliney measured a friction coefficient of 0.14 at 732°C for a sliding interface using a boric oxide coating [9]. Despite these high temperature studies, it appears that neither the lubricity nor the lubrication mechanism of boric oxide and/or boric acid has been reported in the literature. This study provides tribological data that illustrate the unusual lubrication capacity of boric oxide coatings in normal air environments

and proposes a crystal chemical model that describes the lubrication mechanism of this solid. Effects of load and substrate material on friction are also explored.

## 2. Experimental Details

### 2.1 Substrate materials

Two types of materials were chosen as the substrates for boric oxide coatings; hardened AISI M50 tool steel and polycrystalline  $\alpha$ -alumina. These substrates were ideal choices for the elucidation of the effect of (1) substrate hardness on friction and (2) surface chemistry on adhesion between boric oxide coatings and substrate materials. These disk-shaped substrates were 50mm in diameter and 6mm thick, and both had surface finishes of approximately 0.05  $\mu\text{m}$  center-line average (c.l.a.). Base Vickers' hardness values were approximately 7.8 GPa for the M50 and 16 GPa for the alumina. Before deposition of boric oxide, the substrates were cleaned ultrasonically in acetone and methanol for 300 s each and then oven dried at 100°C for 10 min.

### 2.2 Deposition of boric oxide

Boric oxide was deposited on the steel and alumina disks in a high vacuum system equipped with an electron-beam-heated evaporator. The disks were attached to a sample holder above the evaporation source. They were sputter cleaned before evaporation of  $\text{B}_2\text{O}_3$  with a flux of argon ions emitted from a Kaufman-type ion gun operated at 300 V. Vacuum evaporation was carried out at room temperature and at a chamber pressure of  $5 \times 10^{-4}$  Pa. A quartz crystal rate monitor was used to control and estimate the evaporation rate. Coatings evaluated in this study were approximately 2  $\mu\text{m}$  thick. Substrate temperature remained below about 60°C during the entire course of deposition.

### 2.3 Friction Tests

Friction tests were performed with pairs of MJ50 ball- $\text{B}_2\text{O}_3$ -coated M50 disk and sapphire ball- $\text{B}_2\text{O}_3$ -coated alumina disk in a commercial pin-on disk tribometer (CSEM-Tribometer). For comparison, a few pairs were tested without the  $\text{B}_2\text{O}_3$  coatings under a load of 5 N. The M50 balls were 9.5 mm in diameter and had a surface finish of approximately 0.03  $\mu\text{m}$  c.l.a. The sapphire balls were 6.3mm in diameter and had a surface finish of about 0.005  $\mu\text{m}$  c.l.a. These balls were firmly secured to a stationary holder for the ball-on-disk configuration. Disks were attached to a horizontal chuck driven by a variable-speed electric motor. Frictional force was monitored by a linear voltage displacement transducer attached to the ball holder and was recorded continuously. All tests were performed at room temperature (about 23°C) in open air of  $60\% \pm 5\%$  relative humidity. Dead weights of 1, 5, and 10 N were used during tribotests. Tests were conducted at a constant rotational speed of 10-rev  $\text{min}^{-1}$ . The total number of revolutions was 2000. Depending on wear track diameter, sliding velocity ranged from 0.01 to 0.05  $\text{m s}^{-1}$ . The tribometer was calibrated by applying incremental forces to the pin holder in a tangential direction with the increments ranging from 0.1 to 1 N, depending on normal force.

Scanning electron microscopy (SEM) and laser Raman spectroscopy were used for morphological and structural characterization of films and of the sliding surfaces. To overcome charging of insulating coating and substrate materials, a 5mm thick gold-palladium film was sputter deposited onto the surface to be examined by SEM.

## 3. Results

The boric oxide coatings deposited on the steel and alumina disks were colorless and transparent immediately after deposition. Within a few minutes, however, the coatings became dull and took on a color similar to that of mother-of-pearl.

### 3.1 Friction Measurements

#### 3.1.1 M50-M50 pairs




Fig 1. Friction coefficients of M50-M50 pairs with and without boric oxide coatings under loads of 1, 5, and 10 N as a function of the number of revolutions.

Figure 1 shows friction coefficients of M50 test pairs, with and without boric oxide coatings, as a function of number of sliding cycles. The friction coefficient of the M50-M50 pair without a boric oxide coating is initially about 0.4, but increases with distance and stabilizes at a value of 0.77. In contrast, the initial friction coefficients of pairs with a boric oxide film are in the range 0.08-0.11, depending on load (Fig.1). With further sliding, these values decrease sharply and stabilize at 0.04-0.06. The lowest steady state friction coefficient, 0.04, was measured on pairs tested at 5 N. For the 1 N load, the initial and steady state friction coefficients were 0.11 and 0.05 respectively. With a 10 N load, the friction coefficient was initially low, e.g. 0.08. However, it decreased to about 0.036 and then began to increase sharply with further sliding (e.g. beyond 100 rev). Visual inspection of the wear track with a 5 X magnifier revealed that the boric oxide coating was removed from the surface and that wear had occurred on steel.

### 3.1.2 Sapphire – alumina pairs

Figure 2 shows friction coefficients of sapphire-alumina test pairs with and without boric oxide coatings. The friction coefficient of the sapphire-alumina pair is initially about 0.25, increases during successive revolutions and stabilizes at about 0.4. The friction coefficients of pairs with a boric oxide coating vary widely with applied load. For a load of 1 N, the initial friction coefficient is about 0.08. At steady state, the friction coefficient becomes 0.045. For a 5 N load, the friction coefficient is initially about 0.055, but decreases rapidly to about 0.027 and then remains relatively unchanged. With a load of 10 N, the initial friction coefficient is approximately 0.05, but decreases to about 0.025 at steady state.



Fig.2 Friction coefficients of sapphire-alumina test pairs with and without boric oxide coatings under loads of 1, 5, and 10 N as a function of the number of revolutions.

Under the test conditions explored in this study, it was noted that, regardless of test loads and substrate material, the records of frictional force (as recorded on chart paper) were smooth (i.e. fluctuations from the mean were in the  $\pm 1\%$  range of full scale.)

### 3.2 Structural and chemical analysis

Electron microscopy inspection of the disk surfaces revealed that shallow wear tracks had formed during sliding of balls against the boric-oxide-coated disks and that some coating material

had transferred onto the rubbing surfaces of the balls. Wear of balls that were slid against the boric oxide coatings was practically immeasurable except for those in the 10 N tests. A circular wear scar was seen on balls slid against uncoated disks.

Electron microscopy of wear tracks formed on the boric oxide coated steel and alumina disks revealed some plate-like crystallites exhibiting a preferred alignment parallel to the sliding direction (fig.3). Noticeable in the micrograph are micro features suggesting the occurrence of intercrystalline slip, possibly as a result of frictional traction. Plate-like crystallites were also seen in areas away from the rubbing surfaces (Fig.4), but these crystallites appeared to have random orientations.

Micro laser Raman spectroscopy of boric oxide coatings revealed very strong Roman lines at approximately  $499$  and  $880\text{ cm}^{-1}$ , the near-surface structure of the boric oxide coating was found to be identical to that of the boric acid standard within the range surveyed in this study (i.e.  $250\text{-}1000\text{ cm}^{-1}$ ). The values reported here are similar to those (e.g.  $500$  and  $881\text{ cm}^{-1}$ ) reported for bulk boric acid ( $\text{H}_3\text{BO}_3$ ) in ref. 10. The slight discrepancy between measurements may have been due to calibration errors in the instrument used in our study.




Fig. 3. SEM micrograph of the plate-like crystallites found on a wear track of boric-oxide-coated steel disk.





Fig. 4. SEM Micrograph of the plate-like crystallites found in areas away from wear tracks.

#### 4. Discussion

The results demonstrate that (1) in general, low friction can be achieved on surfaces coated with boric oxide and (2) friction coefficient can vary with substrate type, applied load, and sliding distance. For the low friction behavior of boric oxide coatings, we propose the following interpretation. Because of a negative standard heat of reaction, boric oxide reacts spontaneously with moisture in open air and becomes boric acid ( $\text{H}_3\text{BO}_3$ ). This reaction was given in ref. 11 as



$$\Delta H_{298} = - 45.1 \text{ kJ mol}^{-1}$$

We believe that the rapid change in the appearance of boric oxide coatings after exposure to open air was a consequence of the chemical reaction given above. The reaction film, boric acid, was largely responsible for the change from a transparent to an opaque nature in this coating. Structural data obtained through micro laser Raman spectroscopy confirmed the formation of boric acid on boric oxide coatings by revealing Raman lines that are similar to those of bulk boric acid.

What is the mechanism of the low friction character of boric acid film formed on boric oxide coatings? It is known that boric acid crystallizes in a triclinic crystal structure made up of atomic layers parallel to the basal plane [12, 13]. The atoms lying on each layer (e.g. boron, oxygen, and hydrogen) are closely packed and strongly bonded to each other. The bonds between the boron and oxygen atoms are described as mostly covalent with some ionic character, and hydrogen serves to connect the planar boron-oxygen groups to each other. The atomic layers are widely spaced and held together by weak forces, e.g. van der Waals' [13]. A depiction of the unit cell of boric acid is shown in Fig. 5, based on data given in refs. 12 and 13. With its layered crystal structure, boric acid resembles those other solids known for their good lubrication capabilities (e.g. MoS<sub>2</sub>, graphite, and hexagonal boron nitride). Therefore, we believe that the low friction measured on the boric-oxide-coated steel and alumina disks was a direct consequence of the formation of lubricious boric acid films.



Fig 5. Depiction of unit cell and cell parameters of bulk boric acid

Mechanistically, we propose that, under shear stresses, plate-like crystallites (Fig.3) (possibly consisting of several thousand atomic layers) can align themselves parallel to the direction of relative motion; once so aligned, they can slide over one another with relative ease and thus impart low friction. The relatively high friction coefficients observed at the start of the friction tests are attributed to the initially random orientation of crystalline layers (see Fig. 4). It is thought that randomly oriented crystallites shear with greater difficulty and thus give a relatively high friction coefficient. Figure 3 presents some physical evidence that plate-like crystallites were present at the sliding interfaces and that some intercrystalline slip has occurred.

As shown in Figs. 1 and 2, the measured friction coefficient varies with substrate and applied load. This variation between materials can be attributed to the fact that frictional force was lower for sapphire-alumina than for M50-M50. Frictional force, force  $F$  is essentially a product of the shear strength of a solid lubricant film multiplied by the real contact area  $A$  due to elastic and plastic deformation, i.e.  $F = s \times A$  [14]. In our friction tests, we used sapphire balls of 3.1mm radius against the boric-oxide-coated alumina disks, but M50 balls of 4.7mm radius against the boric-oxide-coated M50 disks. It is obvious that, because of the smaller ball radius and greater hardness and elastic modules, the real contact area between the sapphire ball and the boric-oxide-coated alumina disk will be smaller than that between the M50 ball and the boric-

oxide-coated M50 disk. According to the expression given above, a lower frictional force and/or lower friction. For a more thorough understanding of the phenomenon briefly describe above, readers should refer to the original developed by Bowden and Tabor [14] and to a paper by Roberts [4].

For the explanation of lower friction coefficients under heavier loads, we refer to a plastic flow model described by Kanakia and Peterson [15]. According to this model, under low pressures the real contact area  $A$  is controlled largely by film properties, whereas under high pressures it is controlled largely by mechanical properties of the substrate. Under a 1 N properties of boric acid-boric oxide composite layer. Hence, measured friction coefficients were dominated by film properties. Under a low load of 1 N, the steady state friction coefficients of the steel-steel and ceramic-ceramic test pairs using boric acid films are 0.05 and 0.045 respectively, which suggests that perhaps the plastic flow model is in effect. However, under heavier loads, of 5 and 10 N., the measured friction coefficients decrease regardless of substrate material. This trend can be ascribed to the greater effect of substrate properties on the extent of contact areas established between balls and coated disks. The somewhat lower friction coefficients measured on ceramic-ceramic pairs may have been due in part to the smaller radius of the sapphire balls used in these tests. However, contributions due to the higher hardness and elastic modulus of the ceramic-ceramic test pairs are also thought to have substantial effects on the friction levels measured for these pairs. Using a dual fast atom beam technique, Kuwano and Nagai recently produced thin  $\text{MoS}_2$  coatings on surfaces with different hardness values [5]. They noted that friction coefficients measured on hard surfaces were significantly lower than those measured on softer surfaces.

As for the short lifetime of boric oxide coatings on M50 but long lifetime on alumina substrates during sliding under a 10 N load, we believe that chemical compatibility was the dominant factor. Low adhesion is generally observed on coatings deposited by vacuum evaporation processes. However, such an argument cannot be made for this study, because we prepared all the boric oxide coatings under the same conditions. Both substrates were sputter cleaned prior to the deposition of  $\text{B}_2\text{O}_3$ . We believe that another influence, the chemical compatibility, was more prevalent in our study. Boric oxide, which is an oxide ceramic, may have had poor chemical compatibility with the metallic M50 steel but good compatibility with the alumina, which is also an oxide ceramic.

## 5. Conclusions

Under the test conditions of this study, low friction can be achieved on metallic and ceramic surfaces through the use of boric oxide coatings. Low friction is a direct consequence of the spontaneous formation of a boric acid film on boric oxide coatings exposed to open air.

Friction coefficient decreases with increasing load and distance, and varies with substrate type.

Mechanistically, it is proposed that the low friction of boric acid is due to its layered triclinic crystal structure and unique bond characteristics. Under shear stresses, the layers can align themselves parallel to the direction of sliding motion; once so aligned, they can slide one over another, thus providing low friction.

Electron microscopy studies revealed plate-like crystallites with alignment parallel to the sliding surface; some micro features suggest that intercrystalline slip had occurred between the plate-like crystallites while sliding.

Unlike  $\text{MoS}_2$ , which provides low friction in non-humid environments, boric acid is formed in a humid environment and, as demonstrated in this study, can provide low friction in such environments.

## Acknowledgements

The authors thank C.A. Melendres of Argonne National Laboratory for performing the laser Raman spectroscopy. This work was supported by the Tribology Program, U.S. Department of Energy, Energy Conversion and Utilization Technologies Division, under Contract W-31-109-E-38.

## References

- 1 E.W. Roberts and W. B. Price, Proc. Mater. Res. Soc., 140 (1989) 251.
- 2 P.D. Fleischauer and R. Hilton, Proc. Mater. Res. Soc., 140 (1989) 9.
- 3 I.L. Singer, Proc. Mater. Res. Soc., 140 (1989) 215.
- 4 E.W. Roberts, Thin Solid Films, 181 (1990) 461.
- 5 H. Kuwano and K. Nagai, J. Vac. Sci. Technol. A, 4 (1986) 2993.
- 6 F. Pritchard and J. W. Midgley, Wear, 13 (1969) 39.
- 7 W. O. Winer, Wear, 10 (1967) 422.
- 8 M.B. Peterson, S.L. Murray and J.J. Florek, ASLE Trans., 2 (1960) 225.
- 9 R.L. Johnson and H.B. Sliney, Ceram. Bull., 41 (1962) 508.
- 10 R. Janda and G. Heller, Spectrochim. Acta A, 36 (1981) 997.
- 11 E.R. Van Artsdalen and K.P. Anderson, J. Am. Chem. Soc., 73 (1951) 579.
- 12 W. H. Zachariasen, Acta Crystallogr., 7 (1954) 305.
- 13 M. Gajhede, S. Larsen and S. Rettrup, Acta Crystallogr. B, 42 (1986) 545.
- 14 F.P. Bowden and D. Tabor, The Friction and Lubrication of Solids, Oxford University Press, Oxford, 1964.
- 15 M.D. Kanakia and M.B. Peterson, Literature Review of Solid Lubrication Mechanisms, AD A185010, Defense Technical Information Center, Alexandria, VA 1986.