

## **Advances in understanding the structure of borosilicate glasses: A Raman spectroscopy study**

**D. MANARA,<sup>1,\*</sup> A. GRANDJEAN,<sup>1,†</sup> AND D.R. NEUVILLE<sup>2</sup>**

<sup>1</sup>CEA, DEN, DTCD, Service de Confinement des Déchets et Vitriification, 30207 Bagnols Sur Cèze, France

<sup>2</sup>Physique des Minéraux et Magmas, CNRS, Institut de Physique du Globe de Paris, 4, place Jussieu, 75252 Paris Cedex 05, France

### **ABSTRACT**

This study is focused on the behavior of ternary  $\text{SiO}_2\text{-Na}_2\text{O-B}_2\text{O}_3$  borosilicate glasses at temperatures between 298 and 1800 K. Unpolarized Raman spectra were measured up to high temperature.  $\text{SiO}_2\text{-Na}_2\text{O-B}_2\text{O}_3$  glass samples were prepared with different values of the ratio  $R = [\text{Na}_2\text{O}]/[\text{B}_2\text{O}_3]$ , while the ratio  $K = [\text{SiO}_2]/[\text{B}_2\text{O}_3]$  was kept constant and equal to 2.12. Spectra were measured at room temperature in samples with  $0.43 \leq R \leq 1.68$ , and the effect of the modifier content was clearly observed in these glasses, only in partial agreement with previous literature results. In particular, the formation in the glass of sodium-danburite units  $\text{Na}_2\text{O} \cdot \text{B}_2\text{O}_3 \cdot 2\text{SiO}_2$  was postulated. This feature led to a new assessment of  $R^*$ , the critical value of  $R$  above which every new alkali atom added to the system breaks a Fo-O-Fo (Fo = glass former) bridge causing depolymerization of the glass. A revised formula is proposed to obtain the value of  $R^*$  as a function of  $K$ .

Raman spectra measured at high temperature yielded important information about the temperature-dependent evolution of the borosilicate system. In particular, borate and borosilicate units including tetra-coordinated boron seem to be unstable at high temperature, where the formation of metaborate chains or rings is fostered. Above 1500 °C, evaporation of borate compounds is clearly observed, stemming from the small sample size.

**Keywords:** Glass, borosilicate, structure, Raman spectroscopy