

AD-A113 689

UNIVERSAL ENERGY SYSTEMS INC DAYTON OH  
AN OPTIMAL DESIGN OF SIMPLE SYMMETRIC LAMINATES UNDER THE FIRST--ETC(U)  
MAR 82 W J PARK

F/8 11/7

F33615-79-C-5129

UNCLASSIFIED

AFWAL-TR-81-4175

NL

for 1  
2000

END

DATA

FILED

DTIC

AFWAL-TR-81-4175



**AN OPTIMAL DESIGN OF SIMPLE SYMMETRIC  
LAMINATES UNDER THE FIRST PLY FAILURE  
CRITERIA**

**WON J. PARK  
UNIVERSAL ENERGY SYSTEMS, INC.  
DAYTON, OHIO 45432**

**MARCH 1982**

**FINAL REPORT FOR PERIOD OCTOBER 1980-DECEMBER 1981**

**APPROVED FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED**

**MATERIALS LABORATORY  
AIR FORCE WRIGHT AERONAUTICAL LABORATORIES  
AIR FORCE SYSTEMS COMMAND  
WRIGHT-PATTERSON AIR FORCE BASE, OHIO 45433**

**DTIC  
ELECTE  
APR 20 1982  
S H D**

**82 04 20 006**

**AD A113689**

**DTIC FILE COPY**

NOTICE

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

This report has been reviewed by the Office of Public Affairs (ASD/PA) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nations.

This technical report has been reviewed and is approved for publication.

  
\_\_\_\_\_  
STEPHEN W. TSAI, Chief  
Mechanics and Surface Interactions Branch

FOR THE COMMANDER

  
\_\_\_\_\_  
F. D. CHERRY, Chief  
Nonmetallic Materials Division

"If your address has changed, if you wish to be removed from our mailing list, or if the addressee is no longer employed by your organization please notify AFWAL/MLBM, W-PAFB, Ohio 45433 to help us maintain a current mailing list.

Copies of this report should not be returned unless return is required by security considerations, contractual obligations, or notice on a specific document.

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AFWAL-TR-81-4175	2. GOVT ACCESSION NO. DA 2113 689	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) AN OPTIMAL DESIGN OF SIMPLE SYMMETRIC LAMINATES UNDER THE FIRST PLY FAILURE CRITERIA		5. TYPE OF REPORT & PERIOD COVERED October 1980-December 1981
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Won J. Park		8. CONTRACT OR GRANT NUMBER(s) F33615-79-C-5129
9. PERFORMING ORGANIZATION NAME AND ADDRESS Universal Energy Systems, Inc. Dayton, Ohio 45432		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 78011F/MTP 1/05/28
11. CONTROLLING OFFICE NAME AND ADDRESS Materials Laboratory (AFWAL/MLBM) Air Force Wright Aeronautical Laboratories (AFSC)		12. REPORT DATE March 1982
		13. NUMBER OF PAGES 42
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) First Ply Failure Design Variable Ply Orientation Angle		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Optimal design of various types of symmetric laminates for T300/5208 graphite epoxy composites was investigated under the first ply failure criteria. The symmetric laminates considered include continuous laminate and angle ply laminate. The optimal design angles $\theta$ were obtained and presented in graphic form as functions of the loading conditions ( $N_1$ , $N_2$ , $N_6$ ). The results presented here are directly useful for designers for making a choice of composites for optimal performance.		

DTIC  
ELECTED  
APR 20 1982  
S H D

Unclassified

## FOREWORD

This report was prepared in the Mechanics and Surface Interactions Branch (AFWAL/MLBM), Nonmetallic Material Division, Materials Laboratory, Air Force Wright Aeronautical Laboratories, Wright-Patterson AFB, Ohio. The work performed under Contract F33615-79-C-5129, Project UES 718.

The work reported herein was performed during the period October 1980 to September 1981. Dr. Won J. Park is a Senior Scientist from Universal Energy Systems, Inc. and Professor of Mathematics and Statistics at Wright State University.

The author wishes to express his sincere gratitude to Dr. Stephen W. Tsai for his encouragement and guidance in the course of this work.



Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A	

## TABLE OF CONTENTS

Section		Page
I.	INTRODUCTION.....	1
II.	INPLANE STIFFNESS.....	3
III.	CONTINUOUS LAMINATE.....	6
IV.	DESIGN OF LAMINATES.....	7
V.	CONCLUSION.....	9
	REFERENCES.....	10

## LIST OF ILLUSTRATIONS

Figure		Page
1	Continuous Laminate.....	11
2	Laminates A-F.....	12
3-8	Modulus of Laminates A-F.....	13
9-14	Compliance of Laminates A-F.....	19
15-17	Engineering Constants for Laminates A-F.....	25
18-29	Design Angle for Laminates A-F.....	28
30-31	Comparison of Q Values.....	40

## LIST OF TABLES

Table		Page
1	Modulus Components, $A_{ij}$ .....	4
2	Computation of $V^*$ .....	8

## SECTION 1

### INTRODUCTION

One of the fundamental and frequently recurring optimization problems in fiber composite structure is the design of laminates subject to various inplane loading conditions, considering strength and stiffness. It is well understood that, in laminate designs, the most important design variables are ply orientation angle, ply thickness and volume fraction of fibers.

Kicher and Chao [1] has considered an optimal laminate design problem, in which the ply thickness of preassign ply angle was considered as the only design variable under the minimum weight optimization criteria. Under this criteria the volume fraction of fiber is indirectly related to the ply thickness, but ply orientation angle is completely independent in the design and causes a serious difficulty in laminate optimization design.

A new approach in the design of laminates was proposed in this report, which utilizes a first ply failure (FPF) criteria as the objective function in the design. Under the FPF criteria, the ply orientation angle is a very sensitive design variable and the optimal laminate designed has the most strength in the sense of first ply failure criteria.

The design of various simple symmetric laminates (see Figure 2 for the descriptions of laminates A-F) of the composite material T300/5208 was carried out under the FPF criteria. The fraction of fiber content is constant and each ply has equal thickness throughout the laminate.



The design angles  $\phi$  of the laminate A-F are obtained under various loading conditions ( $N_1$ ,  $N_2$ ,  $N_6$ ) and are presented in Figures 18-29. In addition, the modulus, compliance and engineering constants of the laminate A-F are tabulated in terms of the ply design angle  $\phi$  and are presented in Figures 3-17.

It is interesting to compare the optimal design angle  $\phi$  with the corresponding modulus, compliance and engineering constants for these laminates. It is also noted that the FPF optimal criteria can be applied to the design of more general laminates but this requires very sophisticated computer optimization techniques.

SECTION II  
INPLANE STIFFNESS

The composite laminates, having a symmetry of stacking sequence about the midplane surface, behave as a homogeneous anisotropic plate. The effective modulus of the composite laminates is simply the arithmetic average of the modulus of the constituent plies. The main stress strain relations for a composite laminate are, for modulus

$$\begin{aligned} N_1 &= A_{11} \epsilon_1 + A_{12} \epsilon_2 + A_{16} \epsilon_6 \\ N_2 &= A_{21} \epsilon_1 + A_{22} \epsilon_2 + A_{26} \epsilon_6 \\ N_6 &= A_{61} \epsilon_1 + A_{62} \epsilon_2 + A_{66} \epsilon_6 \end{aligned} \quad (1)$$

and for compliance

$$\begin{aligned} \epsilon_1 &= a_{11} N_1 + a_{12} N_2 + a_{16} N_6 \\ \epsilon_2 &= a_{21} N_1 + a_{22} N_2 + a_{26} N_6 \\ \epsilon_6 &= a_{61} N_1 + a_{62} N_2 + a_{66} N_6 \end{aligned} \quad (2)$$

where  $N_1$ ,  $N_2$  and  $N_6$  are stress resultants over the thickness  $h$  of the laminate and are defined by

$$N_i = \int_{-h/2}^{h/2} \sigma_i dz, \quad (i = 1, 2, 6) \quad (3)$$

and  $\epsilon_i$  ( $i=1, 2, 6$ ) are inplane strain components, constant through the thickness. The modulus components  $A_{ij}$  are given in the following table:

Table 1 Modulus Components,  $A_{ij}$

	1	$U_2$	$U_3$
$A_{11}/h$	$U_1$	$V_1^*$	$V_2^*$
$A_{22}/h$	$U_1$	$-V_1^*$	$V_2^*$
$A_{12}/h$	$U_4$		$-V_2^*$
$A_{66}/h$	$U_5$		$-V_2^*$
$A_{16}/h$		$\frac{1}{2}V_3^*$	$V_4^*$
$A_{26}/h$		$\frac{1}{2}V_3^*$	$-V_4^*$

In which  $U_i$  ( $i=1, 2, \dots, 5$ ) are invariances given in Equation (3.15) of Tsai and Hahn [2] and

$$V_{(1,2,3,4)}^* = \frac{1}{h} \int_{-h/2}^{h/2} (\cos 2\theta, \cos 4\theta, \sin 2\theta, \sin 4\theta) dz \quad (4)$$

The engineering constants for the laminate are defined as follows:

$$\begin{aligned} E_1^0 &= 1/ha_{11} \\ E_6^0 &= 1/ha_{66} \\ \nu_{21}^0 &= -a_{21}/a_{11} \end{aligned} \quad (5)$$

The equation of approximate first ply failure surface (strain envelop) is given by

$$\epsilon_1^2 + \epsilon_2^2 + \frac{1}{2}\epsilon_6^2 = 2b^2$$

(see Equation (7.102) of Tsai and Hahn [2]). Let us set

$$Q = \epsilon_1^2 + \epsilon_2^2 + \frac{1}{2}\epsilon_6^2, \quad (6)$$

then FPF optimal criteria is to minimize the value of  $Q$ . The objective function  $Q$  has another meaning, mainly the value  $\sqrt{Q}$  is the norm or length of the strain vector  $(\epsilon_1, \epsilon_2, \epsilon_6 / \sqrt{2})$ . Hence, the FPF criteria minimizing the value of  $Q$  is the equivalent to minimizing the norm of strain vector  $(\epsilon_1, \epsilon_2, \epsilon_6 / \sqrt{2})$ . The laminates that we have considered to design in this report are so simple that  $Q$  is a function of the design angle  $\phi$  only for given loading conditions  $(N_1, N_2, N_6)$ .

### SECTION III

#### CONTINUOUS LAMINATE

It is interesting to consider a symmetric laminate whose ply orientation angle increases uniformly. We call this laminate a continuous laminate. If the ply orientation angle sweeps between  $-\phi$  and  $\phi$ , then  $\phi$  is called the sweeping angle of a continuous laminate. The relation between laminate depth  $Z$  and ply angle  $\theta$  is given by (See Figure 1),

$$Z = \left(\frac{h}{4}\right) \left[ \left(\frac{\theta}{\phi}\right) + 1 \right], \quad -\phi \leq \theta \leq \phi \quad (7)$$

Note that a continuous laminate with one complete revolution of plies has the sweeping angle  $\phi = 90^\circ$ . The modulus and compliance of the continuous laminate for  $0^\circ \leq \phi \leq 90^\circ$  are given in Figure 8 and 14.

In FPF optimal design of the continuous laminate, the sweeping angle  $\phi$  is the only design variable for given loading conditions  $(N_1, N_2, N_6)$ .

SECTION IV  
DESIGN OF LAMINATES

In addition to the continuous laminate, various laminates such as angle ply laminate and angle ply laminate with additional plies of 0, 90, -45 or 45 degree orientations were considered for FPF optimal design. For simplicity, these laminates are named Laminate A, B, ..., F, which are specified in Figure 2. The composite material that is used is T300/5208 and its invariants values (in GPa) are;

$$\begin{aligned} U_1 &= 76.37 & U_2 &= 85.73 & U_3 &= 19.71 \\ U_4 &= 22.61 & U_5 &= 26.88 \end{aligned}$$

Table 2 gives the expression of  $V_i^*$  ( $i=1, 2, 3, 4$ ), where  $V_i^* = V_i/h$ , for the Laminate A-F in terms of design angle  $\phi$ .

It is clearly seen from Equation (1), (2) and (6) and Tables 1 and 2 that  $Q = \epsilon_1^2 + \epsilon_2^2 + \frac{1}{2}\epsilon_6^2$  is a function of  $\phi$  and  $(N_1, N_2, N_6)$ , and hence  $Q$  depends only on  $\phi$  if  $(N_1, N_2, N_6)$  are known values. Therefore under a given stress loading  $(N_1, N_2, N_6)$  the optimization problem is to find the value  $\phi^*$  so that  $Q = Q(\phi^*)$  is the minimum among all values of  $Q = Q(\phi)$  for  $0 \leq \phi \leq 90^\circ$ .

The stresses  $N_1, N_2, N_6$  are normalized by the largest value so that  $0 \leq N_i \leq 1$ ,  $i = 1, 2, 6$ . Accordingly, the laminate thickness  $h$  is set to be 1. The results of optimal design angle  $\phi$  for laminates A-F were presented in Figures 18-29. The cases that  $N_1 = 1$  and  $N_6 = 1$  are considered for each laminate. The case that  $N_2 = 1$  is identical with that of  $N_1 = 1$  if the laminate is rotated by 90 degrees.

Table 2 Computation of  $V^*$

Laminate	Ply Orientation Angle	$V_1^*$	$V_2^*$
A	$-\phi, \phi$	$\cos(2\phi)$	$\cos(4\phi)$
B	$-\phi, 0, \phi$	$\frac{1}{3} [2\cos(2\phi)+1]$	$\frac{1}{3} [2\cos(4\phi)+1]$
C	$-\phi, 90, \phi$	$\frac{1}{3} [2\cos(2\phi)-1]$	$\frac{1}{3} [2\cos(4\phi)+1]$
D	$-\phi, 0, 90, \phi$	$\frac{1}{2} \cos(2\phi)$	$\frac{1}{2} [\cos(4\phi)+1]$
E	$-\phi, -45, 45, \phi$	$\frac{1}{2} \cos(2\phi)$	$\frac{1}{2} [\cos(4\phi)-1]$
F	Continuous Laminate	$\frac{1}{2\phi} \sin(2\phi)$	$\frac{1}{4\phi} \sin(4\phi)$
$V_3^* = 0, V_4^* = 0$			

The comparison of Q values among the laminates A-F is given in Figure 30 and 31. The smaller the Q value the stronger the laminate in FPF criteria. When we apply our results of design angle  $\phi$  in actual laminate design, the thickness of laminate h should be adjusted to meet the original values of stress conditions ( $N_1, N_2, N_6$ ). The computations were carried out by the computer CDC 660 at Wright-Patterson Air Force Base.

## SECTION V

### CONCLUSIONS

The first ply failure criteria is proposed in the composite laminate design. It is found that design angle  $\phi$  is very sensitive under this criteria and the results of design angle  $\phi$  can be directly useful to laminate designers. Among the laminate A-F, laminate F performs overall the best in FPF criteria, and then followed by laminate B under maximum longitudinal stress and laminate E under maximum shear stress.



## REFERENCES

1. T. P. Kicher and T. L. Chao, "Minimum Weight Design of Stiffened Fiber Composite Cylinders," *Journal of Aircraft*, Vol. 8, No. 7, July 1971, pp. 562-568.
2. S. W. Tsai and H. T. Hahn, Introduction to Composite Materials, Technomic Publishing Co., Westport, CT 06880, July 1980.






FIGURE I CONTINUOUS LAMINATE


1. LAMINATE A:  $\{-\phi, \phi\}$




2. LAMINATE B:  $\{-\phi, 0, \phi\}$




3. LAMINATE C:  $\{-\phi, 90, \phi\}$



4. LAMINATE D:  $\{-\phi, 0, 90, \phi\}$



5. LAMINATE E:  $\{-\phi, -45, 45, \phi\}$



6. LAMINATE: F CONTINUOUS LAMINATE




FIGURE 2. LAMINATES A - F




FIGURE 3 MODULUS OF LAMINATE A




FIGURE 4 MODULUS OF LAMINATE B




FIGURE 5 MODULUS OF LAMINATE C




FIGURE 6 MODULUS OF LAMINATE D




FIGURE 7 MODULUS OF LAMINATE E






FIGURE 8 MODULUS OF LAMINATE F




FIGURE 9 COMPLIANCE OF LAMINATE A




FIGURE 10 COMPLIANCE OF LAMINATE B




FIGURE II COMPLIANCE OF LAMINATE C




FIGURE 12 COMPLIANCE OF LAMINATE D




FIGURE 13 COMPLIANCE OF LAMINATE E




FIGURE 14 COMPLIANCE OF LAMINATE F




FIGURE 15 ENGINEERING CONSTANT  $E_1^0$






FIGURE 16 ENGINEERING CONSTANT  $E_6^0$




FIGURE 17 ENGINEERING CONSTANT  $V_{21}^0$




FIGURE 18 LAMINATE A :  $\{-\phi, \phi\}$




FIGURE 19 LAMINATE A :  $\{-\phi, \phi\}$




FIGURE 20 LAMINATE B : [0, - $\phi$ ,  $\phi$ ]




FIGURE 21 LAMINATE B:  $\{0, -\phi, \phi\}$




FIGURE 22 LAMINATE C:  $\{90, -\phi, \phi\}$




FIGURE 23 LAMINATE C:  $\{90-\phi, \phi\}$






FIGURE 24 LAMINATE D :  $\{0,90,-\phi,\phi\}$




FIGURE 25 LAMINATE : D {0,90,- $\phi$ , $\phi$ }




FIGURE 26 LAMINATE E :  $\{-45, 45, -\phi, \phi\}$




FIGURE 27 LAMINATE E :  $\{-45, 45, -\phi, \phi\}$




FIGURE 28 LAMINATE: CONTINUOUS LAMINATE




FIGURE 29 LAMINATE : CONTINUOUS LAMINATE




FIGURE 30 COMPARISON OF Q VALUES




FIGURE 31 COMPARISON OF Q VALUES



FILMED

5-8