



## **Critical Reviews on Engineered Nanoparticles in Environmental Remediation**

**Brij Bhushan Tewari<sup>1\*</sup>**

<sup>1</sup>*Department of Chemistry, Faculty of Natural Sciences, University of Guyana, P.O.Box 101110, Georgetown, Guyana.*

### **Author's contribution**

*The sole author designed, analysed, interpreted and prepared the manuscript.*

### **Article Information**

DOI: 10.9734/CJAST/2019/v36i430242

#### Editor(s):

(1) Dr. Aydin Unay, Professor, Department of Field Crops, Faculty of Agriculture, University of Aydin Adnan Menderes, Turkey.

#### Reviewers:

(1) Subramaniam Jahanadan, Malaysia.

(2) Yongchun Zhu, Shenyang Normal University, China.

(3) V. Madhavi, BVRIT Hyderabad College of Engineering for Women, India.

Complete Peer review History: <http://www.sdiarticle3.com/review-history/49902>

**Review Article**

**Received 01 May 2019**

**Accepted 07 July 2019**

**Published 17 July 2019**

### **ABSTRACT**

Environmental contamination is one of the important issues that the world is facing today, it is always expanding and leading to the grave and harmful effect on the Earth. Nanoparticles have a diameter less than 100 nm exhibit new size-dependent properties compared with the bulk material. Engineered nanoparticles (ENPs) have unique characteristics in addition to the high surface area-to-volume ratio, which may increase their toxicity relative to bulk materials. Due to the high volume production of ENPs products such as carbon nanotubes, titanium dioxide, silver, zinc oxide environmental exposure to these compounds is very common. ENPs have their unique properties and applications in the areas of medicine, food& drink, construction, automotive, textiles, energy, electronics, environment etc. The present critical review is focused on the recent development of the applications of ENPs in the environmental remediation and their toxic effects.

**Keywords:** *Nanotechnology; engineered nanoparticles; environmental remedy; carbonaceous materials; metal oxides; zerovalent metals; polymers; semiconductor devices.*

\*Corresponding author: E-mail: [brijtew@yahoo.com](mailto:brijtew@yahoo.com);

## 1. INTRODUCTION

### 1.1 Definition

According to the International Organization for Standardization (ISO-2010) [1] nanoparticles processes at least one dimension of 1 – 100 nm. Particles have a diameter less than 100 nm exhibit new size-dependent properties compared with the bulk material. These are several engineered nanomaterials such as carbon nanotubes, nanocomposites, quantum dots, fullerenes, quantum wire and nanofibers [2]. Nanomaterials are purposely manufactured by humans to achieve the specific characteristics of materials at the nanometric scale. Natural nanoparticles are erosion dust or volcanic eruption dust or marine spray. Other nanoparticles produced unintentionally during burning wood or burning diesel engines [3]. Nanotechnology is the creation of materials, devices and systems by controlling matter at the nanometer scale (1 – 100 billionths of a meter).

### 1.2 Classification

Nanoparticles are mainly classified into four types [4].


- (i) Zero-dimensional (0D) nanostructure: All of the three dimensions are in the nanometric range, e.g. well-separated nanopowders.
- (ii) One dimensional (1D) nanostructure: Two dimensions are in the nanometric range and the third dimension remains large, e.g. nanotubes, nanorods etc.
- (iii) Two – dimensional (2D) nanostructure: Only one dimension is in the nanometric range while the other two dimensions remain large, e.g. nano thin films, nanorods etc.
- (iv) Three – dimensional (3D) nanostructure: All three dimensions are outside the nanometric size range. It may consist of a group of nanowires, nanotubes, or a different distribution of nanoparticles.

Nanoparticles have novel characteristics due to their high surface/volume ratio which make them more reactive than bulk forms of the same materials [5]. Living organism required trace amounts of some heavy materials including Co, Cu, Fe, Mn, Mo, Sr and Zn these are essential metals but their excessive levels can be toxic to the organism. Heavy metals including Hg, Cr, Cd, As, Pb, Sr are non-essential metals and

considered to be a great threat for aquatic life. The iron oxide nanomaterials have potential nonabsorbent properties in the extraction of these heavy metals from groundwater [6].


Fujishima and Konda [7] demonstrated the potential of TiO<sub>2</sub> semiconductor material to split water into oxygen and hydrogen in the photoelectrochemical cell. Photocatalysis is widely used to describe the process in which the acceleration of a reaction occurs when a material (e.g. semiconductors) interact with light of sufficient energy to produce reactive oxidizing species which can lead to the photocatalytic transformation of a pollutant. During the course of the photocatalytic reaction, a minimum of two events should occur simultaneously in order for the production of reactive oxidizing species. The first involves the oxidation of dissociatively adsorbed H<sub>2</sub>O by photogenerated holes. The second involves the reduction of an electron acceptor by photoexcited electrons. These two reactions lead to the production of a hydroxyl and superoxide radical anions, respectively.

The TiO<sub>2</sub> band gap is 3.2 eV, therefore UV light ( $\lambda \leq 387$  nm) is required. The absorption of photon excites an electron to the conduction band ( $e^-_{CB}$ ) generate a positive hole in the valence band ( $h^+_{VB}$ ) (Eq. 1).



The charge carriers can be trapped as Ti<sup>3+</sup> and O<sup>-</sup> defect sites in the TiO<sub>2</sub> lattice, or they can recombine, dissipating energy [7]. Alternatively, the charge carrier can migrate to the catalyst surface and initiate redox reactions with adsorbates [8]. Positive holes can oxidize OH<sup>-</sup> or water at the surface to produce \*OH radicals (eq. 2), which, are extremely powerful oxidants. The hydroxyl radicals can subsequently oxidize organic pollutants with mineralization producing mineral salts, CO<sub>2</sub> and H<sub>2</sub>O (eq. 5) [9]. Electrons in conduction band can be rapidly trapped by molecular oxygen adsorbed on the titania particles, which is reduced to form superoxide radical anion (O<sub>2</sub><sup>-</sup>) (eq. 4) that may further react with H<sup>+</sup> to generate hydroperoxyl (OOH) (eq. 6) and further electrochemical reduction yields H<sub>2</sub>O<sub>2</sub> (eq. 7) [10,11]. These reactive oxygen species may also contribute to the oxidative pathways such as the degradation of pollutant [eqs. 8 and 9] [7,9,10]. The photocatalytic reactions mentioned above expressed as equations.





### 1.3 Applications

Nanotechnology is fueling a revolution in manufacturing and production, creating new materials used in a variety of different fields, such as cosmetic, pharmaceutical, energy, catalytic material and environmental applications [12–14]. Nanotechnology areas of applications are summarized in Table 1.

The nanotechnological applications in different environmental areas reported by Mansoori et al. [15] are given in Table 2.

The application of engineered nanoparticles (ENPs) reported by several researchers [16–21] is given in Table 3.

Use of graphene for the treatment of greenhouse gases ( $\text{CO}_2$ ,  $\text{NH}_3$ ,  $\text{SO}_2$ ,  $\text{H}_2\text{S}$  and  $\text{N}_2$ ) described by several researchers [22–24]. The application of fullerene B40 and fullerene-like boron nitride nanocage for the treatment of greenhouse gases  $\text{CO}_2$  and  $\text{N}_2\text{O}$  are also reported by workers [25, 26]. The impacts of nanomaterials, carbon nanotubes [27–32], silver nanoparticles [33–35], ZnO and  $\text{TiO}_2$  nanoparticles [36,37] and cerium oxide on human health described by several researchers [38,39]. Nanoparticles also have several applications in drug delivery [40], imaging [41], sensor [42], blood purification [43,44] and tissue engineering [45–47].

**Table 1. Nanotechnology areas of application**

S. no.	Areas	Applications
1	Automotive	Lightweight construction; catalysts; painting; tires; sensors; windshield and body coating
2	Construction	Materials; insulation; flame retardants; surface coatings; mortar
3	Electronics	Display; data memory; laser diodes; fibre optics; optical switches; filters; conductive coatings; antistatic coatings; transistors
4	Engineering	Protective coatings for wood; machines; lubricant-free bearings
5	Food and drink	Packaging; storage life sensors; additives; Juice clarifiers
6	Medicine	Drug delivery system; contrast medium; rapid testing systems; prostheses and implants; antimicrobial agents; in body diagnostic systems
7	Textiles	Surface coatings; “smart” clothes (anti-wrinkle, stain resistant, temperature controlled).
8	Chemical	Filter for paint; composite material; impregnation of papers; adhesives; magnetic fluids.
9	Cosmetics	Sunscreen; lipsticks; skin creams; toothpaste.
10	Energy	Lighting; fuel cells; solar cells; batteries; capacitors.
11	Environmental	Environmental monitoring; soil and groundwater remediation; toxic exposure sensors; fuel changing catalysts; green chemistry.
12	Household	Ceramic coatings for irons; odour removers; cleaner for glass; ceramics; metals.
13	Sports	Ski wax; tennis rackets; golf clubs; tennis balls; antifouling coatings for boats;
14	Military	Neutralization material for chemical weapons; bullet-proof protection.

**Table 2. Nanotechnological applications in different environmental areas**

<b>Type of nanoparticles; Type of treatment; Removal target</b>	<b>Advantage</b>	<b>Disadvantage</b>
Nanoparticles based TiO <sub>2</sub> ; photocatalyst oxidation; organic pollutant	Non-toxicity, water insolubility under most conditions, photostability	High operation cost, hard to recovery, sludge generation
Nanoparticles based iron; Reduction adsorption; heavy metals, anions; organic pollutant (dechlorination)	In situ remediation, soil and water treatment, low cost, safe to handle	Hard to recovery, sludge generation, the cost for sludge disposal, health risk
Nanoparticles based Bimetallic; reduction adsorption; dechlorination, denitrification	Higher reactivity than the iron nanoparticle	Hard to recovery, sludge generation
Nanoclay; Adsorption; heavy metals, anions, organic pollutant	Low cost, Unique structures, Long-term stability, reuse, High sorption capacity, Easy recovery, large surface and pore volume	Sludge generation
Nanotube & fullerene; adsorption; heavy metals, anions, organic pollutant	Treatment of pollution from air and water, exceptional mechanical properties, unique electrical properties, Highly chemical stability	High capital cost, low adsorption capacity, hard to recovery, sludge generation, health risk
Dendrimers; encapsulation; heavy metals, anions, organic pollutant	Simple separation, renewable, large binding capacity, cost-effective, no sludge generation, reduce pollutant to the level of a few ppb, treatment of pollution from soil and water	Costly
Micelles; adsorption; organic pollutant from soil	In situ treatment, high affinity for hydrophobic organic pollutant	Costly
Metal-sorbing vesicles; adsorption; heavy metals	Re-use, high selective uptake profile, high metal affinity	
Magnetite & nanoparticles; adsorption; heavy metals, Organic pollutant	Simple separation, no sludge generation	External magnetically field are required for separation, Costly
Nanofiltration & nanosieve membranes; nanofiltration; the organic and inorganic compound	Low pressure than reverse osmosis (RO)	Costly, prone to membrane fouling

## 2. CRITICAL REVIEWS

Umar et al. [48] have investigated that the simply synthesized  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> nanoparticles can effectively be used as an efficient photocatalyst for the photocatalytic degradation of organic dyes and effective electron mediators for the fabrication of highly sensitive chemical sensors in

the aqueous medium. A review summarizes the use of nanomaterials such as zero-valent iron (nZVI) and carbon nanotubes (CNT) in environment cleanup like groundwater remediation for drinking and reuse, reported by Rajan [49]. Mansouri et al. [50] described various environmental treatment and remediations using different types of nanostructured materials from

air, contaminated waste-water, groundwater, surface water and soil. The nanoparticles studies include titanium dioxide, iron, bimetallic, catalytic particles, clays, carbon nanotube, dendrimers, fullerenes and magnetic nanoparticles. Their advantages and limitations in the environment applications are evaluated and compared with each other and with the existing techniques.

The use of inorganic, carbon-based and polymeric-based nanomaterials has been demonstrated by Guerra et al. [51]. These researchers have reviewed the use of these nanomaterials for the remediation of different environmental contaminants such as dyes, organophosphorous compounds, volatile organic compounds, halogenated herbicides, heavy metals, chlorinated organic compounds, etc.

**Table 3. Applications of engineered nanoparticles**

Engineered nanoparticles		Applications
Carbonaceous compounds	CNTs and their derivatives	Electronics, computers, plastics, catalysts, batteries, conductive coatings, supercapacitors, water purification systems, orthopaedic implants, aircraft, sporting goods, car parts, concrete, ceramics, solar cells, textiles
	Fullerenes	Removal of organometallic compounds, cancer treatment, cosmetics, magnetic resonance imaging, X-ray contrasting agent, anti-viral therapy
Metal Oxides	TiO <sub>2</sub>	Sunscreen lotion, cosmetics, skin care products, solar cells, conductive coatings, sporting goods, paints, cement, windows, electronic coating, bioremediation
	ZnO	Skin care products, bottle coatings, gas purification, contaminant sensors
	CeO <sub>2</sub>	Combustion catalyst in diesel fuels, solar cells, oxygen pumps, coatings, electronics, glass/ceramics, ophthalmic lenses
Semi-conductor devices	Quantum dots	Medical imaging, targeted therapeutics, solar cells, photovoltaic cells, security links, telecommunications
Zero-valence metals	Zero-valent iron	Remediation of water, sediments and soils to remove nitrates, detoxification of organochlorine pesticides and polychlorinated biphenyls
	Nanoparticulate silver	Textiles (e. g., socks, shirts, pants), disinfectant sprays, deodorants, laundry soaps, wound dressings, air filters, toothpaste, baby products (milk bottles, teethers), cosmetics, medical instruments, hardware(computer, mobile phones), food storage containers, cooking utensils, food additive/supplements, appliances (hair dryers, vacuum cleaners, washing machines, refrigerators), coatings/paints
	Colloidal elemental gold	Tumour therapy, flexible conducting inks or films, catalyst, cosmetics, pregnancy tests, anti-microbial coatings
Polymers	Dendrimers	Drug delivery, tumour treatment, manufacture of macrocapsules, nanolatex, coloured glasses, chemical sensors, modified electrodes

Li et al. [52] studied engineered super-paramagnetic iron oxide nanoparticles for environmental applications. The 8 nm iron oxide nanoparticles were synthesized and transferred into the water as stable suspensions by way of an interfacial oleic acid bilayer surface. Once stabilized and characterized, particles-particles and model surface interactions were quantitatively investigated and described as a function of ionic strength, zeta potential, dynamic light scattering and real-time quartz crystal microbalance with dissipation monitoring measurements. The use of metal nano oxides, tungstates and molybdates for the removal of toxic and radioactive species was discussed by Rajkumar [53]. The surface charge of nanomaterials was of great importance as this decided the applications. Antimony phosphate nanoribbons showed a clean separation of uranyl ion from its various mixtures. Nanocrystalline manganese oxide was used for the separation of uranium from different metal ions.

Patil et al. [54] examined the application of nanoscale zero-valent iron, carbon nanotubes and nano-fibres for the remediation of a variety of contaminants including chlorinated compounds, hydrocarbons, organic compounds and heavy metals.

Eco-friendly applications of several nanomaterials that have been used in bioremediation of waste and toxic materials have been discussed by Rizwan et al. [55]. Nanomaterials not only directly catalyzed degradation of waste and toxic materials, which is toxic to microorganism, but also it helps enhance the efficiency of microorganism in the degradation of waste and toxic materials. This also shows that phytoremediation can be applied in the removal of heavy toxic metal from contaminated soil. This work focused on immense applications of nanomaterials in bioremediation.

Khin et al. [56] give an overview of the applications of nanomaterial in environmental remediation. Nanomaterials in various shapes / morphologies, such as nanoparticles, wires, tubes, fibres, etc. function as adsorbents and catalysts and their composites with polymers are used for detection and removal of gases, chemicals, organic pollutants and biological substances such as viruses, bacteria, parasites and antibiotics. Nanomaterials have better environmental remediation properties due to its high surface area and reactivity. They have

developed dendritic nanopolymers for low-pressure filtration process to remove perchlorate and uranium from contaminated water.

A review on the recent development of the commercial available engineered nanoparticles in the environmental remediation and their toxic effects was reported by Kamali et al. [57]. The comparative study of the effectiveness and the toxicity of the engineered nanoparticles for environmental remediation indicated that advanced bimetallic materials such as Fe/Pd, or Fe/Ni can exhibit better performance in degrading the recalcitrant, environmental pollutants on one hand, and lower observed toxicity on the other hand. The copper oxides engineered nanoparticles have shown a relatively high level of toxicity. Nano zero-valent iron (nZVI) is emerging as a new option for the treatment of contaminated groundwater. Taghizadeh et al. [58] has given an overview of the characteristics and application of nano zero valent iron and summarizes its use in groundwater remediation. The nZVI effectively reduces chlorinated organic contaminants (e.g. perchlorobenzene, pesticides, tetrachloroethylene, perchloroethylene) and inorganic anion perchlorate. The nZVI is more effective at reaching deep zones of contamination and is more effective at contaminant degradation than iron of larger size.

Karn et al. [59] have discussed nanoscale zero valent iron in environmental remediation. Nanoscale Fe particles are effective for the remediation and transformation of a variety of environmental contaminants. No groundwater is pumped out for above-ground treatment, and the soil is transported to other places for treatment and disposal. Because of the high cost and lengthy operating periods for pump and treat remedies, in situ groundwater treatment technologies are increasing.

A review on the use of nanomaterials for the remediation of environmental contaminants viz, heavy metals, dyes, organophosphorus compounds, chlorinated organic compounds, and halogenated herbicides described by Guerra et al. [51]. This review provides an overview of inorganic, carbon-based and polymeric-based nanomaterials for environmental remediation.

Muller and Nowack [60] have described three examples of the use of engineered nanomaterials in soil remediation are nanoscale zero-valent iron for the degradation of

halogenated organic compounds, nanoscale calcium peroxide for the destruction of organics (e.g. gasoline) and nanoscale metal oxide for adsorption of metal. The nanoscale zerovalent iron is the only application of nanomaterials in soil and groundwater remediation that has been successfully commercialized. A short review on the application of nanotechnology in the remediation of contaminated groundwater was explained by Agarwal and Joshi [61]. The quantitative removal of chlorpyrifos and malathion pesticides achieved by gold and silver nanoparticles supported on activated alumina.

Chen et al. [62] presented a review which highlights the application of nano zero-valent iron (nZVI) in treating refractory compounds. The use of nZVI has some drawbacks such as (i) magnetic attraction between nano iron particles causes the rapid aggregation of particles (ii) nZVI are more prone to react with dissolved oxygen and oxygen-rich compounds (iii) nZVI exert some degree of toxicity studies suggest that cell membrane disruption and oxidative stress through the generation of  $Fe^{2+}$  and oxidative stress through the generation of  $Fe^{2+}$  and reactive oxygen species by nZVI are the main mechanisms contributing to nZVI cytotoxicity. These drawbacks overcome by immobilizing nZVI particles on suitable solid supports and also to expand the effective pH range of the Fenton reaction.

The nanoparticles made by mechanical and/or microbial action with fundamental building blocks are among the smallest human-made objects and exhibit novel physical, chemical and biological properties: which has wider application for detection, prevention, monitoring and remediation of pollutants. This review paper reported by Pandey and Fulekar [63] highlights that nanotechnology offers great promise for delivering new and improved remediation technology to clean up the environment. The present review discussed methods of synthesis (milling of large particle, precipitation of nanoparticles, SCF technology, emulsion and biogenic) size measurements and characterization (TEM, SEM, XPS and XRD etc.) of nanoparticles use of nanoparticles as sensors (Bio, electrochemical, mass, optical, gas) has also been discussed.

Tagizade Firozjaee et al. [64] described a review on the application of nanotechnology in pesticides removal from aqueous solutions. The aim of this review is to compile and study current

publications regarding pesticides removal by nanotechnology. This study discusses the applications, advantages and limitations various technological processes for removal of pesticides.

A review of different management approaches to reduce the level of metal contamination in soil and finally to the food chain discussed by Singh and Prasad [65]. The heavy metal pollution is very much concerned because of their toxicity for plants, animals and human being and their lack of biodegradability. The applications of nanoparticles for metal remediation have been attracting great research interest due to their exceptional adsorption and mechanical properties, unique electrical property, high chemical stability and large specific surface area.

Mohamed [66] reported a review of the application of nanotechnology in air pollution monitoring. He also reported definition, classification, properties and application of nanoparticles. Air mostly contained pollutants like CO, chlorofluorocarbons, volatile organic compounds, hydrocarbons and nitrogen oxides.

Biogenic uranite nanoparticles and their importance for uranium remediation have been described by Bargar et al. [67]. The first step in biogenic uranite formation is the reduction of U(VI) to U(IV). Electron transfer presumed to be mediated by C-type cytochromes localized either in the periplasm or on the outer membrane. The second step in biogenic uranite formation entails the precipitation of the mineral. The hydrated biogenic uranite due to its diminutive size, the molecular-scale structure, energetics appears to be similar to those of coarser-particles, abiotic, stoichiometric  $UO_2$ . These properties of biogenic uranite nanoparticles make it suitable for the bioremediation of subsurface U(VI) contamination.

Adeleye et al. [68] presented a review on the performances of traditional technologies and nanotechnology for water treatment and environmental remediation were compared with the goal of providing an up-to-date reference on the state of treatment techniques for researchers, industries and policymakers. Case studies were conducted on emulsified zero-valent nanoscale iron for groundwater remediation and nanosized silver-enabled ceramic water filters for drinking water treatment. This review submits that nanotechnology is emerging as a promising

alternative to traditional methods of water treatment and pollution remediation.

The use of iron oxide nanomaterials for the extraction of toxic heavy metals viz. Cd, Cr, As, Pb and Hg from groundwater studied by Neyaz et al. [69]. Naturally occurring iron oxide nanoparticles are magnetite ( $\text{Fe}_3\text{O}_4$ ), maghemite ( $\gamma\text{-Fe}_2\text{O}_3$ ) and hematite ( $\alpha\text{-Fe}_2\text{O}_3$ ) found in environmental sources such as volcanoes and fires. Metal ferrites such as  $\text{MnFe}_2\text{O}_4$ ,  $\text{CoFe}_2\text{O}_4$  and  $\text{NiFe}_2\text{O}_4$  can be formed by constituting Fe(II) with the corresponding metal cations. The selection of the best method for water purification should follow four conditions (i) Treatment flexibility and final efficiency (ii) Reuse of treatment materials (iii) Environmental friendliness (iv) Low cost. Surface modified iron oxide nanoparticles with various functional groups (like  $-\text{COOH}$ ,  $\text{NH}_2$ ,  $-\text{OH}$ ,  $-\text{SH}$ ) tend to be a hot research field due to its unique physicochemical characteristics such as easy and fast separation by applying an external magnetic field, chemical inertness, less toxic by-products, biologically safe and biocompatible etc.

Buzea et al. [70] have conducted studies on sources and toxicity of nanoparticles. Nanotoxicity is now concept to service, the present review reveals the results of life long history of evolution in the presence of nanoparticles, and how the human body, in particular, has adapted to defend itself against nanoparticulate intruders. The key to the toxicity of nanoparticles is their minute size, penetrate the basic biological structure and disrupt their normal function. The toxic effect included tissue inflammation and cell death. Human has always been exposed to tiny particles via dust storms, volcanic ash, and other natural processes, and that our bodily systems are well adapted to protect us from potentially harmful intruders.

The overview of the development of nanotechnology in wastewater treatment and their adverse effect on human health has been described by Zekic et al. [71]. This overview discussed main nanotechnological processes such as nanofiltration, catalysis, photocatalysis, water disinfection, adsorption of pollutants and nanoscale zero-valent iron, the nanomaterials used for water disinfection include chitosan, silver nanoparticles, titanium dioxide, fullerene, carbon nanotubes etc. The present review also described the effect of nanomaterials used in wastewater treatment on human health and the ecosystem.

Hegde Nayana and Pushpa [72] have synthesized nano zero valent iron (nZVI) borohydride via reduction method for the treatment of wastewater in terms of colour and chemical oxygen demand. The nZVI characterized by scanning electron microscope and a particle size analyzer. Batch experiments were carried out under various conditions of pH, dosages and contact time. The COD was reduced to 85% from the initial concentration of 9,600 mg/L. The colour was reduced to 55% from an initial absorbance value of 0.6596 at 655 nm at a pH of 2.48 at 150 min of contact time and at adsorbent doses of 1.5 g. The colour removal capacity increased with a decrease in pH.

The potential for improving the effectiveness of photocatalytic processes by means of semiconductor-metal nanocomposites and the merits of combining two advanced oxidation processes was discussed by Kamat and Meisel [73]. Present work described semiconductor nanoparticles as a photocatalyst ( $\text{TiO}_2$ ) and semiconductor-metals viz: (Ag, Au, Cu and Pt) nanocomposites for improving the efficiency of the photocatalyst. Sensing potential of  $\text{SnO}_2$  and ZnO based semiconductor system has also been discussed. The  $\text{TiO}_2$  photocatalysis is most useful to degrade polar compounds. When highly polar compounds are formed during the oxidation of organic contaminants, complete breakdown to  $\text{CO}_2$  and  $\text{H}_2\text{O}$  is quickly realized.

Ruttkey-Nedecky et al. [74] have summarized the latest findings on the phototoxicity of nanomaterial products based on essential metals used in plant protection. Phototoxicity of nanoparticles may be as a result of the toxicity of substances, which are used for its preparation. The nanoparticles may have to potentiate of inhibitory effects on plant growth in the different developmental stage. It is concluded from the present study that the nanoparticles prepared from essential heavy metals and their oxides have proven to be suitable for use in agriculture. The least phototoxic of these appear to be nanoparticles made from iron oxides and manganese oxides.

The overview of current knowledge of magnetic nanoparticles zeroes valent iron (nZVI), magnetite ( $\text{Fe}_3\text{O}_4$ ) and maghamite ( $\gamma\text{-Fe}_2\text{O}_3$ ) reported by Tang and Lo [75]. This review presented contaminant removal mechanism by magnetic nanoparticles along with factors affecting the ability of contaminant desorption. This review has also discussed aggregation of



magnetic nanoparticles, methods for enhancing stability and toxicological effects owing to magnetic nanoparticles.

Grieger et al. [76] have discussed environmental benefits and risks of use of zero-valent iron nanoparticles (nZVI) for soil and groundwater remediation. They have applied a best and worst case scenario evaluation as a first step to quantitatively evaluate the current state of knowledge regarding the potential environmental risk of nZVI.

A review on the application of nanoscale zero-valent iron and its composites for the removal of heavy metal ions from the environment studied by Zou et al. [77]. Present review show excellent removal capacity and environmental remediation of nZVI based materials for various heavy metal ions [Pb(II), Cr(III), Cd(II), As(III), Cu(II), Zn (II), Ni(II), Sb(II)]. A new look on nZVI based materials [nZVI@Mg(OH)<sub>2</sub>, nZVI–kool, chitosan-based nZVI, bentonite and beta zeolite supported nZVI] and possible interaction mechanism (e.g. adsorption, reduction and oxidation) and latest environmental applications are discussed. The effects of various environmental conditions (e.g. pH, temperature, coexisting cations and oxoanions) and potential problems for the removal of heavy metal ions on nZVI-based materials with the DFT theoretical calculations and EXAFS technology are also discussed.

Verma [78] has summarized sustainable synthetic processes developed during the past two decades involving the use of alternate energy inputs and greener reaction media. Titanium dioxide can be doped with metal (Ag) and non-metal atoms such as S, N, C to enhance its activity in visible light. The evolution in the development of “greener processes” continues from solvent-free reactions to the use of alternative energy-input systems, such as microwave or mechanochemical mixing in benign reaction media such as polyethylene glycol and water. The generation of recyclable nanocomposites, especially originating from biomass and waste that is not even consumed by animals (algal and sorghum residues) can be used as agents for the removal or degradation of pollutants and toxins under visible light, thus encompassing several green chemistry principles concurrently.

A review on synthesis, structure, sizes compositions and surface properties and applications of bimetallic Fe nanoparticles has

been reported by Liu et al. [79]. Reactions between the bimetallic nanoparticles (NPs) and those pollutants categories into four types (i) catalytic replacement reaction for heavy- metal removal, (ii) hydro-dehalogenation for halogenated hydrocarbons, (iii) nitro and azo hydrogenation for nitro and azo compounds and (iv) hydrodeoxygenation for oxyanions. The composition for some bimetallic nanoparticles is Fe CO<sub>3</sub>, Fe<sub>2</sub>Pt<sub>5</sub>, FePt<sub>3</sub>, Fe<sub>0.6</sub> Au<sub>2</sub>, Fe Ni<sub>5</sub>, Fe<sub>45</sub>Pt<sub>55</sub> etc. Compared with monometallic Fe NP's, bimetallic Fe NP' shave considerable separability and catalytic ability to degrade nano biodegradable pollutants.

Metal and metal oxide nanoparticles exhibit unique properties such as sorption, magnetic, chemical reduction, ligand sequestration etc. and have separation, catalysis, environmental remediation sensing and biomedical applications. This review on broad coverage of nanoparticles and polymeric/biopolymeric host materials and their properties have been reported by Sarkar et al. [80]. This review also discusses the role of the Donnan membrane effect exerted by the host functionalized polymer in harnessing the desirable properties of metal and metal oxide nanoparticles for the intended application. Present work is a good channel for the development of new types of hybrid ion exchangers for applications in areas such as heterogeneous catalysis, sensors, health, medicine and drug delivery.

Mukherjee et al. [81] have discussed review on the recent developments and approaches made in the synthesis of nano zero-valent iron (nZVI), structure and characterization of nZVI, challenges faced in the transport of nZVI in the surface environment and the augmentation of the motility of nZVI. They have discussed the effective use of nZVI in remediating organic pollutants (halogenated organic compounds, pharmaceutical waste and azo dyes) and inorganic pollutants (Ni<sup>2+</sup>, PO<sub>4</sub><sup>3-</sup>, Co<sup>2+</sup>, Cu<sup>2+</sup>). Aggregation of nZVI has been reported to be the major drawback for its applications. The modification of nZVI in order to overcome the challenges faced in the transport of nZVI through the soil has also been discussed.

The review focuses on the synthesis, protection, functionalization and application of magnetic nanomaterials (Fe<sub>3</sub> O<sub>4</sub>, γ-Fe<sub>2</sub> O<sub>3</sub>, Mg Fe<sub>2</sub> O<sub>4</sub>, Mn Fe<sub>2</sub>O<sub>4</sub>, Co Fe<sub>3</sub> O<sub>4</sub>, Co Pt<sub>3</sub>, Fe pt) as well as magnetic properties of nanostructured systems reported by Lu et al. [82]. Methods such as co-

precipitation, thermal decomposition, micelle synthesis and hydrothermal synthesis are discussed to control size and shape of magnetic nanoparticles. The protection strategies surfactant/polymer coating, silica coating and carbon coating of nanomaterials are also discussed in order to protect them from corrosion. Suitable polymers for coating are included poly (pyrrole), poly (aniline), poly (alkylacrylates), poly (methylidene malonate) and polyesters such as poly (lactic acid) poly (glycolic acid) and their copolymers. The application of protected nanomaterials in catalysis and biotechnology are briefly reviewed.

Kemp et al. [83] have investigated a review deals with wide-ranging environmental studies of graphene-based composite material (Fe- rGO, Fe<sub>3</sub>O<sub>4</sub>, Fe<sub>3</sub> O<sub>4</sub>- rGO, M Fe<sub>2</sub>O<sub>4</sub>-rGO, Fe C<sub>2</sub> O<sub>4</sub>-rGO, rGO = reduced graphene oxide) on the adsorption of hazardous materials and photocatalytic degradation of pollutants for water remediation. This review also addressed the biological toxicity of graphene applied to environmental remediation. The photocatalyst (TiO<sub>2</sub>- rGO, SnO<sub>2</sub>-rGO, CuO - rGO, WO<sub>3</sub>- rGO, Cu- rGO, Au - rGO) for the degradation of organic pollutants are also discussed.

The synthesis and applications of magnetic graphene nanocomposites (MGNCS) for the removal of heavy metals (Cr, As, Pd, Hg) from the environment was described by Zhu et al. [84]. Their focus was to reveal the potential of MGNCS to reduce the level of heavy metals below EPA requirements. Adsorption behaviour of heavy metals on MGNCS included adsorption kinetics, solution pH effects, concentration effect of both contaminants and adsorbents.

Auffan et al. [85] have defined nanoparticles are the particle that has sizes between 1 and 100 nm (10<sup>-9</sup> m) which show properties that are not found bulk samples of the same material. They reviewed the size-dependent properties of a variety of inorganic nanoparticles and found that about 30 nm do not in general show properties that could require regulatory scrutiny beyond that required for their bulk counterparts.

A review with a set of recommendations for the advancement of the understanding of the role of nanoscale silver in the environment and ecotoxicological research investigated by Fabrega et al. [86]. The present review summarizes synthesis, characterization and bioaccumulation mechanism of silver

nanoparticles. It also present effects of Ag NPs to aquatic organism fish prokaryotes, invertebrates algae and microbes mechanism of toxicity indicated that Ag NPs are more toxic than dissolve silver ion.

Bhattacharya et al. [87] have synthesized mixed oxides such as iron-cerium, iron-manganese, iron-zirconium, iron-titanium, iron-chromium, cerium-manganese, thoroughly characterized in sophisticated instruments like SEM, TEM, FTIR, AFM and employed for water treatment. The rapidly growing use of engineered nanoparticles in a variety of industrial scenarios and their potential for wastewater purification still have challenged how these nanoparticles can be removed in the water cycle.

A review on core/shell nanoparticles: classes, properties, synthesis mechanism characterization and applications described by Chaudhuri and Paria [88]. Core/shell nanoparticles categories as inorganic/inorganic; inorganic/organic; organic / inorganic; organic / organic materials. The choice of shell material of the core/shell nanoparticles generally strongly depends on the end application and use. The magnetic and fluorescence core materials coated with inorganic materials are extensively studied because of their wide applications in the biomedical and electronics fields. The efficiency of a core/shell semiconductors enhanced by a selective coating of the core material with higher band gap shell materials. The core/shell has the potential of direct use in both imaging and selective drug release.

The increasing use of nanomaterials for treatment of groundwater results in their release in the aquatic environment and also their toxic effect to aquatic life nanoparticles are more toxic than a larger particle of the same substance. Liu et al. [89] present a brief summary of technique for nanoparticles removal in water and wastewater but it looks that no treatment can absolutely protect the public from exposure to large scale dissemination of nanomaterials. The technologies for nanoparticles separation from the aquatic environment such as coagulation, electrocoagulation, flotation process, filtration process, biological process, magnetic filtration, capillary electrophoresis etc, are also discussed in the review.

Bezbaruah et al. [90] have investigated trichloroethylene (TCE) remediation using encapsulated nanoscale zero valent iron (nZVI) in

Ca-alginate biopolymer. Encapsulation expected to offer distinct advances over entrapment. This study has demonstrated that nZVI particles can be encapsulated in Ca-alginate without significant reduction in their reactivity. The TCE removal using encapsulated nZVI was 89 – 91% when compared to 88 – 90% removal using bare nZVI over a 2h period. This TCE degradation followed pseudo-first-order kinetics for encapsulated nZVI systems. The use of Ca – alginate encapsulated nZVI can overcome the mobility and settlement problems associated with bare nZVI and can be a potential technique for in situ remediations of groundwater.

An article on preparation, characterization and application of nanoparticles in preconcentration, separation and determination of trace pollutants from various environmental samples was investigated by Kaur and Gupta, [91]. Nanoparticles are a suitable replacement for organic solvent and reactive complexants in the extraction and preconcentration of trace metals and organic compounds from natural water and environmental samples. Chemically modified nanoparticles of silica, titania, zirconia and magnesia with (dithizone, gallic acid, PAN, 8-hydroxyquinoline etc.) are found effective, highly selective and more efficient for the preconcentration of environmental pollutants.

Uzum et al. [92] have synthesized nano zero valent iron (nZVI) from borohydride reduction and examined for the removal of aqueous  $\text{Co}^{2+}$  ions over a wide range of concentrations from 1.0-1000.0 mg/L. The size of nZVI particles was predominantly within the range of 20.0-80.0 nm. The experiment investigated the effects of V/m ratio, concentration, contact time and pH for the removal of  $\text{Co}^{2+}$  ions. Iron nanoparticles demonstrate very rapid uptake and large capacity for the removal of  $\text{Co}^{2+}$  ions. X-ray photoelectron indicate that fixation of  $\text{Co}^{2+}$  ions takes place through the interaction of their ions with the oxohydroxyl groups on the iron nanoparticle surface in addition to the spontaneous precipitate formation on high loading.

Synthesis, properties, toxicology and applications of silver nanoparticles were reported by Tran et al. [93]. Transmission of infectious pathogens to the community has caused outbreaks of disease such as influenza (A/H<sub>5</sub>N<sub>1</sub>), diarrhoea (Escherichia coli), cholera (Vibrio cholera) etc. throughout the world. This review presented the synthesis and antimicrobial effects of Ag – NPs

against various pathogens including bacteria fungi and virus. Some current applications Ag-NPs in water, water – air, surface – disinfection is described. Toxicology considerations of Ag – NPs to humans and ecology are discussed in detail. The future prospects of Ag – NPs for treatment and prevention of currently emerging infections are also discussed. Kharisov et al. [94] have discussed review on iron-containing nanomaterials, their synthesis, properties and environmental applications. Attention is also paid to and polymorphic forms of iron oxides and Fe OOH. Greener methods, coated, doped, supported with polymers or inert inorganic materials, the core-shell nanostructure of iron oxides and gold was discussed. Water disinfection (against viruses and bacteria), toxicity and risks of iron nanomaterial and applications were examined. This review also described use of iron-containing nanomaterials for the remediation of organic contaminants (chlorine-containing pollutants, benzoic and formic acids, dyes) and inorganic cations Zn(II), Cu(II), Cd(II), and Pb(II) and anions (nitrates, biomates, arsenates) from the environment.

Enhanced chitosan/  $\text{Fe}^0$  – nanoparticles beads for hexavalent chromium removal from wastewater studied by Liu et al, [95].  $\text{Fe}^0$  nanoparticles (nZVI) were successfully immobilized on epichlorohydrin/chitosan beads (ECH-CS-nZVI beads) for reduction of Cr(VI) from wastewater. ECH-CS-nZVI beads were characterized by SEM and FTIR. The removal of Cr (VI) using ECH – Cs – nZVI beads was consistent with pseudo-first-order reaction kinetics. This study demonstrated that SCH –CS – n ZVI beads could become an effective and promising technology for in situ remediations of Cr (VI).

The nanoscale zerovalent iron – rectorite (nZVI-R) composite was successfully synthesized through the incorporation of nZVI into the natural rectorite as support by Luo et al. [96]. Iron ions were embedded in the interlayer of rectorite, and then the exchangeable Fe (III) cations were reduced to nZVI by  $\text{NaBH}_4$  in solution. Prepared nZVI-R composite material was characterized using XRD, HR-TFM, XPS and XRF etc. In comparison to commercially available nZVI-Junye, nZVI- Lab and  $\text{Na}^+$  rectorite the synthesized nZVI- R composite in this study showed higher decolourization potential for orange (II). The mechanism for nZVI- R in discolouration of orange (II) was postulated by FTIR. The nZVI- R has potential applications in

cleaning up environmental contaminants such as organic dyes or halogen compounds.

Metal nanoparticles of Au, Ag, Pd and Pt have been synthesized in aqueous media using red grape pomace as a reducing agent and a capping agent described by Baruwati and Verma [97]. The particles are formed within a few seconds when exposing to microwave irradiation at a power level as low as 50 W. Particles could be formed at room temperature, but they tend to be amorphous in nature except for gold. A detailed study of the morphology of ensuring particles with various reaction conditions has been carried out.


Nanoscale zerovalent iron (nZVI) became more effective to remove heavy metals from electroplating wastewater when enhances chitosan (CS) beads were introduced as a support material in permeable reactive barriers (PRBS) investigated by Liu et al. [98]. The SEM images showed that CS – nZVI beads enhanced by ethylene glycol diglycidyl ether (EGDE) had a loose and porous surface with a nucleus – shell – structure. At low concentration (< 40mg/L), heavy metals were removed in order Cd (II) > Cu (II) > Pb (II) > Cr (II). As concentration increased the removal order was changed into Pb (II) > Cu (II) > Cd (II) > Cr (VI). The finding revealed that EGDE – CS – NZVI – beads PRB<sub>s</sub> had the capacity to remediate actual electroplating wastewater and may become an effective and promising technology for remediation of heavy metals:

Scott et al. [99] have reported the effect of vacuum annealing on the structure and surface chemistry of iron nanoparticles (INP). The corrosion resistance and longevity imbued by vacuum annealing of nanoparticles material may prove favourable for applying remediation technologies more effectively in natural and industrial situations. A multidisciplinary approach was used to investigate changes induced by vacuum annealing (< 5 X 10<sup>-8</sup> m bar) at 500°C on the bulk and surface chemistry of INP, in vacuum annealing of INP particle size did not change but surface oxide thickness decreases from 3 – 4 nm to 2 nm. The XRD confirmed that recrystallization of the metallic core had occurred converting a significant fraction of poorly crystalline iron to bcc α-Fe and Fe<sub>2</sub> B phases. The XPS indicated a change in the surface oxide stoichiometry from magnetite (Fe<sub>3</sub> O<sub>4</sub>) towards wustite (Fe O) and migration of boron and carbon to the particle surface.


A novel biosorbent was prepared by the immobilization of phanerochaete chrysosporium with iron oxide magnetic nanoparticles (MNPs) and Ca – alginate by Xu et al. [100]. The structure of prepared MNPs – and Ca – alginate immobilized P. Chrysosporium was confirmed by ESEM, EDS, FTIP and XRD characterization. The prepared MNPs – and Ca – alginate immobilized P. Chrysosporium was capable of removing Pb (II) ions from solution efficiently, in terms of its performance and cost. Present work provides a potential and unique technique for heavy metals removal by enhanced removal capacity and application stability.

De Corte et al. [101] have reported an innovated method for biological synthesis of Pd nanoparticles (bio – Pd). The present review discussed different bio – Pd precipitating microorganisms (Escherichia coli, Klebsiella pneumoniae, anabaena, calothrix, clostridium pasterianum, citrobacter Braaki, etc.) and application of catalyst for the degradation of environmental contaminants (e.g. Cr (VI), ClO<sub>4</sub><sup>-</sup>, Lindane, Chlorophenol, Trichloroethylene etc.). The microbial scaffold allows a green synthesis of NPs and offers some advantages and perspectives for the development of reactor technologies for metal recovery, soil and water treatment.


A short review on the application of nanotechnology in the remediation of contaminated groundwater was described by Agarwal and Joshi [102]. Present article reviewed the status of groundwater quality, the basic idea of nanotechnology for remediation and its practical applicability, ongoing projects and future scope of nanotechnology in India. The use of nano zero-valent iron (nZVI) in the treatment of chlorinated hydrocarbons and metals from hydrocarbon discussed in the article. The practical applicability of Fe<sup>0</sup> particles lies in the fact to get oxidized into +2 and +3 oxidation states thereby reducing other organic as well as inorganic impurities. The metallic iron (Fe<sup>0</sup>) served effectively as an electron donor.



Chlorinated hydrocarbons accept the electrons and undergo reductive dechlorination



from a thermodynamic perspective, the coupling of the reactions (10) and (11) is often energetically highly favourable.



The standard reduction potential of ZVI, ( $\text{Fe}^{2+}/\text{Fe}^{3+}$ ) is 0.44V, which is lower than many organic compounds like chlorinated hydrocarbon and metals such as Pb, Cd, Ni, and Cr, hence these organic compounds and metals are thus prone to reduction by ZVI nanoparticles.

Chandhuri and Paria [103] reported an easy synthesis technique a sulfur doped hollow  $\text{TiO}_2$  nanocatalyst for photodegradation of organic dye under solar light. The sulfur-doped hollow  $\text{TiO}_2$  nanoparticles synthesized by template base sacrificial core technique. The photocatalytic potential of the synthesized catalyst was tested by the degradation of methylene blue dye under solar light. The surface area of synthesized hollow doped nanoparticles comparatively higher ( $318.11 \text{ m}^2\text{g}^{-1}$ ) than  $\text{TiO}_2$  particles ( $130.94 \text{ m}^2\text{g}^{-1}$ ) because of the hollow and porous structure, Sulfur doping on  $\text{TiO}_2$  decreases the band gap from 3.2 – 2.5 eV which make the material more suitable as photocatalyst under solar light. This catalyst can be used effectively for environmental remediation purposes because of high surface area and low band gap.

The biodegradability of fullerenes, single, double, multi-walled as well as COOH functionalized carbon nanotubes and cellulose and starch nanocrystals in the aqueous environment have been investigated by Kummerer et al. [104]. The cellulose and starch nanocrystals are actually better biodegradable than their macroscopic counterparts in aqueous environments whereas fullerenes and CNTS are not at all biodegradable. None of the particles was found to be toxic to micro-organism necessary for oxygen take-up.

Gawande et al. [105] have synthesized  $\text{Fe}_3\text{O}_4$  – cysteine MNPs without any additional source of linkers. The  $\text{Fe}_3\text{O}_4$  – cysteine, MNPs were successfully used for the synthesis of P-amino carbonyl and hydroquinoline. Magnetic organocatalysts can be easily recovered by simple magnetic decantation and their catalytic activity remains unaltered after nine consecutive cycles making them environmentally friendly and widely applicable due to their efficiency, ease of handling and cost-effectiveness.

Synthesis, characterization and manipulation of dendrimer – stabilized iron sulfide nanoparticles were studied by Shi et al. [106]. The Fe S nanoparticles were synthesized using

ethylenediamine core poly (amidoamine) (PAMAM) dendrimer of generation 4 terminated with amino ( $\text{G}_4 - \text{NH}_2$ ), hydroxyl ( $\text{G}_4 - \text{NglyOH}$ ) and carboxyl ( $\text{G}_4 - \text{SAH}$ ) groups, respectively as stabilizers. Deposition of FeS NPs on to mesoporous silica gel microparticles was confirmed by zeta potential and SEM measurements. Study shows that dendrimer – coated silica particles facilitate the much more effective loading of FeS NPs. The synthesis and manipulation of FeS NPs onto mesoporous silica microparticles provide remediation applications.

The potential of nano zero valent iron application for removal of different organic contaminants in different scenario (i. e. groundwater, wastewater etc.,) is studied by Raychaudhury and Scheytt [107]. The reaction efficiencies of nZVI for reduction of nitro-organic compounds are found high. The halogenated compounds with high molecular weights or complex structures (i.e. iodinated contrast media, DDT, polychlorinated biphenyls etc.) has shown lower reaction rates with nZVI compared to the widely studied chlorinated hydrocarbons (i.e. trichloroethylene).

A review on the recent applications of nanotechnology in agro-environmental studies with particular attention to the fate of nanomaterials once introduced in water and soil to the advantages of their use and their possible toxicology reported by Mura et al. [108]. Findings show that the use of nanomaterials can improve the quality of the environment and help to detect and remediate polluted sites. It was noted that not all nanomaterials induce toxic effects e.g.  $\text{TiO}_2$ , carbon black show low toxicity.

Xu et al. [109] investigated review which outline the applications of iron oxide nanomaterials ( $\text{Fe}_3\text{O}_4$  – silica, flower-like iron oxides, hydrous iron oxide MNPs, cysteine coated  $\text{Fe}_2\text{O}_3$  MNPs, amino-modified  $\text{Fe}_3\text{O}_4$  MNPs etc.) for the removal of heavy metals [Cu (II), Cr (VI), As (V), Hg (II), Ni (II) Pb (II) etc] from wastewater. The present review described the use of iron oxide as nanosorbents for heavy metals, organic contaminants, as photocatalyst in photodegradation reactions. The  $\text{Fe}_2\text{O}_3$  can be applied as a sensitizer for  $\text{TiO}_2$  photocatalyst, photo – Fenton like the system has been set up with the existence of iron oxides and oxalate. The outlook for potential applications and further challenges as well as the likely fate of nanomaterials discharge to the environment were discussed.

A review on application of nanoparticles in agriculture (improving seed germination, plant protection, pathogen detection, pesticide/herbicide etc.) and the role these can play in future agriculture production described by Khot et al. [110]. Toxicity of the ecosystem, potential, residue carried – over in foodstuff and nanomaterials phototoxicity are some of the major concerns for the application of nanomaterials in agriculture. There is also need to evaluate the toxicokinetics and toxicodynamics of nanomaterials used for agricultural production. About 1045 residues reported by the Food Administration Department (FAD) as pesticide residue, nanomaterial-based nanosensors can be used to detect such pesticide residue.

Ariga et al. [111] focused especially on materials for environmental remediation based on the concept of materials nano architectonics. Study classified into three categories: (i) Continuous arising problem: Such as removal and degradation of toxic substances including waste due to fossil fuel uses and organic pollutants (ii) Current urgent problem: current emerging topics concerning oil spills and nuclear waste (iii) Breakthrough for future development: advanced method based on supramolecular chemistry and nanotechnology. Toxic substances include removal of fossil waste, degradation of organic pollutants, removal and filtration of other hazardous substances. Current emerging topics included oil spills, nuclear waste, future technology for materials detection include advanced supramolecular systems for sensing. The good knowledge of both basic science and practical usage is required for environmental remediation.

Bhuyan et al. [112] investigated biosynthesis zinc oxide nanoparticles from *Azadirachta indica* for antibacterial and photocatalytic applications. The present work reported low cost, green synthesis of ZnO nanoparticles using 25% (W/V) of neem leaf extract: synthesized nanoparticles characterized by TEM, EDX, XRD, UV-VIS, FT IR. Biosynthesized ZnO was of size 9.6 – 25.5 nm, band gap 3.87 eV and have wurtzite structure. The ZnO nanoparticles have shown good antibacterial (*S. aureus*, *S. pyogenes* and *E. coli*) and photocatalytic (methylene blue degradation) activity. Synthesized ZnO nanoparticles found to act as an effective antimicrobial and photocatalytic agent.

The biosynthesis of inorganic nanoparticles including metallic nanoparticles (Au, Ag, Hg,

CdFe, AuAg, Se, Pt) oxide nanoparticles ( $Fe_3O_4$ ,  $Fe_2O_3$ ,  $TiO_2$ ,  $BaTiO_3$ ,  $ZrO_2$ ) sulfide nanoparticles (ZnS, CdS, FeS) and other typical nanoparticles ( $PbCO_3$ ,  $CdCO_3$ ,  $SrCO_3$ , CdSe) described by Li et al. [113]. The biosynthesis of nanoparticles by microbes is taught to be clean, nontoxic and environmentally acceptable “green chemistry” procedure. The use of microorganism (bacteria, yeast, fungi and actinomycetes) classified into intracellular and extracellular according to the location where nanoparticles are formed. The applications of these biosynthesized nanoparticles include drug delivery, cancer treatment, gene therapy, DNA analysis, antibacterial agent, biosensors, enhancing reaction rates, separation science and MRI. The main drawback of biosynthesis of nanoparticles is a slow process (several or even a few days) instabilities (nanoparticles formed by a microorganism may be decomposed after a certain period of time). These two drawbacks need further study.

Bi et al. [114] demonstrated that metallic Ag nanocrystals can be selectively formed on the entire surface, edges and partial [100] facets or only edges of simple – crystalline  $Ag_3PO_4$  submicro-cubes by simply adjusting the concentrations of ammonia. The photocatalytic performance studies for the decomposition of rhodamine B indicates that  $Ag/Ag_3PO_4$  heterocubes exhibit much higher photocatalytic properties than pure  $Ag_3PO_4$  cubes and Ag nanoparticles under visible light irradiation, which may be due to efficient charge separation at contact interface as well as the enhanced visible light absorption.

The effect of alumina nanoparticles an algal growth investigated by Sadiq et al. [115]. The growth inhibitory effect of alumina nanoparticles was observed on both algal species/72h  $EC_{50}$  value, 45.4 mg/L for *Chlorella* sp: 39.35 mg/L for *Scenedesmus* sp). Bulk alumina also showed toxicity through a lesser extent (72h  $EC_{50}$  value, 110.2 mg/L for *Chlorella* sp; 100.4 mg/L for *Scenedesmus* sp). The concentration-dependent decrease in the chlorophyll content is may be due to the shading effect of alumina particles. The FT – IR, optical and scanning electron microscopic images suggest interaction of the nanoparticles with the cell surface. The entrapment of algal cells in aggregates of alumina nanoparticles may play a pivotal role in toxicity to the algal species.

Chidambaram et al. [116] develop and apply an efficient bioremediation method based on in situ

biosyntheses of bio-Pd nanoparticles and hydrogen. The *C. Pasteurianum* BC1 was used to reduce Pd (II) ions to form Pd nanoparticles (bio-Pd) that primarily precipitated on the cell wall and in the cytoplasm. The *C. Pasteurianum* BC1 cells, loaded with bio-Pd nanoparticles in the presence of glucose were used to fermentative produce hydrogen and effectively catalyze the removal of soluble Cr (VI) via reductive transformation to insoluble Cr (III) species. Batch and aquifer microcosm experiments using *C. Pasteurianum* BC1 cells loaded with bio-Pd showed efficient reductive Cr (VI) removal, while in control experiments with killed or viable but Pd-free bacterial cultures no reductive Cr (VI) removal was observed. The process offers significant advantages over the current groundwater treatment technologies that rely on introducing performed catalytic nanoparticles into groundwater treatment zones and the costly addition of molecular hydrogen to above ground pump and treat system.

Silica colloid-polyelectrolyte-iron oxide nanocomposites with both magnetic and catalytic properties have been synthesized via layer by layer assembly by Che et al. [117]. Dynamic light scattering (DLS) and electrophoretic mobility measurements were employed to monitor the evolution of these structures from silica colloid to silica colloid – polyelectrolyte – iron oxide composite. The experiment was conducted to test dyes (methylene blue, methyl orange) removal capabilities of synthesized nanoparticles silica colloid, polyelectrolyte - functionalized silica colloid (silica PDDA) and silica colloid – polyelectrolyte iron oxide composite (silica – PDDA – IOMMPS). The silica – PDDA – IOMMPS composite is found superior for pollutant removal from aqueous environment mainly due to catalytic property. The finding was rationalized by Langmuir and Freundlich absorption analysis. The silica – PDDA – IOMMPS nanocomposites hybrid material remained catalytically active after six months of storage.

Khan et al. [118] described review for remediation of contaminated soil and groundwater by chlorinated organic pollutants (PCB, TCE, TCA, pesticides, solvents), inorganic anions (perchlorates) metal ions [Cr (VI), Zn (II), Cu (II), Pb (II), Cd(II)] by use nano zerovalent iron. Iron and nickel nanoparticles use for removal of uranium.

A report on the restriction of nanoparticles in environmental cleanup discussed by Snousy and

Zawrah [119]. The objective of the work is to point major challenges facing environmental nanoscience and urges developing eco-friendly techniques to ensure a good quality of life. The use of nanomaterials in environmental applications requires a better understanding of their mobility, bioavailability and toxicity. This work includes subjects on risk assessment/toxicity, exploring the ecological assessment, toxicity, fate, transport and limitations facing nano zerovalent particles in the ecosystems. Future pollution remediation nanomaterials based techniques may include pollution transport by nanoparticles which will have medical, radiological and national defence implications in terms of human health, safety and the environment.

### 3. CONCLUDING REMARKS

1. In this critical review applications of engineered nanoparticles (carbonaceous compounds, metal oxides, semiconductor devices, zerovalent metals, polymers etc) in various environmental remediation areas have been discussed.
2. The nano zerovalent iron, carbon nanotubes, nanoclay, dendrimers, nanoparticle silver, colloidal elemental gold are found to be an effective tool for removal of heavy metals, dyes, phenols, organochlorine, organophosphorus etc from the environment.
3. Carbon nanotubes are found to be an adsorbent for a wide variety of organic compounds from the aquatic environment which includes DDT, chlorobenzene, chlorophenols, trihalomethanes, dyes, pesticides, herbicides, polynuclear aromatic hydrocarbon, p-nitrophenol etc.
4. The inorganic nanoparticles including oxide nanoparticles ( $\text{Fe}_2\text{O}_3$ ,  $\text{TiO}_2$ ,  $\text{ZrO}_2$ ,  $\text{Fe}_3\text{O}_4$ ), metallic nanoparticles (Ag, Au, Hg, Pt, CdFe, Se, AuAg), sulphide nanoparticles (ZnS, FeS, CdS) are found to have well established environmental remediation potential.
5. There are three main challenges for the production and use of nanomaterials (i) cost-effectiveness (ii) impact on human life and environment (iii) use of particular nanotechnology.
6. The nanocatalysts, nanomembranes and nanoadsorbents are found to be most used nanomaterials.
7. The use of nanoparticles in environmental remediation are invariable lead to the

release of nanoparticles in the environment. The potential risk of these nanoparticles in the environment can be assessed by knowing their bioavailability, toxicity, persistence and mobility. The growing use of engineered nanoparticles in environmental remediation raises the question of how these nanoparticles can be removed from the environment. This may also be a challenging field of research for relevant researchers.

## COMPETING INTERESTS

Author has declared that no competing interests exist.

## REFERENCES

1. International Organization for Standardization (ISO) 2010, ISO/DTS 80004 – I, Nanotechnologies – Vocabulary–part 1: Core Terms. 2010; 1-16.
2. Georgakilas V, Perman JA, Tucek J, Boril R, Broad family of carbon nanoallotropes: Classification, chemistry and applications of fullerene, carbon dots, nanotubes, graphene, nanodiamonds and combined superstructures. *Chemical Reviews*. 2015; 115: 4744 – 4822.
3. Wagner S, Gondikas A, Neubauer E, Hofmann T, Von der Kammer F. Spot the difference: Engineered and natural nanoparticles in the environmental release, behavior and fate. *Angewandte Chemie International Edition*. 2014;53:12398-12419.
4. Tiwari JN, Tiwari RN, Kim KS, Zero-dimensional and three-dimensional nanostructured materials for advanced electrochemical energy devices. *Progress in Material Sciences*. 2012;57(4):724-803.
5. Mukherjee PK, Nanomaterials: Materials with immense potential. *Journal of Applicable Chemistry*. 2016;5(4):714-718.
6. Ramapo B, Manjappa S, Puttaiah ET, Monitoring of heavy metal concentration in ground water of Harinaka Taluk, India. *Contemporary Engineering Sciences*. 2010;3:183-190.
7. Fujishima A, Honda K, Electrochemical photolysis of water at a semiconductor electrode. *Nature* 1972;238:37-38.
8. Cozzoli PD, Comparelli R, Fanizza E, Curri ML, Agostino A. Photocatalytic activity of organic – capped anatase TiO<sub>2</sub> nanocrystals in homogenous organic solutions. *Mat. Sci. Eng.* 2003;C23:707-713.
9. Hoffman AJ, Carraway ER, Hoffman M. Photocatalytic production of H<sub>2</sub>O<sub>2</sub> and organic peroxides on quantum sized semiconductor colloids. *Environ. Sci. Technol.* 1994;28:776-785.
10. Emilio CA, Litter MI, Kunst M, Bouchard M, Colbeau-Justin C. Phenol photodegradation on platinized - TiO<sub>2</sub> photocatalysts related to charge- carrier dynamics. *Langmuir*. 2006;22:3606-3613.
11. Choi W, Termin A, Hoffman MR, The role of metal ion dopants in quantum sized  $\{ \text{TiO}_2 \}_2$  : Correlation between photoreactivity and charge carrier recombination dynamics. *J. Phys. Chem. B*. 1998;98:13669-13679.
12. Institute National de Propriedade Intelectual (INPI). *Nanotecnologia*. 2009;6.
13. Sattler KD. *Hand book of nanophysics: Principle and methods*. CRC, New York. 2010;1-23.
14. Logothetidis S, *Nanostructured materials and their applications*. Nanoscience and Technology, Springer-Verlag, Berlin Heidelberg, Germany. 2012;220.
15. Mansoori GA, Batsami TJ, Ahmadpour A , Eshaghi Z, Environmental application for nanotechnology. *Annual Review of Nano Research*. 2008;2(2):1-73.
16. Hansen SF, Michelson ES, Kamper A, Borling B, Stuer-Lauridsen F, Baun A, Categorization framework to aid exposure assessment of nanomaterials in consumer products. *Ecotoxicology*. 2005;17(5):438-447.
17. Brien NO, Cummins E, Recent developments in nanotechnology and risk assessment strategies for addressing public and environmental health concerns. *Hum. Ecol. Risk. Assess.* 2008;14(3):568-592.
18. Bhatt I, Tripathi BN, Interaction of engineered nanoparticles with various components of the environment and possible strategies for their risk assessment. *Chemosphere*. 2011;82(3): 308-317.
19. Quadros ME, Marr LC, Environmental and human health risks of aerosolized silver nanoparticles. *J. Air. Waste Manag. Assoc.* 2010;61(1):770-781.
20. Lee J, Mahendra S, Alvarez PJ, Nanomaterials in the construction industry,



- a review of their applications and environmental health and safety considerations. *ACN Nano*. 2010;4(4): 3580-3590.
21. US Government Accountability Office, Nanomaterials are widely used commerce, but EPA faces challenges in regulating risk. Washington, DC, GAO; 2010.
  22. Petit C, Bondosz TJ. Graphite oxide / Polyoxometalate nano composites as adsorbents of ammonia. *J. Phys, Chem. C*. 2009;113:3800-3809.
  23. Seredych M, Bondosz TJ, Manganese oxide and graphite oxide/MnO<sub>2</sub> composites as reactive adsorbents of ammonia at ambient conditions. *Microporous and Mesoporous Materials*. 2012;150:55-63.
  24. Wu S, He Q, Tan C, Wang Y, Zhang H. Graphene-based electrochemical sensors. *Small*. 2013;9:1160-1172.
  25. Dong H, Lin B, Gilmore K, Hou T, Lee ST, Li Y. B-40 fullerene: An efficient material for CO<sub>2</sub> capture, storage and separation. *Current Applied Physics*. 2015;15:1084-1089.
  26. Esrafil MD. N<sub>2</sub>O reduction over fullerene like boron nitride cage: A DFT study. *Physics Letter A*. 2017;381(25-26):2085-2091.
  27. Simko M, Mattsson MO, Risks from accidental exposures to engineered nanoparticles and neurological health effects: A critical review. *Part Fibre Toxicol*. 2010;7:42.
  28. Peralta Videa JR, Zhao L, Lopez-Moreno ML, Hong J, Gardea-Torresoley JL. Nanomaterials and the environment: A review of biennium 2008-2010. *J. Hazard Mater*. 2010;186:1-15.
  29. Boczkowski J, Hoet P. What's new in nanotoxicology? Implications to public health from a brief review of the literature. *Nanotoxicology*. 2010;4(1):1-4.
  30. Kayat J, Gajbhiye V, Tekade RK, Jain NK. Pulmonary toxicity of carbon nanotubes: A systematic report, *Nanomedicine*. 2011;7(1):40-49.
  31. Cui HF, Vashist SK, Al-Rubeaan K, Luong JH, Sheu FS. Interfacing carbon nanotubes with living mammalian cells and cytotoxicity issues. *Chem. Res. Toxicol*. 2010;23(7):1131-1147.
  32. Salvolainen K, Alenius H, Norppa H, Pylkkanen L, Tuomi T, Kasper G, Risk assessment of engineered nanomaterials and nanotechnologies – a review. *Toxicology*. 2010;269(2-3):92-104.
  33. Ahamed M, Alsalhi MS, Siddiqui MKJ. Silver nanoparticle applications and human health. *Clin. Chim. Acta*. 2010;411(23-24): 1841-1848.
  34. Wijnhoven SWP, Nano-silver- A review of available data and knowledge gaps in human and environmental risk assessment. *Nanotoxicology*. 2009;3(2): 109-138.
  35. Tolaymat TM, El Badaway AM, Genaidy A, Scheckel KG, Luxton TP, Suidan M, An evidence based environmental perspective of manufactured silver nanoparticles in synthesis and application: A systemic review and critical appraisal of peer reviewed scientific papers. *Sci. Total Environ*. 2010;408(5):999-1006.
  36. Schilling K, Bradford B, Castelli D, Dufour E, Nash YF. Human safety review of “nano” titanium dioxide and zinc oxide, *Photochem. Photobiol. Sci*. 2010;9(4):495-509.
  37. Osmond MJ, Mc Call MJ, Zinc oxide nanoparticles in modern sunscreens: An analysis of potential exposure and hazard. *Nanotechnology*. 2010;4(1):15-21.
  38. Tewari AJ, Marr LC, The role of atmospheric transformations in determining environmental impacts of carbonaceous nanoparticles. *J. Environ. Qual*. 2010;39(6):1883-1895.
  39. Lopez-Moreno ML, De La Rosa G, Hernandez-Viezcas JA, Gardea-Torresdey JR. X-ray absorption spectroscopy (XAS) corroboration of the uptake and storage of CeO<sub>2</sub> nanoparticles and assessment of their differential toxicity in four edible plant species, *J. Agri. Food. Chem*. 2010;58(6): 3689-3693.
  40. Ranganathan R, Madanmohan S, Kesavan A, Baskar G, Krishnamurthy YR, Satasham R, Ponraju D, Rayala SK, Venkatraman G, Nanomedicine towards development of patient-friendly drug-delivery systems for oncological applications. *International Journal of Nanomedicine*. 2012;7:1043-1060.
  41. Stendahl JC, Sinusas AJ, Nanoparticles for cardiovascular imaging and therapeutic delivery Part 2: Radiolabeled probes, *Journal of Nuclear Medicine*. 2015;56(11): 1637-1641.
  42. Zheng G, Patolsky F, Cui Y, Wang WU, Lieber CM. Multiplexed electrical detection of cancer markers with nanowire sensor arrays, *Nature Biotechnology*. 2005;23(10): 1294-1301.

43. Herrmann IK, Schlegel A, Graf R, Schumacher CM, Senn N, Hasler M. Nanomagnet-based removal of lead and digoxin from living rats. *Nanoscale*. 2013; 5(15):8718-8723.
44. Kang JH, Super M, Yung CW, Cooper RM, Domansky K, Graveline AR. An extracorporeal blood-cleansing device for sepsis therapy, *Nature Medicine*. 2014; 20(10):1211-1218.
45. Lalwani G, Henslee AM, Farshid B, Lin L, Kasper FK, Qin YX, Mikos AG, Sitharaman B. Two-dimensional nanostructure-reinforced biodegradable polymeric nanocomposites for bone tissue engineering. *Biomacromolecules*. 2013; 14(3):900-909.
46. Lalwani G, Henslee AM, Farshid B, Parmar P, Lin L, Qin YX. Tungsten disulfide nanotubes reinforced biodegradable polymers for bone tissue engineering. *Acta Biomaterialia*. 2013; 9(9):8365-8373.
47. Gobin AM, O'Neal DP, Watkins DM, Halas NJ, Drezek RA, West JL. Near infrared laser-tissue welding using nanoshells as an exogenous absorber, *Laser in Surgery and Medicine*. 2005;37(2):123-129.
48. Umar A, Akhtar MS, Dar DN, Baskontas S, Low-temperature synthesis of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> hexagonal nanoparticles for environmental application and smart sensor applications. *Talanta*. 2013;116(15):1060-1066.
49. Rajan CS. Nanotechnology in ground water remediation. *International Journal of Environmental Science and Development*. 2011;2(3):16-21.
50. Mansoori GA, Rohani-Bastami T, Ahmadpour A, Eshaghi Z, Environmental application of nanotechnology, *Annual Review of Nano Research*. 2008;2(2):439-493.
51. Guerra FD, Attia MF, Whitehead DC, Alexis F, Nanotechnology for environmental remediation, materials and applications. *Molecules*. 2018;23(1760): 1-23.
52. Li W, Liu D, Wu J, Kim C, Fortner JD, Aqueous aggregation and surface deposition processes for engineered superparamagnetic iron oxide nanoparticles for environmental applications. *Environ, Sci. Technol*. 2014; 48(20):11892-11900.
53. Rajkumar J. Nanomaterials as sorbents for environmental remediation. *Archives of Nanomedicine Open Access Journal, (Arch Op Acc J)*. 2018;1(4):71-74.
54. Patil SS, Shedbalkar UU, Truskewycz A, Chopade BA, Ball AS. Nanoparticles for environmental clean-up: A review of potential risks and emerging solutions. *Environmental Technology & Innovation*. 2016;5(5):10-12.
55. Rizwan Md., Singh M, Mitra CK, Morve RK. Ecofriendly application of nanomaterials: Nanobioremediation. *Journal of Nanoparticles, Hindawi Publications*; 2014. Article ID. 431787, pp. 1-7.
56. Khin MM, Nair AS, Babu VJ, Murugan R, Ramakrishna S, A review on nanomaterials for environmental remediation. *Energy Environ. Sci*. 2012;5: 8075-8109.
57. Kamali M, Gomes APD, Khodaparast Z, Seifi T. Review on recent advances in environmental remediation and related toxicity of engineered nanoparticles. *Environmental Engineering and Management Journal*. 2016;15(04):923-934.
58. Taghizadeh M, Kebria DY, Darvishi G, Kootenaei FG. The use of nano zero valent iron in remediation of contaminated soil and groundwater. *International Journal of Scientific Research in Environmental Sciences, (IJSRES)*. 2013;7(7):152-157.
59. Karn B, Kuiken T, Otto M. Nanotechnology and in situ remediation: A review of the benefits and potential risks. *Environmental Health Perspectives*. 2009;117(12):1823-1831.
60. Mueller NC, Nowack B, Nanoparticles for remediation: Solving big problems with little particles. *Elements*. 2010;6:395-400.
61. Agarwal A, Joshi H. Application of nanotechnology in the remediation of contaminated groundwater: A short review. *Recent Research in Science and Technology*. 2010;2(6):51-57.
62. Chen X, Ji D, Wang X, Zhang L, Review on nano zerovalent iron (nZVI): From modification to environmental applications, CEESD, IOP Publishing, IOP Conf. Series: Earth and Environmental Sciences. 2012; 51:012004.
63. Pandey B, Fulekar MH. Nanotechnology: Remediation technologies to clean up the environmental pollutants. *Research Journal of Chemical Sciences*. 2012;2(2): 90-96.

64. TagizadeFirozraee T, Mehrdadi N, Bagdadi M, Nabi-Bidhendi GR. Application of nanotechnology in pesticides removal from aqueous solutions: A review. *Int. J. Nanosci. Nanotechnol.* 2018;14(1):43-56.
65. Singh A, Prasad SM. Remediation of heavy metal contaminated ecosystem: And overview on technology advancement. *Int. J. Environ. Sci. Technol.* 2015;12:353-366.
66. Mohamed EF. Nanotechnology: Future of environment air pollution control. *Environmental Management and Sustainable Development.* 2017;6(20): 429-454.
67. Bargar JR, Bernier-Latmani R, Giammar DE, Tebo BM. Biogenic uranite nanoparticles and their importance for uranium remediation. *Elements.* 2008;4: 407-412.
68. Adeleye AS, Conway JR, Garner K, Huang Y, Su Y, Keller AA. Engineered nanomaterials for water treatment and remediation: Cost benefits and applicability. *Chemical Engineering Journal.* 2016;268:286-662.
69. Neyaz N, Siddiqui WA, Nair KK. Application of surface functionalized iron oxide nanomaterials as a nanosorbents in extraction of toxic heavy metals from groundwater: A review. *International Journal of Environmental Sciences.* 2013; 4(4):472-483.
70. Buzea C, Blandeno IIP, Robbie K. Nanomaterials and nanoparticles: Source and toxicity. *Biointerphases.* 2007;2(4):MR 17-MR 172.
71. Zekic E, Vukovic Z, Halkijevec I, Applications of nanotechnology in wastewater treatment. *Gradevinar.* 2018; 70(4):315-323.
72. Hegde Nayana C, Pushpa T. Nano zero-valent iron for the removal of colour and chemical oxygen demand of textile effluent. *Indian Journal of Advances in Chemical Sciences.* 2016;51:236-238.
73. Kamat PV, Meisal D. Nanoscience opportunities in environmental remediation. *Complete Rendus Chimie.* 2003;6:999-1007.
74. Ruttkay-Nedecky B, Krystofova O, Nejdil L, Adam V. Nanoparticles based on essential metals and their phytotoxicity. *J. Nanobiotechnol.* 2017;15-33.
75. Tang SCN, Lo IMC. Magnetic nanoparticles: Essential factors for sustainable environmental applications. *Water Research.* 2013;47:2613-2632.
76. Grieger KD, Fjordboge A, Hartman NB, Erickson E, Bjerg DL, Baun A, Environmental benefits and risks of zero-valent iron nanoparticles (nZVI) for in situ remediation: Risk mitigation or trade-off. *Journal of Contaminant Hydrology.* 2010; 111:165-183.
77. Zou Y, Wang X, Khan A, Wang P, Liu Y, Alsaedi A, Hayat T, Wang X. Environmental remediation and application of nanoscale zerovalent iron and its composites for the removal of heavy metal ions: A review. *Environ. Sci. Technol.* 2016;50:7290-7304.
78. Verma RS. Journey on greener pathways: From the use of alternate energy to sustainable application of nano-catalysts in synthesis and environmental remediation. *Green Chem.* 2014;16:2027-2041.
79. Liu WJ, Qian TT, Jiang H. Bimetallic Fe nanoparticles: Recent advances in synthesis and application in catalytic elimination of environmental pollutants. *Chemical Engineering Journal.* 2014;236: 448-463.
80. Sarkar S, Guibal E, Quignard F, Sengupta AK. Polymer-supported metals and metal oxide nanoparticles: Synthesis, characterization and applications. *J. Nanopart. Res.* 2012;14:715-730.
81. Mukherjee R, Kumar R, Sinha A, lama Y, Saha AK. A review on synthesis, characterization and applications of nano zero valent iron (nZVI) for environmental remediation. *Critical Reviews in Environmental Science and Technology.* 2016;46:443-466.
82. Lu AH, Salabas EL, Schuth F, Magnetic nanoparticles: Synthesis, protection, functionalization and application. *Angew. Chem. Int. Ed.* 2007;46:1222-1244.
83. Kemp KC, Seema H, Saleh M, Le NH, Mahesh K, Chandra V, Kim KS. Environmental applications using graphenes composites: Water remediation and gas adsorption. *Nanoscale.* 2013;5: 3149-3171.
84. Zhu J, Wai S, Chen M, Gu H, Rapole SB, Pallavkar S, Ho TC, Hopper J, Guo Z. Magnetic nanocomposites for environmental remediation. *Advanced Powder Technology.* 2013;24:459-467.
85. Auffan M, Rose J, Bottero JY, Lowry GV, Jolivet JP, Wiesner MR. Towards a definition of inorganic nanoparticles from an environmental, health and safety

- perspectives. *Nature Nanotechnology*. 2009;242:1-8.
86. Fabrega J, Luonia SN, Tyler CR, Galloway TJ, Lead JR. Silver nanoparticles: Behaviour and effects in the aquatic environment. *Environment International*. 2011;37:517-531.
  87. Bhattacharya S, Saha I, Mukhopadhyay A, Chattopadhyay D, Ghosh UC, Chatterjee D. Role of nanotechnology in water treatment and purification: Potential applications and implications. *International Journal of Chemical Science and Technology*. 2013;3(3):59-64.
  88. Chaudhuri RG, Paria S. Core/Shell nanoparticles: Classes, properties, synthesis mechanism, characterization and applications. *Chem. Rev.* 2012;112:2373-2433.
  89. Liu Y, Tourbin M, Lachaiz S, Guiraud P. Nanoparticles in wastewaters: Hazards, fate and remediation. *Powder Technology*. 2014;255:249-256.
  90. Bezbaruah AN, Shanbhogue SS, Simsek S, Khan E. Encapsulation of iron nanoparticles in alginate biopolymer for trichloroethylene remediation. *J. Nanopart Res.* 2011;13:6673-6681.
  91. Kaur A, Gupta U. A review on applications of nanoparticles for preconcentration of environmental pollutants. *J. Mat. Chem.* 2009;19:8279-8289.
  92. Uzum C, Shahwan T, Eroglu AE, Lieberwirth I, Scott TB, Hallam KR. Application of zero-valent iron nanoparticles for the removal of aqueous  $\text{Co}^{2+}$  ions under various experimental conditions. *Chemical Engineering Journal*. 2008;144:213-220.
  93. Tran QH, Nguyen VQ, Le AT. Silver nanoparticles: Synthesis, properties, toxicology, applications and perspectives. *Adv. Nat. Sci.: Nanosci. Nanotechnol.* 2013;4:033001–033020.
  94. Kharisov BI, Rasika Dias HV, Kharissova OV, Jimenez-Perez VM, Perez BO, Flores BM. Iron-containing nanomaterials: Synthesis properties and environmental applications. *RSC Adv.* 2012;2:9325-9358.
  95. Lu T, Wang Z-L, Zhao L, Yang X. Enhanced chitosan/ $\text{Fe}^0$  – nanoparticles beads of hexavalent chromium removal from waste water. *Chemical Engineering Journal*. 2012;189-190:196-202.
  96. Luo S, Qin P, Shao J, Peng L, Zeng O, Gu JD. Synthesis of reactive nanoscale zerovalent iron using rectorite supports and its application for orange II removal. *Chemical Engineering Journal*. 2013;223:1-7.
  97. Baruwati B, Verma RS. High value products from waste: Grape pomace extract – A three-in-one package for synthesis of metal nanoparticles. *Chem. Sus. Chem.* 2009;2:1041-1044.
  98. Liu T, Yang X, Wang ZL, Yan X. Enhanced chitosan bands-supported  $\text{Fe}^0$  nanoparticles for removal of heavy metal from electroplating wastewater in permeable reactive barriers. *Water Research*. 2013;47:6691-6700.
  99. Scott TB, Dickinson M, Crane RA, Riba O, Hughes GM, Allen GC. The effects of vacuum annealing on the structure and surface chemistry of iron nanoparticles. *J. Nanopart, Res.* 2010;12:1765-1775.
  100. Xu P, Zeng G, Huang D, Hu S, Feng C, Lai C, Zhao M, Huang C, Li N, Wei Z, Xie G. Synthesis of iron oxide nanoparticles and their application in phanerochaete chrysosporium immobilization of Pb (II) removal. *Colloids and Surfaces A: Physiochem. Eng. Aspects.* 2013;419:147-155.
  101. De Corte S, Hennebel T, De Gussem B, Verstraete W, Boon N. Bio-palladium: From metal recovery to catalytic applications. *Microbial Biotechnology*. 2012;5(1):5-17.
  102. Agarwal A, Joshi H. Application of nanotechnology in the remediation of contaminated groundwater: A short review. *Recent Research in Science and Technology*. 2010;2(6):51-57.
  103. Chandhuri RG, Paria S. Visible light induced photocatalytic activity of sulfur doped hollow  $\text{TiO}_2$  nanoparticles, synthesized via a novel route. *Dalton Trans.* 2014;43:5526-5534.
  104. Kummerer K, Menz J, Schubert T, Thielemans W. Biodegradability of organic nanoparticles in the aqueous environment. *Chemosphere*. 2011;82:1387-1392.
  105. Gawande MB, Velhinhe A, Nogueira ID, Ghumman CAA, Teodoro OMND, Branco PS. A facile synthesis of cysteine-ferrite magnetic nanoparticles for application in multicomponent reactions-sustainable protocol, *RSC Adv.* 2012;2:6144-6149.
  106. Shi X, Sun K, Bulogh LP, Bakar Jr. JR. Synthesis, characterization and manipulation of dendrimer-stabilized iron sulfide nanoparticles. *Nanotechnology*. 2006;17:4554-4560.

107. Raychoudhury T, Scheytt T. Potential of zerovalent iron nanoparticles for remediation of environmental organic contaminants in water: A review. *Water Science and Technology*. 2013;68(7): 1424-1439.
108. Mura S, Seddaiu G, Bachini F, Roggero PP, Greppi GF. Advances of nanotechnology in agro-environmental studies. *Italian Journal of Agronomy*. 2013; 8(e 18):127-140.
109. Xu P, Zong GM, Huang DL, Feng CL, Hu S, Zhao MH, Lai C, Wei Z, Huang C, Xieand GX, Lui ZF. Use of iron oxide nanomaterials to wastewater treatment: A review. *Science of Total Environment*. 2012;424:1-10.
110. Khot LR, Sankaran S, Maja JM, Ehsani R, Schuster EW. Applications of nanomaterials in agricultural production and crop protection: A review. *Crop Protection*. 2012;35:64-70.
111. Ariga K, Ishihara S, Abe H, Li M, Hill JP. Materials nanoarchitectonics for environmental remediation and sensing. *J. Mater. Chem*. 2012;22:2369-2377.
112. Bhuyan T, Mishra K, Khanuja M, Prasad R, Varma A. Biosynthesis of zinc oxide nanoparticles from *Azadirachta indica* for antibacterial and photocatalytic applications. *Materials Science Semiconductor Processing*. 2015;32: 5561.
113. Li X, Xu H, Chen ZS, Chen G. Biosynthesis of nanoparticles by microorganisms and their applications. *Journal of Nanomaterials*, Hindawi Publishing Corporation; 2011. Article ID 270974, pp 1-16.
114. Bi Y, Hu H, Ouyang S, Jiao J, Lu G, Ye J. Selective growth of metallic Ag nanocrystals on Ag<sub>3</sub> PO<sub>4</sub> submicro-cubes for photocatalytic applications. *Chem. Eur. J*. 2012;18:14272-14272.
115. Sadiq IM, Pakrashi S, Chandrasekeran N, Mukherjee A. Studies on toxicity of aluminum oxide (Al<sub>2</sub> O<sub>3</sub>) nanoparticles to microalgae species: *Scenedesmus* sp. and *Chlorella* sp. *J. Nanopart Res*. 2011;13: 3287-3299.
116. Chidambaram D, Hennebel T, Taghavi S, Mast J, Boon N, Verstraete D, Lalie DVD, Fitts JP. Concomitant microbial generation of Palladium nanoparticles and hydrogen to immobilize chromate. *Environ. Sci. Technol*. 2010;44:7635-7640.
117. Che HX, Yeap WP, Ahmad AL, Lim L. Layer by layer assembly of iron oxide magnetic nanoparticles decorated silica colloid for water remediation. *Chemical Engineering Journal*. 2014;243:68-76.
118. Khan I, Farhan M, Singh P, Thiagarajan P. Nanotechnology for environmental remediation. *Research Journal of Pharmaceutical Biological and Chemical Sciences (RJPBCS)*. 2014;5(3):1916-1927.
119. Snousy MG, Zawrah SM. Nanoparticles restriction in environmental clean up. *Nano Research and Application*. 2017; 3(1):1-5.

© 2019 Tewari; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

*Peer-review history:*  
The peer review history for this paper can be accessed here:  
<http://www.sdiarticle3.com/review-history/49902>