

Development of Bulk Metallic Glasses and their Composites by Additive Manufacturing – Evolution, Challenges and a Proposed Novel Solution

Muhammad Musaddique Ali Rafique^{1,a*}, Dong Qiu^{1,b} and Milan Brandt^{2,c}

¹School of Engineering, MIT University, Melbourne, VIC, Australia

²Additive Manufacturing Precinct, RMIT University, Melbourne, VIC, Australia

^{a*}ali.rafique@hotmail.com, ^bdong.qiu2@rmit.edu.au, ^cmilan.brandt@rmit.edu.au

Keywords: bulk metallic glass matrix composites, additive manufacturing, solidification, inoculation

Abstract. Bulk metallic glasses (BMGs) and their composites (BMGMCs) have emerged as competitive materials for structural engineering applications exhibiting superior tensile strength, hardness along with very large elastic strain limit. However, they suffer from lack of ductility and subsequent low toughness due to the inherent brittleness of the glassy structure which makes them amenable to failure without appreciable yielding. Various mechanisms and methods have been proposed to counter this effect out of which, recently Additive Manufacturing has gained widespread attention. It is proposed that additive manufacturing can overcome these difficulties in single step due to inherent existence of very high cooling rate in the process which is essential for glass formation. This, when coupled with careful selection of alloy chemistry is proposed to be the best solution to fabricate near net shape parts in a single step with excellent properties. In this report, an effort has been made to describe one possible route to achieve this. Solidification processing employing carefully selected inoculants based on edge to edge matching technique along with the carefully controlled inoculation procedure is proposed to reflect enhanced mechanical properties. It is hypothesized that number density, size and distribution of ductile crystalline phase would best be able to improve microstructure and hence properties. This is meant to be controlled by manipulating type, size and the amount of inoculants. The proposed methodology is claimed to bear maximum potential.

1. Introduction

Very recently, metallic glasses have gained widespread popularity in the scientific community as a completely new material exhibiting very high tensile strength, hardness, elastic strain limit and yield strength at relatively lower density as compared to steel and other high strength alloys [1-3]. They were first discovered in 1960 by Swartz et al. [4] at Caltech. Yet, their use has not been able to get broad acceptance as competing engineering material owing to lack of ductility and glassy structure which is inherently brittle [2]. This brittleness becomes even more prominent at large length-scales (> 1 mm) [5-8] where auxiliary failure mechanisms (shear bands) becomes prominent [9-11]. This adversely affects their suitability for making large-scale machinery components. This limitation can be overcome by introducing plasticity in glassy matrix whilst retaining its high strength simultaneously [12-15]. This may be achieved by various mechanisms such as exploitation of intrinsic ability of glass to exhibit plasticity at very small (nano) length-scales [16, 17], introduction of external obstacles to shear band formation and propagation (*ex-situ* composites) [18, 19], self or external impulse assisted multiplication of shear bands [11, 20], development of ductile phases within the brittle glassy matrix during solidification (*in-situ* composites) [21-24] and transformation inside a ductile crystalline phase e.g. B2 – B19' transformation in Zr-based systems (stress / transformation induced plasticity (TRIP)) [25-28]. The later approach (formation of ductile phase in brittle glass) takes into account the nucleation of primary (ductile) phase either during solidification *in-situ* [29-35] or heat treatment of solidified glassy melt (devitrification) [36-44] and form the basis of ductile bulk metallic glass matrix composites (BMGMC). Although, considerable progress has been made towards increasing the size of “as-cast” ingot of bulk metallic glass, still, the largest possible diameter and length which has been produced by conventional means to date [45], is too small to be used in any structural engineering application. This happens because quenching effect caused by water-

cooled walls of copper mold (also known as suction casting) is not enough to overcome critical cooling rate (R_c) of alloy (~ 0.067 K/s [45]) necessary to produce a uniform bulk glassy ingot of large size/section thickness. In addition to this, the occurrence of the bulk glassy structure is limited to certain specific compositions which have excellent inherent glass forming ability (GFA) [46, 47]. This is not observed in compositions which are strong candidates to be exploited for making large-scale industrial structural components [26, 48-56] with relatively higher critical cooling rates (R_c) (10 K/s [49]). This poses a limitation to this conventional technique and urges the need of advanced manufacturing method which does not carry these shortcomings. Additive manufacturing (AM) has emerged as an answer to this problem. It is proposed as a potential solution to this problem. This technique is envisaged to possess potential [57, 58] to produce bulk metallic glasses [59, 60] and their composites in a single step across a spectrum of compositions [61-64]. It is hypothesized that it will achieve this by exploiting very high cooling rate available instantaneously in transient liquid melt pool [65-67] in an infinitely small region where laser/electron beam strikes solid (laser surface melting / laser solid forming) or powder (selective laser melting/laser engineered net shaping (LENS®)) sample. This, when combined with superior glass forming ability (GFA) of bulk metallic glasses, proposed to effectively and efficiently overcome dimensional limitations; virtually any part carrying fully glassy and composite structure can be manufactured. In addition, rapid liquid pool formation [67] and its rapid cooling results in extremely versatile and beneficial properties in final manufactured part such as combination of high strength, hardness and toughness, controlled microstructure, its refinement [65-67], near dimensional accuracy, consolidation and integrity. The mechanism underlying this is layer – by – layer (LBL) formation, which ensures glass formation in each layer during solidification before proceeding to the next layer. That's how; a large monolithic glassy structure is thought to be produced. This layer – by – layer formation also helps in development of secondary phases precipitating out of glassy matrix in a multicomponent alloy [68-70] as layer preceding fusion layer undergoes another heating cycle (inert atmosphere) below melting temperature (T_m) somewhere in the nose region of time – temperature – transformation (TTT) diagram [59] which not only assists in phase transformation [41, 43] but also helps in increase of toughness, homogenisation and compaction of part. This is a new, promising and growing technique of rapidly forming metal [71], plastic [72], ceramic composite [73] parts by fabricating a near-net shape out of raw material either by powder method or wire method (classified on the basis of additives used). The movement of energy source (laser or electron beam) is dictated by a computer-aided design (CAD) geometry which is fed into a computer at the back end and controlled by computerized numerical control (CNC) [74, 75] system. The process has a wide range of applicability across various industrial sectors ranging from welding [76-81], repair [82, 83], and cladding [84-90] to full scale part development.

However, there is a dearth of knowledge about the exact mechanism of formation (nucleation and growth and/or liquid-liquid transition [91-93]) of ductile phase dendrites or spheroidal intermetallics *in-situ* during solidification of bulk metallic glass matrix composites occurring inside additive manufacturing liquid melt pool which is essential for further advance process improvement and optimisation. Sonication techniques aimed at grain refinement and tuning of the microstructure are proposed to be the best possible solution strategy. Some of these may include; optimal selection of alloy composition [94, 95], casting parameter adjustment by controlling melting current/time and cooling rate [96], melt adjustment by remelting [97], and controlled inoculation by the introduction of refractory metals in solidifying melt [98-100]. This last technique, known as inoculation, is proposed to bear maximum potential. However, this is not rigorously tested on additive manufacturing of bulk metallic glasses and their composites and no real account exist documenting their application. In the present study, an effort has been made to bridge this gap. First, new inoculants are designed based on well-established crystal matching technique known as an edge to edge matching [101, 102]. These new inoculants are proposed to bear a maximum potential to trigger nucleation of primary ductile phase prior to, or concurrently during solidification. Improvement in microstructure and hence ductility and toughness are proposed to be achieved by an increase in number density, size and distribution of ductile phase in the glassy matrix as a function of type, size

and amount of inoculants during solidification. This is a well established technique in foundry engineering [103, 104] and solidification processing [105] to improve the properties of various types of alloys. However, its use in additive manufacturing primarily related to bulk metallic glasses and their composites is still in its infancy. Second, virtually no effort has been made to improve upon the technique of inoculation in conventional Cu mold suction casting as well as additive manufacturing to understand nucleation and growth of ductile crystalline phase dendrites or spheroids *in-situ* during solidification in bulk metallic glass matrix composites. A step forward is taken in the present study to address this gap. Carefully designed inoculants are introduced in bulk metallic glass matrix melt during melting and solidification both in suction casting and additive manufacturing to study their combined synergic effect to refine microstructure and improve upon properties. A step forward is taken to bring together the strengths of different techniques and methodologies at one platform. In essence, an effort is made to form ductile bulk metallic glass metal matrix composites by taking advantage of

- a. Materials chemistry: Two types of multicomponent alloys based on superior glass forming abilities are selected as model systems. Their glass forming ability is used as a measure to manipulate composition and vice versa.
- b. Solidification processing: Liquid melt pool formation, its size, shape and geometry is studied. Movement of liquid in this melt pool and its role dictated by simultaneous heat and mass transfer and fluid dynamics is also observed. Effect of dynamics in dictating solidification behaviour and pattern in crucible free, small Cu crucible and engineered liquid melt pool of additive manufacturing are also studied. The behaviour of inoculant free and well inoculated alloys is studied, compared and used as a measure of establishing a quantification criterion with the help of cooling curves of both types of systems under transient conditions.
- c. Additive manufacturing: Very high cooling rate inherently available in the process is used to (a) not only form glassy matrix but use liquid melt pool formed at very high temperature to trigger nucleation (liquid – solid transformation) of ductile phase in the form of dendrites or spheroids from within the pool “*in-situ*” (This is done by controlling machine parameters in such a way that optimized cooling rate satisfying narrow window of “quenching” bulk metallic glasses is achieved) and (b) to take advantage of heating (heat treatment) of preceding layer to trigger solid – solid transformation (devitrification) again to form ductile phase and achieve high toughness, ductility, homogeneity, consolidation and part integrity eliminating the need of post-processing, before or after treatment and
- d. Crystallographic matching for the design of inoculants: An advanced crystallographic matching technique known as an edge to edge matching [101, 102] is applied for careful design and selection of inoculants bearing maximum potency. It was applied based on the fundamental principle that an inoculant can best be able to serve as nucleation site if its crystal structure matches that of expected or anticipated phase. Expected phase identification is carried out based on the well-established phase diagram of the alloy system under investigation. Number density, size and distribution of ductile phase is taken as a measure to refine microstructure and quantify mechanical properties and it is taken as a function of type, size and amount of nucleates (inoculant). The volume fraction of the crystalline phase was aimed to be measured by ASTM 562 – 11 manual point count method applied on optical micrographs for its rigorous nature, accuracy and robustness.

This article introduces the fundamental science and technology behind bulk metallic glass and their composites to the reader. It emphasizes on very basic inherent mechanisms which are responsible for formation of glassy structure in metals and alloys and highlights factors and / or variables that account for the combination of “high strength, hardness and elastic strain limit” and “poor ductility and toughness” in this very important class of materials. It also highlights and briefly narrates various mechanisms, manufacturing routes, techniques and strategies (*in-situ* and *ex-situ*) which may be used

to manufacture and prove out to be effective to overcome lack of ductility and toughness in these materials. A brief conclusion has been drawn how microstructure design by inoculation with the aim to increase number density, size and distribution of the ductile phase can help reduce brittleness and additive manufacturing as a technique, can serve as vital tool to intrinsically refine microstructure without the need of any additional steps or post processing thus serving as a bridge between inoculation free or assisted microstructure design and manufacturing.

Note: Additive manufacturing (AM) methods can also be classified on the basis of the energy source used (i-e laser-based or electron beam-based).

2. Metallic Glasses (MG) and Bulk Metallic Glasses (BMG)

Metallic glasses (MGs) [5] may be defined as disordered atomic – scale structural arrangement of atoms formed as a result of rapid cooling of binary or multicomponent alloy systems directly from their molten state to below their glass transition temperature with a large undercooling and suppressed kinetics of nucleation in such a way that the supercooled liquid state is retained / frozen-in [99-109]. This results in the formation of a “glassy structure”. The process is very much similar to inorganic/oxide glass formation in which large oxide molecules (such as silica / boride / aluminates / sulphides and sulphates) form a regular network retained in its frozen / supercooled liquid state [110]. The only difference being that; metallic glasses comprise of metallic atoms rather than inorganic compounds. In recent times, their formation, structural arrangement and stability is described more elaborately by “three laws” [111] which are based on atomic size, the number of elements and heats of formation. Their atomic scale behaviour is also based on short-range order (SRO) [112-114] to medium-range order (MRO) [115-117] or long-range disorder [3] (unlike metals – well defined long-range order) and can further be explained by other advanced theories / mechanisms (frustration [118], order in disorder [116, 118, 119] and confusion [120]). Important features which characterizes them are their amorphous structure and unique mechanical properties. Owing to the absence of dislocations, no plasticity is exhibited by BMGs. This results in very high yield strength and elastic strain limits as there is no slip plane for material to flow (by conventional deformation mechanisms). From a fundamental definition point of view, metallic glasses are typically different from bulk metallic glasses in that the former has a fully metallic (monolithic) structure for thicknesses less than 1 mm, whilst the latter is glassy (monolithic) for greater than 1 mm [6, 7]. To date, the largest bulk metallic glass made in the “as-cast” condition is 8 mm diameter and 85 mm in length [45]. There are reports of making large thin castings and casing for smartphones but they are typically less than 1 mm in the maximum thickness [10]. Furthermore, they are characterized by special properties such as glass forming ability (GFA), metastability (which will be described in proceeding sections). Formation and stability of these alloys may be described by their ability to retain glassy state at room temperature. Over a period of time, this has been described in terms of three laws, considered universal for forming any bulk metallic glass system [111]. Any glass forming system consists of elements which must:

1. have a minimum number (at minimum). (greater than 3 constituents is considered beneficial).
2. differ in their atomic size by 12% among the three elements. (Atoms of elements with large size are considered to exhibit superior glass forming ability).
3. have a negative heat of mixing amongst all three element combinations. (This ensures the tendency to de-mix or confuse [120] ensuring retention of the glassy structure at room temperature).

This results in a new structure with a high degree of densely packed atomic configurations, which in turn results in a completely new atomic configuration at a local level with long-range homogeneity and attractive interaction. In general, bulk metallic glasses or bulk glassy alloys (BGA) are typically designed around alloy systems that exhibit (1) a deep eutectic, which decreases the amount of undercooling needed to vitrify the liquid, and (2) alloys that exhibit a large atomic size mismatch, which creates lattice stresses that frustrate crystallisation [111]. These were first proposed by Prof.

Akisha Inoue at WPI – IMR, Tohoku University, Japan [3] followed by Douglas C. Hoffmann and co-workers at Caltech [111] but in essence the message they give out remain same. Some of the important characteristics of these systems are; glass forming ability and metastability responsible for the evolution of the overall glassy structure. Despite their advantages and extremely high strength, metallic glass and their bulk counterparts suffer from following limitations;

- a. They have very poor ductility [2, 121-123]. They do not exhibit any plasticity under tension and exhibit little plastic behaviour under compression [124-126].
- b. They have very poor fracture toughness [13, 127-133]. This severely limits their engineering applications as they cannot absorb the effects of load or cannot transfer stresses safely and fail in a catastrophic manner [134].

Progress has been made in recent years to overcome these problems, but still, experimental results and values obtained are not of considerable practical significance and have very poor reproducibility which renders them unsatisfactory for any practical use [135-137].

3. Ductile Bulk Metallic Glasses

Owing to difficulties encountered during the use of “as-cast” bulk metallic glasses especially for structural applications, schemes were devised from the very early days of BMG research for the increase of ductility in these alloys. In the beginning, efforts were made to increase the plasticity by dispersing controlled porosity [138] but these efforts did not proceed far because of the non-practical nature of the method and other unwanted problems developed in the structure. Then, the focus was directed to address this problem by the basic mechanisms of plasticity and plastic deformation. For example, if the progression of a shear band could be hindered (just like dislocation motion hindrance in crystalline alloys) by impeding its motion, substantial increase in ductility could be achieved. This is achieved by two fundamental mechanisms a) increased number of shear bands increase the obstacles (“arrests”) to the paths of material flow. Hence, it would be difficult for the material to flow [139-146] and b) strain energy dissipation resulting from shear band formation at the interface between a crystalline phase and the amorphous matrix. One of the ways, this helped was the introduction of new processes of forming by controlled application of force in the presence of heat (thermoplastic forming) [147, 148] and in certain range where material flow under constant stress (super plastic forming) [149] which were tried as far as 10 years ago. Further techniques consisted of (1) *Ex-situ* introduction of second phase reinforcements (particles [19, 150, 151], flakes [152], fibres [153-155], ribbons [156], whiskers [157, 158]) which offer a barrier to the movement of shear bands along one plane and provide a pivot for their multiplication, (2) *In-situ* nucleation and growth of primary phase reinforcements in the form of equiaxed dendrites or spheroids which are ductile in nature and not only provide means to increase ductility by themselves but also offer a pivot for multiplication of shear bands [159, 160], (3) reducing the size of the glass to nanometre and ductile phase to micrometre [27], (4) making the plastic front (local plastically deformed region ahead and around a shear band) of shear bands to match with plane of restriction (difficult flow) in crystal lattice of ductile phase thus creating easy path for shear band to multiply (not yet investigated idea of author), and (5) heating the alloy to cause temperature induced structural change (devitrification) [161-165]. The drive for all these mechanisms is different. For example, it is known that shear bands are responsible for the catastrophic failure of bulk metallic glasses [166] and any hindrance to their motion by pinning or branching (three dimensional network spread throughout the volume) would cause a difficulty with which they will move (along one direction at very high speed) causing abrupt failure. This gave rise to fundamental mechanisms of toughening [13, 167]. A similar effect could be achieved through the external addition to (*ex-situ*), or internal manipulation of (*in-situ*), the structure of the material. Of these, only devitrification was first envisaged as the dominant mechanism for increase in fracture toughness and hardness as early as 1979 by Robert Freed and co-workers at MIT [161]. It was known thermodynamically, numerically [168] and tested experimentally [169-172] since the early days that structurally constrained glass relaxes during heating known as

“devitrification” [161]. The driving force for devitrification [165, 173] came as a result of natural impulse as bulk metallic glass possess the natural tendency to undergo structural change [161] (solid-state phase transformation) when subjected to a temperature similar to heat treatment for crystalline metallic alloys. This resulted in a new class of bulk metallic glass called ductile bulk metallic glass [174-182]. The research on other mechanisms was adopted with the passage of time [12] giving rise to more versatile materials known as ductile bulk metallic glass matrix composites.

4. Ductile Bulk Metallic Glass Matrix Composites (BMGMCs)

As introduced briefly in the previous section, a significant improvement in the mechanical properties of bulk metallic glass was reported for the first time in 2000 [12]. Ductile crystalline phase was successfully incorporated within the glassy matrix of Zr based alloys containing Be in the form of three-dimensional network. It formed *in-situ* during solidification thus giving birth to the “so-called” family of *in-situ* dendrite / metallic glass matrix composites. These materials are formed as a result of conventional solute partitioning mechanisms as observed in other metallurgical alloys resulting in the copious formation of a ductile phase β -(Ti-Zr-Nb) in case of Ti-based composites [12], α -Zr B2 spheroid intermetallic in the case of Zr-based composites without Be [94, 96, 183, 186] or transformed B2 (B19' martensite) in the case of Zr-Cu-Al-Co shape memory bulk metallic glass matrix composites (a special class of BMGMCs) [21, 185, 187-191]) predominantly (not always) in the form of three dimensional dendrites or spheroids emerging directly from the liquid during solidification. Devitrification and formation of ordered structures in these alloys can be explained by the help of “phase separation” or “quenched in” nuclei [192-196]. This is another very important route for the fabrication of these alloys. They also comprise of a family of bulk metallic glass matrix composites which are formed by more advanced transformation mechanisms (liquid-state phase separation) [197-200] which have recently become observable owing to more advanced characterisation techniques employing container less levitated sample solidification [92, 201] and its observation under Synchrotron radiation [202-205] or zero and micro-gravity conditions on board international space station. This renders them with special properties (enhanced plasticity and compressive strength) not otherwise attainable by other conventional processing routes or in simple binary and ternary compositions. This, however, is seldom the case and is not readily observed as compared to solid-state phase separation [197] which is the dominant mechanism in these alloys. More advanced mechanisms of forming these materials are by local microstructural evolution by phase separation right at shear bands [206]. It is noted that liquid–solid phase separation occurs at the onset of the shear band and becomes the cause of microstructural evolution. A few notable classes of alloys that constitute these types of ductile composites are Ti-based BMGMCs [55, 56, 207-212], Ti-based shape memory BMGMC [213], Zr-Cu-Al-Ti [214, 215], Zr-Cu-Al-Ni [52], and Zr-Cu-Al-Co shape memory BMGMC [51]. Each has their own mechanisms of formation and individual phases are formed by liquid – solid or solid – solid phase transformations. From process perspective, their production methods ranges from conventional melting and casting in vacuum (gravity or pressure assisted production) [216-221], twin roll casting (TRC) [222, 223], semi – solid processing (including thermoplastic forming (TPF)) [60, 148, 224, 225] to modern day additive manufacturing (AM) [69, 70, 226-231]. Their detailed discussion is beyond the scope of present work and is described elsewhere [59, 69, 70, 232-240] (see supporting information).

5. Very Recent Trends and Triumphs

Some of the modern approaches to the problem of achieving ductility and toughness are fundamental in nature based on basic understanding and comprehension of engineering and metallurgy. For example, a recent study details the size effects on the stability of shear band development and propagation. This interesting review [241] documents very recent developments and progresses in ductile bulk metallic glass matrix composites in the form of important phenomena of shear banding which ultimately results in increased ductility and toughness in otherwise brittle solids. As discussed above, the formation of stress induced transformation (TRIP) inside a ductile phase dendrite is another

promising way of achieving increased ductility while maintaining high strength and hardness. Although it is a relatively old idea, which was exploited some years ago by means of indentation and conventional deformations [145, 242-245], it has attracted the attention of researchers as new methods of forming and transformation (especially since *in-situ* liquid – solid transformation [28]) have evolved with time. The quest for obtaining a ductile BMGMC with enhanced optimal ductility with enough large size still continues to push boundaries of what could be achieved. In this regard, very recently, researchers at Yale University and IFW Dresden, Germany have made further promising progress in detailing what could be found elsewhere [136].

6. Bulk Metallic Glasses by Additive Manufacturing

Processing of BMGMCs by additive manufacturing (AM) [59, 60] is slowly, progressively, and surely growing as a successful technique for their production on a large-scale. Various forms of AM processes (selective laser sintering (SLS), selective laser melting (SLM) [61], laser engineered net shaping (LENS®) [246], direct laser deposition (DLD) [239, 240], electron beam melting (EBM)) are slowly but surely attracting the attention of scientists around the globe to exploit their potential to be used as large-scale industrial technique(s) for the production of BMGMCs. Despite the inherent bottlenecks in the AM processes, there have been successful reports about the production of bulk metallic glasses preferentially by selective laser melting (SLM) – form of additive manufacturing involving complete fusion. Various types of glassy structures (e.g. Al [35, 236], Zr [69, 70, 84, 87, 88, 226, 228-230, 247], Fe [62, 238], Ti [248], and Cu [228]) based BMGMCs have been successfully produced using selective laser melting.

As described earlier, it is well known that incipient metal fusion, its transience, progression (movement) and subsequent deposition out of melt pool following metallurgical principles (solute partitioning, alloy diffusion and capillary action to form droplets) follows a layer by layer (LBL) pattern. In this LBL pattern, as top fusion layer traverses its path dictated by CAD geometry fed at back end (.stl file), a heat affected zone (HAZ) is generated preceding the tip of the laser. This HAZ is very much similar to HAZ observed in other fusion welding processes. The metal following it is usually found in the form of solidified fine equiaxed grains. This tendency is a consequence of natural phenomena happening in the fusion layer which results in good glassy structure (high GFA) in bulk metallic glasses provided melt pool temperature is high enough to cause complete melting and heat is rapidly quenched out of making a monolithic glassy structure. This results in the hard-brittle layer. Now, as the complete path in this first layer is traversed, it is descended by few microns (dictated by initial alloy properties and machine parameters), and is supplied with a new layer of metal /alloy powder by the help of scraper/roller. The laser again starts traversing its path based on previously fed CAD pattern. This layer again reaches melting temperature and incipient fusion/melting takes place at laser/metal contact point. However, this time, a unique new phenomenon takes place. As the layer is currently in contact with laser melts, it generates enough heat for the layer beneath it to reach a certain high temperature as well (usually $0.5 T_m$ and $> T_x$). This heating of the lower layer is used to take the alloy back into the nose region of time – temperature – transformation (TTT) diagram which causes its crystallization (solid – solid transformation (devitrification)). Depending on the alloy chemistry and amount of time spent at a temperature above T_x (in the nose region of the curve), there could be (i) complete glassy structure, (ii) partial glassy structure or (iii) complete crystalline structure (no glass). The last is usually meant to be avoided during bulk metallic glass processing and the second is desirable. Some of mechanisms occurring are presented in below figures (Figure 1 - 4).




Figure 1: Schematic time – temperature – transformation diagram for bulk metallic glass matrix composites (indicating cooling rates) of monolithic glass formation as well as thermoplastic forming [59].




Figure 2: Schematic time – temperature – transformation diagram illustrating the processing method of BMG formers [60]. 1) Direct casting, 2) Thermoplastic forming [60].




Figure 3: Actual time – temperature – transformation diagram for $Zr_{58.5}Nb_{12.8}Ni_{12.8}Cu_{15.6}Al_{10.3}$ measured on samples that were cooled from above T_L (blue circles) and heated from below T_g (red squares) prior to isothermal measurement [60].




Figure 4: Actual time – temperature – transformation diagram for $Pd_{43}Ni_{10}Cu_{27}P_{20}$ processed while fluxing in B_2O_3 (squares) or absence of B_2O_3 (circles) [60].

There is, however, a very narrow window of composition and temperature during which complete glass formation or complete crystalline structure formation could be avoided. (a) Only alloys with very high glass forming ability should be selected from the composition perspective and (b) should be tailored to cool with sufficiently high enough cooling rate (could be calculated from exact TTT diagram) which should cause *in-situ* equiaxed ductile phase dendrite or spheroid formation during primary solidification in the first layer retarding the complete glassy state formation. Once, *in-situ* structure is formed, re-heating of the lower layer to a temperature in the nose region of the TTT diagram during devitrification does not have much effect on further crystallization (due to kinetics

(solute partitioning)) provided, it should not be purposefully allowed to stay there for a long time. In the general process, from a fundamental theoretical standpoint, 100% monolithic glassy structure, giving rise to a glassy matrix with fully grown *in-situ* crystalline dendrites does not further undergo transformation to another crystalline phase (as they have already transformed from their metastable glassy state). A powerful impulse on this could be caused by the introduction of carefully selected potent inoculants which are added to alloy melt during the melting stage. These may serve as active nuclei for the preferential heterogeneous nucleation of ductile phase dendrites during primary solidification ensuring the least formation of metastable glassy state which in turn reduces the possibility of conversion of glass to crystallites during subsequent heating of the layer (devitrification stage) as there is no glass (all the metastable or unstable phase have already been transformed to their thermodynamically stable state). No such effort has been made in the past to exploit this unique crystallographic feature of alloying in additive manufacturing. This forms the basis of the present research. Few leading groups in the world have recently produced bulk metallic glasses by additive manufacturing. Some of these is narrated here. Flores, K. M. et. al. [229, 230] successfully studied the effect of heat input on the microstructure of Zr-based BMGs manufactured via LENS[®]. They observed the formation of unique spherulites within the heat affected zone (HAZ) at high laser input (10^4 K/sec) which disappeared as laser power is reduced (Fig – 2) (supporting information). These spherulites bearing unique crystal morphology seem to bypass isothermal cooling microstructures, a phenomenon not observed previously. The same effect was observed in their earlier studies on Cu-based BMGs [228]. In another study, researchers [232] studied the effect of compositionally gradient alloy systems to manufacture BMGs and high entropy alloys (HEAs) composite layers via LENS[®]. They aimed at finding an optimized composition at which the effect of both alloy systems could be obtained in conjunction. Alloy systems consisting of Zr₅₇Ti₁₅Al₁₀Cu₂Ni₈ (BMG) to CoCrFeNiCu_{0.5} (HEA) (first gradient) and TiZrCuNb (BMG) to (TiZrCuNb)₆₅Ni₃₅ (HEA) (second gradient) were used and processed at 400 W, 166 mm/s and 325 W, 21 and 21 mm/s respectively. Using selected area electron diffraction (SAED) patterns, they successfully reported the formation of the fully amorphous region in the first gradient and amorphous matrix/crystalline dendrite composite structure (Fig – 3) in the second gradient in individual melt pools (supporting information). Increasing the speed caused a slight variation in morphology and composition. Their results were consistent with their earlier investigations [231, 249]. However, the effect of reduced power and/or increased speed is needed to validate the glass forming ability of these systems. Zhang, Y, et. al. [70], investigated the effect of laser melting in the form of surface remelting and solid forming on well-known Zr₅₅Cu₃₀Al₁₀Ni₅ hypoeutectic system. They observed that despite the repeated melting of the alloy, four times on its surface (LSM) during a single trace, there was no effect on its glassy state. However, during laser solid forming (LSF), distinct crystallization was observed in the HAZ between adjacent traces and subsequent layers after the first two layers. A series of phase evolution was observed in the deposited microstructure as it moved from molten pool to HAZ in these microstructures, NiZr₂ type nanocrystals and equiaxed dendrites form from rapid solidification during laser surface melting (LSM) whilst Cu₁₀Zr₇ type dendrites form as a result of crystallization of pre-existed nuclei in the already formed amorphous substrate. This paved the way for better understanding and application of LSM and LSF in terms of GFA and crystallization. Another group at the University of Western Australia led by Prof. T. B Sercombe developed Al-based BMGs by SLM [234-236]. They showed that an empirical laser power exists (120W) at which the width and smoothness of the scan track are optimal, i.e. defects (cracks (parallel, perpendicular and at 45° to scan track) and pores) at the edge of the trace are almost eliminated. Crystallization, preferred orientation and melt pool depth was observed to have a direct relationship with laser power whilst pool width was observed to have an inverse relationship. Four distinct regions of scan track (fully crystalline (~100 nm), partially crystalline (~500 nm), boundary between the amorphous bulk metallic glass and bigger crystals and edge of HAZ (no crystal)) were identified. They further studied preferred orientation and found it to be a major effect of devitrification (both by very high laser power (pressure wave) and temperature (oxidation)) as measured by EDS. A few more notable studies have been reported very recently by leading research groups around the globe in which Fe_{68.3}C_{6.9}Si_{2.5}B_{6.7}P_{8.7}Cr_{2.3}Mo_{2.5}Al_{2.1} (at.%) [238],

Fe-Cr-Mo-W-C-Mn-Si-B [250], other Fe-based BMGs [62, 251, 252], Ti–24Nb–4Zr–8Sn [253], other Ti-based BMGs [254], Al₈₅Nd₈Ni₅Co₂ [237], Al-based BMGs [255-258], Zr-based BMGs [69, 70, 84, 259, 260], and biomaterials and implants [261, 262] have been processed by selective laser sintering/selective laser melting (SLS/SLM). The interested reader is referred to cited literature.

7. Research Opportunities

In the present research, an effort has been made to microstructurally control and tune the properties of Zr-based BMGs by controlling the number density (d_c) of a ductile primary phase CuZr-B2 spheroidal intermetallic, its grain size and dispersion within the bulk alloy by conventional and additive manufacturing routes. This novel idea stems from the fact that the inoculation of an otherwise passive melt can cause precipitation of certain specific phases prior to another microstructural change in a solidifying alloy. This effectively can be used for the evolution of preferred phases and therefore can be used to affect the properties of the alloy. It is envisaged that the careful selection of potent inoculants which can best serve as sites for preferential nucleation of ductile phase only can best be used to increase their number density and dispersion within the bulk of the alloy. It has been previously reported that the three-dimensional arrangement of the network of ductile phase equiaxed dendrites or spheroids in bulk alloy can effectively serve as a source of the impediment of shear band motion and can serve as a junction for their multiplication [12, 263]. Further, there are methods by which only high potency inoculants whose crystal structure matches that of the crystal structure of the precipitating phase can be selected preferentially as compared to other inoculants. This is known as “edge-to-edge” matching (E2EM) [101, 102, 264, 265]. Selection of nucleates by this method and then controlled inoculation by them employing careful casting process and controlling its conditions can serve as an effective means for increasing the number density, size and distribution of ductile phase dendrites or spheroids within the bulk. This fact has been successfully exploited in the present research. Following research opportunities are sought after;

1. Production of series of samples by
 - a. Conventional vacuum arc melting and suction casting and
 - b. Additive manufacturing

carrying varying percentages of inoculants. These samples are sought after to study the effect of cooling rate and inoculation on microstructure refinement.

2. Their detailed characterization by employing optical and scanning electron microscopy and qualitative as well as quantitative microstructure analysis of both optical and electron micrographs.
3. Quantitative microscopy by ASTM method 562-11 on optical micrographs.
4. Indentation hardness and drawing of a correlation between hardness and tensile strength.
5. Toughness measurement employing three-point bend test.
6. Development of correlation of crack length with fracture toughness.
7. Detailed tensile testing aimed at not only the measurement of yield strength and tensile strength but also toughness by measuring the area under the stress strain curve.

The studies are meant to increase the toughness of otherwise brittle alloys. These studies are proposed to be the first step of the manufacturing of glassy composites by additive manufacturing.

8. Conclusion

Nucleation and growth phenomena in single component (pure metals), binary and multicomponent alloys are rather well understood. Classical nucleation theory provides many answers to the behaviour of these melts. Bulk metallic glass and their composites are relatively new class of materials which

have recently emerged on the surface of science and technology and gained attention due to their unique properties. Traditionally, they were produced using conventional methods (Cu mould suction casting and twin roll casting) in which their metastable phase (glass) and any *in-situ* ductile precipitates (stable phase) are nucleated based on their ability to surpass the activation energy barrier. In addition, these processes impart very high cooling rate to castings which is essential for retention of supercooled liquid (glass) at room temperature explained by the phenomena of confusion, ordering, frustration and vitrification. Very recently, with the advent and popularity of additive manufacturing, interest has sparked to exploit the inherent and fundamental advantages present in this unique process to produce bulk metallic glasses and their composites. Additive manufacturing techniques are useful in achieving this objective as the very high cooling rate in fusion liquid melt pool is already present inherently to assist the formation of a glassy structure which is suppression of “kinetics” and prolonging of undercooling (“thermodynamics”) two main phenomena responsible for any phase transformation. However, *in-situ* nucleation of primary phase equiaxed dendrites or spherulites during solidification and then microstructural evolution (*solute diffusion* and *capillary assisted*) is not well understood till date. A huge gap exists in literature as to how the ductility and toughness of these materials can be improved. Solidification techniques aimed at improvement of microstructure and grain refinement are proposed to be the best possible answers. Inoculation, which is a well established foundry technique is proposed to be exploited as potential bottleneck removal. A step by step method is described aimed at the design of new nucleates by understanding the basic crystal structure and chemistry of evolving ductile phase. Edge to edge matching method is proposed as a solution strategy. These inoculants are introduced carefully during melting and subsequent solidification in both conventional Cu mold suction casting and additive manufacturing process. Careful control of processing conditions along with a certain specific amount (percentage) of inoculants is proposed to enhance the mechanical properties. Microstructural qualification is done by detailed qualitative and quantitative optical and electron microscopy along with hardness measurement. Tensile testing and measurement of toughness are also aimed at by measuring the area under the curve. It is hypothesized that this methodology (solidification processing) will serve as best possible solution to improve the long standing debate about ductility and toughness of bulk metallic glasses and their composites manufactured either by Cu mold suction casting or modern additive manufacturing.

Supporting Information

1. General limitations and research gap

Although various efforts have been made and success stories have been reported which aim at finally achieving increased ductility to a certain extent, still, in most cases, brittle intermetallic form and deteriorate over time mechanical properties. Despite advances and triumphs, there are still a number of unresolved issues from processing (chemistry, physics, metallurgy and engineering (tooling, machinery)), structure (phase identification and their behaviour), properties (mechanical, physical and functional) viewpoint which limits their application, further use in more advanced applications, commercialization and large-scale production. For example, as described earlier, despite being able to be produced in bulk form, still, the largest ingot casted as the bulk metallic glass is just 80 mm in diameter and 100 mm in length [45]. Liquidmetal Technologies® has been able to produce various types of shapes in “cast” form but these are formed by adopting very expensive tooling and are very thin in their profiles [60]. There are very few successful efforts to make parts with tensile strength greater than 980 MPa in Al-based BMGs [266]. Despite its advantages, twin roll casting remains a novice technique for manufacturing of BMGs of all types. Only Ti-based BMGs could be produced with ease because of their increased fluidity. Zr-based BMGs still has the biggest limitation for large-scale production as these are viscous and their transformations are sluggish because of suppressed kinetics. There is very little effort on the functional use of BMGs [267]. Reproducibility of these alloys is another outstanding debate and contradictions exist about their behaviour from laboratory to laboratory. The effect of microstructural control parameters and their tuning with a variety of materials and physical parameters is not known. Lastly, additive manufacturing [83, 268], though

promising technique and presently being named as “future” has serious drawbacks (microstructure, modelling, metallurgy, mechanical properties, anisotropy) for the use of Al- [63], Fe- [57, 71, 238, 269], Ti- [254, 262] and Zr-based [69, 70, 87, 226, 229, 230] bulk metallic glasses and their composites.




Figure 5: (a) SEM backscattered electron image of *in-situ* composite microstructure (x 200) (b) shear band pattern array from failed surface showing their crossing dendrites [12].




Figure 6: Cross-sectional backscattered SEM images of laser-deposited layers on the amorphous substrates processed at a laser power of 150 W. (a) and (b) Microstructures obtained at a laser travel speed of 14.8 mm/s. The featureless melt zone is shown in (a) surrounded by a crystalline heat affected zone (HAZ), and the isolated spherulites of the heat affected zone (HAZ) are shown in (b). (c) Increasing the laser travel speed to 21.2 mm/s reduced the formation of the HAZ to only a few isolated spherulites [229].




Figure 7: (a) TEM BF image of the laser surface melted region processed with a laser power of 325 W and a travel speed of 83 mm/s and (b) TEM BF image with the corresponding electron diffraction pattern of the crystalline dendrite (lower left inset) and amorphous matrix (upper right inset) [232].

References

- [1] Telford, M., The case for bulk metallic glass. *Materials Today*, 2004. 7(3): p. 36-43.
- [2] Schuh, C.A., T.C. Hufnagel, and U. Ramamurty, Mechanical behavior of amorphous alloys. *Acta Materialia*, 2007. 55(12): p. 4067-4109.
- [3] Inoue, A. and A. Takeuchi, Recent developments and application products of bulk glassy alloys. *Acta Materialia*, 2011. 59(6): p. 2243-2267.
- [4] Klement, W., R.H. Willens, and T.L. Duwez, Non-crystalline Structure in Solidified Gold-Silicon Alloys. *Nature*, 1960. 187(4740): p. 870-870.
- [5] Chen, H.S., Thermodynamic considerations on the formation and stability of metallic glasses. *Acta Metallurgica*, 1974. 22(12): p. 1505-1511.
- [6] Drehman, A.J., A.J. Greer, and D. Turnbull, Bulk formation of a metallic glass: Pd₄₀Ni₄₀P₂₀. *Applied Physics Letters*, 1981. 41(8): p. 716-717.
- [7] Kui, H.W., A.L. Greer, and D. Turnbull, Formation of bulk metallic glass by fluxing. *Applied Physics Letters*, 1984. 44(6): p. 615-616.
- [8] Wang, W.H., C. Dong, and C.H. Shek, Bulk metallic glasses. *Materials Science and Engineering: R: Reports*, 2004. 44(2-3): p. 45-89.
- [9] Chen, Y.Q. and E. Ma, Atomic-level structure and structure-property relationship in metallic glasses. *Progress in Materials Science*, 2011. 56(4): p. 379-473.
- [10] Qiao, J., H. Jia, and P.K. Liaw, Metallic glass matrix composites. *Materials Science and Engineering: R: Reports*, 2016. 100: p. 1-69.
- [11] Trexler, M.M. and N.N. Thadhani, Mechanical properties of bulk metallic glasses. *Progress in Materials Science*, 2010. 55(8): p. 759-839.
- [12] Hays, C.C., C.P. Kim, and W.L. Johnson, Microstructure Controlled Shear Band Pattern Formation and Enhanced Plasticity of Bulk Metallic Glasses Containing *in situ* Formed Ductile Phase Dendrite Dispersions. *Physical Review Letters*, 2000. 84(13): p. 2901-2904.
- [13] Hofmann, D.C., et al., Designing metallic glass matrix composites with high toughness and tensile ductility. *Nature*, 2008. 451(7182): p. 1085-1089.

- [14] Hofmann, D.C., Shape Memory Bulk Metallic Glass Composites. *Science*, 2010. 329(5997): p. 1294-1295.
- [15] Wu, Y., et al., Designing Bulk Metallic Glass Composites with Enhanced Formability and Plasticity. *Journal of Materials Science & Technology*, 2014. 30(6): p. 566-575.
- [16] Guo, H., et al., Tensile ductility and necking of metallic glass. *Nat Mater*, 2007. 6(10): p. 735-739.
- [17] Jang, D. and J.R. Greer, Transition from a strong-yet-brittle to a stronger-and-ductile state by size reduction of metallic glasses. *Nat Mater*, 2010. 9(3): p. 215-219.
- [18] Choi—Yim, H., Synthesis and Characterization of Bulk Metallic Glass Matrix Composites. 1998, California Institute of Technology.
- [19] Choi-Yim, H., et al., Processing, microstructure and properties of ductile metal particulate reinforced Zr57Nb5Al10Cu15.4Ni12.6 bulk metallic glass composites. *Acta Materialia*, 2002. 50(10): p. 2737-2745.
- [20] Lee, M.L., Y. Li, and C.A. Schuh, Effect of a controlled volume fraction of dendritic phases on tensile and compressive ductility in La-based metallic glass matrix composites. *Acta Materialia*, 2004. 52(14): p. 4121-4131.
- [21] Pauly, S., et al., Transformation-mediated ductility in Cu-Zr-based bulk metallic glasses. *Nat Mater*, 2010. 9(6): p. 473-477.
- [22] Wu, Y., et al., Bulk Metallic Glass Composites with Transformation-Mediated Work-Hardening and Ductility. *Advanced Materials*, 2010. 22(25): p. 2770-2773.
- [23] Song, K.K., et al., Triple yielding and deformation mechanisms in metastable Cu47.5Zr47.5Al5 composites. *Acta Materialia*, 2012. 60(17): p. 5990-6012.
- [24] Wu, D.Y., et al., Glass-forming ability, thermal stability of B2 CuZr phase, and crystallization kinetics for rapidly solidified Cu—Zn alloys. *Journal of Alloys and Compounds*, 2016. 664: p. 99-108.
- [25] Kim, C.P., et al., Realization of high tensile ductility in a bulk metallic glass composite by the utilization of deformation-induced martensitic transformation. *Scripta Materialia*, 2011. 65(4): p. 304-307.
- [26] Gao, W.-h., et al., Effect of Co and Al addition on martensitic transformation and microstructure in ZrCu-based shape memory alloys. *Transactions of Nonferrous Metals Society of China*, 2015. 25(5): p. 850-855.
- [27] Zhai, H., H. Wang, and F. Liu, A strategy for designing bulk metallic glass composites with excellent work-hardening and large tensile ductility. *Journal of Alloys and Compounds*, 2016. 664: p. 322-330.
- [28] Song, W., et al., Microstructural Control via Copious Nucleation Manipulated by In Situ Formed Precipitates: Large-Sized and Ductile Metallic Glass Composites. *Advanced Materials*, 2016: p. n/a-n/a.
- [29] Pekarskaya, E., C.P. Kim, and W.L. Johnson, In situ transmission electron microscopy studies of shear bands in a bulk metallic glass based composite. *Journal of Materials Research*, 2001. 16(09): p. 2513-2518.
- [30] Zhang, Q., Haifeng Zhang, Zhengwang Zhu, Zhuangqi Hu, Formation of High Strength In-situ Bulk Metallic Glass Composite with Enhanced Plasticity in Cu50Zr47.5Ti2.5 Alloy. *Materials Transactions*, 2005. 46(3): p. 730 - 733.
- [31] Zhu, Z., et al., Ta-particulate reinforced Zr-based bulk metallic glass matrix composite with tensile plasticity. *Scripta Materialia*, 2010. 62(5): p. 278-281.

- [32] Fan, C., R.T. Ott, and T.C. Hufnagel, Metallic glass matrix composite with precipitated ductile reinforcement. *Applied Physics Letters*, 2002. 81(6): p. 1020-1022.
- [33] Hu, X., et al., Glass forming ability and in-situ composite formation in Pd-based bulk metallic glasses. *Acta Materialia*, 2003. 51(2): p. 561-572.
- [34] Cheng, J.-L., et al., Innovative approach to the design of low-cost Zr-based BMG composites with good glass formation. *Scientific Reports*, 2013. 3: p. 2097.
- [35] Wu, F.F., et al., Effect of annealing on the mechanical properties and fracture mechanisms of a $\text{Zr}_{56.2}\text{Ti}_{13.8}\text{Nb}_{5.0}\text{Cu}_{6.9}\text{Ni}_{5.6}\text{Be}_{12.5}$ bulk-metallic-glass composite. *Physical Review B*, 2007. 75(13): p. 134201.
- [36] Chen, H.S., Ductile-brittle transition in metallic glasses. *Materials Science and Engineering*, 1976. 26(1): p. 79-82.
- [37] Antonione, C., et al., Phase separation in multicomponent amorphous alloys. *Journal of Non-Crystalline Solids*, 1998. 232–234: p. 127-132.
- [38] Fan, C., C. Li, and A. Inoue, Nanocrystal composites in Zr–Nb–Cu–Al metallic glasses. *Journal of Non-Crystalline Solids*, 2000. 270(1–3): p. 28-33.
- [39] Fan, C. and A. Inoue, Ductility of bulk nanocrystalline composites and metallic glasses at room temperature. *Applied Physics Letters*, 2000. 77(1): p. 46-48.
- [40] Basu, J., et al., Microstructure and mechanical properties of a partially crystallized La-based bulk metallic glass. *Philosophical Magazine*, 2001. 83(15): p. 1747-1760.
- [41] Fan, C., et al., Properties of as-cast and structurally ordered Zr-based bulk metallic glasses. *Journal of Non-Crystalline Solids*, 2006. 354(1–2): p. 174-179.
- [42] Gu, J., et al., Effects of annealing on the hardness and elastic modulus of a $\text{Cu}_{36}\text{Zr}_{48}\text{Al}_{18}\text{Ag}_8$ bulk metallic glass. *Materials & Design*, 2011. 47: p. 706-710.
- [43] Tan, J., et al., Correlation between Internal States and Strength in Bulk Metallic Glass, in *PRICM*. 2013, John Wiley & Sons, Inc., p. 3199-3206.
- [44] Krämer, L., et al., Production of Bulk Metallic Glasses by Severe Plastic Deformation. *Metals*, 2015. 5(2): p. 720-726.
- [45] Nishiyama, N., et al., The world's biggest glassy alloy ever made. *Intermetallics*, 2012. 30: p. 19-24.
- [46] Inoue, A., N. Nishiyama, and T. Matsuda, Preparation of Bulk Glassy $\text{Pd}_{40}\text{Ni}_{10}\text{Cu}_{30}\text{P}_{20}$ Alloy of 40 mm Diameter by Water Quenching. *Materials Transactions, JIM*, 1996. 37(2): p. 181-184.
- [47] He, Y., B. Schwarz, and J.I. Archuleta, Bulk glass formation in the Pd–Ni–P system. *Applied Physics Letters*, 1996. 69(13): p. 1861-1863.
- [48] Inoue, A., T. Zhang, and T. Masumoto, Zr–Al–Ni Amorphous Alloys with High Glass Transition Temperature and Significant Supercooled Liquid Region. *Materials Transactions, JIM*, 1990. 31(3): p. 177-183.
- [49] Peker, A. and W.L. Johnson, A highly processable metallic glass: $\text{Zr}_{41.2}\text{Ti}_{13.8}\text{Cu}_{12.5}\text{Ni}_{10.0}\text{Be}_{22.5}$. *Applied Physics Letters*, 1993. 63(17): p. 2342-2344.
- [50] Tan, J., et al., Study of mechanical property and crystallization of a ZrCoAl bulk metallic glass. *Intermetallics*, 2011. 19(4): p. 567-571.

- [51] Biffi, C.A., A. Figini Albisetti, and A. Tuissi. CuZr based shape memory alloys: effect of Cr and Co on the martensitic transformation. in *Materials Science Forum*. 2013. Trans Tech Publ.
- [52] Cheng, J.L. and G. Chen, Glass formation of Zr–Cu–Ni–Al bulk metallic glasses correlated with $L \rightarrow \text{Zr}_2\text{Cu} + \text{ZrCu}$ pseudo binary eutectic reaction. *Journal of Alloys and Compounds*, 2013. 577: p. 451-455.
- [53] Chen, G., et al., Enhanced plasticity in a Zr-based bulk metallic glass composite with in situ formed intermetallic phases. *Applied Physics Letters*, 2009. 95(8): p. 081908.
- [54] Jeon, C., et al., Effects of Effective Dendrite Size on Tensile Deformation Behavior in Ti-Based Dendrite-Containing Amorphous Matrix Composites Modified from Ti-6Al-4V Alloy. *Metallurgical and Materials Transactions A*, 2015. 46(1): p. 235-250.
- [55] Chu, M.Y., et al., Quasi-static and dynamic deformation behaviors of an in-situ Ti-based metallic glass matrix composite. *Journal of Alloys and Compounds*, 2015. 640: p. 305-311.
- [56] Wang, Y.S., et al., The role of the interface in a Ti-based metallic glass matrix composite with in situ dendrite reinforcement. *Surface and Interface Analysis*, 2014. 46(5): p. 293-298.
- [57] Gibson, I., W.D. Rosen, and B. Stucker, Development of Additive Manufacturing Technology, in *Additive Manufacturing Technologies: Rapid Prototyping and Direct Digital Manufacturing*. 2010, Springer US: Boston, MA. p. 36-58.
- [58] Spears, T.G. and S.A. Gold, In-process sensing in selective laser melting (SLM) additive manufacturing. *Integrating Materials and Manufacturing Innovation*, 2016. 5(1): p. 1-25.
- [59] Pauly, S., et al., Processing metallic glasses by selective laser melting. *Materials Today*, 2013. 16(1-2): p. 37-41.
- [60] Schroers, J., Processing of Bulk Metallic Glasses. *Advanced Materials*, 2010. 22(14): p. 1566-1597.
- [61] Li, X.P., et al., Selective laser melting of Zr-based bulk metallic glasses: Processing, microstructure and mechanical properties. *Materials & Design*, 2016. 112: p. 217-226.
- [62] Zheng, B., et al., Processing and Properties of Fe-Based Metallic Glass Components via Laser-Engineered Net Shaping. *Metallurgical and Materials Transactions A*, 2009. 40(5): p. 1235-1245.
- [63] Olakanmi, E.O., R.F. Cochrane, and K.W. Dalgarno, A review on selective laser sintering/melting (SLS/SLM) of aluminium alloy powders: Processing, microstructure, and properties. *Progress in Materials Science*, 2015. 74: p. 401-477.
- [64] Buchbinder, L. et al., High Power Selective Laser Melting (HP SLM) of Aluminum Parts. *Physics Procedia*, 2011. 12: p. 271-278.
- [65] Li, Y., and D. Gu, Thermal behavior during selective laser melting of commercially pure titanium powder: Numerical simulation and experimental study. *Additive Manufacturing*, 2014. 1-4: p. 109.
- [66] Yap, C.Y., et al., Review of selective laser melting: Materials and applications. *Applied Physics Reviews*, 2015. 2(4): p. 041101.
- [67] Romano, J., et al., Temperature distribution and melt geometry in laser and electron-beam melting processes – A comparison among common materials. *Additive Manufacturing*, 2015. 8: p. 1-11.
- [68] Sun, H. and K.M. Flores, Microstructural Analysis of a Laser-Processed Zr-Based Bulk Metallic Glass. *Metallurgical and Materials Transactions A*, 2010. 41(7): p. 1752-1757.

- [69] Yang, G., et al., Laser solid forming Zr-based bulk metallic glass. *Intermetallics*, 2012. 22: p. 110-115.
- [70] Zhang, Y., et al., Microstructural analysis of Zr55Cu30Al10Ni5 bulk metallic glasses by laser surface remelting and laser solid forming. *Intermetallics*, 2015. 66: p. 22-30.
- [71] Frazier, W.E., Metal Additive Manufacturing: A Review. *Journal of Materials Engineering and Performance*, 2014. 23(6): p. 1917-1928.
- [72] Wong, K.V. and A. Hernandez, A Review of Additive Manufacturing. *ISRN Mechanical Engineering*, 2012. 2012: p. 10.
- [73] Travitzky, N., et al., Additive Manufacturing of Ceramic-Based Materials. *Advanced Engineering Materials*, 2014. 16(6): p. 729-754.
- [74] Baufeld, B., E. Brandl, and O. van der Biest, Wire based additive layer manufacturing: Comparison of microstructure and mechanical properties of Ti-6Al-4V components fabricated by laser-beam deposition and shaped metal deposition. *Journal of Materials Processing Technology*, 2011. 211(6): p. 1146-1158.
- [75] Chen, Y., C. Zhou, and J. Lao, A layerless additive manufacturing process based on CNC accumulation. *Rapid Prototyping Journal*, 2011. 17(3): p. 211-227.
- [76] Kawahito, Y., et al., High-power fiber laser welding and its application to metallic glass Zr55Al10Ni5Cu30. *Materials Science and Engineering: B*, 2008. 154(1-3): p. 105-109.
- [77] Kim, J.H., et al., Pulsed Nd:YAG laser welding of Cu54Ni6Zr22Ti18 bulk metallic glass. *Materials Science and Engineering: A*, 2007. 449(1-5): p. 872-875.
- [78] Li, B., et al., Laser welding of Zr45Cu48Al7 bulk metallic glassy alloy. *Journal of Alloys and Compounds*, 2006. 413(1-2): p. 118-121.
- [79] Wang, G., et al., Laser welding of Ti40Cr25Ni30Cu12Be20 bulk metallic glass. *Materials Science and Engineering: A*, 2010. 528(1): p. 31-37.
- [80] Wang, H.S., et al., Combination of a Nd:YAG laser and a liquid cooling device to (Zr53Cu30Ni9Al8)Si0.5 bulk metallic glasses welding. *Materials Science and Engineering: A*, 2010. 528(1): p. 338-341.
- [81] Wang, H.-S., et al., The effects of initial welding temperature and welding parameters on the crystallization behaviors of laser spot welded Zr-based bulk metallic glass. *Materials Chemistry and Physics*, 2011. 129(1): p. 547-552.
- [82] Acharya, R. and S. Das, Additive Manufacturing of IN100 Superalloy Through Scanning Laser Epitaxy for Turbine Engine Hot-Section Component Repair: Process Development, Modeling, Microstructural Characterization, and Process Control. *Metallurgical and Materials Transactions a-Physical Metallurgy and Materials Science*, 2015. 46a(9): p. 3864-3875.
- [83] Samuel, W.J., et al., The metallurgy and processing science of metal additive manufacturing. *International Materials Reviews*, 2016. 61(5): p. 315-360.
- [84] Harooni, A., et al., Processing window development for laser cladding of zirconium on zirconium alloy. *Journal of Materials Processing Technology*, 2016. 230: p. 263-271.
- [85] Wu, X. and Y. Hong, Fe-based thick amorphous-alloy coating by laser cladding. *Surface and Coatings Technology*, 2001. 141(2-3): p. 141-144.
- [86] Wu, X., B. Xu, and Y. Hong, Synthesis of thick Ni66Cr5Mo4Zr6P15B4 amorphous alloy coating and large glass-forming ability by laser cladding. *Materials Letters*, 2002. 56(5): p. 838-841.

- [87] Yue, T.M. and Y.P. Su, Laser cladding of SiC reinforced Zr65Al7.5Ni10Cu17.5 amorphous coating on magnesium substrate. *Applied Surface Science*, 2008. 255(5, Part 1): p. 1692-1698.
- [88] Yue, T.M., Y.P. Su, and H.O. Yang, Laser cladding of Zr65Al7.5Ni10Cu17.5 amorphous alloy on magnesium. *Materials Letters*, 2007. 61(1): p. 209-212.
- [89] Zhang, P., et al., Synthesis of Fe–Ni–B–Si–Nb amorphous and crystalline composite coatings by laser cladding and remelting. *Surface and Coatings Technology*, 2011. 206(6): p. 1229-1236.
- [90] Zhu, Q., et al., Synthesis of Fe-based amorphous composite coatings with low purity materials by laser cladding. *Applied Surface Science*, 2007. 253(17): p. 7060-7064.
- [91] Lan, S., et al., Structural crossover in a supercooled metallic liquid and the link to a liquid-to-liquid phase transition. *Applied Physics Letters*, 2016. 108(21): p. 211907.
- [92] Zu, F.-Q., Temperature-Induced Liquid-Liquid Transition in Metallic Melts: A Brief Review on the New Physical Phenomenon. *Metals*, 2015. 5(1): p. 395.
- [93] Wei, S., et al., Liquid–liquid transition in a strong bulk metallic glass-forming liquid. *Nat Commun*, 2013. 4.
- [94] Song, K.K., et al., Strategy for pinpointing the formation of B2 CuZr in metastable CuZr-based shape memory alloys. *Acta Materialia*, 2011. 59(17): p. 6620–6630.
- [95] Wu, Y., et al., Formation of Cu–Zr–Al bulk metallic glass composites with improved tensile properties. *Acta Materialia*, 2011. 59(8): p. 2928-2936.
- [96] Song, K.K., et al., Thermal stability and mechanical properties of Cu46Zr46Ag8 bulk metallic glass and its composites. *Materials Science and Engineering: A*, 2013. 559(Supplement C): p. 711-718.
- [97] Liu, Z., et al., Pronounced ductility in CuZr primary bulk metallic glass composites with optimized microstructure through melt adjustment. *APL Advances*, 2012. 2(3): p. 032176.
- [98] Liu, Z., et al., Microstructural tailoring and improvement of mechanical properties in CuZr-based bulk metallic glass composite. *Acta Materialia*, 2012. 60(6): p. 3128-3139.
- [99] Song, K.K., et al., Effect of Ta particles on the microstructure and mechanical properties of metastable Cu47.5Zr47.5Al5 alloy. *Materials Science and Engineering: A*, 2013. 587(Supplement C): p. 372-380.
- [100] Liu, Z.Q., H. Wang, and T. Zhang, Bulk metallic glass composites ductilized by core–shell structured dual crystalline phases through controlled inoculation. *Intermetallics*, 2014. 45(Supplement C): p. 24-28.
- [101] Kelly, M. and M.-X. Zhang, Edge-to-edge matching—The fundamentals. *Metallurgical and Materials Transactions A*, 2006. 37(3): p. 833-839.
- [102] Kelly, M. and M.-X. Zhang, Edge-to-edge matching—a new approach to the morphology and crystallography of precipitates. in *Materials Forum*. 1999.
- [103] Taylor, H.F., *Foundry engineering*. 1959: Wiley.
- [104] Heine, R.W., C.R. Loper, and P.C. Rosenthal, *Principles of Metal Casting*. 1955: McGraw-Hill.
- [105] Flemings, M.C., *Solidification Processing*. 1974: McGraw-Hill.
- [106] Greer, A.L., *Metallic Glasses*. *Science*, 1995. 267(5206): p. 1947-1953.
- [107] Güntherodt, H.J., *Metallic glasses*, in *Festkörperprobleme 17: Plenary Lectures of the Divisions “Semiconductor Physics” “Metal Physics” “Low Temperature Physics” “Thermodynamics and Statistical Physics” “Crystallography” “Magnetism” “Surface Physics” of the German Physical Society Münster*, March 7–12, 1977, J. Treusch, Editor. 1977, Springer Berlin Heidelberg: Berlin, Heidelberg. p. 25-53.

- [108] Inoue, A., High Strength Bulk Amorphous Alloys with Low Critical Cooling Rates (<I>Overview</I>). Materials Transactions, JIM, 1995. 36(7): p. 866-875.
- [109] Johnson, W.L., Bulk Glass-Forming Metallic Alloys: Science and Technology. MRS Bulletin, 1999. 24(10): p. 42-56.
- [110] Matthieu, M., Relaxation and physical aging in network glasses: a review. Reports on Progress in Physics, 2016. 79(6): p. 066504.
- [111] Hofmann, D.C. and W.L. Johnson. Improving Ductility in Nanostructured Materials and Metallic Glasses: "Three Laws". in Materials Science Forum. 2010. Trans Tech Publ.
- [112] Shi, Y. and M.L. Falk, Does metallic glass have a backbone? The role of percolating short range order in strength and failure. Scripta Materialia, 2006. 54(3): p. 381-386.
- [113] Mattern, N., et al., Short-range order of Cu-Zr metallic glasses. Journal of Alloys and Compounds, 2009. 485(1-2): p. 163-169.
- [114] Jiang, M.Q. and L.H. Dai, Short-range-order effects on intrinsic plasticity of metallic glasses. Philosophical Magazine Letters, 2010. 90(4): p. 269-277.
- [115] Zhang, F., et al., Composition-dependent stability of the medium-range order responsible for metallic glass formation. Acta Materialia, 2014. 81: p. 337-344.
- [116] Sheng, H.W., et al., Atomic packing and short-to-medium-range order in metallic glasses. Nature, 2006. 439(7075): p. 419-425.
- [117] Cheng, Y.Q., E. Ma, and H.W. Sheng, Atomic Level Structure in Multicomponent Bulk Metallic Glass. Physical Review Letters, 2009. 103(24): p. 245501.
- [118] Nelson, D.R., Order, frustration, and defects in liquid-like glasses. Physical Review B, 1983. 28(10): p. 5515-5535.
- [119] Ma, E., Tuning order in disorder. Nat Mater, 2015. 14(6): p. 547-552.
- [120] Greer, A.L., Confusion by design. Nature, 1993. 366(6453): p. 303-304.
- [121] Guo, S.F., et al., Fe-based bulk metallic glasses: Brittle or ductile? Applied Physics Letters, 2014. 105(16): p. 161801.
- [122] Gu, X.J., S.J. Poon, and J. Shiflet, Mechanical properties of iron-based bulk metallic glasses. Journal of Materials Research, 2007. 22(2): p. 344-351.
- [123] Xi, X.K., et al., Fracture of Brittle Metallic Glasses: Brittleness or Plasticity. Physical Review Letters, 2005. 94(12): p. 125510.
- [124] Chen, H.-H. and C.-K. Tsai, The Microstructural Evolution and Mechanical Properties of Zr-Based Metallic Glasses under Different Strain Rate Compressions. Materials, 2015. 8(4): p. 1831.
- [125] Xu, J., et al., Deformation and failure behavior of a hydrostatically extruded Zr₃₈Ti₁₇Cu_{10.5}Co₁₂Be_{22.5} bulk metallic glass/porous tungsten phase composite under dynamic compression. Composites Science and Technology, 2008. 68(15-16): p. 3396-3400.
- [126] Chen, H.S., Plastic flow in metallic glasses under compression. Scripta Metallurgica, 1973. 7(9): p. 931-935.
- [127] Flores, K.M. and R.H. Dauskardt, Fracture and deformation of bulk metallic glasses and their composites. Intermetallics, 2004. 12(7-9): p. 1025-1029.
- [128] Lowhaphandu, P. and J.J. Lewandowski, Fracture toughness and notched toughness of bulk amorphous alloy: Zr-Ti-Ni-Cu-Be. Scripta Materialia, 1998. 38(12): p. 1811-1817.
- [129] Lowhaphandu, P., et al., Deformation and fracture toughness of a bulk amorphous Zr-Ti-Ni-Cu-Be alloy. Intermetallics, 2000. 8(5-6): p. 487-492.

- [130] Conner, R.D., et al., Fracture toughness determination for a beryllium-bearing bulk metallic glass. *Scripta Materialia*, 1997. 37(9): p. 1373-1378.
- [131] Gilbert, C.J., R.O. Ritchie, and W.L. Johnson, Fracture toughness and fatigue-crack propagation in a Zr-Ti-Ni-Cu-Be bulk metallic glass. *Applied Physics Letters*, 1997. 71(4): p. 476-478.
- [132] Xu, J., U. Ramamurty, and E. Ma, The fracture toughness of bulk metallic glasses. *JOM*, 2010. 62(4): p. 10-18.
- [133] Kimura, H. and T. Masumoto, Fracture toughness of amorphous metals. *Scripta Metallurgica*, 1975. 9(3): p. 211-221.
- [134] Chen, M., Mechanical Behavior of Metallic Glasses: Microscopic Understanding of Strength and Ductility. *Annual Review of Materials Research*, 2008. 38(1): p. 445-469.
- [135] Hufnagel, T.C., C.A. Schuh, and M.L. Falk, Deformation of metallic glasses: Recent developments in theory, simulations, and experiments. *Acta Materialia*, 2016. 109: p. 375-393.
- [136] Sarac, B. and J. Schroers, Designing tensile ductility in metallic glasses. *Nature Communications*, 2013. 4: p. 2158.
- [137] Ritchie, R.O., The conflicts between strength and toughness. *Acta Mater*, 2001. 10(11): p. 817-822.
- [138] Wada, T., A. Inoue, and A.L. Greer, Enhancement of room-temperature plasticity in a bulk metallic glass by finely dispersed porosity. *Applied Physics Letters*, 2005. 86(25): p. 251907.
- [139] Donovan, P.E. and W.M. Stobbs, Shear band interactions with crystals in partially crystallised metallic glasses. *Journal of Non-Crystalline Solids*, 1982. 55(1): p. 61-76.
- [140] Leng, Y. and T.H. Courtney, Multiple shear band formation in metallic glasses in composites. *Journal of Materials Science*, 1991. 26(3): p. 558-591.
- [141] Liu, L.F., et al., Behavior of multiple shear bands in Zr-based bulk metallic glass. *Materials Chemistry and Physics*, 2000. 93(1): p. 174-177.
- [142] Huang, R., et al., Inhomogeneous deformation in metallic glasses. *Journal of the Mechanics and Physics of Solids*, 2002. 50(5): p. 1011-1027.
- [143] Spaepen, F., A microscopic mechanism for steady state inhomogeneous flow in metallic glasses. *Acta Metallurgica*, 1977. 25(4): p. 407-415.
- [144] Steif, P.S., F. Spaepen, and J.W. Hutchinson, Strain localization in amorphous metals. *Acta Metallurgica*, 1982. 30(3): p. 447-455.
- [145] Flores, M., Structural changes and stress state effects during inhomogeneous flow of metallic glasses. *Scripta Materialia*, 2006. 54(3): p. 327-332.
- [146] Donovan, P.E. and W.M. Stobbs, The structure of shear bands in metallic glasses. *Acta Metallurgica*, 1981. 29(8): p. 1419-1436.
- [147] Li, N., W. Chen, and L. Liu, Thermoplastic Micro-Forming of Bulk Metallic Glasses: A Review. *JOM*, 2016. 68(4): p. 1246-1261.
- [148] Sarac, B., et al., Three-Dimensional Shell Fabrication Using Blow Molding of Bulk Metallic Glass. *Journal of Microelectromechanical Systems*, 2011. 20(1): p. 28-36.
- [149] Schroers, J., The superplastic forming of bulk metallic glasses. *JOM*, 2005. 57(5): p. 35-39.
- [150] Dandliker, R.B., R.D. Conner, and W.L. Johnson, Melt infiltration casting of bulk metallic-glass matrix composites. *Journal of Materials Research*, 1998. 13(10): p. 2896-2901.

- [151] Jiang, Y. and K. Qiu, Computational micromechanics analysis of toughening mechanisms of particle-reinforced bulk metallic glass composites. *Materials & Design* (1980-2015), 2015. 65: p. 410-416.
- [152] Sun, Y.F., et al., Formation, thermal stability and deformation behavior of graphite-flakes reinforced Cu-based bulk metallic glass matrix composites. *Materials Science and Engineering: A*, 2006. 435–436: p. 132-138.
- [153] Conner, R.D., R.B. Dandliker, and W.L. Johnson, Mechanical properties of tungsten and steel fiber reinforced Zr_{41.25}Ti_{13.75}Cu_{12.5}Ni₁₀Be_{22.5} metallic glass matrix composites. *Acta Materialia*, 1998. 46(17): p. 6089-6102.
- [154] Lee, K., et al., Direct observation of microfracture process in metallic-continuous fiber-reinforced amorphous matrix composites fabricated by liquid pressing process. *Materials Science and Engineering: A*, 2010. 527(4–5): p. 941-946.
- [155] Wadhwa, P., J. Heinrich, and R. Busch, Processing of copper fiber reinforced Zr_{41.2}Ti_{13.8}Cu_{12.5}Ni_{10.0}Be_{22.5} bulk metallic glass composites. *Scripta Materialia*, 2007. 56(1): p. 73-76.
- [156] Cytron, S.J., A metallic glass-metal matrix composite. *Journal of Materials Science Letters*, 1982. 1(5): p. 211-213.
- [157] Deng, S.T., et al., Metallic glass fiber-reinforced Cu-based bulk metallic glass. *Scripta Materialia*, 2011. 64(1): p. 85-88.
- [158] Wang, Z., et al., Microstructure and mechanical behavior of metallic glass fiber-reinforced Al alloy matrix composites. *Scientific Reports*, 2016. 6: p. 24384.
- [159] Jiang, J.-Z., et al., Low-Density High-Strength Bulk Metallic Glasses and Their Composites: A Review. *Advanced Engineering Materials*, 2015. 17(6): p. 761-780.
- [160] Qiao, J., In-situ Dendrite/Metallic Glass Matrix Composites: A Review. *Journal of Materials Science & Technology*, 2013. 29(6): p. 685-701.
- [161] Freed, R.L. and J.B. Vanderhoff, Effects of devitrification on the mechanical properties of Cu₄₆Zr₅₄ metallic glass. *Metallurgical Transactions A*, 1979. 10(11): p. 1621-1626.
- [162] Akhtar, D. and R.D.K. Misra, Effect of thermal relaxation on diffusion in a metallic glass. *Scripta Metallurgica*, 1980. 20(5): p. 627-631.
- [163] Liu, C., E. Pineda, and D. Crespo, Mechanical Relaxation of Metallic Glasses: An Overview of Experimental Data and Theoretical Models. *Metals*, 2015. 5(2): p. 1073.
- [164] Qiao, J.C. and M. Pernetier, Dynamic Mechanical Relaxation in Bulk Metallic Glasses: A Review. *Journal of Materials Science & Technology*, 2014. 30(6): p. 523-545.
- [165] Tiller, R.E. and F. Spaepen, The kinetics of structural relaxation of a metallic glass. *Acta Metallurgica*, 1980. 28(12): p. 1781-1788.
- [166] Greer, A.L., Y.Q. Cheng, and E. Ma, Shear bands in metallic glasses. *Materials Science and Engineering: R: Reports*, 2013. 74(4): p. 71-132.
- [167] Gludovatz, B., et al., Size-dependent fracture toughness of bulk metallic glasses. *Acta Materialia*, 2014. 70: p. 198-207.
- [168] Ogata, S., et al., Atomistic simulation of shear localization in Cu–Zr bulk metallic glass. *Intermetallics*, 2006. 14(8–9): p. 1033-1037.
- [169] Packard, C.E. and C.A. Schuh, Initiation of shear bands near a stress concentration in metallic glass. *Acta Materialia*, 2007. 55(16): p. 5348-5358.

- [170] Pampillo, C.A., Localized shear deformation in a glassy metal. *Scripta Metallurgica*, 1972. 6(10): p. 915-917.
- [171] Zhou, M., A.J. Rosakis, and G. Ravichandran, On the growth of shear bands and failure-mode transition in prenotched plates: A comparison of singly and doubly notched specimens. *International Journal of Plasticity*, 1998. 14(4): p. 435-451.
- [172] Pan, D., et al., Experimental characterization of shear transformation zones for plastic flow of bulk metallic glasses. *Proceedings of the National Academy of Sciences*, 2008. 105(39): p. 14769-14772.
- [173] Tsao, S.S. and F. Spaepen, Structural relaxation of a metallic glass near equilibrium. *Acta Metallurgica*, 1985. 33(5): p. 881-889.
- [174] Das, J., et al., "Work-Hardenable" Ductile Bulk Metallic Glass. *Physical Review Letters*, 2005. 94(20): p. 205501.
- [175] Schroers, J. and W.L. Johnson, Ductile Bulk Metallic Glass. *Physical Review Letters*, 2004. 93(25): p. 255506.
- [176] Jiang, W.H., et al., Ductility of a Zr-based bulk-metallic glass with different specimen's geometries. *Materials Letters*, 2006. 60(29-30): p. 3537-3541.
- [177] Das, J., et al., Plasticity in bulk metallic glasses investigated via the strain distribution. *Physical Review B*, 2007. 76(9): p. 092203.
- [178] Chen, L.Y., et al., New Class of Plastic Bulk Metallic Glass. *Physical Review Letters*, 2008. 100(7): p. 075501.
- [179] Abdeljawad, F., M. Fontus, and M. Heataja, Ductility of bulk metallic glass composites: Microstructural effects. *Applied Physics Letters*, 2011. 98(3): p. 031909.
- [180] Magagnosc, D.J., et al., Tunable Tensile Ductility in Metallic Glasses. *Scientific Reports*, 2013. 3: p. 1096.
- [181] Lu, X.L., et al., Gradient Confinement Induced Uniform Tensile Ductility in Metallic Glass. *Scientific Reports*, 2013. 3: p. 112.
- [182] Yao, K.F., et al., Superductile bulk metallic glass. *Applied Physics Letters*, 2006. 88(12): p. 122106.
- [183] Ding, J., et al., Large-size CuZr-based Bulk Metallic Glass Composite with Enhanced Mechanical Properties. *Journal of Materials Science & Technology*, 2014. 30(6): p. 590-594.
- [184] Jiang, F., et al., Microstructure evolution and mechanical properties of Cu₄₆Zr₄₇Al₇ bulk metallic glass composite containing CuZr crystallizing phases. *Materials Science and Engineering: A*, 2007. 467(1-2): p. 139-145.
- [185] Liu, Z.Q., et al., Microstructure and Compressive Properties of <I>In-Situ</I> Martensite CuZr Phase Reinforced ZrCuNiAl Metallic Glass Matrix Composite. *MATERIALS TRANSACTIONS*, 2010. 51(5): p. 1033-1037.
- [186] Liu, Z.Q., et al., Microstructural percolation assisted breakthrough of trade-off between strength and ductility in CuZr-based metallic glass composites. *Scientific Reports*, 2014. 4: p. 4167.
- [187] Schryvers, D., et al., Unit cell determination in CuZr martensite by electron microscopy and X-ray diffraction. *Scripta Materialia*, 1997. 36(10): p. 1119-1125.
- [188] Seo, J.W. and D. Schryvers, TEM investigation of the microstructure and defects of CuZr martensite. Part I: Morphology and twin systems. *Acta Materialia*, 1998. 46(4): p. 1165-1175.
- [189] Seo, J.W. and D. Schryvers, TEM investigation of the microstructure and defects of CuZr martensite. Part II: Planar defects. *Acta Materialia*, 1998. 46(4): p. 1177-1183.

- [190] Song, K., Synthesis, microstructure, and deformation mechanisms of CuZr-based bulk metallic glass composites. 2013.
- [191] Song, K.K., et al., Correlation between the microstructures and the deformation mechanisms of CuZr-based bulk metallic glass composites. *AIP Advances*, 2013. 3(1): p. 012116.
- [192] Kim, D.H., et al., Phase separation in metallic glasses. *Progress in Materials Science*, 2013. 58(8): p. 1103-1172.
- [193] Sun, L., et al., Phase Separation and Microstructure Evolution of Zr₄₈Cu₃₆Ag₈Al₈ Bulk Metallic Glass in the Supercooled Liquid Region. *Rare Metal Materials and Engineering*, 2016. 45(3): p. 567-570.
- [194] Antonowicz, J., et al., Early stages of phase separation and nanocrystallization in Al-rich bulk metallic glasses studied using SAXS/WAXS and HRTEM methods. *Reviews on Advanced Materials Science*, 2008. 18(5): p. 454-458.
- [195] Park, B.J., et al., Phase Separating Bulk Metallic Glass: A Hierarchical Composite. *Physical Review Letters*, 2006. 96(24): p. 245503.
- [196] Kelton, K.F., A new model for nucleation in bulk metallic glasses. *Philosophical Magazine Letters*, 1998. 77(6): p. 337-344.
- [197] Chang, H.J., et al., Synthesis of metallic glass composites using phase separation phenomena. *Acta Materialia*, 2010. 58(7): p. 2483-2491.
- [198] Kündig, A.A., et al., In situ formed two-phase metallic glass with surface fractal microstructure. *Acta Materialia*, 2004. 52(8): p. 2441-2448.
- [199] Oh, J.C., et al., Phase separation in Cu₄₂Zr₄₃Al₇Ag₈ bulk metallic glass. *Scripta Materialia*, 2005. 53(2): p. 165-169.
- [200] Park, E.S. and D.H. Kim, Phase separation and enhancement of plasticity in Cu–Zr–Al–Y bulk metallic glasses. *Acta Materialia*, 2006. 54(10): p. 2597-2604.
- [201] Paradis, P.-F., et al., Material properties measurements and particle beam interactions studies using electrostatic levitation. *Materials Science and Engineering: R: Reports*, 2014. 76: p. 1-53.
- [202] Guo, G.-Q., et al., How Can Synchrotron Radiation Techniques Be Applied for Detecting Microstructures in Amorphous Alloys? *Metals*, 2015. 5(4): p. 2048.
- [203] Guo, G.-Q., et al., Detecting Structural Features in Metallic Glass via Synchrotron Radiation Experiments Combined with Simulations. *Metals*, 2015. 5(4): p. 2093.
- [204] Michalik, S., et al., Structural modifications of swift-ion-bombarded metallic glasses studied by high-energy x-ray synchrotron radiation. *Acta Materialia*, 2014. 80: p. 309-316.
- [205] Yi, J., et al., In situ high-energy X-ray diffraction studies of deformation-induced phase transformations in Ti-based amorphous alloy composites containing ductile dendrites. *Acta Materialia*, 2013. 61(13): p. 5008-5017.
- [206] Yi, J., et al., Glass-Forming Ability and Crystallization Behavior of Al₈₆Ni₉La₅ Metallic Glass with Si Addition *Advanced Engineering Materials*, 2016. 18(6): p. 972-977.
- [207] Huang, Y.J., J. Shen, and J.F. Sun, Bulk metallic glasses: Smaller is softer. *Applied Physics Letters*, 2007. 90(8): p. 081919.
- [208] Oh, Y.S., et al., Microstructure and tensile properties of high-strength high-ductility Ti-based amorphous matrix composites containing ductile dendrites. *Acta Materialia*, 2011. 59(19): p. 7277-7286.

- [209] Kim, K.B., et al., Heterogeneous distribution of shear strains in deformed Ti_{66.1}Cu₈Ni_{4.8}Sn_{7.2}Nb_{13.9} nanostructure-dendrite composite. *physica status solidi (a)*, 2005. 202(13): p. 2405-2412.
- [210] He, G., et al., Novel Ti-base nanostructure-dendrite composite with enhanced plasticity. *Nat Mater*, 2003. 2(1): p. 33-37.
- [211] Wang, Y., et al., Investigation of the microcrack evolution in a Ti-based bulk metallic glass matrix composite. *Progress in Natural Science: Materials International*, 2014. 24(2): p. 121-127.
- [212] Zhang, T., et al., Dendrite size dependence of tensile plasticity of in situ Ti-based metallic glass matrix composites. *Journal of Alloys and Compounds*, 2014. 583: p. 593-597.
- [213] Gargarella, P., et al., Ti-Cu-Ni shape memory bulk metallic glass composites. *Acta Materialia*, 2013. 61(1): p. 151-162.
- [214] Hofmann, D.C., et al., New processing possibilities for highly toughened metallic glass matrix composites with tensile ductility. *Scripta Materialia*, 2008. 59(7): p. 684-687.
- [215] Chu, J.P., Annealing-induced amorphization in a glass-forming thin film. *JOM*, 2009. 61(1): p. 72-75.
- [216] Inoue, A. and T. Zhang, Fabrication of Bulky Zr-Based Glassy Alloys by Suction Casting into Copper Mold. *Materials Transactions, JIM*, 1995. 36(9): p. 1184-1187.
- [217] Inoue, A. and T. Zhang, Fabrication of Bulk Glassy Zr₅₅Al₁₀Ni₅Cu₃₀ Alloy of 30 mm in Diameter by a Suction Casting Method. *Materials Transactions, JIM*, 1995. 37(2): p. 185-187.
- [218] Lou, H.B., et al., 73 mm-diameter bulk metallic glass rod by copper mould casting. *Applied Physics Letters*, 2011. 99(5): p. 051910.
- [219] Qiao, J.W., et al., Synthesis of ductile Zr-based bulk metallic glass matrix composites by the copper-mould suction casting and the Bridgman solidification. *Journal of Alloys and Compounds*, 2009. 477(1-2): p. 43-49.
- [220] Wall, J.J., et al., A combined cup/suction-casting machine for the manufacture of bulk-metallic-glass materials. *Review of Scientific Instruments*, 2006. 77(3): p. 033902.
- [221] Figueroa, I., et al., Preparation of Cu-based bulk metallic glasses by suction casting. 2007.
- [222] Inoue, A. et al., Production methods and properties of engineering glassy alloys and composites. *Intermetallics*, 2015. 58: p. 20-30.
- [223] Wang, P., et al., Simulation of solidification microstructure in twin-roll casting strip. *Computational Materials Science*, 2010. 49(1, Supplement): p. S135-S139.
- [224] Hofmann, D.C., et al., Semi-solid induction forging of metallic glass matrix composites. *JOM*, 2009. 61(12): p. 11-17.
- [225] Khalifa, H.E., Bulk metallic glasses and their composites : composition optimization, thermal stability, and microstructural tunability. 2009.
- [226] Chen, B., et al., Improvement in mechanical properties of a Zr-based bulk metallic glass by laser surface treatment. *Journal of Alloys and Compounds*, 2010. 504: p. S45-S47.
- [227] Santos, E.C., et al., Rapid manufacturing of metal components by laser forming. *International Journal of Machine Tools and Manufacture*, 2006. 46(12-13): p. 1459-1468.
- [228] Sun, H. and K.M. Flores, Laser deposition of a Cu-based metallic glass powder on a Zr-based glass substrate. *Journal of Materials Research*, 2008. 23(10): p. 2692-2703.

- [229] Sun, H. and K. Flores, Microstructural analysis of a laser-processed Zr-based bulk metallic glass. *Metallurgical and Materials Transactions A*, 2010. 41(7): p. 1752-1757.
- [230] Sun, H. and K.M. Flores, Spherulitic crystallization mechanism of a Zr-based bulk metallic glass during laser processing. *Intermetallics*, 2013. 43: p. 53-59.
- [231] Welk, B.A., et al., Phase Selection in a Laser Surface Melted Zr-Cu-Ni-Al-Nb Alloy. *Metallurgical and Materials Transactions B*, 2014. 45(2): p. 547-554.
- [232] Welk, B.A., M.A. Gibson, and H.L. Fraser, A Combinatorial Approach to the Investigation of Metal Systems that Form Both Bulk Metallic Glasses and High Entropy Alloys. *JOM*, 2016. 68(3): p. 1021-1026.
- [233] Borkar, T., et al., A combinatorial assessment of $\text{Al}_x\text{CrCuFeNi}_2$ ($0 < x < 1.5$) complex concentrated alloys: Microstructure, microhardness, and magnetic properties. *Acta Materialia*, 2016. 116: p. 63-76.
- [234] Li, X.P., et al., The role of a low-energy-density re-scan in fabricating crack-free $\text{Al}_{85}\text{Ni}_5\text{Y}_6\text{Co}_2\text{Fe}_2$ bulk metallic glass composites via selective laser melting. *Materials & Design*, 2014. 63: p. 407-411.
- [235] Li, X.P., et al., Selective laser melting of an $\text{Al}_{86}\text{Ni}_6\text{Y}_4.5\text{Co}_{1.5}$ metallic glass: Processing, microstructure evolution and mechanical properties. *Materials Science and Engineering: A*, 2014. 606: p. 370-379.
- [236] Li, X.P., et al., Effect of substrate temperature on the interface bond between support and substrate during selective laser melting of Al-Ni-Co-La metallic glass. *Materials & Design* (1980-2015), 2015. 65: p. 1-6.
- [237] Prashanth, K.G., et al., Production of high strength $\text{Al}_{65}\text{Nd}_8\text{Ni}_5\text{Co}_2$ alloy by selective laser melting. *Additive Manufacturing*, 2015. 6: p. 1-10.
- [238] Jung, H.Y., et al., Fabrication of Fe-based bulk metallic glass by selective laser melting: A parameter study. *Materials & Design*, 2015. 66: p. 703-708.
- [239] Thompson, S.M., et al., An overview of Direct Laser Deposition for additive manufacturing; Part I: Transport phenomena, modeling and diagnostics. *Additive Manufacturing*, 2015. 8: p. 36-62.
- [240] Shamsaei, N., et al., An overview of Direct Laser Deposition for additive manufacturing; Part II: Mechanical behavior, process parameter optimization and control. *Additive Manufacturing*, 2015. 8: p. 12-35.
- [241] Yang, Y. and C.T. Liu, Size effect on stability of shear-band propagation in bulk metallic glasses: an overview. *Journal of Materials Science*, 2012. 47(1): p. 55-67.
- [242] Yang, Y. and M.L. Falk, Stress-induced structural transformation and shear banding during simulated nano-indentation of a metallic glass. *Acta Materialia*, 2007. 55(13): p. 4317-4324.
- [243] Jiang, W.H. and M. Atzmon, Mechanically-assisted nanocrystallization and defects in amorphous alloys: A high-resolution transmission electron microscopy study. *Scripta Materialia*, 2006. 54(3): p. 333-336.
- [244] Dodd, B. and Y. Bai, *Adiabatic Shear Localization: Frontiers and Advances*. 2012: Elsevier.
- [245] Jiang, W.H., F.E. Pinkerton, and M. Atzmon, Deformation-induced nanocrystallization: A comparison of two amorphous Al-based alloys. *Journal of Materials Research*, 2005. 20(03): p. 696-702.
- [246] Smugeresky, J., et al., Laser engineered net shaping (LENS) process: optimization of surface finish and microstructural properties. *Advances in Powder Metallurgy and Particulate Materials--1997.*, 1997. 3: p. 21.

- [247] Wang, H.-S., H.-G. Chen, and J.S.-C. Jang, Microstructure evolution in Nd:YAG laser-welded (Zr₅₃Cu₃₀Ni₉Al₈)Si_{0.5} bulk metallic glass alloy. *Journal of Alloys and Compounds*, 2010. 495(1): p. 224-228.
- [248] Vandenbroucke, B. and J.P. Kruth, Selective laser melting of biocompatible metals for rapid manufacturing of medical parts. *Rapid Prototyping Journal*, 2007. 13(4): p. 196-203.
- [249] Cunliffe, A., et al., Glass formation in a high entropy alloy system by design. *Intermetallics*, 2012. 23: p. 204-207.
- [250] Balla, V.K. and A. Bandyopadhyay, Laser processing of Fe-based bulk amorphous alloy. *Surface and Coatings Technology*, 2010. 205(7): p. 2661-2667.
- [251] Basu, A., et al., Laser surface coating of Fe-Cr-Mo-Y-B-C bulk metallic glass composition on AISI 4140 steel. *Surface and Coatings Technology*, 2008. 202(12): p. 2623-2631.
- [252] Matthews, D.T.A., et al., Laser engineered surfaces from glass forming alloy powder precursors: Microstructure and wear. *Surface and Coatings Technology*, 2009. 203(13): p. 1833-1843.
- [253] Zhang, L.C., et al., Manufacture by selective laser melting and mechanical behavior of a biomedical Ti-24Nb-4Zr-8Sn alloy. *Scripta Materialia*, 2011. 65(1): p. 23-24.
- [254] Dutta, B. and F.H. Froes, Chapter 1 - The Additive Manufacturing of Titanium Alloys, in *Additive Manufacturing of Titanium Alloys*. 2016, Butterworth-Heinemann. p. 1-10.
- [255] Yan, M., et al., The influence of topological structure on bulk glass formation in Al-based metallic glasses. *Scripta Materialia*, 2011. 65(9): p. 755-758.
- [256] Mu, J., et al., Synthesis and Properties of Al-Ni-La Based Metallic Glass. *Advanced Engineering Materials*, 2009. 11(7): p. 530-532.
- [257] Yang, B.J., et al., Al-rich bulk metallic glasses with plasticity and ultrahigh specific strength. *Scripta Materialia*, 2009. 61(4): p. 423-426.
- [258] Yang, B.J., et al., Developing aluminum-based bulk metallic glasses. *Philosophical Magazine*, 2010. 90(23): p. 3215-3224.
- [259] Balla, V.K., et al., Laser-assisted Ti/ZrO₂ coating on Ti for load-bearing implants. *Acta Biomaterialia*, 2009. 5(7): p. 2800-2809.
- [260] Balla, V.K., et al., Direct laser processing of a tantalum coating on titanium for bone replacement structures. *Acta Biomaterialia*, 2010. 6(6): p. 2329-2334.
- [261] Wang, X., et al., Topological design and additive manufacturing of porous metals for bone scaffolds and orthopaedic implants: A review. *Biomaterials*, 2016. 83: p. 127-141.
- [262] Johnson, W.D., Rosen, and B. Stucker, Medical Applications for Additive Manufacture, in *Additive Manufacturing Technologies: Rapid Prototyping to Direct Digital Manufacturing*. 2010, Springer US: Boston, MA. p. 400-414.
- [263] Hays, C.C., C.P. Kim, and W.L. Johnson, Improved mechanical behavior of bulk metallic glasses containing in situ formed ductile phase dendrite dispersions. *Materials Science and Engineering: A*, 2001. 304-306: p. 650-655.
- [264] Zhang, M.X. and P.M. Kelly, Edge-to-edge matching and its applications: Part I. Application to the simple HCP/BCC system. *Acta Materialia*, 2005. 53(4): p. 1073-1084.
- [265] Zhang, M.X. and P.M. Kelly, Edge-to-edge matching model for predicting orientation relationships and habit planes—the improvements. *Scripta Materialia*, 2005. 52(10): p. 963-968.

- [266] Akihisa, I., et al., Aluminum-Based Amorphous Alloys with Tensile Strength above 980 MPa (100 kg/mm²). Japanese Journal of Applied Physics, 1988. 27(4A): p. L479.
- [267] Inoue, A., Bulk amorphous and nanocrystalline alloys with high functional properties. Materials Science and Engineering: A, 2001. 304–306: p. 1-10.
- [268] Qian, M., Metal Powder for Additive Manufacturing. JOM, 2015. 67(3): p. 536-537.
- [269] Kruth, J.P., et al., Selective laser melting of iron-based powder. Journal of Materials Processing Technology, 2004. 149(1–3): p. 616-622.

RETRACTED