



# Enzymatic Modifications of Chitin, Chitosan, and Chitooligosaccharides

Michał Benedykt Kaczmarek<sup>1,2</sup>, Katarzyna Struszczyk-Swita<sup>1</sup>, Xingkang Li<sup>2</sup>,  
Mirosława Szczęsna-Antczak<sup>1</sup> and Maurycy Daroch<sup>2\*</sup>

<sup>1</sup> Institute of Technical Biochemistry, Lodz University of Technology, Łódź, Poland, <sup>2</sup> School of Environment and Energy, Peking University Shenzhen Graduate School, Shenzhen, China

## OPEN ACCESS

### Edited by:

Inder Mohan Saxena,  
University of Texas at Austin,  
United States

### Reviewed by:

Goutam Thakur,  
Manipal Institute of Technology, India  
PaYaM ZarrinTaj,  
Urmia University, Iran

### \*Correspondence:

Maurycy Daroch  
m.daroch@pkusz.edu.cn

### Specialty section:

This article was submitted to  
Biomaterials,  
a section of the journal  
Frontiers in Bioengineering and  
Biotechnology

**Received:** 27 June 2019

**Accepted:** 12 September 2019

**Published:** 27 September 2019

### Citation:

Kaczmarek MB, Struszczyk-Swita K,  
Li X, Szczęsna-Antczak M and  
Daroch M (2019) Enzymatic  
Modifications of Chitin, Chitosan, and  
Chitooligosaccharides.  
*Front. Bioeng. Biotechnol.* 7:243.  
doi: 10.3389/fbioe.2019.00243

Chitin and its N-deacetylated derivative chitosan are two biological polymers that have found numerous applications in recent years, but their further deployment suffers from limitations in obtaining a defined structure of the polymers using traditional conversion methods. The disadvantages of the currently used industrial methods of chitosan manufacturing and the increasing demand for a broad range of novel chitosan oligosaccharides (COS) with a fully defined architecture increase interest in chitin and chitosan-modifying enzymes. Enzymes such as chitinases, chitosanases, chitin deacetylases, and recently discovered lytic polysaccharide monooxygenases had attracted considerable interest in recent years. These proteins are already useful tools toward the biotechnological transformation of chitin into chitosan and chitooligosaccharides, especially when a controlled non-degradative and well-defined process is required. This review describes traditional and novel enzymatic methods of modification of chitin and its derivatives. Recent advances in chitin processing, discovery of increasing number of new, well-characterized enzymes and development of genetic engineering methods result in rapid expansion of the field. Enzymatic modification of chitin and chitosan may soon become competitive to conventional conversion methods.

**Keywords:** chitin, chitosan, chitooligosaccharides, enzymatic modifications, lytic polysaccharide monooxygenase, chitin deacetylase, chitinase, chitosanase

## INTRODUCTION

The interest in natural polymers has increased substantially over the last three decades. Chitin, the second most abundant, after cellulose, biopolymer on earth can be obtained from many sources including marine crustacean shell-waste material, insects, and exoskeleton of invertebrates. The worldwide market for Chitosan Derivatives is expected to grow at a CAGR (Compound Annual Growth Rate) of roughly 6.3% over the next 5 years, will reach 53 million USD in 2024, from 36 million USD in 2019 (Global Info Research, 2019), driven by the growing investments in new drug development, emerging biomedical applications and expanding non-medical uses such as detoxification of water and wastewater. There is also an increased interest in organic farming and certified use of biodegradable chitosan products as fertilizers (Global Industry Analysts Inc., 2016). Research on these biopolymers focuses, among other issues, on the search for new and improved production methods. Key areas of interest include: enzymatic conversion (Roberts, 2008), chemical, or physical modifications of polysaccharides to extend their applicability (Zhao et al., 2013) exploration of the mechanisms of biological activity of the said polymers and products of their physical, chemical or enzymatic degradation, and the biochemical and molecular characterization of chitosanalytic and chitinolytic enzymes synthesized by numerous organisms (Duo-Chuan, 2006; García-Fraga et al., 2015).

Biotransformation of chitin into chitosan through enzymatic deacetylation can be achieved with chitin deacetylases (EC 3.5.1.41, ChDa). This enzymatic reaction has several advantages over the traditional chemical processes, most importantly, the production of chitosan with higher molecular weight and the desired degree of deacetylation (Tsigos et al., 2000). Other enzymes involved in chitin and chitosan conversion are chitinases (EC 3.2.1.14) and chitosanases (EC 3.2.1.132). Both of them catalyze the hydrolysis of glycosidic bonds but differ in substrate specificity, hydrolysing bonds of chitin and chitosan, respectively (Jaworska, 2012). Obtained chitooligosaccharides can be further enzymatically modified by chitooligosaccharides deacetylases (EC 3.5.1.105, CODa) to obtain products with desired chain arrangement (Hirano et al., 2017). In recent years, lytic polysaccharide monoxygenases (LPMOs) (EC 1.14.99.53–56) attracted the attention of scientists. Generally, these enzymes are capable of cleaving glycolic bond in crystalline forms of polysaccharides through oxidizing either C1 or C4 of the glucopyranose ring. Chitin-active LPMO was first demonstrated in 2010 for the *Serratia marcescens* AA10 (CBP21) (Vaaje-Kolstad et al., 2010). In contrast to glycoside hydrolases (GHs), such as chitinases and chitosanases, LPMOs are capable of directly cleaving glycolic bonds in highly crystallized chitin (Mutahir et al., 2018). To date, LPMOs with chitinolytic activities have been identified in carbohydrate auxiliary activity families AA10, AA11, and AA15 (Hemsworth et al., 2015). Currently, all these enzymes are increasingly seen as useful tools toward biotechnological production of chitosan and chitooligosaccharides (COS), especially when a controlled, non-degradative, and well-defined process is required (Hamer et al., 2015). The main limitation of enzymatic methods lies in the multi-step character of this process and high costs of enzyme production, which makes them unfavorable from an economic point of view (Kim and Rajapakse, 2005).


## CHITIN, CHITOSAN, AND CHITOOLOGOSACCHARIDES: GENERAL CHARACTERIZATION

Chitin is defined as  $\beta$ -(1–4) linked linear cationic heteropolymer consisting of 2-acetamide-2-deoxy-D-glucopyranose (N-acetyl-D-glucosamine, GlcNAc) and randomly distributed units

**Abbreviations:** COS, chitooligosaccharides; CAGR, Compound Annual Growth Rate; ChDa, chitin deacetylase; CODa, chitooligosaccharides deacetylase; LPMOs, lytic polysaccharide monoxygenases; GHs, glycoside hydrolases; GlcNAc, 2-acetamide-2-deoxy-D-glucopyranose, N-acetyl-D-glucosamine; GlcN, 2-amino-2-deoxy-D-glucopyranose, D-glucosamine; DA, degree of acetylation; MW, molecular weight; DP, degree polymerization; DD, degree of deacetylation; DMF, dimethylformamide; DMSO, Dimethyl Sulfoxide; FA, fraction of acetylation; PA, pattern of acetylation; LDL, low-density lipoproteins; CE4, carbohydrate esterase family 4; CAZY, Carbohydrate-Active Enzymes Database; WSCT-50, water-soluble chitin with DD 50%; ACE, angiotensin-converting enzyme; TLC, thin-layer chromatography; GH-18, GH-19, GH-20, glycosyl hydrolase families; LMWCh, low molecular weight chitosan; LPS, lipopolysaccharides; GAGs, glycosaminoglycans; NF- $\kappa$ B, nuclear factor  $\kappa$ B; mTOR, mechanistic target of rapamycin; AMPK, AMP-Activated Protein Kinase; ATRA, all-trans-retinoic acid; PEC, polyelectrolyte complexes; LMW, low molecular weight; IRES, internal ribosome entry site.

of 2-amino-2-deoxy-D-glucopyranose (D-glucosamine, GlcN) (Figure 1). The degree of chitin acetylation (DA) exceeds 90%, and its molecular weight (MW) can be as high as  $1 \times 10^6$ – $2.5 \times 10^6$  Da, which corresponds to a degree of polymerization (DP) of ca. 5,000–10,000 (Mourya and Inamdar, 2008). The presence of acetamido groups enables the formation of numerous inter- and intramolecular hydrogen bonds between linear chitin chains. Moreover, these groups are situated near the hydroxyl groups in the *trans* position, which results in a high degree of crystallinity and lack of solubility in water and organic solvents. Research studies on chitin revealed that this biopolymer displays many unique properties. For example, it inhibits the growth of bacteria, fungi and viruses, has a tremendous chelating ability, exhibits high affinity for proteins, it, therefore, makes it valuable for immobilization of enzymes (Synowiecki and Al-Khateeb, 2003; Younes and Rinaudo, 2015). Due to its biodegradability, biocompatibility, non-toxicity, physiological inertness and gel-forming properties, chitin has found countless applications in different industries, e.g., food, cosmetic, pharmaceutical, manufacturing of synthetic materials, agriculture, and even electronics for the production of biosensors (Rinaudo, 2006).

Unfortunately, due to the lack of solubility and its highly ordered crystalline structure resistant to physical and chemical agents, the use of chitin is limited in many cases. Therefore, the N-deacetylated derivative of chitin—chitosan, which is soluble in aqueous solutions of both organic and inorganic acids was found to have a practical advantage. This cationic polymer also consists of  $\beta$ -(1–4) linked N-acetyl-D-glucosamine and prevailing D-glucosamine residues. Chitosan does not refer to a single unique substance, but rather to many copolymers with a different ratio of GlcN to GlcN and GlcNAc residues). The degree of deacetylation (DD) of commercial preparations of chitosan are within 70–95%, and their MW ranges from  $10^4$  to  $10^6$  g/mol (Moura et al., 2011). Chitosans exists as a heterogenic group of oligomers and polymers which differ in their degree of polymerization (DP), a fraction of acetylation (FA), and their pattern of acetylation (PA) (Kohlhoff et al., 2017). Compared to chitin, this N-deacetylated derivative is much less common in nature and is manufactured industrially by hydrolyzing amino acetyl groups of chitin. The polymer is also naturally present in the cell walls of filamentous fungi primarily classified to the *Zygomycetes* class (Synowiecki and Al-Khateeb, 1997; Chatterjee et al., 2005). Despite significant similarities in the molecular structures of chitin and chitosan, the physicochemical characteristics of both biopolymers and the reactions they undergo are often surprisingly distinct. Both polymers possess reactive hydroxyl and amino groups (in different molecular ratios), but lower crystallinity of chitosan makes it more accessible for reagents (Mourya and Inamdar, 2008). Probably, the most crucial difference between chitin and chitosan in terms of their applications is in their DD and solubility. Chitosan is soluble in most aqueous acid solutions such as acetic, formic, lactic, citric acids below its pKa (pH around 6.5), and some others solvents such as dimethylsulfoxide, p-toluene sulfonic acid (Roy et al., 2017). The chemical modification of molecular structure of chitosan can significantly improve the solubility of the polymer in different solvents. Yang



et al. (2015) synthesized chitosan-graft-polycaprolactone which was soluble in dimethylformamide (DMF), dimethyl sulfoxide (DMSO), ethanol and toluene. O-alkylated chitosan synthesized in an ionic liquid solvent was soluble chloroform, ethanol, water and acetic acid (Chen H. et al., 2012). Monomethyl-modified chitosan obtained by modification of chitosan with monomethyl fumaric acid in an ionic liquid solution, showed excellent solubility in water, which significantly increased the spectrum of its applications (Wang et al., 2015).

The biological applications of chitin and chitosan are highly limited due to their high molecular weight, poor solubility and high viscosity of chitosan solutions. Chito oligosaccharides (COS), which are the products of chitin and chitosan degradation, are seen as an excellent alternative. COS also consists of  $\beta$ -(1-4) linked N-acetyl-D-glucosamine and prevailing D-glucosamine residues. The DP of COS varies from 2 to 20 units in a segment which gives an average MW lower than 3,900 Da. Each oligosaccharide differs in the FA and in the sequence of GlcN and GlcNAc residues. Heterochito oligosaccharides are composed of GlcN and GlcNAc comprising both units, while homochito oligosaccharides are exclusively composed of GlcN or GlcNAc. Hetero oligosaccharides differ in the DP, DD, and position of N-acetyl residues in the oligomer chain (Liaqat and

Eltem, 2018). The water solubility of COS is associated with their shorter chain lengths and free amino groups in D-glucosamine units (Bahrke, 2008). The solubility of COS depends on the degree of polymerization. For example, oligomers with DP 2-4 are soluble in methanol but oligomers with DP more than 5 are less soluble (Mourya et al., 2011). However, it is generally assumed that COS are insoluble in ethanol, propanol, butanol, acetone, ethyl acetate, partially soluble in methanol, and dimethyl sulfoxide but fully soluble in water (Liaqat and Eltem, 2018). Because of the higher solubility than chitin and chitosan in generally available solvents COS have gained an increasing interest in many laboratories and industries. The biological activity of oligosaccharides depends on their structure and is mainly dependent on their DP, MW, DA, FA, and PA (Li et al., 2016).

## CHITIN AND CHITOSAN PRODUCTION METHODS

### Chitin Production Methods

The primary source of raw materials to produce chitin and its N-deacetylated derivatives are wastes of the fishing industry. Exoskeletons of marine organisms, including shrimp, crab, crayfish, krill, squid, are widely used for

this purpose (Abdou et al., 2008). Nowadays, chitin and chitosans are obtained by two types of extraction methods: chemical and biotechnological. Chemical processes which involve the use of strong acids and bases are currently the most widely used methods in both laboratory and industrial-scale production.

The process of chitin extraction and its transformation into chitosan includes three major steps: demineralization, deproteinization, and deacetylation. Additionally, decolorization process using various organic and inorganic solvents such as glacial acetone (Soon et al., 2018), sodium hypochlorite (Srinivasan et al., 2018) can be employed to eliminate pigments. Demineralization step is performed to remove the calcium carbonate and calcium chloride, which are the main inorganic constituents of the exoskeletons of crustaceans. For this, inorganic acids such as HCl, HNO<sub>3</sub>, and H<sub>2</sub>SO<sub>4</sub> (Kumar Gadgery and Bahekar, 2017), and strong organic acids HCOOH and CH<sub>3</sub>COOH (Regis et al., 2015) are used. The most common acid used in the production of chitin is hydrochloric acid, due to its high efficiency in the removal of the minerals. The next major step in chitin extraction is deproteinization of raw materials. This step is performed using alkali solution to remove proteins. A wide range of chemical reagents have been tested for protein removal including NaOH, Na<sub>2</sub>CO<sub>3</sub>, NaHCO<sub>3</sub>, KOH, K<sub>2</sub>CO<sub>3</sub>, Ca(OH)<sub>2</sub>, Na<sub>2</sub>SO<sub>4</sub>, NaHSO<sub>4</sub>, CaHSO<sub>4</sub>, Na<sub>3</sub>PO<sub>4</sub>, and Na<sub>2</sub>S (Younes and Rinaudo, 2015). However, the most commonly used is NaOH solution. The chemical extraction of chitin involves large amounts of hazardous alkaline and acid wastes which are dangerous for the environment. Biological methods offer an alternative way to extract chitin and chitosan. Many research results are indicating that the chemical deproteinization of chitin can be replaced by enzymatic methods. Hamdi et al. (2017) extracted chitin from blue crab *Portunus segnis* and shrimp *Penaeus kerathurus* using chemical demineralization and enzymatic deproteinization approaches. The use of *P. segnis* crude extract with proteolytic activity resulted in deproteinization degree (DP) of 85 and 91% for blue crab and shrimp, respectively. Castro et al. (2018) extracted chitin from *Allopetrolisthes punctatus* crab biomass using biotechnological method. Demineralization and deproteinization of crab biomass were carried out using lactic acid fermentation, by *Lactobacillus plantarum* sp. 47. Extracted and purified chitin, after 60 h fermentation, showed 99.6 and 95.3% demineralization and deproteinization, respectively, using low concentrations of acids and bases. Dun et al. (2019) presented a new strategy for chitin extraction by simultaneous enzymatic hydrolysis and fermentation. *Bacillus coagulans* LA204 and proteinase K were used to remove minerals and proteins from crayfish shell waste powder. After 48 h of fermentation, the deproteinization efficiency, demineralization efficiency, and chitin recovery reached 93, 91, and 94%, respectively. Despite the many disadvantages of chemical methods, they are still prevalent approach for chitin processing in the industrial most likely due to short extraction time. **Table 1** shows a comparison of chemical and biotechnological methods of chitin production.

## Chitosan Production Methods

Currently, there are two well-known methods of chitosan preparation. The first approach is to extract chitosan directly from cell walls of molds. The second approach utilizes thermo-chemical or enzymatic methods of chitin deacetylation to remove the N-acetyl groups from chitin. The first microbiological method of chitosan preparation was developed by White, Foulton and Farin in 1979 (Da Silva Amorim et al., 2001). Despite superior properties of microbiological chitosan, such as more efficient sorption of metals, compared to its counterparts obtained by the chemical N-deacetylation of chitin, this method did not find widespread application in industry. The main disadvantage of this approach is the insufficient amount of chitosan extracted from the cell walls of microorganisms. The chitosan content depends on the strain and ranges from 0.3 g (*Mucor rouxii* DSM 0201) (Davoust and Hansson, 1992) to 1.8 g (*Absidia coerulea* ATCC 14076) (Jaworska and Konieczna, 2001) per 1 dm<sup>3</sup> of culture medium.

Nowadays, chitosan is manufactured industrially through thermo-chemical hydrolysis of chitin's amide bonds. Commercial preparations of chitosan are available in several forms such as solutions, flakes, fine powder, beads, and fibers (Hayes, 2012). Thermo-chemical methods of converting chitin to chitosan are used extensively on an industrial scale because of their low costs and suitability for mass production. In principle, chitin can be deacetylated using either acids or alkalis. Since glycosidic bonds are very susceptible to acid hydrolysis; the alkali-catalyzed deacetylation is used more frequently to avoid unwanted chain termination (Younes and Rinaudo, 2015). For this purpose, 50% NaOH solution is most often used at high temperature (Soon et al., 2018; Srinivasan et al., 2018). It had to be mentioned that the characteristics of extracted chitosan differ depending on the extraction method and the source from which chitin is isolated (Marei et al., 2016). Samar et al. (2013) improved conventional deacetylation method by adding of microwave irradiation. Obtained degree of deacetylation reached 95% with 90% chitosan yield. El Knidri et al. (2016) replaced the conventional method of chitin extraction and its transformation into chitosan by an alternative process intensified with microwave irradiation in all production steps: demineralization, deproteinization and deacetylation. Obtained results showed that chitosan, with a DD of 82.73%, was successfully prepared in 24 min *via* microwave irradiation method, while a much longer time of 6–7 h was needed for preparing chitosan with the same degree of deacetylation (DD = 81.5%), using a conventional heating method. Despite a relatively high efficiency of thermo-chemical methods, these processes have many disadvantages, such as high-energy consumption and a large amount of waste alkaline solution resulting in environmental pollution. Many factors impact the basic properties of obtained chitosans, such as the process duration (Tsaih and Chen, 2003), the temperature and number of repetitions of alkaline steps (Tolaimate et al., 2000), and the concentration and type of alkali reagent (Younes et al., 2014). These methods are very difficult to control, resulting in a mixture of heterogeneous species with different physicochemical properties that are difficult to fractionate into



TABLE 1 | Chitin production methods.

Method	Chitin production							
	Source	Demineralization	DM [%]	Deproteinization	DP [%]	References	Advantages	Disadvantages
Chemical process	Resting eggs	1:50 (w/v); 1 M HCl 16 h, 65–75°C	NI	1:5 (v/v); 1 M NaOH 20 h, 65°C	NI	Kaya et al., 2013	Short processing time; Used at the industrial scale; Complete removal of organic salts;	Environmentally unfriendly; Solubilized minerals and proteins cannot be used as human and animal nutrients; Uncontrolled hydrolysis of the product;
	<i>Zophobas morio</i> larvae	1:30 (w/v); 1 M HCl	–	1:20 (w/v); 1 M HCl 30 min, 100 RPM, 35°C	–	Soon et al., 2018		
	Shrimp shells	75 min, RT, 150 RPM	–	1:20 (w/v); 0.5–2 M NaOH 20 h, 80°C, 100 RPM	–	Srinivasan et al., 2018		
				1:30 (w/v); 3M NaOH 75 min, RT, 150 RPM				
Enzymatic deproteinization and chemical demineralization	Blue crab	1:10 (w/v); 0.55 M HCl 30 min, 4°C	NI	20 g Crab/Shrimp shell powder, crude protease extract from <i>P. segnis</i> pH 8.0, 50°C, 3 h	~85	Hamdi et al., 2017	Limited amount of hazardous waste for the environment; Complete removal of organic salts;	Solubilized minerals and proteins cannot be used as human and animal nutrients; Uncontrolled hydrolysis of the product; Relatively long processing time; Limited to laboratory- scale;
	Shrimp Shellfish powder	1:2 (w/v); 1.5 N HCl 2 h, RT	NI 99	10 g powder; crude protease extracted from <i>Erwinia chrysanthemi</i> 37°C, 16 h	~91 ~95	Sami, 2010		
	Shrimp	1:10 (w/v) 1.5 M HCl 6 h, 25°C	100	1:20 crude protease extracted from <i>B. cereus</i> SV1 to pretreated shrimp wastes pH 8.0, 3 h, 40°C	~89	Manni et al., 2010		
Liquid fermentation and chemical demineralization	Shrimp shells	1:10(w/v); 0.5 M HCl 3 baths, 4°C, 30 RPM, 30 min	100	Two crude enzymes in separate reactions crude protease from <i>Bacillus majavensis</i> A21–7.75 U/mg, 60°C, 6 h, pH 9.0 crude protease from <i>Scorpaena scrofa</i> 10 U/mg, 50°C, pH 9.0	96	Younes et al., 2016		
	Shrimp	1:50 (w/v); 1.25 M HCl 1 h, RT	NI	<i>Brevibacillus parabrevis</i> grown on medium containing 3%(w/v) shrimp waste, 37°C, 150 RPM, 5 days	73–96*	Doan et al., 2019b		
Liquid fermentation	Crab shells	<i>Lactobacillus plantarum</i> sp. 47 grown on medium containing 85% (w/v) raw material 32°C, 60 h		~95	~99	Castro et al., 2018	High quality of the final product; Environmentally safe; Removed minerals and proteins may be used as human and animal nutrients; Products with predicted physicochemical properties	Long processing time; Limited to laboratory- scale;
	Shrimp wastes	<i>Lactobacillus brevis</i> – solid state fermentation on minced shrimp wastes 30°, 192 h	96		67.3	Aranday- García et al., 2017		
	Shrimp waste	<i>Pseudomonas aeruginosa</i> grown on medium containing 5% (w/v) shrimp 37°C, 100 RPM, 144 h	92		82	Sedaghat et al., 2017		
	Shrimp head	<i>Streptococcus thermophilus</i> grown on medium containing 10% (w/v) shrimp head 42°C, 64 h, pH 5.00	~94		92	Mao et al., 2013		
Simultaneous enzymatic hydrolysis and fermentation	Shell waste	<i>Becillus coagulans</i> LA204 grown on medium containing 5%(w/v) crayfish shell powder (CSP) and 1,000 U proteinase K kg <sup>-1</sup> (CSP) 50°C, 48 h	93		91	Dun et al., 2019		

\*Depending on the shrimp source.

desired products with known characteristics. Additional factors such as the presence and type of reducing agent, the gases constituting the reaction environment (nitrogen or air), particle size, and the source of raw material may influence the degree of deacetylation and the average molecular weight of the obtained products (Younes and Rinaudo, 2015). Younes et al. (2014) investigated that sodium borohydride (reducing agent), and nitrogen atmosphere do not have a significant effect on the DA of chitosan but was found to have a protective effect against chitosan degradation during deacetylation. Moreover, the acetyl groups of the resulting products are distributed irregularly with certain hot spots of acetylation. It has a significant impact on the solubility and properties of obtained chitosans (Aiba, 1991). The most significant disadvantage of these methods lies in uncontrolled hydrolysis of chitin, which occurs spontaneously, following the treatment with concentrated alkali and high temperature. A study carried out by Struszyk (2000) demonstrated that the decrease in MW could reach even 86% in comparison to MW of the used substrate. It has been found that the use of oxygen scavengers and reducing agents, such as thiophenol and sodium borohydride ( $\text{NaBH}_4$ ), may limit polymer degradation (Younes and Rinaudo, 2015). However, the consequence is the increase in the process costs and the amount of hazardous chemical waste.

To overcome these problems, enzymatic methods can be used. Due to the eco-friendly nature of these methods, they attract significant interest. Moreover, the use of enzymes prevents irregular deacetylation and molecular weight reduction caused by acid and alkali treatment. Rass-Hansen et al. (2007) used chitin deacetylase isolated from *Colletotrichum lindemuthianum* for deacetylation of pre-treated chitin substrates extracted by liquid fermentation using microorganisms mixture consisting of *Lactobacillus salvarius*, *Enterococcus faecium* and *Pedococcus acidilactici* strains. The main disadvantage of the enzymatic method is that the enzyme preparations are not able to efficiently deacetylate native chitin substrates. Pareek et al. (2013) proved that the efficiency of enzymatic deacetylation is strictly dependent on the method of pre-treatment of the substrate. Depending on the form of substrate preparation, they obtained a degree of deacetylation of the product in the range from 62 to 79%. **Table 2** shows a comparison of chemical and biotechnological methods of chitosan production.

Despite numerous advantages of biotechnological methods, which undoubtedly include: the ability to control the process (no uncontrolled degradation of the polymer chain), desired physicochemical properties of the obtained products, no negative impact on the environment; conventional methods of chitin and chitosan production are still the most commonly used commercially because of their short extraction time and high efficiency of the process.

## Chitooligosaccharides Production Methods

As it was mentioned the biological activities of COS are significantly influenced by the DA, DP, MW, FA, and PA; therefore, it is crucial that the chitooligosaccharides production

methods are reproducible and easy to control. At present COS can be obtained through physical, chemical, electrochemical and enzymatic degradation of chitin and chitosan. Currently, commercially available chitooligosaccharides are usually prepared by hydrolysis of chitin with concentrated acids and enzymatic hydrolysis of chitin and chitosan. The most commonly used chemical methods of chitooligosaccharides production include acid degradation and oxidative degradation of chitin and chitosan. Trombotto et al. (2008) described the two-step method of obtaining homogeneous series of chitin/chitosan oligomers varying from DA 0–90% with a narrow distribution of DPs within 2 and 12. The first step includes chemical depolymerization of fully deacetylated chitosan using 12 M hydrochloric acid. The obtained COS were partially N-acetylated in hydroalcoholic solution of acetic anhydride. It has been demonstrated that COS production can be carried out in nitrous acid environment (Tømmeraas et al., 2001). Another example of chemical depolymerization of chitinous substrates is the use of hydrogen peroxide. Chitooligosaccharides with DP ranging from 2 to 9 were produced using  $\text{H}_2\text{O}_2$  using phosphotungstic acid as a catalyst in homogenous phase (Xia et al., 2013). Due to the relatively high efficiency and simplicity of the process, chemical hydrolysis is the most frequently used traditional chitin and chitosan digestion method. However, chemical reactions are difficult to control and can lead to the production of various by-products which are problematic in the purification of the chitooligosaccharides. Besides, chemical degradation leads to a mixture of products of varying DP and DA.

Enzymatic methods, which are an excellent alternative to conventional processes, gained interest as precise tools for the production of COS with desired physicochemical and biological properties. Enzymatic production of COS can be carried out by using specific enzymes such as chitinases, chitosanases, and non-specific enzymes like carbohydrases and proteases (Kim and Je, 2010). Rafael Olicón-Hernández et al. (2017) described enzymatic hydrolysis of colloidal chitin using extracellular chitosanase from *Bacillus thuringiensis*. Obtained mixtures of chitooligosaccharides obtained by *in vitro* depolymerization of colloidal chitin substrates consist of the chitobiose to the chitohexaose. Chitin from fungal waste mycelia pre-treated by alkali was degraded by recombinant chitinase from *Lactococcus lactis*. The main product in the obtained hydrolysate was N,N'-diacetylchitobiose. The yield of the product from waste mycelium was around 10% with estimated purity of around 70%. Addition of snailase into the reaction mixture significantly increased the yield COS to 24% with purity of 78% (Lv et al., 2016). Mallakuntla et al. (2017) described chitinase from *Enterobacter cloacae* which exhibit transglycosylation activity. The profile of hydrolytic products among which predominant was chitobiose, indicated that the chitinase was an endo-acting enzyme. Transglycosylation reaction catalyzed by chitinase resulted in the formation of longer chitooligosaccharides by joining trimeric to hexameric COS for a prolonged duration. As already mentioned, COS can also be produced by hydrolysis of chitin and chitosan using non-specific enzymes. Xie et al. (2011) used complex enzymes compound of commercial cellulose, pectinase and  $\alpha$ -amylase to degrade the large molecular chain of chitosan rapidly under slightly acidic

TABLE 2 | Chitosan production methods.

Method	Chitosan production						References	Advantages	Disadvantages
	Source	Demineralization	Deproteinization	Deacetylation	DD [%]	Chitosan yield [%]			
Chemical process	Locus	1:15 (w/v); 1 M HCl	1:15 (w/v); 1 M NaOH	50% NaOH 8 h, 100°C	98	–	Marei et al., 2016	Short processing time; Used at the industrial scale; Complete removal of organic salts;	Environmentally unfriendly; a large volume of concentrated alkali solution at high temperature Solubilized minerals and proteins cannot be used as human and animal nutrients;
	Honey bee				96				
	Beetles				95				
	Shrimp				75				
	<i>Zophobas morio</i> larvae				65–81				
Shrimp shells	1:30 (w/v); 1 M HCl 75 min, RT, 150 RPM	1:30 (w/v); 3 M NaOH 75 min, RT, 150 RPM	1:50 (w/v); 50% NaOH 50 min, 90°C	–	35	Srinivasan et al., 2018	Uncontrolled hydrolysis of the product;		
Chemical process combined with microwave techniques	Cuttlefish pens	1:40 (w/v); 1 M HCl 3 h, RT	1:20 (w/v); 1 M NaOH 24 h, 70°C	1:15(w/v); 45% NaOH 15 min, 600 W	93	–	Al Sagheer et al., 2009	Limited amount of hazardous waste for the environment; Complete removal of organic salts;	Solubilized minerals and proteins cannot be used as human and animal nutrients; Uncontrolled hydrolysis of the product; Relatively long processing time;
	Shrimp waste	1:10 (w/v); 2% HCl 12 h, 30°C	1:10 (w/v); 4% NaOH 12 h, 90°C	1:10; 50% NaOH 1,400 W, 10 min, 60 mesh	~95	~90	Samar et al., 2013	Limited to laboratory-scale;	
	Shrimp shells	1:10 (w/v); 3 M HCl 8 min, 500 W	1:10 (w/v); 10 NaOH 8 min, 160–350 W	1:20 (w/v); 50% NaOH 8 min, 350 W	~83		El Knidri et al., 2016		
Liquid fermentation and chemical deacetylation	Shrimp waste	<i>Pseudomonas aeruginosa</i> grown on medium containing 5% (w/v) shrimp 37°C, 100 RPM, 144 h		50% NaOH in an autoclave 50% NaOH, 100°C 50% NaOH microwaves	88 ~77 ~44	~88	Sedaghat et al., 2017	Limited amount of hazardous waste for the environment; Removed minerals and proteins may be used as human and animal nutrients;	Long processing time; Limited to laboratory-scale;
Liquid fermentation and enzymatic deacetylation	Minced prawn shell	<i>Lactobacillus salvarius</i> , <i>Enterococcus faecium</i> and <i>Pedococcus acidilactici</i> 30°C, 250 RPM, 120 h		Pre-treated in different way chitin substrates were mixed with chitin deacetylase from <i>Colletotrichum lindemuthianum</i> 1:1 (v/v); 24 h, 50°C	–	–	Rass-Hansen et al., 2007	High quality of final product; Environmentally safe; Removed minerals and proteins may be used as human and animal nutrients;	Long processing time; Limited to laboratory-scale;

(Continued)

TABLE 2 | Continued

Source	Chitin chemical pre-treatment	Deacetylation	DD [%]	Chitosan yield [%]	References	Advantages	Disadvantages
Chemical and enzymatic deacetylation	Commercial chitin 45% phosphoric acid, 40 min; Precipitation by addition of 6M NaOH to pH 8. Cold solution of 20% NaOH and 0.2% SDS, 60 min, 4°C Overnight at -20°C and neutralized with 6 N HCl 20% HCl, 20 min, RT Precipitation in cold distilled water 100 ml of 60% calcium chloride in methanol solution Precipitation in 1% calcium citrate 25% formic acid, RT	Pretreated chitin deacetylated by chitin deacetylase from <i>Penicillium oxalicum</i> SAE <sub>M</sub> -51 24 h, 50°C	62	-	Pareek et al., 2013	Relatively short processing time; Highly deacetylated products; Limited amount of hazardous waste for the environment;	Limited to laboratory scale;

conditions. Results indicated that complex enzymes could result in low molecular weight chitosan ranged from 1,000 to 4,000 after enzymatic degradation for 2 h without changing chitosan glycosidic ring structure and DD.

There have been many reports indicating that ultrasonic microwave and gamma rays could be used to prepare COS with little contamination but, unfortunately with relatively low proactivity. Popa-Nita et al. (2009) evidenced the existence of two mechanisms involved in the ultrasonically induced chitosan depolymerization. The effect of the first is the rapid disruption of polymer chains while reducing polydispersity. The second mechanism is different and results in formation of short polymer chains and oligomers with an increase in polydispersity. Using different conditions of ultrasonic depolymerization COS ranging from DP 2–11 with maximum concentration of DP 3 were obtained. Baxter et al. (2005) suggested that ultrasonic treatment of chitosan in the medium to low power range can replace chemical and enzymatic methods that are currently used to depolymerize chitosan. The results of their research indicate that in the presence of acetic acid ultrasonication can be utilized to reduce molecular weight of chitosan while maintaining the degree of acetylation. Gamma irradiation was also successfully used to depolymerize chitosan. Choi et al. (2002) applied Co-60 gamma irradiation to depolymerize chitosan in acetic acid solution. The rapid decrease in viscosity of the solution was observed with the production of COS with DP ranging from 2 to 4. In recent years, hydrodynamic cavitation has gained considerable interest in the context of polymer degradation. Depolymerization takes place as the liquid is passed through a constriction, which leads to higher bubble densities and subsequent increase in local pressure. Wu et al. (2014) degraded chitosan by swirling cavitation, which is a variation of hydrodynamic cavitation. The intrinsic viscosity reduction rate of chitosan was 83.65% with no change in the DD of the products. So far, physical methods of COS production have not been investigated too frequently and their large-scale efficiencies have not been established. An interesting alternative to the COS production methods described so far is electrochemical method, which is easy to control and contamination free. Unfortunately, there are some significant problems such as the short electrode life and easy failure. Gu et al. (2013) used Ti/Sb-SnO<sub>2</sub> electrode as anode, stainless steel as cathode for degrading chitosan. The molar mass of chitosan dramatically decreased with reaction time and the chemical structure of degraded chitosan was not obviously modified. The above-described methods for the production of COS have their advantages and disadvantages. The Table 3 lists the most important of them.

## ENZYMATIC MODIFICATION OF CHITIN AND CHITOSAN

Disadvantages of currently used thermo-chemical methods of chitin and chitosan industrial-scale manufacturing and increasing demand for a range of their derivatives with fully defined architecture have drawn attention to the enzymatic



**TABLE 3** | Advantages and disadvantages of chitoooligosaccharides production methods.


COS production method	Advantages	Disadvantages
Chemical depolymerization	High efficiency simple to handle	Harmful to the environment difficult to control lead to the production of various by-products mixtures of products of varying DP and DA
Physical depolymerization	Easy purification and little contamination lack of waste harmful to the environment	Low productivity energy-consuming
Enzymatic depolymerization	Easy to control easy accessibility products with desired properties no additional products modification	High costs of enzymes preparations
Electrochemical depolymerization	Easy to operate contamination-free	Short electrode life easy to fail

methods of polymer modification. Enzymatic pathways for chitin and chitosan conversion are shown in **Figure 2** (Jung and Park, 2014).

Efficient conversion of chitin into specific chitosan can be catalyzed by chitin deacetylases (EC 3.5.1.41, ChDa). According to the classification of enzymes, a group of enzymes that catalyze the COS deacetylation reaction should also be distinguished. Chitin deacetylases and chitoooligosaccharides deacetylases [EC 3.5.1.105 (CODa)]. ChDas and CODa are a group of enzymes catalyzing the hydrolysis of acetamido groups of N-acetyl-D-glucosamine residues in chitin, chitosan and chitoooligosaccharides, respectively (Li et al., 2007; Pacheco et al., 2013). Both of these groups of enzymes are classified in the carbohydrate esterase family 4 (CE4) in the CAZY database (Lombard et al., 2014). These enzymes share a conserved region known as the NodB homology domain due to its similarity to the NodB oligosaccharide deacetylase, one of the first CE4 enzymes to be characterized (John et al., 1993). The activity of these enzymes has been discovered in several fungi, marine bacteria, and insects (Tsigos et al., 2000; Hirano et al., 2015). Chitin and chitoooligosaccharides deacetylases have a wide range of molecular masses, ranging from 12 to 150 kDa. The optimum temperature for the activity of most ChDa varies from 30 to 60°C (Grifoll-Romero et al., 2018). Fungal ChDa can exist as intracellular (e.g., from *Mucor rouxii*, *Absidia orhidis*) or extracellular enzymes (e.g., produced by *Mucor circinelloides*, *Colletotrichum lindemuthianum*, *Aspergillus nidulans*) (**Table 4**) (Jaworska, 2012; Kaczmarek et al., 2016). Thanks to the catalytic capabilities of these enzymes, and significant thermal stabilities ChDa are more often seen as suitable tools for biotechnological chitosan production. Currently, the challenge is to develop enzymatic methods that enable the conversion of the native form of chitin to its deacetylated derivatives. Martinou et al.

(1997) indicated that two chitin deacetylases isolated from *Absidia coerulea* and *Mucor rouxii* are not able to efficiently modify native chitin. They suggest that the pre-treatment of crystalline chitin is, therefore, a necessary step before addition of an enzyme in order to improve the accessibility of the acetyl groups and to enhance the yield and the rate of the deacetylation reaction. A contrasting study conducted by Win and Stevens (2001) showed that the pre-treatment of chitin using various physical and chemical conditions did not result in a more efficient enzymatic deacetylation catalyzed by ChDa from *Absidia coerulea*. However, decrystallised chitin superfine (SF) obtained by dissolution of native chitin in specific solvents followed by fast precipitation, pre-treated with 18% formic acid, appeared to be a suitable substrate for fungal deacetylase. In this way, chitin (10% DD) was deacetylated by the enzyme into chitosan with DD of 90%. Kim et al. (2008) in his research tested a variety of substrates such as crystalline-β-chitin, chitin and chitosans with different DD, water-soluble chitin (DD 50%) (WSCT-50), glycol chitin and other chitin derivatives. Obtained results indicated that chitin deacetylases isolated from *Mortierella* sp. are only capable of the efficient deacetylation of WSCT-50, glycol chitin, and crab chitosan (DD 71) with a relative activity 100, 35, and 49%, respectively. However, Tuveng et al. (2017) described extracellular ChDa from marine *Arthrobacter* species which showed activity against insoluble β-chitin. Unfortunately, no efficient enzymatic method of deacetylation of crystalline, native chitin has been developed so far.

However, the use of these enzymes can significantly reduce the dependence on conventional chitosan's production methods. It has been demonstrated that ChDa and CODa isolated from different sources exhibit different catalytic mechanisms, indicating that a variety of well-defined chitoooligosaccharides can be produced during a single enzymatic reaction. The mechanism of action of enzymes that modify monomers within the polymer chain is commonly classified as multiple-attack, multiple chains, or single-chain mechanism (**Figure 3**) (Grifoll-Romero et al., 2018). For example, exo-type ChDa from *M. rouxii*, hydrolyses the acetyl groups of chitinous polymers such as glycol chitin, colloidal chitin, chitosan, chitin, and chitoooligosaccharides (DP 1–7) from non-reducing end according to the progressive multiple-attack mechanism. The binding of the enzyme to the polysaccharide chain is followed by a number of sequential deacetylations, after which the enzyme binds to another region of the polymeric chain. This mechanism generates a block-copolymer structure with GlcN units within the GlcNAc chain (Araki and Ito, 1975; Martinou et al., 1998). Martinou et al. (1998) indicated that the length of the COS has a significant impact on enzyme activity. It has been shown that *M. rouxii* chitin deacetylase cannot effectively deacetylate COS with DP < 3. On the other hand (GlcNAc)<sub>4</sub> and (GlcNAc)<sub>5</sub> were fully deacetylated by the enzyme, while in the case of (GlcNAc)<sub>3</sub>, (GlcNAc)<sub>6</sub>, and (GlcNAc)<sub>7</sub> the reducing-end residues were always intact. Fungal ChDa from *Colletotrichum lindemuthianum* was another enzyme with a thoroughly investigated mode of action. Unlike the ChDa from *M. rouxii* the *C. lindemuthianum* protein is an endo-type extracellular enzyme catalyzing the hydrolysis of acetamido groups according to a multiple-chain mechanism. The



enzyme forms an active complex with the polymer chain and catalyzes the hydrolysis of only one acetyl group. After hydrolysis enzyme dissociates from complex and the cycle restarts. This mode of action generates binary heteropolysaccharides with a random distribution of deacetylated units (Blair et al., 2006). Tokuyasu et al. (1997) indicated that  $(\text{GlcNac})_3$  and  $(\text{GlcNac})_4$  were fully deacetylated, whereas the reducing-end residues  $(\text{GlcNac})_2$  could not be deacetylated. Recombinant chitin deacetylase from *Pestalotiopsis* sp. deacetylates all residues of the substrates (DP2-DP6) leaving unmodified GlcNac residue at the reducing end and the last two GlcNac units from the non-reducing end. Obtained results indicated that enzyme catalyzed the deacetylation reaction through a multiple-chain mechanism (Cord-Landwehr et al., 2016). Another example of an enzyme that works according to this mechanism is CE4 deacetylase isolated from a marine *Arthrobacter* species which was active against chitosan, acetylxylan, insoluble chitin and COS with DP ranging from 2 to 6 (Tuveng et al., 2017). In the single chain mechanism, the processive enzyme catalyzed a number of deacetylation reactions on a single substrate molecule leading to sequential deacetylation. Enzymes of bacterial origin, which are capable of deacetylation of chitoooligosaccharides show this mechanism of action (Li et al., 2007). Chitoooligosaccharides

deacetylase described by Li et al. (2007) produced COS lacking only one acetyl group compared to the substrates. ChDa and CODa with diverse activities against chitoooligosaccharides are powerful tools for the production of COS with desired properties. **Table 5** presents examples of ChDa and CODa with well-characterized activities against COS with different DP.


Presently, COS are manufactured industrially by chemical or physical depolymerization of the respective polymers (Aam et al., 2010; Mourya et al., 2011). Unfortunately, their production involves harsh thermo-chemical treatment, resulting in a high cost of processes and in large amounts of generated chemical wastes which are environmentally unfriendly. Moreover, the production is challenging to control and leads to broad heterogeneous mixtures. In this context, it should be mentioned that the biological and physicochemical properties of COS are also strongly dependent on the DA, DP, and MW. Jeon and Kim (2000) found that antibacterial and antifungal activity of COS grew with an increase of DP. Additionally, the inhibitory effect was much stronger for COS with lower DA than for those with a high degree of acetylation. It has been reported that COS with higher DA exhibited the highest ACE (angiotensin-converting enzyme) inhibitory effect, which prevents increases in blood pressure (Park et al., 2003). Huang et al. (2006) established

**TABLE 4** | The biochemical properties of known fungal chitin deacetylases.

Organism	pH optimum	Temp. optimum (°C)	Molecular mass (kDa)	Activation	Inhibition	Substrate specificity	References
<i>Pestalotiopsis</i> sp.	8.0	55	ND	–	Fe <sup>2+</sup> , Mn <sup>2+</sup>	Active against: soluble chitosan, colloidal chitin the activity increases with the increase of the DA of the substrate inactive against: insoluble $\alpha$ -chitin and $\beta$ -chitin	Cord-Landwehr et al., 2016
<i>Colletotrichum lindemuthianum</i>	11.5–12.0	60	33	Co <sup>2+</sup> , Zn <sup>2+</sup> (1 mM)	Co <sup>2+</sup> (10 mM), Ni <sup>2+</sup> , Fe <sup>2+</sup> , Cu <sup>2+</sup> , Mn <sup>2+</sup>	active against: glycol chitin, partially N-deacetylated water soluble chitin, chitin oligomers inactive against: N-acetylglucosamine.	Tokuyasu et al., 2009
<i>Rhizopus circinans</i>	5.5–6.0	37	75	Mn <sup>2+</sup> , Mg <sup>2+</sup>	Cu <sup>2+</sup>	Active against: glycol chitin, partially deacetylated chitin, native chitin, low activity against chitoheptoses, colloidal chitin	Gauthier et al., 2008
<i>Aspergillus nidulans</i> CECT 2544	7.0	50	27	–	Cd <sup>2+</sup> , Co <sup>2+</sup> , Ag <sup>2+</sup> , Ca <sup>2+</sup> , Sn <sup>2+</sup> , Pb <sup>2+</sup> , Zn <sup>2+</sup> , Mg <sup>2+</sup> , Mn <sup>2+</sup> (40 mM)	Active against: glycol chitin, acetylated oligomers, chitin, colloidal chitin, $\alpha$ -1 $\rightarrow$ 3, 1 $\rightarrow$ 6-N-acetylgalactosamine-galactan	Alfonso et al., 1995
<i>Saccharomyces cerevisiae</i>	8.0	50	43	Co <sup>2+</sup>	Mg <sup>2+</sup> , Ca <sup>2+</sup> , Zn <sup>2+</sup> , Cu <sup>2+</sup>	Active against: hexa-N-acetylchitoheptose	Martinou et al., 2002
<i>Mucor rouxii</i> ATCC 24905	5.8	50	ND	Zn <sup>2+</sup> , Ca <sup>2+</sup> , Co <sup>3+</sup>	Mn <sup>2+</sup> , Fe <sup>2+</sup> , Fe <sup>3+</sup>	Active against: colloidal chitin, carboxymethylcellulose, crystalline chitin and dissolved chitosan with DA 6%.	Kolodziejska et al., 1999
<i>Scopulariopsis brevicaulis</i>	7.5	55	55	ND	ND	Active against: crystalline chitin, water-soluble chitosan (54% DD), N-acetyl-chitooligosaccharides with DP of 2–6, but not for GlcNAc	Cai et al., 2006

that the molecular weight of COS also played a significant role in their antitumor activity. Thus, the attention is increasingly being focused on enzymatic methods, especially those using specific enzymes, such as chitosanases and chitinases (Abdel-Aziz et al., 2014). Generally, chitinases are defined as a group of enzymes that catalyze the cleavage of chitin. The enzyme nomenclature committee has defined **chitinases** (EC 3.2.1.14) as the enzymes capable of performing endohydrolysis of  $\beta$ -1,4-linkages in chitin. Many authors distinguish another subclass of chitinases, endochitinases— **$\beta$ -N-acetylhexosaminidases** (EC 3.2.1.52), that catalyze the hydrolysis of terminal non-reducing N-acetyl-D-hexosamine residues in chitin (Duo-Chuan, 2006). Chitinases, which represent a class of glycosidic hydrolases, were found in many organisms, including viruses, bacteria, fungi, insects, higher plants, and mammals, in which they fulfill different functions (Karthik et al., 2014). Fungal chitinases have a wide range of molecular masses, ranging from 30 to 108 kDa. The optimum temperature for the activity of most fungal chitinases varies from 20 to 40°C. It has been reported that enzymes isolated from two thermophilic fungi *Thermomyces lanuginosus* (Zhang M. et al., 2015) and *Talaromyces emersonii* (McCormack et al., 1991) exhibit higher optimum temperature and thermostability. The recombinant Chit1 from *Thermomyces*

*lanuginosus* exhibited optimum activity at 50°C and retained 56% of its activity at 60°C after 30 min, while Chit2 was optimally active at 40°C and retained 71% of its activity at 50°C after 60 min (Zhang J. et al., 2015). **Table 6** shows examples of chitinases of microbial origin. Based on amino acid sequence similarity of catalytic domains, chitinases have been classified into glycosyl hydrolase families GH-18 and GH-19, which do not share a typical structure. GH-18 chitinases are characterized by a ( $\beta/\alpha$ )<sub>8</sub> barrel fold, while GH-19 chitinases are characterized by a high content of  $\alpha$ -helices (Stoykov et al., 2015). These two families exhibit different mechanisms of catalysis. It has been shown that chitinases from the GH-18 family use retaining mechanism yield  $\beta$ -anomer hydrolysis products, whereas family GH-19 result in the  $\alpha$ -anomer (an inverting mechanism) (Brameld and Goddard, 2002). Meanwhile, exochitinases, i.e.,  $\beta$ -N-acetylhexosaminidases, have been assigned to the GH-20 family (Karthik et al., 2014). The GH-18 family chitinases are found in bacteria, fungi, yeast, viruses, plants and animals, while members of the GH-19 family have mostly been identified in plants. The GH-20 family includes bacterial and human chitinases (Duo-Chuan, 2006; Karthik et al., 2014). It has been proven that some organisms can produce more than one kind of chitinases. For example, the mycoparasite *Stachybotrys elegans*



produces two exochitinases ( $\beta$ -N-acetylhexosaminidases) and one endochitinase (Taylor et al., 2003). Chitinases have the unique ability to hydrolyse GlcNAc-GlcNAc bonds makes these enzymes capable of hydrolysing chitin and to some extent, partially acetylated chitosan as well.

Song et al. (2018) investigated the degradation patterns of chitin oligosaccharides using chitinase purified from pear pollen *Pyrus bretschneiderilia*. During 24-h reaction the enzyme acted as an endo-type chitinase and effectively degraded (GlcNAc)<sub>5</sub> and (GlcNAc)<sub>6</sub> to (GlcNAc)<sub>2</sub>, (GlcNAc)<sub>3</sub>, (GlcNAc)<sub>4</sub>; and to (GlcNAc)<sub>2</sub>, (GlcNAc)<sub>3</sub>, (GlcNAc)<sub>4</sub>, (GlcNAc)<sub>5</sub>, respectively. However, no degradation occurred for (GlcNAc)<sub>2</sub> and (GlcNAc)<sub>3</sub>. The highest enzymatic activity was observed at 37°C, at pH 3 after a 3-h incubation. Chitinase from thermophilic *Humicola grisea* was studied by Kumar et al. (2017). Thin-layer chromatography (TLC) revealed that the enzyme could effectively produce COS using colloidal chitin as a substrate. After 30 min of incubation at 60°C a substantial increase in (GlcNAc), (GlcNAc)<sub>2</sub>, and (GlcNAc)<sub>3</sub> was noticed. Prolonged incubation (up to 240–300 min) resulted in a further increase in (GlcNAc) concentration. Another study on chitinase was conducted by Moon et al. (2017). They used partially purified chitinase from *Serratia marcescens* to investigate the patterns of degradation of (GlcNAc)<sub>2–4</sub>. With (GlcNAc)<sub>4</sub> as a substrate, the highest concentration of (GlcNAc)<sub>1–3</sub> was obtained at

50°C, whereas at 70°C only (GlcNAc)<sub>2</sub> was detected. Moreover, TLC analysis revealed that the most substantial amount of (GlcNAc)<sub>1–3</sub> was produced at pH 5.0–6.0. The obtained results indicated that the reaction conditions may have a significant impact on the mode of the action of a biocatalyst.

**Chitosanases** (EC 3.2.1.132) constitute a family of enzymes capable of performing endohydrolysis of a  $\beta$ -1,4-glycosidic bond between GlcN residues in partially acetylated chitosan, from the reducing end. There is also another class of enzymes, **exo- $\beta$ -D-glucosaminidase** (EC 3.2.1.165) that attack chitosan from its non-reducing end (Thadathil and Velappan, 2014). The activity of chitosanases has been observed in many different microorganisms, including bacteria, cyanobacteria, fungi, and plants (Thadathil and Velappan, 2014) in which they occur as intra- or extracellular enzymes. Most bacteria and fungi secrete chitosanases extracellularly except for fungi belonging to the class *Zygomycetes* [e.g., *Absidia orchidis* (Jaworska, 2012), *Mucor rouxii* (Alfonso et al., 1992), *M. circinelloides* (Struszczyk et al., 2009; Struszczyk-Swita et al., 2017)]. Intracellular chitosanases were also found in plants (Osswald et al., 1994). The biochemical properties of chitosanases depend on the source of enzymes, and their properties are summarized in **Table 7**. Most chitosanases are characterized by molecular masses, ranging from 10 to 75 kDa. However, many exceptions can be found in the literature; for example,



**TABLE 5** | Examples of ChDa and CODa with characterized activity against COS with different DP.

Source	ID Uniprot or GenBank	Substrates	Products PA	References
<i>Aspergillus nidulans</i>	Q5AAA0	DP 2–5 activity increased with increased DP	DP2 GlcN-GlcNAc DP3-6 GlcN <sub>n</sub>	Liu et al., 2017
<i>Podospora anserine</i>	XP_001912680.1	Polymeric chitosans with different DAs	DP <sub>n</sub> GlcN	Hoßbach et al., 2018
<i>Puccinia graminis</i>	XP_003323413.1	DP 4–6 activity increased with increased DP	GlcNAc-GlcNAc-GlcN <sub>n-2</sub>	Naqvi et al., 2016
<i>Pastolotiopsis</i> sp.	APH81274.1	DP 4–6	GlcNAc-GlcNAc-GlcN <sub>n-3</sub> -GlcNAc	Cord-Landwehr et al., 2016
<i>Pachonia chlamydosporia</i>		DP 4–6 non-active against DP < 4	GlcNAc-GlcN-GlcN-GlcNAc <sub>n-3</sub>	Aranda-Martinez et al., 2018
<i>Vibrio cholerae</i>	Q9KSH6	DP 2–6 activity increased with decreased DP	GlcNAc-GlcN-GlcNAc <sub>n-2</sub>	Li et al., 2007
<i>Shewanella baltica</i>	ABN60929.1	DP 2–4; increase in activity DP2>DP4>DP3	DP2 GlcNAc-GlcN DP 3–4 GlcNAc-GlcN-GlcNAc <sub>n-2</sub>	Hirano et al., 2017
<i>Saccharomyces cerevisiae</i>		DP 4	GlcN-GlcNAc- GlcNAc- GlcNAc GlcNAc- GlcN- GlcNAc- GlcNAc GlcNAc- GlcNAc- GlcN- GlcNAc GlcN- GlcN- GlcNAc- GlcNAc GlcN- GlcNAc- GlcN- GlcNAc GlcNAc- GlcN- GlcN- GlcNAc GlcN- GlcN- GlcN- GlcNAc	Zhu et al., 2019

**TABLE 6** | The biochemical properties of chitinases.

Organism	pH optimum	Temp. optimum (°C)	Molecular mass (kDa)	Activation	Inhibition	Substrate specificity	References
<i>Paenibacillus pasadenensis</i> CS0611	5.0	50	69	–	Mn <sup>2+</sup> , Mg <sup>2+</sup> and Co <sup>2+</sup>	Active against: colloidal chitin, chitin powder, crab shell powder Inactive against: chitosan, carboxymethyl cellulose and cellulose	Guo et al., 2017
<i>Streptomyces albolongus</i> ATCC 27414	5.5	55	47	Mn <sup>2+</sup> , Ba <sup>2+</sup> , Na <sup>+</sup>	Fe <sup>3+</sup> , Cu <sup>2+</sup> , Na <sub>2</sub> EDTA and SDS	Active against: colloidal chitin, chitin powder, chitosan, colloidal chitin	Gao et al., 2018
<i>Humicola grisea</i>	3.0	70	50	Mn <sup>2+</sup> , Co <sup>2+</sup> , NH <sub>4</sub> <sup>+</sup> and Mg <sup>2+</sup>	Hg <sup>2+</sup> , Ca <sup>2+</sup> , Cu <sup>2+</sup> , K <sup>+</sup> and EDTA	Active against: (GlcNAc) <sub>2</sub> , (GlcNAc) <sub>3</sub> And colloidal chitin	Kumar et al., 2018
<i>Thermobifida fusca</i> reveals Tfu_0580	6.0	30	ND	Ca <sup>2+</sup> and Mn <sup>2+</sup>	–	active against: (p-NP-(GlcNAc) <sub>3</sub> ), (p-NP-(GlcNAc) <sub>2</sub> )	Yan and Fong, 2018
<i>Aspergillus terreus</i>	5.6	50	60	Ca <sup>2+</sup> , Mn <sup>2+</sup> and Na <sup>2+</sup>	Cd <sup>2+</sup> , Zn <sup>2+</sup> , pb <sup>2+</sup> and Hg <sup>2+</sup>	ND	Farag et al., 2016
<i>Penicillium</i> sp. LYG 0704	5.0	50	41	Mg <sup>2+</sup> and Mo <sup>2+</sup>	Fe <sup>2+</sup> and Hg <sup>2+</sup>	ND	Lee et al., 2009

chitosanase from *Aspergillus fumigatus* KH-94 has larger molecular weight of 108 kDa (Thadathil and Velappan, 2014). The optimum pH of microbial chitosanases' activity ranges from 4 to 8, while the optimum temperature varies from 30 to 60°C and is closely associated with the growth conditions of the microorganism that synthesizes them. Thermostable chitosanases have been reported in several articles (Chen X. et al., 2012; Zitouni et al., 2013; Doan et al., 2019a). Thermostability is particularly useful during enzymatic hydrolysis at higher

temperatures, allowing chitosan to be dissolved at higher concentrations (Zitouni et al., 2013).

Based on their amino acid sequences, chitosanases are classified into seven families of glycoside hydrolases (GH-3, GH-5, GH-7, GH-8, GH-46, GH-75, and GH-80), further grouped into four classes based on their cleavage specificity (Weikert et al., 2017). GH-46, GH-75, and GH-80 contain only chitosanases, while the families GH-5, GH-7, and GH-8 contain other glycoside hydrolases, such as cellulase and xylanase (Viens




**TABLE 7** | The biochemical properties of chitosanases.

Organism	pH optima	Temp. optima (°C)	Molecular mass (kDa)	Isoforms	Activation	Inhibition	Substrate specificity	References
<i>Bacillus licheniformis</i> MB-2	6-7	70	75	–	Mn <sup>2+</sup> , Co <sup>2+</sup> , Ca <sup>2+</sup> , urea	Ni <sup>2+</sup> , Zn <sup>2+</sup>	Active against: chitosan with different DD; glycol chitosan, colloidal chitosan Inactive against: glycol chitin, colloidal chitin	Ekowati et al., 2006
<i>Paenibacillus</i> sp. 1794	4.8	80–85	40	–	ND	ND	Active against: chitosan, carboxymethylcellulose, chitosan or cellulose-derived hexasaccharides inactive against: chitin	Zitouni et al., 2013
<i>Mucor circinelloides</i>	5.5–6	37	42	–	Ca <sup>2+</sup> , Mn <sup>2+</sup> , Mg <sup>2+</sup>	Hg <sup>2+</sup> , Cu <sup>2+</sup> , Ag <sup>2+</sup>	Active against: chitosan with high DD inactive against: colloidal chitin, sodium salt of carboxymethylcellulose, starch	Struszczuk et al., 2009
<i>Aspergillus</i> QD-2	5.6	55	ND	–	ND	ND	ND	Zhang et al., 2012
<i>Gongronella</i> sp. JG	5.6	55–60	28	–	Mn <sup>2+</sup> , Ca <sup>2+</sup> , Sr <sup>2+</sup>	EDTA-	Active against: colloidal chitosan inactive against: colloidal chitin, carboxymethylcellulose	Wang J. et al., 2008
<i>Serratia marcescens</i> TKU011	5	50	21	–	–	EDTA, Mn <sup>2+</sup> , Fe <sup>2+</sup>	Active against: chitosans with different DD inactive against: colloidal chitin and chitin	Wang S. et al., 2008
<i>Anabaena fertilissima</i>	7.5	27	ND	–	Cu <sup>2+</sup> , Zn <sup>2+</sup>	Ag <sup>+</sup> , Fe <sup>3+</sup> , Hg <sup>2</sup>	Active against: glycol chitosan, colloidal chitin, CM-chitosan, and colloidal chitosan (low)	Gupta et al., 2012
<i>Streptomyces roseolus</i>	5	50	41	–	Mg <sup>2+</sup>	Cu <sup>2+</sup> , Co <sup>2+</sup> , Mn <sup>2+</sup> , Zn <sup>2+</sup>	Active against: colloidal chitosan, glycol chitosan (weakly), glycol chitin (weakly)	Jiang et al., 2012
<i>Bacillus cereus</i> D-11	6	60	41	–	–	Hg <sup>2+</sup> Pb <sup>2+</sup> Cu <sup>2+</sup>	Active against: colloidal chitosans very low activity against glycol chitosan, chitosan powder, chitin	Gao et al., 2008
<i>Acinetobacter calcoaceticus</i> TKU024	6	50	27	CHSA1	–	Mn <sup>2+</sup>	CHSA1 and CHSA2 active against: chitosans with different DD, chitin	Wang et al., 2011
<i>Acinetobacter calcoaceticus</i> TKU024	7	60	66	CHSA2	–	Mn <sup>2+</sup>		
<i>Staphylococcus capitis</i>	7	30	35	–	Mn <sup>2+</sup> Zn <sup>2+</sup> , Cu <sup>2+</sup>	Ba <sup>2+</sup> , Mg <sup>2+</sup> , Ca <sup>2+</sup> and Ni <sup>2+</sup>	Active against: soluble chitosan, colloidal chitosan, powdered chitosan inactive against colloidal chitin, carboxymethylcellulose	Sun et al., 2018

et al., 2015). All known chitosanases can cleave GlcN-GlcN bond, while class I chitosanases can additionally cleave GlcNAc-GlcN bond. The best-known example of a class I chitosanase is an enzyme from *Streptomyces* sp. N174 which belongs to the GH-46 family. Another example of GH-46 chitosanase is an enzyme from *Bacillus* MH-K1, which was classified into class III. Enzymes belonging to this class are capable of cleaving GlcN-GlcNAc bond, in addition to GlcN-GlcN. Class II chitosanases, such as these from *Bacillus* sp. No. 7-M (GH-8), are limited to cleave GlcN-GlcN bonds exclusively. Another extensively studied and recently introduced a class of chitosanases is class IV belonging to the GH-46 family. Ando et al. (2008) revealed that chitosanases from this class could cleave all bonds except GlcNAc-GlcNAc. It was previously thought that chitosanases,

in general, are not able to hydrolyse GlcNAc-GlcNAc bond. Surprisingly, results obtained by Heggset et al. (2010) abolished a clear distinction between chitinases and chitosanases. Strikingly, the chitosanase from *Streptomyces coelicolor* A3(2) was able to cleave all glycosidic bonds, including GlcNAc-GlcNAc. Until now, the members of the GH46 family have been the best characterized among all chitosanases. The chitosanases from GH46 family have a highly electronegative substrate-binding cleft, in contrast to other glycoside hydrolases of various substrate specificities (Viens et al., 2015). A high content of acidic residues (Asp and Glu) in the substrate-binding cleft is thought to be responsible for the high specificity of these proteins and their poor recognition of chitinous and highly N-acetylated substrates (Marcotte et al., 1996). Most chitosanases of the GH46 family are



$\alpha$ -helical proteins, composed of two lobes which are separated by a substrate-binding cleft. The best-known enzyme from this family, in terms of structure and mechanism of hydrolysis of the  $\beta$ -1,4-glycosidic bond, is chitosanase isolated from the bacterial strain *Streptomyces* sp. N174. The molecular structure of this enzyme shows ten  $\alpha$ -helices and three  $\beta$ -sheets. This chitosanase is dumbbell-shaped and 55 Å long containing two globular domains connected through a bent 27-residue backbone helix. The domain forms cleft, 10 Å wide and 12 Å deep. The binding of chitosan to the active site suggests that the mechanisms of substrate and catalytic binding may be similar to other glycohydrolases. The X-ray structure suggested that Glu 22 and Asp 40 are essential for the catalytic function of this chitosanase (Marcotte et al., 1996). The chitosanase from *Bacillus* MH-K1 has two globular upper and lower domains, which generate the active site cleft for the substrate binding. The molecular folding is similar to the described earlier chitosanase from *Streptomyces* sp. N174, but there is only 20% identity at the amino acid sequence level between both chitosanases. There are three regions of markedly different topology. The disulfide bridge between Cys50 and Cys124 joins the  $\beta$ 1 strand and the  $\alpha$ 7 helix is unique to the structure and not conserved among other chitosanases. The orientation of two backbone helices, connecting the two domains, is also distinct. The helix is responsible for the differences in size and shape of the active site cleft in these two chitosanases. The discussed differences of the active site cleft are believed to be behind different substrate specificities of these enzymes. It has been proved that the size and shape of the cleft are such that the substrate sugar with the acetyl groups at positions suitable for the specific cleavage reaction can be accommodated in the active site, which affords reaction specificity for substrate recognition of this chitosanase (Saito et al., 1999).

Most recent classification of chitosanases is based on the ability of enzymes to cleave bonds at GlcNAc residues positioned at a (−1) or (+1) subsite (Figure 4). It has been proven that this ability varies, especially when substrates have a different fraction of acylation. Weikert et al. (2017) showed that the current classification system is no longer tenable and might not be applicable to chitosanases. Conflicts with the recent

classification are observed for the reactions in which high FA (fraction of acetylation) oligomers were used as substrates. They recommended a chitosanases classification system which is based on specificity and preferences toward subsite (−2) to (+2). Gercke et al. (2019) used rational protein engineering methods to produce modified chitosanase from *Bacillus* sp. The obtained enzyme was specific toward subsite (−3) to (+3) and able to produce DP4 COS by hydrolysing fully deacetylated substrates.

It has been reported that chitosanases from different sources may exhibit different catalytic mechanisms dependent, among other factors, on the DD of substrates (Sinha et al., 2016). Moreover, microbial chitosanases produce a relatively higher yield of COS, comparing to enzymes from other sources (Kim and Rajapakse, 2005). Kohlhoff et al. (2017) characterized chitosanase from *Alternaria alternata*. The enzyme showed a specific cleavage pattern exclusively toward bonds following GlcN-GlcNAc pairs. Moreover, the optimum activity was observed against moderately acetylated chitosans, low activity against fully acetylated or fully deacetylated chitosans, and no activity against glycol chitin. Qin et al. (2018) conducted a controllable preparation of COS in mild conditions (30°C, pH 5.5) using a novel cold-adapted chitosanase from a Rhizobacterium *Gynuella sunshinyii*. With chitosan as a substrate, the main products obtained were (GlcNAc)<sub>2</sub> and (GlcNAc)<sub>3</sub> (yield = 94.6%). The enzyme belongs to the GH-46 family and showed no catalytic specificity toward chitin. Studies on chitosanase produced by *B. subtilis* conducted by Su et al. (2017) showed a promising ability of this enzyme to hydrolyse chitosan to (GlcNAc)<sub>2</sub>, (GlcNAc)<sub>3</sub> and (GlcNAc)<sub>4</sub>. Nidheesh et al. (2015) investigated chitoooligomers production by crude chitosanase from *Purpureocillium lilacinum* CFRNT12. The enzyme was tested on different chitosan substrates (colloidal and crystalline chitosan). For both substrate forms, the maximum concentration of chitoooligomers was observed after 24 h of hydrolysis. The enzyme performed the endo- type of hydrolysis. Chitosan trimers and tetramers accounted for the majority of the product.

The efficiency of traditional glycoside hydrolases (GHs), such as chitinases and chitosanases, is highly limited due to the strong crystallinity and insolubility of chitin in an aqueous environment.

To tackle this problem, pre-treatment of native chitin is necessary for efficient depolymerization of the substrate. Traditionally, chitin is treated with strong acids, such as hydrochloric acid (for colloidal chitin) (Guo et al., 2017) or phosphoric acid (for swollen chitin) (Bansode and Bajekal, 2006), to maximize its enzymatic accessibility. In contrast to conventional GHs, Lytic Polysaccharide Monooxygenases (LPMOs) are capable of directly cleaving glycolic bonds in highly crystallized chitin, increasing its accessibility for subsequent enzymatic processing (Eijsink et al., 2019).

LPMOs (EC 1.14.99.53-56) are enzymes capable of cleaving glycolic bond in crystalline polysaccharides through oxidizing either C1 or C4 of the glucopyranose ring. The oxidation mechanism requires a reductant (such as ascorbic acid), an oxygen-containing co-substrate ( $O_2$  or  $H_2O_2$ ), and a single bound copper ion. LPMOs share a typical immunoglobulin-like  $\beta$ -sandwich core structure, and most LPMOs are single domain enzymes (Vaaje-Kolstad et al., 2017). LPMOs have been assigned to auxiliary activity (AA) families AA9, AA10, AA11, AA13, AA14, and AA15 in the Carbohydrate-Active Enzymes (CAZy) database (Tandrup et al., 2018). These enzymes act on a range of polysaccharides including cellulose, chitin, starch, xyloglucan, glucomannan, and cellodextrins. Chitin-active LPMO was first demonstrated in 2010 for the *Serratia marcescens* AA10 (CBP21) (Vaaje-Kolstad et al., 2010). To date, LPMOs with chitinolytic activity has been expanded to families AA10, AA11, and AA15 (Hemsworth et al., 2015). The majority of chitinolytic LPMOs reported to date have been observed in fungi and bacteria in organisms such as *Streptomyces gresius*, *Enterococcus faecalis*, and *Bacillus thuringiensis*. The presence of chitinolytic LPMO genes has also been reported in a virus (Chiu et al., 2015) and even an arthropod (Sabbadin et al., 2018). Bai et al. reported that chitinolytic AA10 LPMO genes are present in about one-third of terrestrial bacterial genomes but absent in strict anaerobes (Bai et al., 2016).

Additionally, when combined with GHs, LPMOs contribute synergistically to overall substrate solubilization and thus significantly reduce the load of enzyme cocktails (Mutahir et al., 2018). Nakagawa et al. (2013) studied the enzymatic depolymerization of  $\alpha$ -chitin with varying particle size and crystallinity produced by mechanical pre-treatment. It was found that the synergies between LPMO (CBP21 from *S. marcescens*) and monocomponent chitinases were clear for all substrates but more significant for substrates with high degrees of crystallinity. Hamre et al. (2015) reported that LMPO (CBP21) could boost the apparent  $k_{cat}$  values of exo-active chitinases ChiA and ChiB, of which the apparent  $k_{cat}$  values were boosted from  $1.7 \text{ s}^{-1}$  and  $1.7 \text{ s}^{-1}$  to  $11.1$  and  $13.9 \text{ s}^{-1}$ , respectively. However, such effect was not observed in endo-active chitinase ChiC. Mekasha et al. (2017) optimized the proportion of chitinases (*SmChiA*, *SmChiB*, *SmChiC*), an LMPO (*SmLPMO10A*) and a beta-N-acetylhexosaminidase (*SmCHB*) for the saccharification of shrimp and crab chitins. It was found that when *SmLPMO10A* was present at 3 and 2%, for shrimp and crab chitin, respectively, the corresponding saccharification yields reached 70%-75%. These results were significantly higher than those of a "minimal" cocktail of *SmChiA* and *SmCHB* where only 40% yield of

saccharification was achieved. LPMOs could also be used to prepare functionalized chitin materials. Wang et al. (2018) successfully introduced 35 nmol of carboxylate ( $COO^-$ ) moieties per milligram of  $\alpha$ -chitin with a new LPMO *FfAA11*, without affecting the crystallinity of the chitin fibers. In the same research, LPMO in combination with a chemical method was also employed to transform recalcitrant chitins into desirable functionalized (nano)materials.

## BIOLOGICAL ACTIVITY OF CHITIN AND ITS DERIVATIVES

The specific properties of chitin provide numerous potential applications of this biopolymer. Unfortunately, the use of chitin is significantly limited due to the low reactivity and lack of solubility in water and common organic solvents. The most useful chitin derivative is chitosan, which is beneficial for biomedical applications due to biocompatibility, biodegradability and low toxicity. The most important biological activities of chitosan and its degradation products (COS) include antimicrobial, antiviral, antitumor, and antioxidant activities. The spectrum of antimicrobial activity of chitosan and COS includes bacteria, filamentous fungi, and yeast. Chitosan, however, shows its antimicrobial activity only in an acidic medium because of its poor solubility above pH 6.5. Thus, water-soluble COS may be good candidates as a polycationic biocide. The mechanism of their antimicrobial activity has not yet been clearly explained. According to Liaquat and Eltem (2018) contradictions in the proposed mechanisms may be the result of the use of various microorganisms and methods in research, as well as the quality, purity and characteristics of the COS being analyzed. One of the theories explaining this mechanism says that the inhibitory effect of chitosan and COS on bacterial growth is related to their polycationic nature, resulting from the presence of free  $-NH_2$  groups in units of D-glucosamine forming the chains of these compounds. This enables them to bind strongly to carboxyl groups with negative charge of compounds building external cell membranes of microorganisms (Kittur et al., 2003; Vishu Kumar et al., 2005, 2007). Chitosan and its oligomers can reduce the permeability of the cell membrane, forming a coating on its surface and thereby blocking cell access to external nutrients, which leads to its death (Vishu Kumar et al., 2007). It is generally recognized that the number of  $-NH_2$  groups and also the antibacterial activity often increases with the simultaneous increase of their DP value (Vishu Kumar et al., 2005). The higher activity of chitosan degradation products in relation to the high molecular biopolymer is explained by the possibility of the former penetrating the cells, where they block RNA transcription as a result of adsorption with bacterial DNA (Kim et al., 2003; Mei et al., 2015). The mechanism of interaction of chitosan and its degradation products with bacterial cells depends to a large extent on the structure of the cell wall of a given microorganism. In the case of gram-positive bacteria having a cytoplasmic membrane covered with a cell wall formed of several dozen layers of peptidoglycan containing negative GlcNAc, N-acetylmuramic acid, numerous amino acids, or teichoic acids,

primarily for strong binding characterized by the opposite charge COS and LMWCh. This causes deformation of the bacterial cell wall, which in turn is associated with the exposure of the cytoplasmic membrane to osmotic shock, the burst of the cytoplasm and ultimately the death of bacteria. In contrast, the gram-negative bacterial cell contains an outer membrane consisting, among others from lipopolysaccharides (LPS) and proteins; a cell wall with only 1–3 layers of peptidoglycan and a cytoplasmic membrane. Negatively charged O-specific side polysaccharide chains form an ionic type combination with COS or LMWCh amine groups. In the case of COS, cell access to external nutrients is blocked. Due to the strong binding of LPS side chains to the outer membrane of the cell, its destruction does not occur—as was the case with the gram-positive group of bacteria. The smaller the DP of chitosan degradation products and the higher the electronegative charge of bacteria, the easier the associated and aggregation of these compounds occurs, and thus the blockade of the supply of external nutrients and the final cell death (Vishu Kumar et al., 2005). On the other hand, the charge of oligomers with a higher DP, i.e., LMWCh, is large enough to remove the LPS associated with them from the cell membrane and subsequently to cell lysis (mechanism as in the case of gram-positive bacteria) (Vishu Kumar et al., 2007).

The antimicrobial properties of chitosan and its degradation products depend on many factors, including their source and concentration, molecular weight and deacetylation degree, and the strain of the microorganism on which they were tested (Kyoon et al., 2003; Liu et al., 2006; Li et al., 2014; Laokuldilok et al., 2017; Bonilla et al., 2019; Shi et al., 2019). It was found that in the case of COS, their DP with a value of not less than five is essential for antibacterial activity of fully deacetylated COS (Li et al., 2014). Jeon et al. (2001) indicated that COS exhibits antimicrobial activity against Gram-positive and Gram-negative bacteria. However, high-molecular-weight COSs (5 000–10 000 Da) exhibited higher antimicrobial activity than low-molecular-weight COSs. It has been proven that positively charged COSs interact with negatively charged bacterial cell walls, resulting in suppression of the metabolic activity of bacteria by reducing nutrient permeation through the cell wall. Therefore, the death rate of bacterial cells increases upon an increase in the DD of COSs (Tsai et al., 2002). On the other hand, reports are confirming that acetylated sequences in COS structure are essential for their antimicrobial activities, and COS comprising more number of acetylated sequences (less number of free amino groups) have shown higher antimicrobial activities (Sánchez et al., 2017). Further work is needed to determine the mechanism of antimicrobial activity of chitosans and COS and to affect their activity primarily DD and DP. Examples of antimicrobial activities of chitosan and chitoooligosaccharides are summarized in **Table 8**. The antifungal activity of chitosan is commonly used in agriculture for the reduction of mycelial growth, sporangial production, release of zoospores, germination of cysts and the induction of local and systemic resistance (Atia et al., 2005) Additionally, results reported by Mei et al. (2015) proved the potential of COS for clinical application. Enzymatically produced, well-characterized chitoooligosaccharides exhibited excellent antifungal properties

**TABLE 8 |** The antimicrobial activities of chitosan and its degradation products.

Chitosan/COS		Activity against	References
MW [kDa]/DP	DD [%]		
MW 1–10	75	<i>Vibrio parahaemolyticus</i>	Park et al., 2004
MW 8; 66; 197	85	<i>E. coli</i> , <i>S. aureus</i> , <i>Candida albicans</i> , <i>C. tropicalis</i>	Zhang et al., 2019
DP 2–12	–	<i>Alternaria alternata</i> , <i>Rhizopus stoloniformis</i> , <i>Botrytis cinerea</i>	Oliveira et al., 2008
MW 49.5; 138 and 142	91	<i>E. coli</i> , <i>S. aureus</i> , <i>C. albicans</i>	Pan et al., 2019
MW 3 0–10; 10–5; < 5	84	<i>E. coli</i> , <i>Listeria monocytogenes</i>	Sánchez et al., 2017
MW 5.1; 14.3 and 41.1	99	<i>E. coli</i> , <i>Salmonella typhimurium</i> , <i>Salmonella enteritidis</i>	Laokuldilok et al., 2017
MW 194		<i>Staphylococcus aureus</i>	
MW 28	89	<i>S. typhimurium</i>	Jeon et al., 2001

against dermatophyte fungus *Trichophyton rubrum* in a guinea pig model.

There are several reports on the antiviral properties of chitosan and COS, but the mechanism of their activity has also not yet been clearly explained. Chitosan, as well as its degradation products, most likely inhibit viral infections by reducing virus infectivity and inducing the resistance of plant and animal organisms. Suppression of infectivity may also be associated with preventing the absorption of viral particles into the cell membrane. The sulphated COS with MW in the range of 3–5 kDa is an effective compound to stop replication of HIV-1 virus by blocking viral entry and virus-cell fusion probably via disrupting the binding of HIV-1 to CD4 cell surface receptor (Artan et al., 2009). The study of antiviral activity of chitosan oligomers with MW from 17 to 2 kDa and DD 98.5, 83, and 75% were tested against the tobacco mosaic virus by Davydova et al. (2011). The obtained results confirmed that these samples inhibited the formation of local necrosis induced by the virus by 50–90%.

Chitosan and COS-like chitosans can be considered as potential anticancer agents because of their anti-tumor activities. Unfortunately, the mechanism of their action on tumor cells has not been elucidated to date. Huang et al. (2006) proposed a hypothesis according to which COS as a negatively charged polysaccharides that can adsorb on a cancer cell. The electrostatic interactions between cancer cells and polycationic polymer significantly change the permeability of cancer cells. Mattaveewong et al. (2016) suggest that tumor cells are not killed directly by COS. These small oligosaccharides suppress the NF- $\kappa$ B and mechanistic target of rapamycin (mTOR)



by AMP-Activated Protein Kinase (AMPK) activation. Recent research revealed the potential of COS as an immunostimulatory agent which may be used in anticancer therapies related to immunomodulation (Zheng et al., 2016; Xing et al., 2017). The molecular weight of COS has an essential effect on anticancer activity. It has been reported that chitohexanoses are the most promising oligomers to manifest the anticancer effect (Xiong et al., 2009; Li et al., 2011). Wang et al. (2007) published the results of studies confirming the influence of the degree of COS acetylation on anticancer activity. The antiangiogenic activity of acetylated COSs was significantly stronger than the parent oligosaccharide. Other research indicated that antiangiogenic activity of COS is also dependent on FA and DP of oligomers and that the FA is more critical of the two parameters (Wu et al., 2012). Chitosan and its derivatives were used as transporters of anti-cancer drugs. It has been investigated that anticancer agents conjugated with chitosan can execute anticancer effects with a decrease of side effects and gradual release of free drug in the cancer tissues (De Campos et al., 2001; Janes et al., 2001). Liposome-chitosan nanoparticles were used to obtain dose-dependent tumor-weight inhibition drug release system, which showed promising results in *in vivo* studies (Li et al., 2009). Yin et al. (2017) reported that the COS (MW 2,000–5,000 Da) tethered on the liposomes through disulphide linkers (-SS-) to cholesterol may be an excellent platform for cytoplasmic delivery of anticancer drugs. An amphiphilic all-trans-retinoic acid (ATRA) conjugated COS nanoparticles also revealed the promising potential as drug carriers for co-delivery of ATRA, paclitaxel, and other hydrophobic therapeutic agents (Zhang J. et al., 2015).

In recent years, the possibility of using chitosan and COS as free radical scavengers are also of significant interest. It is known that the mechanism of their antioxidant activity is associated with the presence of free amino group in the glucopyranose rings, which by reacting with free radicals form stable forms of macro-radicals. In addition, the  $-NH_2$  groups exhibit chelating properties concerning many metal ions, including  $Fe^{2+}$ , which are activators in the formation of hydroxyl radicals—the most dangerous for the human body. Antioxidant activities of chitosan and COS are affected by DD and MW (Park et al., 2004; Zhao et al., 2013). Studies by Park et al. (2004) suggested that the scavenging activity of chitosan depended on its DD and chitosan with a higher DD exhibited better scavenging activity. In contrast, chitosan oligosaccharides (MW 5 kDa, DD 97%) and its derivatives tested by Zhao et al. (2013) showed a higher scavenging effect than chitosan used to obtain them (MW 120 kDa, DD 97%). Like other properties of chitooligosaccharides, their antioxidant activity is also dependent on the physicochemical properties of COS. Studies attempted to determine the relationship between antioxidant activity of COS and their MW indicated that that low MW (5,000 Da) COS had shown the highest antioxidant capabilities. Additionally, it has been found that the antioxidant activity of COS can be predicted based on the composition of oligomers expressed as the ratio of acetylated vs. deacetylated units (Mengibar et al., 2013). Antioxidant activity of COS is another promising characteristic which can be used to produce value-added products for food

preservation and functional food. Studies conducted by Yang et al. (2017) play an active part in the prevention of beer flavor deterioration by inhibiting the formation of staling compounds and increasing radical scavenging activity. The activity of COS was dependent on the molecular weight of oligomers. Additionally, COS showed radical scavenging activity in the finished beer, which is expected to improve the shelf life stability during beer storage.

The biodegradability of chitin and chitosan was principally attributed to their susceptibility to enzymatic hydrolysis by lysozyme, that exists in all human body tissues. It has been demonstrated that chitosan can also be metabolized in animal and human tissues by the combined action of lipase and chitosanases (Poshina et al., 2018). Thus, chitosan and its derivatives have been considered as promising vehicles for oral prolonged-release drugs and as a matrix in drug release systems in the form of beads and granules. Physical hydrogels of chitosan which are usually used for this purpose can be formed by various reversible links such as ionic interactions (crosslinked hydrogels) and polyelectrolyte complexes (PEC), or secondary interactions (chitosan/poly(vinyl alcohol) complexed hydrogels), grafted chitosan hydrogels, and entangled hydrogels (Berger et al., 2004). PECs of chitosan with polyanions of natural origin like pectin, alginate, carboxymethyl cellulose, or with synthetic ones like poly (acrylic acid) have been discovered as matrices for controlled-release systems (Berger et al., 2004). Chandy et al. (2002) reported that chitosan-polyethylene glycol-alginate microspheres are suitable materials for the delivery of low molecular weight (LMW) heparin with antithrombotic properties. Chitosan and its derivatives can be used to form products with haemostatic properties. It has been found that in the initial phase of chitosan/blood interactions, plasma proteins absorb on chitosan-based systems. In the next step, the adhesion and activation of platelets occur, which leads to the formation of a thrombus (Yeh and Lin, 2008). It was claimed that chitosan was hypocholesterolemic and hypolipidemic (Domard and Domard, 2002). Pan et al. (2016) investigated that functional food based on the chitosan and its derivatives effectively improve liver lipids metabolism and protect the liver from the oxidized trauma by enhancing hepatic function. Biocompatible, natural and synthetic carriers are commonly used in tissue engineering techniques as a support for initial cell attachment and subsequent tissue formation. Chitosan shows a similar spatial structure as glycosaminoglycans (GAGs) found in the extracellular matrix of several human tissues. The physical and chemical properties of chitosan facilitate the adhesion of the cells and maintenance of the differentiating functions (Croisier and Jérôme, 2013). Gelatin-chitosan hydrogels were successfully used as a culture substratum for respiratory epithelial cells. However, two-dimensional gel conformation was not sufficient to induce very high ciliogenesis and mucus secretion (Risbud et al., 2001). A three-dimensional biodegradable hydroxyapatite/chitosan-gelatin network was used as a biomimetic scaffold for bone cells growth and proliferation. The obtained cell/scaffold constructs had good biomineralization effect after 3 weeks in culture (Zhao et al., 2002). As a polycationic biopolymer, chitosan and its derivatives can form complexes with nucleic acids. This property



was utilized in gene transfection experiments, in which chitosan with DD around 80–90% has proved useful as a gene carrier for *in vitro* and *in vivo* processes (Köping-Höggård et al., 2001; Mao et al., 2001; Kwon et al., 2013). It has been demonstrated that the reduction of chitosan DD results in a reduction of DNA binding efficiency and consequently in a decreased expression of transfected genes (Kiang et al., 2004; Huang et al., 2005). Furthermore, complexes formed with higher molecular weight chitosan are more stable and demonstrate higher transfection efficiency (Bordi et al., 2014). In addition to the indicated examples of chitosan applications, this biopolymer has been used in many other industries, e.g., as adsorbents for dye removal from water and wastewater (Vakili et al., 2014), as ingredients of cosmetic that increases the water-resistance of emulsions protecting against sun irradiation and consequently enhances its film-forming ability (Aranaz et al., 2018), as a food ingredient (Shahidi et al., 1999), as a carrier for enzyme immobilization (Biró et al., 2008; Hou et al., 2019).

As it was mentioned, conventional methods of chitosan and chitooligosaccharides preparation are difficult to control and often lead to a mixture of products with different properties. The indicated examples clearly show that the biological activities of COS are significantly affected by the DA, DP, MW, FA, and PA; therefore it is crucial to develop fully controlled production methods of chitosan and chitooligosaccharides—application of appropriate enzymes (biocatalysts) can be very helpful in achieving this goal.

## ENZYMATIC TRANSFORMATIONS OF CHITIN/CHITOSAN—WHAT THE FUTURE HOLDS?

The disadvantages of the currently used industrial methods of chitosan manufacturing and the increasing demand for a broad range of novel chitosan oligosaccharides with a fully defined architecture attract growing interest in the chitin- and chitosanolytic enzymes. Due to their unique abilities, these enzymes are increasingly seen as a useful tool toward biotechnological chitosan and COS production, especially when a controlled non-degradative and well-defined process is required.

As previously mentioned, enzymatic modification of chitin includes deacetylation of chitin into chitosan and depolymerization of chitin or chitosan into acetylated or deacetylated chitooligosaccharides, respectively. Unfortunately, the chemical structure and highly crystalline character of native chitin seem to limit the accessibility of the enzyme to reactive polymer groups. The solution of the problem may be the application of multiple chitin- and chitosanolytic enzyme cocktails or complexes enabling comprehensive modification of the native substrate. Recent research indicated that the chitinases of microbial origin could depolymerise and thus potentially to loosen the crystalline chitin structure (Guo et al., 2017). Considerable interest emerged by the discovery of chitin active lytic polysaccharide monoxygenases (LPMOs), which are capable of directly cleaving glycolic bonds in highly crystalline chitin (Mutahir et al., 2018). Moreover, it was

found that the synergies between LPMO (CBP21 from *S. marcescens*) and monocomponent chitinases were clear for all substrates but more significant for substrates with high degrees of crystallinity (Mekasha et al., 2017). Accordingly, the pre-action of enzymes capable of fragmenting the chitin chain can significantly increase the susceptibility of the intermediates to the action of chitosanases, chitin deacetylases, and chitooligosaccharides deacetylases. The joint action of sequential enzymes in multiple-enzyme cocktails or complexes yield efficient transfer of an intermediate from one enzyme to the next enzyme, thereby resulting in an enhanced reaction rate. Simultaneous use of chitin- and chitosanolytic enzymes involved in chitin and chitosan modification can significantly reduce the diffusional length of the intermediates along the multi-reaction pathway. High substrate specificity of enzymes involved in the multienzymatic mixture, potentially allows obtaining products with strictly defined chain arrangement, and thus desirable biological properties. The proposed solution can eliminate the problems associated with the relatively low efficiency of modification of native chitin by currently known enzymes.

The multi-step character of enzymatic chitin modification processes and high costs of enzymes preparations are other limiting factors enabling the application of enzymatic route on a wide range. Substantial improvement in the cost-effectiveness of enzymatic processes can be obtained by the assembly of numerous enzymes and co-enzymes *in vitro* in so-called cascade biocatalysis (You et al., 2012; Liu et al., 2013). Expression of fusion proteins with multifunctional activity can also significantly reduce the cost of enzymatic methods (Iturrate et al., 2009) and provide desirable binding properties toward the chitin (Hou et al., 2019). However, it is sometimes challenging to obtain multifunctional proteins that keep the activity and substrate specificity of native enzymes. Another strategy involves a co-expression of genes coding enzymes required for multi-step processes. By simultaneously producing several enzymes, it is possible to significantly reduce the costs of the process in which the use of several biocatalysts is required. Commonly, a multi-gene expression is based on constructs harboring the pathway genes under the separate control of the same or different promoters and terminators. Unfortunately, the repeated use of homologous sequences typically results in genetic instability. On the other hand, the use of different regulatory sequences results in the expression of individual genes with different efficiencies (Geier et al., 2015). The multi-gene expression from single, polycistronic transcript can be used to reduce the number of regulatory elements. Since eukaryotes generally do not express polycistronic operons, other regulatory elements are needed to initiate the multi-gene expression. One way to achieve polycistronic expression is the use of internal ribosome entry sites (IRES). The IRES serves as a launching pad for the internal initiation of translation. The approach allows expression of two or more genes from a single transcript. However, these sequences are relatively large (~500 bp) which significantly affects the size of constructs used for transformation, thereby lowering the efficiency of the process. Moreover, the application of IRES in polycistronic expression results in as much as a 10-fold lower

expression of the downstream coded protein (Douin et al., 2004; Ha et al., 2010). Another approach involves the use of viral self-processing 2A sequences. These short oligopeptides (around 20 aa) responsible for the phenomenon of ribosomal skipping (Donnelly et al., 2001) have been identified in several members of the picornavirus family, where they participate in a self-cleavage of viral polypeptides to generate the mature viral proteins. These sequences have been successfully used for the production of therapeutic proteins, antibodies, vaccines and in gene therapy, both in transgenic mice and animals cells (Ha et al., 2010). The ribosomal skipping activity of 2A sequences has been implemented for polycistronic expression of proteins in transgenic plants (Penn, 2000) and yeasts (Geier et al., 2015).

Another exciting alternative that can increase the efficiency of enzymatic methods for the production of chitin derivatives is the creation of multi-enzymatic complexes that allow the cascade effect of biocatalysts. Most naturally occurred cascade enzymes in metabolic pathways are spatially held together by non-covalent protein-protein interactions (Srere, 2002). This makes the active sites of each enzyme closer together triggering the phenomenon of substrate channeling, wherein an intermediary metabolic product of one enzyme is passing directly to another active site (another enzyme) without its release into the reaction medium. Wilner et al. (2009) obtained even 30 fold increase in reaction efficiency by linking horse peroxidase and glucose oxidase by DNA scaffolds of different length. Moehlenbrock et al. (2010) significantly improved the current and power density of biofuel cells through the chemical, covalent linkage of proteins

using the mitochondria isolated from *Saccharomyces cerevisiae*. Kim and Hahn (2014) synthesized cascade-enzymes scaffold system applied to the improved production of 2,3-butanediol. The functioning of the system was based on cohesin-dockerin interactions, which allowed to increase the production titer up to 37%. The current state of knowledge and modern methods of genetic engineering, molecular biology and related sciences give a real chance to develop an efficient and controlled method of enzymatic modification of chitin and its derivatives.

## AUTHOR CONTRIBUTIONS

MK devised the topic, collected most of the data, participated in preparation of draft manuscript, and participated in assembly and editing of the final manuscript. KS-S and XL collected data and participated in preparation of draft manuscript. MS-A participated in preparation draft manuscript. MD devised the topic participated in preparation of draft manuscript and participated in assembly and editing of the final manuscript.

## FUNDING

Tenure-track fund and Shenzhen Knowledge and Innovation Basic Research Grant JCYJ20180302153648993 both to MD, China Post-doctoral Science Foundation Grant No. 2018M641094 to XL. The funders had no role in study design, data collection and analysis, interpretation, the decision to publish, or preparation of the manuscript.

## REFERENCES

- Aam, B. B., Heggset, E. B., Norberg, A. L., Sørli, M., Vårum, K. M., and Eijsink, V. G. H. (2010). Production of chitoooligosaccharides and their potential applications in medicine. *Mar. Drugs* 8, 1482–1517. doi: 10.3390/md8051482
- Abdel-Aziz, S. M., Kahil, T., and Keera, A. A. (2014). Kinetic behavior of free and *in situ* immobilized chitosanases produced by the fungus *Mucor rouxii*. *World Appl. Sci. J.* 30, 1–9. doi: 10.5829/idosi.wasj.2014.30.01.13980
- Abdou, E. S., Nagy, K. S. A., and Elsabee, M. Z. (2008). Extraction and characterization of chitin and chitosan from local sources. *Bioresour. Technol.* 99, 1359–1367. doi: 10.1016/j.biortech.2007.01.051
- Aiba, S. (1991). Studies on chitosan: 3. Evidence for the presence of random and block copolymer structures in partially N-acetylated chitosans. *Int. J. Biol. Macromol.* 13, 40–44. doi: 10.1016/0141-8130(91)90008-1
- Al Sagheer, F. A., Al-Sughayer, M. A., Muslim, S., and Elsabee, M. Z. (2009). Extraction and characterization of chitin and chitosan from marine sources in Arabian Gulf. *Carbohydr. Polym.* 77, 410–419. doi: 10.1016/j.carbpol.2009.01.032
- Alfonso, C., Martínez, M. J., and Reyes, F. (1992). Purification and properties of two endochitosanases from *Mucor rouxii* implicated in its cell wall degradation. *FEMS Microbiol. Lett.* 95, 187–194. doi: 10.1111/j.1574-6968.1992.tb05364.x
- Alfonso, C., Nuero, O. M., Santamaría, F., and Reyes, F. (1995). Purification of a heat-stable chitin deacetylase from *Aspergillus nidulans* and its role in cell wall degradation. *Curr. Microbiol.* 30, 49–54. doi: 10.1007/BF00294524
- Ando, A., Saito, A., Arai, S., Usuda, S., Furuno, M., Kaneko, N., et al. (2008). Molecular characterization of a novel family-46 chitosanase from *Pseudomonas* sp. A-01. *Biosci. Biotechnol. Biochem.* 72, 2074–2081. doi: 10.1271/bbb.80175
- Araki, Y., and Ito, E. (1975). A pathway of chitosan formation in *Mucor rouxii* enzymatic deacetylation of chitin. *Eur. J. Biochem.* 55, 71–78. doi: 10.1111/j.1432-1033.1975.tb02139.x
- Aranaz, I., Acosta, N., Civera, C., Elorza, B., Mingo, J., Castro, C., et al. (2018). Cosmetics and cosmeceutical applications of chitin, chitosan and their derivatives. *Polymers* 10:213. doi: 10.3390/polym10020213
- Aranda-Martinez, A., Grifoll-Romero, L., Aragunde, H., Sancho-Vaello, E., Biarnés, X., Lopez-Llorca, L. V., et al. (2018). Expression and specificity of a chitin deacetylase from the nematophagous fungus *Pochonia chlamydosporia* potentially involved in pathogenicity. *Sci. Rep.* 8:2170. doi: 10.1038/s41598-018-19902-0
- Aranday-García, R., Román Guerrero, A., Ifuku, S., and Shirai, K. (2017). Successive inoculation of *Lactobacillus brevis* and *Rhizopus oligosporus* on shrimp wastes for recovery of chitin and added-value products. *Process Biochem.* 58, 17–24. doi: 10.1016/j.procbio.2017.04.036
- Artan, M., Karadeniz, F., Karagozlu, M. Z., Kim, M.-M., and Kim, S.-K. (2009). Anti-HIV-1 activity of low molecular weight sulfated chitoooligosaccharides. *Carbohydr. Res.* 345, 656–662. doi: 10.1016/j.carres.2009.12.017
- Atia, M. M. M., Buchenauer, H., Aly, A. Z., and Abou-Zaid, M. I. (2005). Antifungal activity of chitosan against phytophthora infestans and activation of defence mechanisms in tomato to late blight. *Biol. Agric. Hortic.* 23, 175–197. doi: 10.1080/01448765.2005.9755319
- Bahrke, S. (2008). *Mass Spectrometric Analysis of Chitoooligosachharides and Their Interaction With Proteins*. Available online at: <http://opus.kobv.de/ubp/volltexte/2008/2017/> (accessed August 18, 2019).
- Bai, Y., Eijsink, V. G. H., Kielak, A. M., van Veen, J. A., and de Boer, W. (2016). Genomic comparison of chitinolytic enzyme systems from terrestrial and aquatic bacteria. *Environ. Microbiol.* 18, 38–49. doi: 10.1111/1462-2920.12545
- Bansode, V. B., and Bajekal, S. S. (2006). Characterization of chitinases from microorganisms isolated from Lonar lake. *Indian J. Biotechnol.* 5, 357–363.

- Baxter, S., Zivanovic, S., and Weiss, J. (2005). Molecular weight and degree of acetylation of high-intensity ultrasonicated chitosan. *Food Hydrocoll.* 19, 821–830. doi: 10.1016/j.foodhyd.2004.11.002
- Berger, J., Reist, M., Mayer, J. M., Felt, O., and Gurny, R. (2004). Structure and interactions in chitosan hydrogels formed by complexation or aggregation for biomedical applications. *Eur. J. Pharm. Biopharm.* 57, 35–52. doi: 10.1016/S0939-6411(03)00160-7
- Biró, E., Németh, A. S., Sisak, C., Feczkó, T., and Gyenis, J. (2008). Preparation of chitosan particles suitable for enzyme immobilization. *J. Biochem. Biophys. Methods* 70, 1240–1246. doi: 10.1016/j.jppt.2007.11.005
- Blair, D. E., Hekmat, O., Schüttelkopf, A. W., Shrestha, B., Tokuyasu, K., Withers, S. G., et al. (2006). Structure and mechanism of chitin deacetylase from the fungal pathogen *Colletotrichum lindemuthianum*. *Biochemistry* 45, 9416–9426. doi: 10.1021/bi0606694
- Bonilla, F., Chouljenko, A., Lin, A., Young, B. M., Sai Goribidanur, T., Blake, J. C., et al. (2019). Chitosan and water-soluble chitosan effects on refrigerated catfish fillet quality. *Food Biosci.* 31:100426. doi: 10.1016/j.foodbi.2019.100426
- Bordi, F., Chronopoulou, L., Palocci, C., Bomboi, F., Di Martino, A., Cifani, N., et al. (2014). Chitosan-DNA complexes: effect of molecular parameters on the efficiency of delivery. *Colloids Surfaces A Physicochem. Eng. Asp.* 460, 184–190. doi: 10.1016/j.colsurfa.2013.12.022
- Brameld, K. A., and Goddard, W. A. (2002). The role of enzyme distortion in the single displacement mechanism of family 19 chitinases. *Proc. Natl. Acad. Sci. U.S.A.* 99, 4276–4281. doi: 10.1073/pnas.95.8.4276
- Cai, J., Yang, J., Du, Y., Fan, L., Qiu, Y., Li, J., et al. (2006). Purification and characterization of chitin deacetylase from *Scopulariopsis brevicaulis*. *Carbohydr. Polym.* 65, 211–217. doi: 10.1016/j.carbpol.2006.01.003
- Castro, R., Guerrero-Legarreta, I., and Bórquez, R. (2018). Chitin extraction from *Allopetrolisthes punctatus* crab using lactic fermentation. *Biotechnol. Rep.* 20:e00287. doi: 10.1016/j.btre.2018.e00287
- Chandy, T., Rao, G. H. R., Wilson, R. F., and Das, G. S. (2002). Delivery of LMW heparin via surface coated chitosan/peg-alginate microspheres prevents thrombosis. *Drug Deliv. J. Deliv. Target. Ther. Agents* 9, 87–96. doi: 10.1080/10426500290095584
- Chatterjee, S., Adhya, M., Guha, A. K., and Chatterjee, B. P. (2005). Chitosan from *Mucor rouxii*: production and physico-chemical characterization. *Process Biochem.* 40, 395–400. doi: 10.1016/j.procbio.2004.01.025
- Chen, H., Cui, S., Zhao, Y., Wang, B., Zhang, S., Chen, H., et al. (2012). O-alkylation of chitosan for gene delivery by using ionic liquid in an *in-situ* reactor. *Engineering* 5, 114–117. doi: 10.4236/eng.2012.410b029
- Chen, X., Zhai, C., Kang, L., Li, C., Yan, H., Zhou, Y., et al. (2012). High-level expression and characterization of a highly thermostable chitosanase from *Aspergillus fumigatus* in *Pichia pastoris*. *Biotechnol. Lett.* 34, 689–694. doi: 10.1007/s10529-011-0816-0
- Chiu, E., Hijnen, M., Bunker, R. D., Boudes, M., Rajendran, C., Aizel, K., et al. (2015). Structural basis for the enhancement of virulence by viral spindles and their *in vivo* crystallization. *Proc. Natl. Acad. Sci. U.S.A.* 112, 3973–3978. doi: 10.1073/pnas.1418798112
- Choi, W. S., Ahn, K. J., Lee, D. W., Byun, M. W., and Park, H. J. (2002). Preparation of chitosan oligomers by irradiation. *Polym. Degrad. Stability* 78, 533–538. doi: 10.1016/S0141-3910(02)00226-4
- Cord-Landwehr, S., Melcher, R. L. J., Kolkenbrock, S., and Moerschbacher, B. M. (2016). A chitin deacetylase from the endophytic fungus *Pestalotiopsis* sp. efficiently inactivates the elicitor activity of chitin oligomers in rice cells. *Sci. Rep.* 6, 1–11. doi: 10.1038/srep38018
- Croisier, F., and Jérôme, C. (2013). Chitosan-based biomaterials for tissue engineering. *Eur. Polym. J.* 49, 780–792. doi: 10.1016/j.eurpolymj.2012.12.009
- Da Silva Amorim, R. V., De Souza, W., Fukushima, K., and De Campos-Takaki, G. M. (2001). Faster chitosan production by Mucoralean strains in submerged culture. *Braz. J. Microbiol.* 32, 20–23. doi: 10.1590/S1517-83822001000100005
- Davoust, N., and Hansson, G. (1992). Identifying the conditions for development of beneficial mycelium morphology for chitosan-producing *Absidia* spp. in submerged cultures. *Appl. Microbiol. Biotechnol.* 36, 618–620. doi: 10.1007/BF00183238
- Davydova, V. N., Nagorskaya, V. P., Gorbach, V. I., Kalitnik, A. A., Reunov, A. V., Solov'eva, T. F., et al. (2011). Chitosan antiviral activity: dependence on structure and depolymerization method. *Appl. Biochem. Microbiol.* 47, 103–108. doi: 10.1134/S0003683811010042
- De Campos, A. M., Sánchez, A., and Alonso, M. J. (2001). Chitosan nanoparticles: a new vehicle for the improvement of the delivery of drugs to the ocular surface. Application to cyclosporin A. *Int. J. Pharm.* 224, 159–168. doi: 10.1016/S0378-5173(01)00760-8
- Doan, C. T., Tran, T. N., Nguyen, V. B., Nguyen, A. D., and Wang, S. L. (2019a). Production of a thermostable chitosanase from shrimp heads via *paenibacillus mucilaginosus* TKU032 conversion and its application in the preparation of bioactive chitosan oligosaccharides. *Mar. Drugs* 17:E217. doi: 10.3390/md17040217
- Doan, C. T., Tran, T. N., Nguyen, V. B., Vo, T. P. K., Nguyen, A. D., and Wang, S. L. (2019b). Chitin extraction from shrimp waste by liquid fermentation using an alkaline protease-producing strain, *Brevibacillus parabrevis*. *Int. J. Biol. Macromol.* 131, 706–715. doi: 10.1016/j.ijbiomac.2019.03.117
- Domard, A., and Domard, M. (2002). “Chitosan: structure-properties relationship and biomedical applications” in *Polymeric Biomaterials*, ed S. Dumitriu (Boca Raton, FL: CRC Press), 187–202. doi: 10.1201/9780203904671.ch9
- Donnelly, M. L. L., Hughes, L. E., Luke, G., Mendoza, H., Ten Dam, E., Gani, D., et al. (2001). The “cleavage” activities of foot-and-mouth disease virus 2A site-directed mutants and naturally occurring “2A-like” sequences. *J. Gen. Virol.* 82, 1027–1041. doi: 10.1099/0022-1317-82-5-1027
- Douin, V., Bornes, S., Creancier, L., Rochaix, P., Favre, G., Prats, A. C., et al. (2004). Use and comparison of different internal ribosomal entry sites (IRES) in tricistronic retroviral vectors. *BMC Biotechnol.* 4:16. doi: 10.1186/1472-6750-4-16
- Dun, Y., Li, Y., Xu, J., Hu, Y., Zhang, C., Liang, Y., et al. (2019). Simultaneous fermentation and hydrolysis to extract chitin from crayfish shell waste. *Int. J. Biol. Macromol.* 123, 420–426. doi: 10.1016/j.ijbiomac.2018.11.088
- Duo-Chuan, L. (2006). Review of fungal chitinases. *Mycopathologia* 161, 345–360. doi: 10.1007/s11046-006-0024-y
- Eijsink, V. G. H., Petrovic, D., Forsberg, Z., Mekasha, S., Røhr, Å. K., Várnai, A., et al. (2019). On the functional characterization of lytic polysaccharide monoxygenases (LPMOs). *Biotechnol. Biofuels.* 12:58. doi: 10.1186/s13068-019-1392-0
- Ekowati, C., Hariyadi, P., Witarto, A. B., Hwang, J. K., and Suhartono, M. T. (2006). Biochemical characteristics of chitosanase from the Indonesian *Bacillus licheniformis* MB-2. *Mol. Biotechnol.* 33, 93–102. doi: 10.1385/MB:33:2:93
- El Knidri, H., El Khalfaouy, R., Laajeb, A., Addaou, A., and Lahsini, A. (2016). Eco-friendly extraction and characterization of chitin and chitosan from the shrimp shell waste via microwave irradiation. *Process Saf. Environ. Prot.* 104, 395–405. doi: 10.1016/j.psep.2016.09.020
- Farag, A. M., Abd-Elnabey, H. M., Ibrahim, H. A. H., and El-Shenawy, M. (2016). Purification, characterization and antimicrobial activity of chitinase from marine-derived *Aspergillus terreus*. *Egypt. J. Aquat. Res.* 42, 185–192. doi: 10.1016/j.ejar.2016.04.004
- Gao, L., Sun, J., Secundo, F., Gao, X., Xue, C., and Mao, X. (2018). Cloning, characterization and substrate degradation mode of a novel chitinase from *Streptomyces albolongus* ATCC 27414. *Food Chem.* 261, 329–336. doi: 10.1016/j.foodchem.2018.04.068
- Gao, X. A., Ju, W. T., Jung, W. J., and Park, R. D. (2008). Purification and characterization of chitosanase from *Bacillus cereus* D-11. *Carbohydr. Polym.* 72, 513–520. doi: 10.1016/j.carbpol.2007.09.025
- García-Fraga, B., da Silva, A. F., López-Seijas, J., and Sieiro, C. (2015). Optimized expression conditions for enhancing production of two recombinant chitinolytic enzymes from different prokaryotic domains. *Bioprocess Biosyst. Eng.* 38, 2477–2486. doi: 10.1007/s00449-015-1485-5
- Gauthier, C., Clerisse, F., Dommes, J., and Jaspard-Versali, M. F. (2008). Characterization and cloning of chitin deacetylases from *Rhizopus circinans*. *Protein Expr. Purif.* 59, 127–137. doi: 10.1016/j.pep.2008.01.013
- Geier, M., Fauland, P., Vogl, T., and Glieder, A. (2015). Compact multi-enzyme pathways in *P. pastoris*. *Chem. Commun.* 51, 1643–1646. doi: 10.1039/C4CC08502G
- Gercke, D., Regel, E. K., Singh, R., and Moerschbacher, B. M. (2019). Rational protein design of *Bacillus* sp. MN chitosanase for altered substrate binding and production of specific chitosan oligomers. *J. Biol. Eng.* 13:23. doi: 10.1186/s13036-019-0152-9



- Global Industry Analysts Inc. (2016). *Chitin and Chitosan Derivatives Market Trends (MCP-2039)*. 1–174. Available online at: <http://www.strategyr.com/MCP-2039.asp> (accessed February 19, 2017).
- Global Info Research (2019). *Global Chitosan Derivatives Market 2019 by Manufacturers, Regions, Type and Application, Forecast to 2024 - Market Study Report*. Global Info Research.
- Grifoll-Romero, L., Pascual, S., Aragunde, H., Biarnés, X., and Planas, A. (2018). Chitin deacetylases: structures, specificities, and biotech applications. *Polymers* 10:E352. doi: 10.3390/polym10040352
- Gu, Z., Cai, Q., Liu, Y., and Li, F. (2013). Electrochemical degradation of chitosan using Ti/Sb-SnO<sub>2</sub> electrode. *J. Polym. Environ.* 21, 479–486. doi: 10.1007/s10924-012-0532-4
- Guo, X., Xu, P., Zong, M., and Lou, W. (2017). Purification and characterization of alkaline chitinase from *Paenibacillus pasadenensis* CS0611. *Chinese J. Catal.* 38, 665–672. doi: 10.1016/S1872-2067(17)62787-6
- Gupta, V., Prasanna, R., Srivastava, A. K., and Sharma, J. (2012). Purification and characterization of a novel antifungal endo-type chitosanase from *Anabaena fertilissima*. *Ann. Microbiol.* 62, 1089–1098. doi: 10.1007/s13213-011-0350-2
- Ha, S. H., Liang, Y. S., Jung, H., Ahn, M. J., Suh, S. C., Kweon, S. J., et al. (2010). Application of two bicistronic systems involving 2A and IRES sequences to the biosynthesis of carotenoids in rice endosperm. *Plant Biotechnol. J.* 8, 928–938. doi: 10.1111/j.1467-7652.2010.00543.x
- Hamdi, M., Hammami, A., Hajji, S., Jridi, M., Nasri, M., and Nasri, R. (2017). Chitin extraction from blue crab (*Portunus segnis*) and shrimp (*Penaeus kerathurus*) shells using digestive alkaline proteases from *P. segnis* viscera. *Int. J. Biol. Macromol.* 101, 455–463. doi: 10.1016/j.jbiomac.2017.02.103
- Hamer, S. N., Cord-Landwehr, S., Biarnés, X., Planas, A., Waegeman, H., Moerschbacher, B. M., et al. (2015). Enzymatic production of defined chitosan oligomers with a specific pattern of acetylation using a combination of chitin oligosaccharide deacetylases. *Sci. Rep.* 5:8716. doi: 10.1038/srep08716
- Hamre, A. G., Eide, K. B., Wold, H. H., and Sorlie, M. (2015). Activation of enzymatic chitin degradation by a lytic polysaccharide monoxygenase. *Carbohydr. Res.* 407, 166–169. doi: 10.1016/j.carres.2015.02.010
- Hayes, M. (ed.). (2012). “Chitin, chitosan and their derivatives from marine rest raw materials: potential food and pharmaceutical applications” in *Marine Bioactive Compounds: Sources, Characterization and Applications*, (Boston, MA: Springer), 115–128. doi: 10.1007/978-1-4614-1247-2\_4
- Heggset, E. B., Dybvik, A. I., Hoell, I. A., Norberg, A. L., Sorlie, M., Eijsink, V. G. H., et al. (2010). Degradation of chitosans with a family 46 chitosanase from *Streptomyces coelicolor* A3(2). *Biomacromolecules* 11, 2487–2497. doi: 10.1021/bm1006745
- Hemsworth, G. R., Johnston, E. M., Davies, G. J., and Walton, P. H. (2015). Lytic polysaccharide monoxygenases in biomass conversion. *Trends Biotechnol.* 33, 747–761. doi: 10.1016/j.tibtech.2015.09.006
- Hirano, T., Shiraiishi, H., Ikejima, M., Uehara, R., Hakamata, W., and Nishio, T. (2017). Chitin oligosaccharide deacetylase from *Shewanella baltica* ATCC BAA-1091. *Biosci. Biotechnol. Biochem.* 81, 547–550. doi: 10.1080/09168451.2016.1254529
- Hirano, T., Sugiyama, K., Sakaki, Y., Hakamata, W., Park, S.-Y., and Nishio, T. (2015). Structure-based analysis of domain function of chitin oligosaccharide deacetylase from *Vibrio parahaemolyticus*. *FEBS Lett.* 589, 145–151. doi: 10.1016/j.febslet.2014.11.039
- Hofsbach, J., Bußwinkel, F., Kranz, A., Wattjes, J., Cord-Landwehr, S., and Moerschbacher, B. M. (2018). A chitin deacetylase of *Podospora anserina* has two functional chitin binding domains and a unique mode of action. *Carbohydr. Polym.* 183, 1–10. doi: 10.1016/j.carbpol.2017.11.015
- Hou, J., Li, X., Kaczmarek, M. B., Chen, P., Li, K., Jin, P., et al. (2019). Accelerated CO<sub>2</sub> hydration with thermostable Sulfurhydrogenibium azorensis carbonic anhydrase-chitin binding domain fusion protein immobilised on chitin support. *Int. J. Mol. Sci.* 20:1494. doi: 10.3390/ijms20061494
- Huang, M., Fong, C. W., Khor, E., and Lim, L. Y. (2005). Transfection efficiency of chitosan vectors: effect of polymer molecular weight and degree of deacetylation. *J. Control. Release* 106, 391–406. doi: 10.1016/j.jconrel.2005.05.004
- Huang, R., Mendis, E., Rajapakse, N., and Kim, S. K. (2006). Strong electronic charge as an important factor for anticancer activity of chitoooligosaccharides (COS). *Life Sci.* 78, 2399–2408. doi: 10.1016/j.lfs.2005.09.039
- Iturrate, L., Sánchez-Moreno, I., Doyagüez, E. G., and García-Junceda, E. (2009). Substrate channelling in an engineered bifunctional aldolase/kinase enzyme confers catalytic advantage for C–C bond formation. *Chem. Commun.* 1721–1723. doi: 10.1039/b822345a
- Janes, K. A., Fresneau, M. P., Marazuela, A., Fabra, A., and Alonso, M. J. (2001). Chitosan nanoparticles as delivery systems for doxorubicin. *J. Control. Release* 73, 255–267. doi: 10.1016/S0168-3659(01)00294-2
- Jaworska, M. M. (2012). Kinetics of enzymatic deacetylation of chitosan. *Cellulose* 19, 363–369. doi: 10.1007/s10570-012-9650-3
- Jaworska, M. M., and Konieczna, E. (2001). The influence of supplemental components in nutrient medium on chitosan formation by the fungus *Absidia orchidis*. *Appl. Microbiol. Biotechnol.* 56, 220–224. doi: 10.1007/s002530000591
- Jeon, Y. J., and Kim, S. K. (2000). Production of chitoooligosaccharides using an ultrafiltration membrane reactor and their antibacterial activity. *Carbohydr. Polym.* 41, 133–141. doi: 10.1016/S0144-8617(99)00084-3
- Jeon, Y. J., Park, P. J., and Kim, S. K. (2001). Antimicrobial effect of chitoooligosaccharides produced by bioreactor. *Carbohydr. Polym.* 44, 71–76. doi: 10.1016/S0144-8617(00)00200-9
- Jiang, X., Chen, D., Chen, L., Yang, G., and Zou, S. (2012). Purification, characterization, and action mode of a chitosanase from *Streptomyces roseolus* induced by chitin. *Carbohydr. Res.* 355, 40–44. doi: 10.1016/j.carres.2012.05.002
- John, M., Rohrig, H., Schmidt, J., Wieneke, U., and Schell, J. (1993). Rhizobium NodB protein involved in modulation signal synthesis is a chitoooligosaccharide deacetylase. *Proc. Natl. Acad. Sci. U.S.A.* 90, 625–629. doi: 10.1073/pnas.90.2.625
- Jung, W. J., and Park, R. D. (2014). Bioproduction of chitoooligosaccharides: present and perspectives. *Mar. Drugs* 12, 5328–5356. doi: 10.3390/md12115328
- Kaczmarek, M., Struszczyk-Swita, K., Florczak, T., Szczesna-Antczak, M., and Antczak, T. (2016). Isolation, molecular cloning and characterisation of two genes coding chitin deacetylase from *Mucor circinelloides* IBT-83. *Prog. Chem. Appl. Chitin its Deriv.* 21, 93–103. doi: 10.15259/PCACD.21.09
- Karthik, N., Akanksha, K., Binod, P., and Pandey, A. (2014). Summary for policymakers. *Clim. Change 2013 Phys. Sci. Basis* 52, 1–30.
- Kaya, M., Sargin, I., Tozak, K. Ö., Baran, T., Erdogan, S., and Sezen, G. (2013). Chitin extraction and characterization from *Daphnia magna* resting eggs. *Int. J. Biol. Macromol.* 61, 459–464. doi: 10.1016/j.jbiomac.2013.08.016
- Kiang, T., Wen, J., Lim, H. W., and Leong, K. W. (2004). The effect of the degree of chitosan deacetylation on the efficiency of gene transfection. *Biomaterials* 25, 5293–5301. doi: 10.1016/j.biomaterials.2003.12.036
- Kim, J. Y., Lee, J. K., Lee, S., and Park, H. (2003). Synthesis of chitoooligosaccharide derivative with quaternary ammonium group and its antimicrobial activity against *Streptococcus mutans*. *Int. J. Biol. Macromol.* 32, 23–27. doi: 10.1016/S0141-8130(03)00021-7
- Kim, S., and Hahn, J. S. (2014). Synthetic scaffold based on a cohesin-dockerin interaction for improved production of 2,3-butanediol in *Saccharomyces cerevisiae*. *J. Biotechnol.* 192, 192–196. doi: 10.1016/j.jbiotec.2014.10.015
- Kim, S.-K. and Je, J.-Y. (2010). “Continuous production of Chitoooligosaccharides by enzymatic hydrolysis” in *Chitin, Chitosan, Oligosaccharides and Their Derivatives: Biological Activities and Applications*, ed S.-K. Kim (Boca Raton, FL: CRC Press), 185–195.
- Kim, S. K., and Rajapakse, N. (2005). Enzymatic production and biological activities of chitosan oligosaccharides (COS): a review. *Carbohydr. Polym.* 62, 357–368. doi: 10.1016/j.carbpol.2005.08.012
- Kim, Y.-J., Zhao, Y., Oh, K.-T., Nguyen, V.-N., and Park, R.-D. (2008). Enzymatic deacetylation of chitin by extracellular chitin deacetylase from a newly screened *Mortierella* sp. DY-52. *J. Microbiol. Biotechnol.* 18, 759–66.
- Kittur, F. S., Vishu Kumar, A. B., and Tharanathan, R. N. (2003). Low molecular weight chitosans - Preparation by depolymerization with *Aspergillus niger* pectinase, and characterization. *Carbohydr. Res.* 338, 1283–1290. doi: 10.1016/S0008-6215(03)00175-7
- Kohlhoff, M., Niehues, A., Wattjes, J., Bénéteau, J., Cord-Landwehr, S., El Gueddari, N. E., et al. (2017). Chitinase: a fungal chitosan hydrolyzing enzyme with a new and unusually specific cleavage pattern. *Carbohydr. Polym.* 174, 1121–1128. doi: 10.1016/j.carbpol.2017.07.001
- Kołodziejska, I., Malesa-Ciećwierz, M., Lerska, A., and Sikorski, Z. (1999). Properties of chitin deacetylase from crude extracts of *Mucor rouxii* mycelium. *J. Food Biochem.* 23, 45–57. doi: 10.1111/j.1745-4514.1999.tb00004.x

- Köping-Höggård, M., Tubulekas, I., Guan, H., Edwards, K., Nilsson, M., Vårum, K. M., et al. (2001). Chitosan as a nonviral gene delivery system. Structure-property relationships and characteristics compared with polyethylenimine *in vitro* and after lung administration *in vivo*. *Gene Ther.* 8, 1108–1121. doi: 10.1038/sj.gt.3301492
- Kumar Gadgey, K., and Bahekar, A. (2017). Studies on extraction methods of chitin from crab shell and investigation of its mechanical properties. *Int. J. Mech. Eng. Technol.* 8, 220–231.
- Kumar, M., Brar, A., Vivekanand, V., and Pareek, N. (2017). Production of chitinase from thermophilic *Humicola grisea* and its application in production of bioactive chitoooligosaccharides. *Int. J. Biol. Macromol.* 104, 1641–1647. doi: 10.1016/j.ijbiomac.2017.04.100
- Kumar, M., Brar, A., Vivekanand, V., and Pareek, N. (2018). Process optimization, purification and characterization of a novel acidic, thermostable chitinase from *Humicola grisea*. *Int. J. Biol. Macromol.* 116, 931–938. doi: 10.1016/j.ijbiomac.2018.05.125
- Kwon, J. T., Jiang, H. L., Minai-Tehrani, A., Woo, C. G., Choi, M., Cho, C. S., et al. (2013). Gene expression and pulmonary toxicity of chitosan-graft-polyethylenimine as aerosol gene carrier. *Iran. J. Pharm. Res.* 12, 281–286.
- Kyoon, H., Lee, S. H., Park, N. Y., and Meyers, S. P. (2003). Comparison of physicochemical, binding, and antibacterial properties of chitosans prepared without and with deproteinization process. *J. Agric. Food Chem.* 26, 7659–7663. doi: 10.1021/jf030226w
- Laokuldilok, T., Potivas, T., Kanha, N., Surawang, S., Seesuriyachan, P., Wangtueai, S., et al. (2017). Physicochemical, antioxidant, and antimicrobial properties of chitoooligosaccharides produced using three different enzyme treatments. *Food Biosci.* 18, 28–33. doi: 10.1016/j.fbio.2017.03.004
- Lee, Y. G., Chung, K. C., Wi, S. G., Lee, J. C., and Bae, H. J. (2009). Purification and properties of a chitinase from *Penicillium* sp. LYG 0704. *Protein Expr. Purif.* 65, 244–250. doi: 10.1016/j.pep.2008.12.004
- Li, K., Xing, R., Liu, S., and Li, P. (2016). Advances in preparation, analysis and biological activities of single chitoooligosaccharides. *Carbohydr. Polym.* 139, 178–190. doi: 10.1016/j.carbpol.2015.12.016
- Li, N., Zhuang, C., Wang, M., Sun, X., Nie, S., and Pan, W. (2009). Liposome coated with low molecular weight chitosan and its potential use in ocular drug delivery. *Int. J. Pharm.* 379, 131–138. doi: 10.1016/j.ijpharm.2009.06.020
- Li, X., Wang, J., Chen, X. J., Tian, J. H., Li, L. H., Zhao, M. Y., et al. (2011). Effect of chitoooligosaccharides on cyclin D1, bcl-xl and bcl-2 mRNA expression in A549 cells using quantitative PCR. *Chinese Sci. Bull.* 56, 1629–1632. doi: 10.1007/s11434-010-4501-9
- Li, X., Wang, L.-X., Wang, X., and Roseman, S. (2007). The chitin catabolic cascade in the marine bacterium *Vibrio cholerae*: characterization of a unique chitin oligosaccharide deacetylase. *Glycobiology* 17, 1377–1387. doi: 10.1093/glycob/cwm096
- Li, Y., Liu, H., Xu, Q.-S., Du, Y.-G., and Xu, J. (2014). Chitosan oligosaccharides block LPS-induced O-GlcNAcylation of NF- $\kappa$ B and endothelial inflammatory response. *Carbohydr. Polym.* 99, 568–578. doi: 10.1016/j.carbpol.2013.08.082
- Liaqat, F., and Eltem, R. (2018). Chitoooligosaccharides and their biological activities: a comprehensive review. *Carbohydr. Polym.* 184, 243–259. doi: 10.1016/j.carbpol.2017.12.067
- Liu, F., Banta, S., and Chen, W. (2013). Functional assembly of a multi-enzyme methanol oxidation cascade on a surface-displayed trifunctional scaffold for enhanced NADH production. *Chem. Commun.* 49, 3766–3768. doi: 10.1039/c3cc40454d
- Liu, N., Chen, X.-G., Park, H.-J., Liu, C.-G., Liu, C.-S., Meng, X.-H., et al. (2006). Effect of MW and concentration of chitosan on antibacterial activity of *Escherichia coli*. *Carbohydr. Polym.* 64, 60–65. doi: 10.1016/j.carbpol.2005.10.028
- Liu, Z., Gay, L. M., Tuveng, T. R., Agger, J. W., Westereng, B., Mathiesen, G., et al. (2017). Structure and function of a broad-specificity chitin deacetylase from *Aspergillus nidulans* FGSC A4. *Sci. Rep.* 7:1746. doi: 10.1038/s41598-017-02043-1
- Lombard, V., Golaconda Ramulu, H., Drula, E., Coutinho, P. M., and Henrissat, B. (2014). The carbohydrate-active enzymes database (CAZy) in 2013. *Nucleic Acids Res.* 42, D490–D495. doi: 10.1093/nar/gkt1178
- Lv, M., Hu, Y., Gänzle, M. G., Lin, J., Wang, C., and Cai, J. (2016). Preparation of chitoooligosaccharides from fungal waste mycelium by recombinant chitinase. *Carbohydr. Res.* 430, 1–7. doi: 10.1016/j.carres.2016.04.019
- Mallakuntla, M. K., Vaikuntapu, P. R., Bhuvanachandra, B., Das, S. N., and Podile, A. R. (2017). Transglycosylation by a chitinase from *Enterobacter cloacae* subsp. *cloacae* generates longer chitin oligosaccharides. *Sci. Rep.* 7:5113. doi: 10.1038/s41598-017-05140-3
- Manni, L., Ghorbel-Bellaaj, O., Jellouli, K., Younes, I., and Nasri, M. (2010). Extraction and characterization of chitin, chitosan, and protein hydrolysates prepared from shrimp waste by treatment with crude protease from *Bacillus cereus* SV1. *Appl. Biochem. Biotechnol.* 162, 345–357. doi: 10.1007/s12010-009-8846-y
- Mao, H. Q., Roy, K., Troung-Le, V. L., Janes, K. A., Lin, K. Y., Wang, Y., et al. (2001). Chitosan-DNA nanoparticles as gene carriers: synthesis, characterization and transfection efficiency. *J. Control. Release* 70, 399–421. doi: 10.1016/S0168-3659(00)00361-8
- Mao, X., Zhang, J., Kan, F., Gao, Y., Lan, J., Zhang, X., et al. (2013). Antioxidant production and chitin recovery from shrimp head fermentation with *Streptococcus thermophilus*. *Food Sci. Biotechnol.* 22, 1023–1032. doi: 10.1007/s10068-013-0179-5
- Marcotte, E. M., Monzingo, A. F., Ernst, S. R., Brzezinski, R., and Robertas, J. D. (1996). X-ray structure of an anti-fungal chitosanase from *Streptomyces* N174. *Nat. Struct. Biol.* 3, 155–162. doi: 10.1038/nsb0296-155
- Marei, N. H., El-Samie, A., Salah, T., Saad, G. R., and Elwahy, A. H. M. (2016). Isolation and characterization of chitosan from different local insects in Egypt. *Int. J. Biol. Macromol.* 82, 871–877. doi: 10.1016/j.ijbiomac.2015.10.024
- Martinou, A., Bouriotis, V., Stokke, B. T., and Vårum, K. M. (1998). Mode of action of chitin deacetylase from *Mucor rouxii* on partially N-acetylated chitosans. *Carbohydr. Res.* 331, 71–78. doi: 10.1016/S0008-6215(98)00183-9
- Martinou, A., Koutsoulis, D., and Bouriotis, V. (2002). Expression, purification, and characterization of a cobalt-activated chitin deacetylase (Cda2p) from *Saccharomyces cerevisiae*. *Protein Expr. Purif.* 24, 111–116. doi: 10.1006/prep.2001.1547
- Martinou, A., Tsigos, I., and Bouriotis, V. (1997). “Preparation of chitosan by enzymatic deacetylation” in *Chitin Handbook*, eds R. Muzzatelli and M. Peter (Italy: European Chitin Society; Atec), 501–505.
- Mattaveewong, T., Wongkrasant, P., Chanchai, S., Pichyangkura, R., Chatsudthipong, V., and Muanprasat, C. (2016). Chitosan oligosaccharide suppresses tumor progression in a mouse model of colitis-associated colorectal cancer through AMPK activation and suppression of NF- $\kappa$ B and mTOR signaling. *Carbohydr. Polym.* 145, 30–36. doi: 10.1016/j.carbpol.2016.02.077
- McCormack, J., Hackett, T. J., Tuohy, M. G., and Coughlan, M. P. (1991). Chitinase production by *Talaromyces emersonii*. *Biotechnol. Lett.* 13, 677–682. doi: 10.1007/BF01086326
- Mei, Y. X., Dai, X. Y., Yang, W., Xu, X. W., and Liang, Y. X. (2015). Antifungal activity of chitoooligosaccharides against the dermatophyte *Trichophyton rubrum*. *Int. J. Biol. Macromol.* 77, 330–335. doi: 10.1016/j.ijbiomac.2015.03.042
- Mekasha, S., Byman, I. R., Lynch, C., Toupalová, H., Anděra, L., Næs, T., et al. (2017). Development of enzyme cocktails for complete saccharification of chitin using mono-component enzymes from *Serratia marcescens*. *Process Biochem.* 56, 132–138. doi: 10.1016/j.procbio.2017.02.021
- Mengibar, M., Mateos-Aparicio, I., Miralles, B., and Heras, Á. (2013). Influence of the physico-chemical characteristics of chito-oligosaccharides (COS) on antioxidant activity. *Carbohydr. Polym.* 97, 776–782. doi: 10.1016/j.carbpol.2013.05.035
- Moehlenbrock, M. J., Toby, T. K., Waheed, A., and Minteer, S. D. (2010). Metabolon catalyzed pyruvate/air biofuel cell. *J. Am. Chem. Soc.* 132, 6288–6289. doi: 10.1021/ja101326b
- Moon, C., Seo, D. J., Song, Y. S., Hong, S. H., Choi, S. H., and Jung, W. J. (2017). Antifungal activity and patterns of N-acetyl-chitoooligosaccharide degradation via chitinase produced from *Serratia marcescens* PRNK-1. *Microb. Pathog.* 113, 218–224. doi: 10.1016/j.micpath.2017.10.039
- Moura, C. M. de, Moura, J. M. de, Soares, N. M., and Pinto, L. A. de A. (2011). Evaluation of molar weight and deacetylation degree of chitosan during chitin deacetylation reaction: used to produce biofilm. *Chem. Eng. Process. Process Intensif.* 50, 351–355. doi: 10.1016/j.cep.2011.03.003



- Mourya, V. K., and Inamdar, N. N. (2008). Chitosan-modifications and applications: opportunities galore. *React. Funct. Polym.* 68, 1013–1051. doi: 10.1016/j.reactfunctpolym.2008.03.002
- Mourya, V. K., Inamdar, N. N., and Choudhari, Y. M. (2011). Chitoooligosaccharides: synthesis, characterization and applications. *Polym. Sci. Ser. A* 53, 583–612. doi: 10.1134/S0965545X11070066
- Mutahir, Z., Mekasha, S., Loose, J. S. M., Abbas, F., Vaaje-Kolstad, G., Eijsink, V. G. H., et al. (2018). Characterization and synergistic action of a tetramodular lytic polysaccharide monoxygenase from *Bacillus cereus*. *FEBS Lett.* 592, 2562–2571. doi: 10.1002/1873-3468.13189
- Nakagawa, Y. S., Eijsink, V. G. H., Totani, K., and Vaaje-Kolstad, G. (2013). Conversion of  $\alpha$ -chitin substrates with varying particle size and crystallinity reveals substrate preferences of the chitinases and lytic polysaccharide monoxygenase of *Serratia marcescens*. *J. Agric. Food Chem.* 61, 11061–11066. doi: 10.1021/jf402743e
- Naqvi, S., Cord-Landwehr, S., Singh, R., Bernard, F., Kolkenbrock, S., El Gueddari, N. E., et al. (2016). A recombinant fungal chitin deacetylase produces fully defined chitosan oligomers with novel patterns of acetylation. *Appl. Environ. Microbiol.* 82, 6645–6655. doi: 10.1128/AEM.01961-16
- Nidheesh, T., Pal, G. K., and Suresh, P. V. (2015). Chitoooligomers preparation by chitosanase produced under solid state fermentation using shrimp by-products as substrate. *Carbohydr. Polym.* 121, 1–9. doi: 10.1016/j.carbpol.2014.12.017
- Oliveira, E. N. Jr., El Gueddari, N. E., Moerschbacher, B. M., Peter, M. G., and Franco, T. T. (2008). Growth of phytopathogenic fungi in the presence of partially acetylated chitoooligosaccharides. *Mycopathologia.* 166, 163–74. doi: 10.1007/s11046-008-9125-0
- Osswald W, Shapiro J, McDonald R, Niedz R, Nairn C, Hearn C, M. R. (1994). Identification and characterization of acidic chitinases from sweet orange callus tissue. *Plant Cell Physiol.* 35, 811–820. doi: 10.1093/oxfordjournals.pcp.a078662
- Pacheco, N., Trombotto, S., David, L., and Shirai, K. (2013). Activity of chitin deacetylase from *Colletotrichum gloeosporioides* on chitinous substrates. *Carbohydr. Polym.* 96, 227–232. doi: 10.1016/j.carbpol.2013.03.051
- Pan, C., Qian, J., Fan, J., Guo, H., Gou, L., Yang, H., et al. (2019). Preparation nanoparticle by ionic cross-linked emulsified chitosan and its antibacterial activity. *Colloids Surfaces A* 568, 362–370. doi: 10.1016/j.colsurfa.2019.02.039
- Pan, H., Yang, Q., Huang, G., Ding, C., Cao, P., Huang, L., et al. (2016). Hypolipidemic effects of chitosan and its derivatives in hyperlipidemic rats induced by a high-fat diet. *Food Nutr. Res.* 60. doi: 10.3402/fnr.v60.31137
- Pareek, N., Vivekanand, V., Agarwal, P., Saroj, S., and Singh, R. P. (2013). Bioconversion to chitosan: a two stage process employing chitin deacetylase from *Penicillium oxalicum* SAE M-51. *Carbohydr. Polym.* 96, 417–425. doi: 10.1016/j.carbpol.2013.04.005
- Park, P. J., Je, J. Y., and Kim, S. K. (2003). Angiotensin I converting enzyme (ACE) inhibitory activity of hetero-chitoooligosaccharides prepared from partially different deacetylated chitosans. *J. Agric. Food Chem.* 51, 4930–4934. doi: 10.1021/jf0340557
- Park, P. J., Je, J. Y., and Kim, S. K. (2004). Free radical scavenging activities of differently deacetylated chitosans using an ESR spectrometer. *Carbohydr. Polym.* 55, 17–22. doi: 10.1016/j.carbpol.2003.05.002
- Penn, I. (2000). Cancers in renal transplant recipients. *Adv. Ren. Replace. Ther.* 7, 147–156. doi: 10.1053/rr.2000.5269
- Popa-Nita, S., Lucas, J. M., Ladavière, C., David, L., and Domard, A. (2009). Mechanisms involved during the ultrasonically induced depolymerization of chitosan: characterization and control. *Biomacromolecules* 10, 1203–1211. doi: 10.1021/bm8014472
- Poshina, D. N., Raik, S. V., Poshin, A. N., and Skorik, Y. A. (2018). Accessibility of chitin and chitosan in enzymatic hydrolysis: a review. *Polym. Degrad. Stab.* 156, 269–278. doi: 10.1016/j.polymdegradstab.2018.09.005
- Qin, Z., Chen, Q., Lin, S., Luo, S., Qiu, Y., and Zhao, L. (2018). Expression and characterization of a novel cold-adapted chitosanase suitable for chitoooligosaccharides controllable preparation. *Food Chem.* 253, 139–147. doi: 10.1016/j.foodchem.2018.01.137
- Rafael Olicón-Hernández, D., Alberto Vázquez-Landaverde, P., Cruz-Camarillo, R., Irene Rojas-Avelizapa, L., Tomas, S., and Miguel Hidalgo, D. (2017). Preparative Biochemistry and Biotechnology Comparison of chitoooligosaccharide production from three different colloidal chitosans using the endochitonsanolytic system of *Bacillus thuringiensis*) Comparison of chito-oligosaccharide production from three di. *Prep. Biochem. Biotechnol.* 47, 116–122. doi: 10.1080/10826068.2016.1181086
- Rass-Hansen, J., Falsig, H., Jørgensen, B., and Christensen, C. H. (2007). Perspective Bioethanol: fuel or feedstock. *J. of Chemical Technol. Biotechnol.* 82, 329–333. doi: 10.1002/jctb.1665
- Regis, B., Marius, S., Sandrine, B., Roux Karine, L., Del Pino, R. J., Jean-Pascal, B., et al. (2015). Kinetic study of solid phase demineralization by weak acids in one-step enzymatic bio-refinery of shrimp cuticles. *Elsevier Ltd.* 50, 2215–2223. doi: 10.1016/j.procbio.2015.09.017
- Rinaudo, M. (2006). Chitin and chitosan: properties and applications. *Prog. Polym. Sci.* 31, 603–632. doi: 10.1016/j.progpolymsci.2006.06.001
- Risbud, M., Endres, M., Ringe, J., Bhonde, R., and Sittinger, M. (2001). Biocompatible hydrogel supports the growth of respiratory epithelial cells: possibilities in tracheal tissue engineering. *J. Biomed. Mater. Res.* 56, 120–127. doi: 10.1002/1097-4636(200107)56:1<120::aid-jbm1076>3.0.co;2-w
- Roberts, G. A. F. (2008). Thirty years of progress in chitin and chitosan. *Prog. Chem. Appl. Chitin its Deriv.* 8, 7–15.
- Roy, J. C., Salaün, F., Giraud, S., Ferri, A., Chen, G., and Guan, J. (2017). “Solubility of chitin: solvents, solution behaviors and their related mechanisms,” in *Solubility of Polysaccharides*, ed Z. Xu (IntechOpen). doi: 10.5772/intechopen.71385
- Sabbadin, F., Hemsforth, G. R., Ciano, L., Henrissat, B., Dupree, P., Tryfona, T., et al. (2018). An ancient family of lytic polysaccharide monoxygenases with roles in arthropod development and biomass digestion. *Nat. Commun.* 9:756. doi: 10.1038/s41467-018-03142-x
- Saito, J.-I., Kita, A., Higuchi, Y., Nagata, Y., Ando, A., and Miki, K. (1999). *Crystal Structure of Chitosanase from Bacillus circulans MH-K1 at 1.6-Å Resolution and Its Substrate Recognition Mechanism\**. Available online at: <http://www.jbc.org/> (accessed September 5, 2019).
- Samar, M. M., El-Kalyoubi, M. H., Khalaf, M. M., and Abd El-Razik, M. M. (2013). Physicochemical, functional, antioxidant and antibacterial properties of chitosan extracted from shrimp wastes by microwave technique. *Ann. Agric.* 58, 33–41. doi: 10.1016/j.a0as.2013.01.006
- Sami, A. J. (2010). Deletion of amino acid residues 33-46 in growth hormone alters the hydrophobicity of the molecule. *African J. Biotechnol.* 9, 711–717. doi: 10.5897/AJB09.1262
- Sánchez, Á., Mengíbar, M., Rivera-Rodríguez, G., Moerschbacher, B., Acosta, N., and Heras, A. (2017). The effect of preparation processes on the physicochemical characteristics and antibacterial activity of chitoooligosaccharides. *Carbohydr. Polym.* 157, 251–257. doi: 10.1016/j.carbpol.2016.09.055
- Sedaghat, F., Yousefzadi, M., Toiserkani, H., and Najafipour, S. (2017). Bioconversion of shrimp waste *Penaeus merguensis* using lactic acid fermentation: an alternative procedure for chemical extraction of chitin and chitosan. *Int. J. Biol. Macromol.* 104, 883–888. doi: 10.1016/j.ijbiomac.2017.06.099
- Shahidi, F., Arachchi, J. K. V., and Jeon, Y. J. (1999). Food applications of chitin and chitosans. *Trends Food Sci. Technol.* 10, 37–41. doi: 10.1016/S0924-2244(99)00017-5
- Shi, L., Fang, B., Yong, Y., Li, X., Gong, D., Li, J., et al. (2019). Chitosan oligosaccharide-mediated attenuation of LPS-induced inflammation in IPEC-J2 cells is related to the TLR4/NF- $\kappa$ B signaling pathway. *Carbohydr. Polym.* 219, 269–279. doi: 10.1016/j.carbpol.2019.05.036
- Sinha, S., Chand, S., and Tripathi, P. (2016). Recent progress in chitosanase production of monomer-free chitoooligosaccharides: bioprocess strategies and future applications. *Appl. Biochem. Biotechnol.* 180, 883–899. doi: 10.1007/s12010-016-2140-6
- Song, Y. S., Lee, S. H., Cho, J. A., Moon, C., Seo, D. J., and Jung, W. J. (2018). Expression and degradation patterns of chitinase purified from Xuehuali (*Pyrus bretschneiderilia*) pollen. *Int. J. Biol. Macromol.* 107, 446–452. doi: 10.1016/j.ijbiomac.2017.09.010
- Soon, C. Y., Tee, Y. B., Tan, C. H., Rosnita, A. T., and Khalina, A. (2018). Extraction and physicochemical characterization of chitin and chitosan from *Zophobas morio* larvae in varying sodium hydroxide concentration. *Int. J. Biol. Macromol.* 108, 135–142. doi: 10.1016/j.ijbiomac.2017.11.138
- Srere, P. (2002). Complexes of sequential metabolic enzymes. *Annu. Rev. Biochem.* 56, 89–124. doi: 10.1146/annurev.bi.56.070187.000513

- Srinivasan, H., Kanayairam, V., and Ravichandran, R. (2018). Chitin and chitosan preparation from shrimp shells *Penaeus monodon* and its human ovarian cancer cell line, PA-1. *Int. J. Biol. Macromol.* 107, 662–667. doi: 10.1016/j.ijbiomac.2017.09.035
- Stoykov, Y. M., Pavlov, A. I., and Krastanov, A. I. (2015). Chitinase biotechnology: production, purification, and application. *Eng. Life Sci.* 15, 30–38. doi: 10.1002/elsc.201400173
- Struszczyk, M. H. (2000). *Herstellung von Chitosan und einige Anwendungen*. Available at: [https://www.researchgate.net/publication/252779927\\_Herstellung\\_von\\_Chitosan\\_und\\_einige\\_Anwendungen](https://www.researchgate.net/publication/252779927_Herstellung_von_Chitosan_und_einige_Anwendungen) (accessed January 24, 2017).
- Struszczyk, K., Szczesna-Antczak, M., Walczak, M., Pomianowska, E., and Antczak, T. (2009). Isolation and purification of *Mucor circinelloides* intracellular chitosanolytic enzymes. *Carbohydr. Polym.* 78, 16–24. doi: 10.1016/j.carbpol.2009.04.010
- Struszczyk-Swita, K., Stanczyk, Ł., Szczesna-Antczak, M., and Antczak, T. (2017). Scale-up of PUF-immobilized fungal chitosanase–lipase preparation production. *Prep. Biochem. Biotechnol.* 47, 909–917. doi: 10.1080/10826068.2017.1365240
- Su, P. C., Hsueh, W. C., Chang, W. S., and Chen, P. T. (2017). Enhancement of chitosanase secretion by *Bacillus subtilis* for production of chitosan oligosaccharides. *J. Taiwan Inst. Chem. Eng.* 79, 49–54. doi: 10.1016/j.jtice.2016.12.040
- Sun, H., Cao, R., Li, L., Zhao, L., and Liu, Q. (2018). Cloning, purification and characterization of a novel GH46 family chitosanase, Csn-CAP, from *Staphylococcus capitis*. *Process Biochem.* 75, 146–151. doi: 10.1016/j.procbio.2018.09.021
- Synowiecki, J., and Al-Khateeb, N. A. (2003). Production, properties, and some new applications of chitin and its derivatives. *Crit. Rev. Food Sci. Nutr.* 43, 145–171. doi: 10.1080/10408690390826473
- Synowiecki, J., and Al-Khateeb, N. A. A. Q. (1997). Mycelia of *Mucor rouxii* as a source of chitin and chitosan. *Food Chem.* 60, 605–610. doi: 10.1016/S0308-8146(97)00039-3
- Tandrup, T., Frandsen, K. E. H., Johansen, K. S., Berrin, J.-G., and Lo Leggio, L. (2018). Recent insights into lytic polysaccharide monoxygenases (LPMOs). *Biochem. Soc. Trans.* 46, 1431–1447. doi: 10.1042/BST20170549
- Taylor, G., Jabaji-Hare, S., Charest, P. M., and Khan, W. (2003). Purification and characterization of an extracellular exochitinase,  $\beta$ -N-acetylhexosaminidase, from the fungal mycoparasite *Stachybotrys elegans*. *Can. J. Microbiol.* 48, 311–319. doi: 10.1139/w02-020
- Thadathil, N., and Velappan, S. P. (2014). Recent developments in chitosanase research and its biotechnological applications: a review. *Food Chem.* 150, 392–399. doi: 10.1016/j.foodchem.2013.10.083
- Tokuyasu, K., Ohnishi-Kameyama, M., and Hayashi, K. (2009). Purification and characterization of extracellular chitin deacetylase from *Colletotrichum lindemuthianum*. *Biosci. Biotechnol. Biochem.* 60, 1598–1603. doi: 10.1271/bbb.60.1598
- Tokuyasu, K., Ono, H., Ohnishi-Kameyama, M., Hayashi, K., and Mori, Y. (1997). Deacetylation of chitin oligosaccharides of dp 2-4 by chitin deacetylase from *Colletotrichum lindemuthianum*. *Carbohydr. Res.* 303, 353–358. doi: 10.1016/S0008-6215(97)00166-3
- Tolaimate, A., Desbrières, J., Rhazi, M., Alagui, A., Vincendon, M., and Vottero, P. (2000). On the influence of deacetylation process on the physicochemical characteristics of chitosan from squid chitin. *Polymer* 41, 2463–2469. doi: 10.1016/S0032-3861(99)00400-0
- Tømmeraaas, K., Vårum, K. M., Christensen, B. E., and Smidsrød, O. (2001). *Preparation and Characterisation of Oligosaccharides Produced by Nitrous Acid Depolymerisation of Chitosans*. Available online at: [www.elsevier.com/locate/carres](http://www.elsevier.com/locate/carres) (accessed August 29, 2019). doi: 10.1016/S0008-6215(01)00130-6
- Trombotto, S., Ladavière, C., Delolme, F., and Domard, A. (2008). Chemical preparation and structural characterization of a homogeneous series of chitin/chitosan oligomers. *Biomacromolecules* 9, 1731–1738. doi: 10.1021/bm800157x
- Tsai, G. J., Su, W. H., Chen, H. C., and Pan, C. L. (2002). Antimicrobial activity of shrimp chitin and chitosan from different treatments and applications of fish preservation. *Fish. Sci.* 68, 170–177. doi: 10.1046/j.1444-2906.2002.00404.x
- Tsaih, M. L., and Chen, R. H. (2003). The effect of reaction time and temperature during heterogenous alkali deacetylation on degree of deacetylation and molecular weight of resulting chitosan. *J. Appl. Polym. Sci.* 88, 2917–2923. doi: 10.1002/app.11986
- Tsigos, I., Martinou, A., Kafetzopoulos, D., and Bouriotis, V. (2000). Chitin deacetylases: new, versatile tools in biotechnology. *Trends Biotechnol.* 18, 305–312. doi: 10.1016/S0167-7799(00)01462-1
- Tuveng, T. R., Rothweiler, U., Udatha, G., Vaaje-Kolstad, G., Smalås, A., and Eijsink, V. G. H. (2017). Structure and function of a CE4 deacetylase isolated from a marine environment. *PLoS ONE* 12:e0187544. doi: 10.1371/journal.pone.0187544
- Vaaje-Kolstad, G., Forsberg, Z., Loose, J. S., Bissaro, B., and Eijsink, V. G. (2017). Structural diversity of lytic polysaccharide monoxygenases. *Curr. Opin. Struct. Biol.* 44, 67–76. doi: 10.1016/j.sbi.2016.12.012
- Vaaje-Kolstad, G., Westereng, B., Horn, S. J., Liu, Z., Zhai, H., Sørli, M., et al. (2010). An oxidative enzyme boosting the enzymatic conversion of recalcitrant polysaccharides. *Science* 330, 219–222. doi: 10.1126/science.1192231
- Vakili, M., Rafatullah, M., Salamatinia, B., Abdullah, A. Z., Ibrahim, M. H., Tan, K. B., et al. (2014). Application of chitosan and its derivatives as adsorbents for dye removal from water and wastewater: a review. *Carbohydr. Polym.* 113, 115–130. doi: 10.1016/j.carbpol.2014.07.007
- Viens, P., Lacombe-Harvey, M. È., and Brzezinski, R. (2015). Chitosanases from family 46 of glycoside hydrolases: from proteins to phenotypes. *Mar. Drugs* 13, 6566–6587. doi: 10.3390/md13116566
- Vishu Kumar, A. B., Varadaraj, M. C., Gowda, L. R., and Tharanathan, R. N. (2005). Characterization of chito-oligosaccharides prepared by chitosan analysis with the aid of papain and Pronase, and their bactericidal action against *Bacillus cereus* and *Escherichia coli*. *Biochem. J* 391, 167–175. doi: 10.1042/BJ20050093
- Vishu Kumar, A. B., Varadaraj, M. C., Gowda, L. R., and Tharanathan, R. N. (2007). Low molecular weight chitosans-Preparation with the aid of pronase, characterization and their bactericidal activity towards *Bacillus cereus* and *Escherichia coli*. *Biochim. Biophys. Acta* 1770, 495–505. doi: 10.1016/j.bbagen.2006.12.003
- Wang, D., Li, J., Salazar-Alvarez, G., McKee, L. S., Srivastava, V., Sellberg, J. A., et al. (2018). Production of functionalised chitins assisted by fungal lytic polysaccharide monoxygenase. *Green Chem.* 20, 2091–2100. doi: 10.1039/C8CG00422F
- Wang, J., Zhou, W., Yuan, H., and Wang, Y. (2008). Characterization of a novel fungal chitosanase Csn2 from *Gongronella* sp. *JG. Carbohydr. Res.* 343, 2583–2588. doi: 10.1016/j.carres.2008.08.004
- Wang, S. L., Peng, J. H., Liang, T. W., and Liu, K. C. (2008). Purification and characterization of a chitosanase from *Serratia marcescens* TKU011. *Carbohydr. Res.* 343, 1316–1323. doi: 10.1016/j.carres.2008.03.030
- Wang, S. L., Tseng, W. N., and Liang, T. W. (2011). Biodegradation of shellfish wastes and production of chitosanases by a squid pen-assimilating bacterium, *Acinetobacter calcoaceticus* TKU024. *Biodegradation* 22, 939–948. doi: 10.1007/s10532-011-9453-5
- Wang, Z., Zheng, L., Li, C., Zhang, D., Xiao, Y., Guan, G., et al. (2015). Modification of chitosan with monomethyl fumaric acid in an ionic liquid solution. *Carbohydr. Polym.* 117, 973–979. doi: 10.1016/j.carbpol.2014.10.021
- Wang, Z., Zheng, L., Yang, S., Niu, R., Chu, E., and Lin, X. (2007). N-Acetylchitoooligosaccharide is a potent angiogenic inhibitor both in vivo and in vitro. *Biochem. Biophys. Res. Commun.* 357, 26–31. doi: 10.1016/j.bbrc.2007.03.094
- Weikert, T., Niehues, A., Cord-Landwehr, S., Hellmann, M. J., and Moerschbacher, B. M. (2017). Reassessment of chitosanase substrate specificities and classification. *Nat. Commun.* 8, 1–11. doi: 10.1038/s41467-017-01667-1
- Wilner, O. I., Weizmann, Y., Gill, R., Lioubashevski, O., Freeman, R., and Willner, I. (2009). Enzyme cascades activated on topologically programmed DNA scaffolds. *Nat. Nanotechnol.* 4, 249–254. doi: 10.1038/nnano.2009.50
- Win, N. N., and Stevens, W. F. (2001). Shrimp chitin as substrate for fungal chitin deacetylase. *Appl. Microbiol. Biotechnol.* 57, 334–341. doi: 10.1007/s002530100741
- Wu, H., Aam, B. B., Wang, W., Norberg, A. L., Sørli, M., Eijsink, V. G. H., et al. (2012). Inhibition of angiogenesis by chitoooligosaccharides with specific degrees of acetylation and polymerization. *Carbohydr. Polym.* 89, 511–518. doi: 10.1016/j.carbpol.2012.03.037

- Wu, Y., Huang, Y., Zhou, Y., and Yang, F. (2014). Degradation of chitosan by swirling cavitation. *Innov. Food Sci. Emerg. Technol.* 23, 188–193. doi: 10.1016/j.ifset.2014.02.001
- Xia, Z., Wu, S., and Chen, J. (2013). Preparation of water soluble chitosan by hydrolysis using hydrogen peroxide. *Int. J. Biol. Macromol.* 59, 242–245. doi: 10.1016/j.ijbiomac.2013.04.034
- Xie, H., Jia, Z., Huang, J., and Zhang, C. (2011). Preparation of low molecular weight chitosan by complex enzymes hydrolysis. *Int. J. Chem.* 3, 47–53. doi: 10.5539/ijc.v3n2p180
- King, R., Liu, Y., Li, K., Yu, H., Liu, S., Yang, Y., et al. (2017). Monomer composition of chitoooligosaccharides obtained by different degradation methods and their effects on immunomodulatory activities. *Carbohydr. Polym.* 157, 1288–1297. doi: 10.1016/j.carbpol.2016.11.001
- Xiong, C., Wu, H., Wei, P., Pan, M., Tuo, Y., Kusakabe, I., et al. (2009). Potent angiogenic inhibition effects of deacetylated chitohexaose separated from chitoooligosaccharides and its mechanism of action *in vitro*. *Carbohydr. Res.* 344, 1975–1983. doi: 10.1016/j.carres.2009.06.036
- Yan, Q., and Fong, S. S. (2018). Cloning and characterization of a chitinase from *Thermobifida fusca* reveals Tfu\_0580 as a thermostable and acidic endochitinase. *Biotechnol. Rep.* 19:e00274. doi: 10.1016/j.btre.2018.e00274
- Yang, F., Luan, B., Sun, Z., Yang, C., Yu, Z., and Li, X. (2017). Application of chitoooligosaccharides as antioxidants in beer to improve the flavour stability by protecting against beer staling during storage. *Biotechnol. Lett.* 39, 305–310. doi: 10.1007/s10529-016-2248-3
- Yang, L., Zhang, J., He, J., Zhang, J., and Gan, Z. (2015). Homogeneous synthesis of amino-reserved chitosan-graft-polycaprolactone in an ionic liquid and the application in cell cultivation. *Polym. Int.* 64, 1045–1052. doi: 10.1002/pi.4912
- Yeh, H. Y., and Lin, J. C. (2008). Surface characterization and *in vitro* platelet compatibility study of surface sulfonated chitosan membrane with amino group protection-deprotection strategy. *J. Biomater. Sci. Polym. Ed.* 19, 291–310. doi: 10.1163/156856208783720985
- Yin, X., Chi, Y., Guo, C., Feng, S., Liu, J., Sun, K., et al. (2017). Chitoooligosaccharides modified reduction-sensitive liposomes: enhanced cytoplasmic drug delivery and osteosarcomas-tumor inhibition in animal models. *Pharm. Res.* 34, 2172–2184. doi: 10.1007/s11095-017-2225-0
- You, C., Myung, S., and Zhang, Y. H. P. (2012). Facilitated substrate channeling in a self-assembled trifunctional enzyme complex. *Angew. Chemie Int. Ed.* 51, 8787–8790. doi: 10.1002/anie.201202441
- Younes, I., Ghorbel-Bellaaj, O., Chaabouni, M., Rinaudo, M., Souard, F., Vanhaverbeke, C., et al. (2014). Use of a fractional factorial design to study the effects of experimental factors on the chitin deacetylation. *Int. J. Biol. Macromol.* 70, 385–390. doi: 10.1016/j.ijbiomac.2014.06.051
- Younes, I., Hajji, S., Rinaudo, M., Chaabouni, M., Jellouli, K., and Nasri, M. (2016). Optimization of proteins and minerals removal from shrimp shells to produce highly acetylated chitin. *Int. J. Biol. Macromol.* 84, 246–253. doi: 10.1016/j.ijbiomac.2015.08.034
- Younes, I., and Rinaudo, M. (2015). Chitin and chitosan preparation from marine sources. Structure, properties and applications. *Mar. Drugs* 13, 1133–1174. doi: 10.3390/md13031133
- Zhang, G., Li, X., Xu, X., Tang, K., Vu, H., Gao, P., et al. (2019). Antimicrobial activities of irradiation-degraded chitosan fragments. *Food Biosci.* 29, 94–101. doi: 10.1016/j.fbio.2019.03.011
- Zhang, H., Sang, Q., and Zhang, W. (2012). Statistical optimization of chitosanase production by *Aspergillus* sp. QD-2 in submerged fermentation. *Ann. Microbiol.* 62, 193–201. doi: 10.1007/s13213-011-0246-1
- Zhang, J., Han, J., Zhang, X., Jiang, J., Xu, M., Zhang, D., et al. (2015). Polymeric nanoparticles based on chitoooligosaccharide as drug carriers for co-delivery of all-trans-retinoic acid and paclitaxel. *Carbohydr. Polym.* 129, 25–34. doi: 10.1016/j.carbpol.2015.04.036
- Zhang, M., Puri, A. K., Govender, A., Wang, Z., Singh, S., and Permaul, K. (2015). The multi-chitinolytic enzyme system of the compost-dwelling thermophilic fungus *Thermomyces lanuginosus*. *Process Biochem.* 50, 237–244. doi: 10.1016/j.procbio.2014.11.008
- Zhao, D., Wang, J., Tan, L., Sun, C., and Dong, J. (2013). Synthesis of N-furoyl chitosan and chito-oligosaccharides and evaluation of their antioxidant activity *in vitro*. *Int. J. Biol. Macromol.* 59, 391–395. doi: 10.1016/j.ijbiomac.2013.04.072
- Zhao, F., Yin, Y., Lu, W. W., Leong, J. C., Zhang, W., Zhang, J., et al. (2002). Preparation and histological evaluation of biomimetic three-dimensional hydroxyapatite/chitosan-gelatin network composite scaffolds. *Biomaterials* 23, 3227–3234. doi: 10.1016/S0142-9612(02)00077-7
- Zhao, Y., Park, R. D., and Muzzarelli, R. A. A. (2010). Chitin deacetylases: properties and applications. *Mar. Drugs* 8, 24–46. doi: 10.3390/md8010024
- Zheng, B., Wen, Z. S., Huang, Y. J., Xia, M. S., Xiang, X. W., and Qu, Y. L. (2016). Molecular weight-dependent immunostimulative activity of low molecular weight chitosan via regulating NF-KB and AP-1 Signaling Pathways in RAW264.7 macrophages. *Mar. Drugs* 14:E169. doi: 10.3390/md14090169
- Zhu, X.-Y., Zhao, Y., Zhang, H.-D., Wang, W.-X., Cong, H.-H., and Yin, H. (2019). Characterization of the specific mode of action of a chitin deacetylase and separation of the partially acetylated chitosan oligosaccharides. *Mar. Drugs* 17:E74. doi: 10.3390/md17020074
- Zitouni, M., Fortin, M., Scheerle, R. K., Letzel, T., Matteau, D., Rodrigue, S., et al. (2013). Biochemical and molecular characterization of a thermostable chitosanase produced by the strain *Paenibacillus* sp. 1794 newly isolated from compost. *Appl. Microbiol. Biotechnol.* 97, 5801–5813. doi: 10.1007/s00253-012-4483-4

**Conflict of Interest:** The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

Copyright © 2019 Kaczmarek, Struszczyk-Swita, Li, Szczesna-Antczak and Daroch. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) and the copyright owner(s) are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.