

FIELD EMISSION FROM SINGLE AND FEW-LAYER GRAPHENE FLAKES

S. Santandrea^a, F. Giubileo^a, V. Grossi^b,
S. Santucci^b, M. Passacantando^b, T. Schroeder^c,
G. Lupina^c and A. Di Bartolomeo^a

^aDipartimento di Fisica, Centro NANO_MATES, Università degli Studi di Salerno,
and CNR-SPIN Salerno, via Ponte don Melillo, 84084 Fisciano (SA), Italy

^bDipartimento di Fisica, Università degli Studi dell'Aquila, via Vetoio, 67100 Coppito, LAquila, Italy

^cIHP, Im Technologiepark 25, 15236 Frankfurt (Oder), Germany

Graphene, consisting of a single- or few-graphite layers, has a very high aspect ratio (thickness to lateral size ratio) and a dramatically enhanced local electric field is expected at its edges; it shares many similar or even superior properties as carbon nanotubes (CNTs) and, as CNTs, has high potentiality for field emission (FE) applications [1-3]. So far, most of the work has been performed on graphene films [4,5] or on graphene/polymer composites [6] reporting FE from graphene edges or pleats at low applied fields; no observation of FE current from the inner, flat part of graphene flakes has been reported [7]. We report observation of FE current from the inner, flat part of single- and few- layer graphene flakes, which can make the fabrication of graphene based cathodes easier for FE applications [8].

Single- and few-layer graphene sheets were prepared by mechanical exfoliation of highly ordered pyrolytic graphite and transferred by scotch-tape method on SiO₂ layer thermally grown on p-type Si substrate. The thickness of the SiO₂ layer was chosen to ~ 300 nm. Raman spectroscopy was further exploited to give confirmation of the single- or few-layer graphene. Taking advantage of a special setup, consisting of a two-probe nanomanipulation system (two tungsten tips with curvature radius < 100 nm) operating in a scanning electron microscope (SEM) and connected to external source measurement units (SMUs), we investigate FE currents by applying electric fields up to $2 \text{ kV}/\mu\text{m}$. The tips, one in contact with graphene and the second at a varying distance from it, were used as the cathode and the anode, respectively.

We show that a high and stable FE current (up to $1 \mu\text{A}$), well described by the usual FowlerNordheim (FN) model over five orders of magnitude, can be achieved with a turn-on field of $\sim 600 \text{ V}/\mu\text{m}$. This high field is not surprising since the electrons are emitted from a flat surface, which do not benefit from the high field enhancement factor of a tiplike shape. We tested also the emission stability from the flat inner part of single-layer graphene flake, due to its relevance for practical applications. Experimentally, we applied a constant bias and monitored the current over periods of several hours, over which a stable process was confirmed.

References

- [1] W. A. de Heer *et al.*, Science, 270 (1995) 1179.
- [2] M. Passacantando *et al.*, Nanotechnology, 19 (2008) 395701.
- [3] A. Di Bartolomeo *et al.*, Carbon, 45 (2007) 2957.
- [4] S. W. Lee *et al.*, Nanoscale Res. Lett., 4 (2009) 1218.
- [5] J. Liu *et al.*, Appl. Phys. Lett., 97 (2010) 033109.
- [6] G. Eda *et al.*, H. Unalan, Appl. Phys. Lett., 93 (2008) 233502.
- [7] Z. Xiao *et al.*, ACS Nano, 4 (2010) 6332.
- [8] S. Santandrea *et al.*, Appl. Phys. Lett., 98 (2011) 163109.