

# Fracture toughness to understand stretch-flangeability and edge cracking resistance in AHSS

D. Casellas<sup>1,3</sup>, A. Lara<sup>1</sup>, D. Frómeta<sup>1</sup>, D. Gutiérrez<sup>1</sup>, S. Molas<sup>1</sup>, Ll.Pérez<sup>1</sup>, J. Rehr<sup>2</sup> and C. Suppan<sup>2</sup>

<sup>1</sup> *Fundació CTM Centre Tecnològic, Plaça de la Ciència 2, 08243 Manresa, Spain*

<sup>2</sup> *voestalpine Stahl GmbH, voestalpine-Straße 3, 4020 Linz, Austria*

<sup>3</sup> *Luleå University of Technology, 971 87 Luleå, Sweden*

Corresponding author: [daniel.casellas@ctm.com.es](mailto:daniel.casellas@ctm.com.es)

## Abstract

1 The edge fracture is considered as a high risk for automotive parts, especially for parts made of  
2 Advanced High Strength Steels (AHSS). The limited ductility of AHSS makes them more  
3 sensitive to the edge damage. The traditional approaches, such as those based on ductility  
4 measurements or forming limit diagrams, are unable to predict this type of fractures. Thus,  
5 stretch-flangeability has become an important formability parameter in addition to tensile and  
6 formability properties. The damage induced in sheared edges in AHSS parts affects stretch-  
7 flangeability, because the generated microcracks propagates from the edge. Accordingly, a  
8 fracture mechanics approach may be followed to characterize the crack propagation resistance.  
9 With this aim, this work addresses the applicability of fracture toughness as a tool to understand  
10 crack-related problems, as stretch-flangeability and edge cracking, in different AHSS grades.  
11 Fracture toughness was determined by following the essential work of fracture methodology  
12 and stretch-flangeability was characterized by means of hole expansions tests. Results show a  
13 good correlation between stretch-flangeability and fracture toughness. It allows postulating  
14 fracture toughness, measured by the essential work of fracture methodology, as a key material  
15 property to rationalize crack propagation phenomena in AHSS.

16

17 **Key words:** Stretch-flangeability, AHSS, Essential Work of Fracture, fracture toughness.

18 **1. INTRODUCTION**

19 Cutting or shearing operations are widely used in metal sheet forming industries to produce  
20 final components. It is well known that cut or sheared edges may present damage in terms of  
21 surface irregularities, microvoids and microcracks. The degree of such damage at the cut edge  
22 is known as edge integrity. It is known to influence part quality in materials with limited  
23 ductility when sheared edges are subjected to bending or stretching in subsequent forming  
24 operations. This is the case for the so-called AHSS (Advanced High Strength Steels) that are  
25 extensively implemented in the automotive industry to reduce weight and increase  
26 crashworthiness (a modern vehicle body contains about 30-50 % of AHSS [1]).

27

28 Although AHSS have contributed to the huge improvement of today's vehicles, they have also  
29 introduced new challenges which are still only solved partially. In the last years, many works  
30 focused on springback and formability prediction of these steels [2-6]. However, less attention  
31 has been given to the cracking phenomena observed for some AHSS grades at cut or sheared  
32 edges (Figure 1). Edge cracking is associated with sheared areas that expands during forming  
33 operations involving stretch flanging or hole expansion. This process increases the flange edge  
34 length during the deformation [7]. Typical examples of stretch flanges in the automotive  
35 industry include cut-outs in automotive inner panels and corners of window panels, hub-holes  
36 of wheel discs, hidden joints, etc. Edge cracking compromises part quality and it is a serious  
37 production problem, because if it is not accounted for in the overall design, the load paths  
38 through the vehicle frame in a crash situation can be misdirected and the resultant intrusion  
39 levels can exceed target levels. Such problem was not observed in mild steels, whose high  
40 ductility prevents the cut edge from cracking, and less knowledge and expertise is available to  
41 immediately solve it in industrial parts [8, 9].

42 AHSS are more sensitive to the crack edge integrity, so their crack edge resistance depends on  
43 the hole preparation method (punching, laser cutting waterjet cutting...), as well as on the steel  
44 microstructure to tolerate the induced damage [10-12]. Hence, the edge fracture can be  
45 considered as a high risk for AHSS automotive components. The traditional approaches, such  
46 as the Forming Limit Diagram (FLD), are unable to predict this type of fracture and great efforts  
47 have been made to develop failure criteria that could predict edge fracture [9]. In this sense,  
48 stretch-flangeability has become a particularly important formability parameter in addition to  
49 tensile properties, especially for parts under heavy deformation conditions, to rationalize edge  
50 cracking problems.

51 The stretch-flangeability in low C Steels and AHSS has been studied well, but the results  
52 obtained in some AHSS grades were initially surprising, since stretch-flangeability increases  
53 when the material strength also increases and ductility diminishes [6, 11, 13]. This observation  
54 is in the opposite way of the thinking for ductile steels, where it is accepted that ductility  
55 improves flangeability. In dual-phase steels this behavior is explained by the hardness  
56 difference between ferrite and martensite [14-16]. On the other hand, the works of Fonstein et  
57 al. [17] and Takahashi et al. [18] approached the problem from a fracture mechanics point of  
58 view and proposed that fracture toughness can be used to rationalize the observed behavior for  
59 AHSS. However, this approach is not intensively applied to metal sheets yet because fracture  
60 toughness cannot be readily measured by standard characterization techniques. It means that  
61 fracture or crack propagation phenomena in metal sheets, as the observed behavior in stretch-  
62 flangeability tests, cannot be rationalized in terms of intrinsic mechanical properties, which  
63 hampers process and material optimization. Aimed at filling this gap of knowledge, the  
64 objective of the present work is to measure and use fracture toughness as a tool to understand  
65 crack-related problems in AHSS sheets, as stretch-flangeability or edge cracking resistance.

## 66 2. MATERIALS AND EXPERIMENTAL PROCEDURE

### 67 2.1. Materials

68 Different AHSS grades were studied: (a) two commercially available cold forming grades, a  
69 dual phase steel (DP1000) and a complex phase steel (CP1000); (b) three 3<sup>rd</sup> generation AHSS  
70 grades: TBF (Trip-aided Bainitic ferrite) steel, Q&P (Quenching & partitioning) steel , and  
71 mixed TBF/Q&P microstructure; (c) two microstructures of hot stamped boron steel: one in-  
72 press hardened condition, named as PHS1500 and another one with an additional tempering  
73 treatment, named as PHS1000.

74 *Table I* shows the chemical composition of the investigated steels. Microstructure of these steel  
75 grades has been studied by means of scanning electron microscopy (SEM) after electro-  
76 polishing. The corresponding microstructures can be seen in Figures 2 to 4. CP-like grades  
77 (CP1000 and mixed TBF/Q&P) as well as the Q&P grade show a homogeneous matrix of  
78 bainite/tempered martensite. Q&P and mixed TBF/Q&P also contain retained austenite. In  
79 DP1000 and TBF grades the matrix consists of a mixture of ferrite, bainitic ferrite,  
80 bainite/tempered martensite, martensite and retained austenite. PHS1500 consists of a  
81 homogeneous martensitic matrix, which is slightly auto-tempered during cooling. The  
82 tempering treatment for PHS1000 basically leads to relaxation of the tetragonal martensite  
83 lattice by formation of carbides, which can be observed as white lines and spots in Figure 4b.

84

### 85 2.2. Tensile Tests

86 Conventional axial tensile tests were performed according to EN-ISO6892-1 with the  
87 specimens oriented transversally to the rolling direction. Table II shows the results.

### 88 2.3. Hole Expansion Test

89 Looking at stretch-flangeability, the hole expansion test (HET) closely resembles the process  
90 under production conditions to form such flanges starting with punched holes. This is the most

91 used method to evaluate the suitability of the sheet steel for forming such “flanges”. The value  
92 obtained in this test is the Hole Expansion Ratio (HER), which is calculated using the initial  
93 hole diameter ( $D_0$ ) and the diameter at first through thickness crack apparition ( $D_h$ ) as follows:

$$94 \quad \text{HER}[\%] \text{ or } \lambda = \left[ \frac{D_h - D_0}{D_0} \right] \cdot 100 \quad (1)$$

95 HER indicates the maximum diametrical expansion that a circular punched hole can reach when  
96 a conical tool is forced into it until a crack in the hole edge extends through the full sheet  
97 thickness. The HET were carried out in a universal testing machine using a conical punch with  
98 an angle of  $60^\circ$  according to ISO16630 standard [19]. The initial hole diameter was 10 mm and  
99 the driving speed of the conical punch was 1 mm/s. The punching clearance was set to 12 %,  
100 because it is following standard recommendations and previous work where it is experimentally  
101 assessed that this value gives rise to the maximum HER in AHSS [11]. The followed punching  
102 and flanging processes are shown in Figure 5. Three samples of 100 x 100 mm from each steel  
103 were tested. A clamping force of 50 KN was applied to the test piece to prevent any material  
104 draw-in from the clamping area during the test. During the HET the emerging and extension of  
105 cracks were detected by a digital image correlation equipment (DIC) located below the tool.  $D_h$   
106 was measured from the image at which the first through-thickness crack was observed, before  
107 remove the punch.

#### 108 ***2.4. Measurement of fracture toughness in thin sheets***

109 In fracture mechanics, the fracture toughness is defined as the energy spent in the creation of  
110 two surfaces at the crack tip that give rise to crack propagation. For ductile materials  
111 experimental approaches based on elastic-plastic fracture mechanics allow determining the  
112 crack propagation resistance, as the J-integral (giving the value of  $J_C$ ), the J-R curve or the  
113 CTOD measurement. The experimental complexity of standardized methods and the difficulty  
114 for transferring the obtained values to thin sheet components have given rise to a lack of  
115 knowledge regarding toughness of metal sheets. As a consequence, the fracture toughness of

116 the AHSS sheets is not known. For thin plates an alternative method to characterize fracture  
117 toughness was developed in the 80s; the EWF (Essential Work of Fracture) methodology. It  
118 was successfully applied to characterize ductile alloys, and the obtained toughness value was  
119 found to be equivalent to  $J_C$  by many authors [20-27]. Nowadays it is commonly applied to  
120 characterize polymeric thin films following a protocol developed by the ESIS (European  
121 Structural Integrity Society), but it is not extensively used for thin steel sheets. Recent works  
122 show that the EWF methodology can be applied to AHSS sheets [27-31].

123

124 The EWF is experimentally evaluated by following the methodology developed by Cotterell  
125 and Reddel [20]. These authors proposed that the total work of fracture ( $W_f$ ) during the ductile  
126 fracture can be separated into two components: i) The essential work of fracture ( $W_e$ ) spent in  
127 the fracture process zone (FPZ) in front of the crack tip, and ii) non-essential plastic work ( $W_p$ )  
128 dissipated in an outer region as a consequence of plastic deformation. Double Edge Notched  
129 Tensile (DENT) specimen (Figure 6) is particularly suitable for fracture mechanics tests  
130 because the transverse stress between the notches is tensile and there is no buckling. In DENT  
131 specimens if the material in front of the crack tip of the two notches, the ligament, is completely  
132 yielded and the plastic zone is confined to the notched ligament, then the plastic work performed  
133 for total fracture is proportional to the plastic volume at crack initiation and the work performed  
134 at the FPZ is proportional to the fractured area. It can be expressed as:

$$135 \quad W_f = W_e + W_p = w_e l t + w_p \beta l^2 t \quad (2)$$

136 Where  $\beta$  is a shape factor that depends on the shape of the plastic zone,  $t$  is the sheet thickness  
137 and  $l$  is the ligament length between the two notches. The specific work of fracture ( $w_f$ ) is  
138 obtained by dividing equation (2) by the initial ligament area  $l t$ . Thus, equation (2) can be  
139 rewritten as:

140

141 
$$\frac{W_f}{lt} = w_f = w_e + w_p \beta l \quad (3)$$

142

143 If  $w_f$  is plotted against the ligament length  $l$ , a straight line with a positive intercept, which is  
144 the specific essential work of fracture ( $w_e$ ), is obtained.

145 When applying the EWF methodology to metal sheets it should be kept in mind that the  
146 obtained values of  $w_e$  are greatly affected by the notch root radius. Such effect has been  
147 experimentally demonstrated in mild and dual-phase steels [30, 31]. The effect of the notch root  
148 radius on the fracture toughness measurement is well known in plain strain fracture toughness  
149 tests, below a critical notch root radius value the fracture toughness measurements are  
150 independent of the notch radius and fracture toughness is considered as a material intrinsic  
151 property. To avoid the effect of notch root radius, the ASTM E399 procedure for evaluating the  
152 fracture toughness suggests the nucleation of a fatigue crack at the notch root. This fatigue crack  
153 has the lowest possible radius at the crack tip, ensuring valid fracture toughness values.  
154 Similarly, in the EWF methodology, notches with the lowest possible root radius must be used  
155 (Figure 6). However,  $w_e$  is not fully a material intrinsic property because it is influenced by  
156 necking of the fracture process zone and this in turn depends on the thickness of the sheet  
157 material.

158

159 In the present work  $W_f$  was measured by loading DENT specimens of 240x55 mm, extracted  
160 transversally to the sheet rolling direction, in a universal testing machine with a speed of 1  
161 mm/min. The displacement was measured with a video extensometer with gauge length of 50  
162 mm. Specimens ligaments length ranges from 6 mm to 16 mm. About 3 to 5 specimens were  
163 tested up to fracture for each ligament length. The plot of  $w_f$  against  $l$  gives the values of  $w_e$ , as  
164 detailed before. Linear fitting was performed using a confidence interval of 95%.

## 165 **3. RESULTS**

### 166 ***3.1. Hole Expansion Test***

167 Figure 7 shows the measured HER values. They are similar to previously reported results for  
168 other AHSS, as DP780, DP980 and press hardened steels [6]. They are also considerably lower  
169 than those obtained with mild steels, where HER ranges from 100 to 140% [6, 30, 32]. HER  
170 values show relatively large scatter, as has been reported by other authors in AHSS [6, 33].  
171 Figure 8 shows pictures of the first crack extension around the flange in DP1000 and CP1000  
172 steels determined with the DIC technique. From figure 8 the poor hole expansion of DP1000  
173 before the first crack extension can be seen, whilst CP1000 steel presents a much greater hole  
174 expansion capacity than the DP steel. As expected CP-like microstructures as those in CP, Q&P,  
175 PHS1000 and TBF/Q&P show high HER values, meanwhile DP-like microstructures, as DP  
176 and TBF, show low HER values. It is in agreement with previous works on multiphase steels,  
177 containing mixtures of ferrite, bainite and martensite, as CP and DP. In such steels the  
178 combination of a soft phase, ferrite, with a hard phase, martensite or bainite, give rise to high  
179 strain hardening coefficients and large ductility. Damage in DP and CP steels is related to the  
180 hardness difference between phases. Strain localizes in ferrite and promotes void generation at  
181 the ferrite/martensite interface. Thus, finer microstructures as well as replacement of martensite  
182 by bainite give rise to higher damage resistant microstructures and show higher HER values  
183 [15-18]. PHS1500 presents the lowest HER values because the microstructure is martensite,  
184 with lower damage resistance than DP and CP ones.

### 185 ***3.2. Essential Work of Fracture***

186 The definition of the EWF methodology imposes that the crack tip must be yielded before the  
187 onset of crack propagation. In DENT specimens it means that the material between the two



188 notches must be fully yielded. This constraint is satisfied in mild steels [26], but the higher yield  
189 strength of AHSS implies that this condition must be verified for the studied AHSS. DIC  
190 analysis was performed for all the steels studied and showed that at maximum load in samples  
191 with the largest ligament length, the ligament area is fully yielded and that the plastic zone  
192 morphology is almost circular. Both requirements must be fulfilled to obtain valid values of  $w_e$   
193 from equation (3). Figure 9 shows DIC analysis on the shortest and largest ligament for DP1000  
194 and PHS15000. The measured values of  $w_e$  are shown in Figure 10.

195

196 Similarly to the HER results, a relationship between microstructure and toughness can be seen;  
197 CP-like grades (CP1000, TBF/Q&P and Q&P grades) show higher EWF values than DP-type  
198 steels (DP1000 and TBF). PHS1500 presents also one of the lowest toughness values, a value  
199 which increases significantly after the tempering treatment done at PHS1000.

200

#### 201 **4. DISCUSSION**

202 Figure 11a shows the relationship between HER and tensile strength for the studied steels,  
203 together with results for mild steels and other AHSS grades extracted from reference 6. Results  
204 for mild steel and AHSS with tensile strength lower than 800MPa show an almost linear  
205 correlation between HER and tensile strength and elongation, so HER linearly decreases when  
206 tensile strength increases. When HER values are plotted against elongation, the opposite trend  
207 is observed (Figure 11b). However, such relationships are not followed by the here investigated  
208 AHSS grades, with tensile strength above 800 MPa. This experimental behavior is in agreement  
209 with previous works for AHSS, where it is stated that ductility or elongation cannot be used to  
210 rationalize stretch flangeability in AHSS [13, 14, 34, 35].

211

212 Stretch flangeability is dictated by the propagation of cracks through the material thickness,  
213 thus the HET values could be related to the material resistance to crack propagation, which is  
214 the fracture toughness. Fonstein et al. [17] and Takahashi et al. [18] also stated that stretch-  
215 flangeability is controlled by the propagation of cracks or defects introduced during hole cutting  
216 and showed that tougher materials (measured in terms of  $J_{IC}$ ) give rise to higher HER values.  
217 Aimed at proving such correlation, the results of EWF have been used to rationalize the HER  
218 values in the current work. It is shown in Figure 12. The experimental values of HER and  $w_e$   
219 correlate very well and fits an almost linear relationship, i.e. the tougher materials present  
220 higher HER values, whilst lower HER ones are associated with lower  $w_e$ . Accordingly, fracture  
221 toughness of AHSS sheets, in terms of  $w_e$ , can be used to properly rationalize stretch-  
222 flangeability in AHSS. These results allow to postulate that fracture toughness becomes a  
223 relevant material property when designing AHSS with improved crack edge resistance.

224

## 225 5. CONCLUSIONS

226 Based on the experimental results of stretch-flangeability and fracture toughness measurements  
227 performed by means of the EWF methodology for several grades of AHSS with high tensile  
228 strength, the following conclusions can be drawn:

- 229 • The EWF methodology can be applied to AHSS sheets with very high tensile  
230 strength, up to 1500 MPa, to estimate fracture toughness.
- 231 • Classical mechanical properties, such as ultimate tensile strength and elongation, are  
232 unable to predict HER in AHSS with high tensile strength (above 800MPa).
- 233 • The values of fracture toughness, in terms of  $w_e$ , show the same trend as stretch-  
234 flangeability for the investigated steels.
- 235 • Fracture toughness is the material property to rationalize the observed improvement  
236 of stretch-flangeability for some AHSS microstructures. Furthermore, fracture

237 toughness may help to understand the cracking related phenomena in AHSS, as edge  
238 cracking.  
239

## ACKNOWLEDGEMENTS

This investigation has been partially funded by the Catalan government under grant TECCTA-13-1-0005 and by the European Commission, Research Fund for Coal and Steel, under grant agreement RFSR-CT-2014-00015 (Tough-Sheet).

## REFERENCES

- [1] N. Lutsey: Report UCD-ITS-RR-10-10. Davis, CA: *Institute of Transportation Studies*, University of California, 2010.
- [2] P.Chen, M. Koç: *J. Mat. Proc. Tech.*, 2007, vol. 190, pp. 189-198.
- [3] P. Tsipouridis, E. Werner, C. Kremaszky, E. Trag: *Steel Res. Int.*, 2006, vol. 77, pp. 654–667.
- [4] P. J. Jacques: *Current Opinion in Solid State and Material Science*, 2004, vol. 8, pp. 259-265.
- [5] A. Karelova, C. Kremaszky, M. Dünckelmeyer, E. Werner, T. Hebesberger, A. Pichler: *Mat. Sci. &Tech. (MS&T)*, 2009, pp. 1358-1368.
- [6] X. Chen, H. Jiang, Z. Cui, C. Lian, C. Lu: *Proc. Eng.*, 2014, vol. 81, pp. 718-723.
- [7] V. Uthaisangsuk, U. Prahl, W. Bleck: *Comp. Mat. Sci.*, 2009, pp. 617-623.
- [8] X. Wu, H. Bahmanpour, K. Schmid: *J. Mat. Proc. Tech.*, 2012, vol. 212, pp. 1209-1224.
- [9] M. Luo, T. Wierzbicki: *Int. J. of Solids and Struct.*, 2010, vol. 47, pp. 3084-3102.
- [10] D.J. Thomas: *J. Fail. Anal. and Preven.*, 2013, vol. 13(4), pp. 451-462.
- [11] D. Gutiérrez, J. Escaler, A. Lara, D. Casellas, J.M. Prado: *Proceedings of the IDDRG2011*.
- [12] K. Watanabe, M. Tachibana, K. Koyanagi, K. Motomura: *LS-Dyna Conference*, 2006.
- [13] P. Larour, H. Pauli, J. Freudenthaler, A. Grünsteidl: *Proceedings of the IDDRG2011*.
- [14] X. Fang, Z. Fan, B. Ralph, P. Evans, R. Underhill: *J. of Mat. Sci.*, 2003, vol. 38, pp. 3877-3882.

- [15] K. Hasegawa, K Kawamura, T. Urabe, Y. Hosoya: *ISIJ International*, 2004, pp. 603-609.
- [16] G. Avramovic-Cingaraa, Y. Ososkova, M.K. Jain, D.S. Wilkinson: *Mat. Sci & Eng. A*, 2009, vol. A516, pp. 7-16.
- [17] N. Fonstein, H-J. Jun, G. Huang, S. Sriram, B. Yan: *Mat. Sci. and Tech.* 2011, pp. 634-641.
- [18] Y. Takahashi, O. Kawanom, K. Ushiodam, S. Aihara: *Asia Steel Int. Conference*, 2012.
- [19] *ISO/TS16630*. Metallic materials – Method of hole expanding test, 2003.
- [20] B. Cotterell, J.K. Reddel: *Int. J. Fracture*, 1977, pp. 267-277.
- [21] Y.W. Mai, P. Powell: *J. Polym. Sci.*, 1991, vol. 29, pp. 785-793.
- [22] B. Cotterell, A. G. Atkins: *Int. J. Fract.*, 1996, vol. 81, pp. 357-372.
- [23] J. Wu, Y.W. Mai: *Pol. Eng. and Sci.*, 1996, vol. 36, pp. 2275 - 2288.
- [24] Y. Marchal, K. Schmidt, T. Pardoen, R. Knockaert. I. Doghri: *ECF 11. Mechanisms and Mechanics of Damage and Failure*, 1996, pp. 2259-2265.
- [25] T. Pardoen, Y. Marchal, F. Delannay: *J. Mech. Phys. Sol.*, 1999, vol. 47, pp. 2093-2123.
- [26] T. Pardoen, F. Hachez, B. Marchioni, P.H. Blyth, A.G. Atkins: *J. of Mec. and Physics of Solids*, 2004, vol. 52, pp. 423-452.
- [27] G. Lacroix, T. Pardoen, P.J. Jacques: *Act. Mat.*, 2008, vol. 56, pp. 3900-3913.
- [28] R. Muñoz, A. Lara, D. Casellas: *Proceedings of the IDDRG2011 International Conference*, 2011.
- [29] D. Gutiérrez, Ll. Pérez, A. Lara, D. Casellas, J.M. Prado: *19th European Conference on Fracture (ECF19)*, 2012.
- [30] O. Akourri, M. Louah, A. Kifani, G. Gilbert, G. Pluvinage: *Eng. Fract. Mech.*, 2000, pp. 491-505.
- [31] D. Gutiérrez, Ll. Pérez, A. Lara, D. Casellas, J.M. Prado: *Revista de Metalurgia*, 2013, vol. 49, no. 1, pp. 45-54.

- [32] K. Mori, Y. Abe, Y. Suzui: *J. Mat. Proc. Tech.*, 2010, vol. 210, pp. 653-659.
- [33] P. Larour, J. Freudenthaler, A. Grünsteidl, K.Wang: *Proceedings of the IDDRG2014*.
- [34] M. Kapp: *PhD Thesis. Erich Schmid Institute of Materials Science*, 2011.
- [35] H. Mohrbacher: *Adv. in Manuf.*, 2013, vol. 1, pp. 28-41.

## TABLES

**Table I. Chemical composition, in weight %.**

Steel grade	C	Si	Mn	Cr	B	Al
CP1000	~0,1	<0,5	1,8-2,2			
DP1000	~0,15					
TBF	~0,2				<0,003	
Q&P	~0,1	0,5-1,0	2,2-2,6	<0,7		-
TBF/Q&P	~0,1					
PHS1500						
PHS1000	~0,2	~0,2	~1,2		~0,003	

**Table II. Mechanical properties: yield strength (YS), ultimate tensile strength (UTS), Total elongation and hardening exponent (n). Thickness (t) for all grades is also given.**

Steel grade	t [mm]	YS [MPa]	UTS [MPa]	Elongation [%]	n
CP1000	1,4	920	1008	8.8	0.05
DP1000	1,4	738	1027	10.3	0.10
TBF	1,5	725	1019	14.7	0.12
Q&P	1,4	909	1209	7.4	0.09
TBF/Q&P	1,4	876	1026	11.3	0.09
PHS1500	1,5	1075	1552	5.2	0.08
PHS1000	1,5	988	1007	7.3	0.05

## FIGURE CAPTIONS

**Figure 1.** Cracks produced in cold formed AHSS automotive parts.

**Figure 2.** Microstructure of: (a) CP1000 steel and (b) DP1000 steel.

**Figure 3.** Microstructure of 3<sup>rd</sup> generation AHSS: (a) TBF, (b) Q&P and (c) TBF/Q&P grade.

**Figure 4.** Microstructure of press hardened steels: (a) PHS1500, (b) PHS1000.

**Figure 5.** Hole punching and hole expansion procedure followed in this work according to ISO16630 [19].

**Figure 6.** Double Edge-Notched specimen (DENT) indicating the fracture and plastic zone.

**Figure 7.** HER values of the investigated steels, together with reported results for other AHSS [6].

**Figure 8.** First crack extension in the hole edge of CP1000 and DP1000 steels (orange arrows).

**Figure 9.** Strain analysis on DP1000 and PHS1500. At maximum load the ligament area is fully yielded. DIC images show in red the material area over the yield stress.

**Figure 10.**  $w_e$  values obtained from the investigated steels

**Figure 11.** Correlation between HER and mechanical properties of AHSS and new generation steels, together with published data for mild steel and AHSS [6].

**Figure 12.** Correlation between HER and EWF of AHSS and new generation steels.