

Electronic Supplementary Information (ESI)

## Hybrid Structure of Cobalt Monoxide Nanowire @ Nickel Hydroxidenitrate Nanoflake Aligned on Nickel Foam for High-Rate Supercapacitor


Cao Guan<sup>a,c</sup>, Jinping Liu<sup>a</sup>, Chuanwei Cheng<sup>a</sup>, Hongxing Li<sup>a</sup>, Xianglin Li<sup>a</sup>, Weiwei Zhou<sup>a</sup>, Hua Zhang<sup>b</sup>, and Hongjin Fan<sup>\*a,c</sup>

<sup>a</sup>Division of Physics and Applied Physics, School of Physical and Mathematical Sciences, Nanyang Technological University, 21 Nanyang Link, 637371 Singapore. Email: [fanhj@ntu.edu.sg](mailto:fanhj@ntu.edu.sg)

<sup>b</sup>School of Materials Science and Engineering, Nanyang Technological University, 639798 Singapore.

<sup>c</sup>Energy Research Institute @ NTU (ERIAN), 50 Nanyang Drive, 637553 Singapore.

### I. CV and charge-discharge testing of the nickel foam



**Fig. S1.** A nickel foam ( $330 \text{ g/m}^2$ ) was tested independently (a) at a scan rate of  $10 \text{ mV/s}$  in a CV testing; (b) at a charge-discharge rate of  $5 \text{ mA/cm}^2$ .

#### Calculation:

As both nickel foam substrate and active materials contribute to the charge-discharge behavior of the electrode<sup>1</sup>, and they are under the same current, charge-discharge time and potential window, formula (1):  $C = It / m\Delta V$  can be converted to<sup>2</sup>:

$$It/\Delta V = C_s * m_s + C_a * m_a,$$

where  $C_s$ ,  $m_s$  is the capacitance and the mass of the nickel foam substrate,  $C_a$ ,  $m_a$  is the capacitance and the mass of the active materials.

For a typical charge-discharge process of the hybrid structure on nickel foam (for example, current density is  $5 \text{ mA/cm}^2$ ), the contribution of  $1 \text{ cm}^2$  nickel foam can be calculated independently from the above curve in Fig. S1b with formula (1),

$$\begin{aligned} C_s * m_s &= It/\Delta V = (5 \text{ mA/cm}^2 * 1 \text{ cm}^2) * 6.72 \text{ s} / 0.51 \text{ V} \\ &= \sim 66 \text{ mF} \end{aligned}$$

And according to Fig. 4c, under the same current density, the contribution of the hybrid structure on  $1 \text{ cm}^2$  nickel foam is,


$$\begin{aligned} C_a * m_a &= It' / \Delta V - C_s * m_s \\ &= (5 \text{ mA/cm}^2 * 1 \text{ cm}^2) * 251 \text{ s} / 0.51 \text{ V} - 66 \text{ mF} \\ &= 2395 \text{ mF}, \end{aligned}$$

$$(C_s * m_s) / (C_a * m_a) = 66 \text{ mF} / 2395 \text{ mF} = 2.89\%$$

Thus the **contribution of nickel foam in this case is 2.89% of the total capacity of the hybrid structure.**

## II. NiHON powder sample testing and specific capacitance calculation

For nickel hydroxidenitrate powder synthesis, 0.25 M Ni(NO<sub>3</sub>)<sub>2</sub> ethanol solution was first prepared, and then transferred to a Teflon-lined stainless steel autoclave to react at 130 °C for 3 h. After cooling down to room temperature, the green precipitation was washed with deionized water and dried at 60 °C to obtain the final sample.



**Fig. S2.** Powder sample of NiHON has been tested and showed a capacitance of ~1200 F/g at 10.5 A/g.

If we could simply add CoO (307 F/g at 4.55 A/g) and NiHON with the same mass ratio to that in the hybrid structure (CoO: ~2.2 mg, NiHON: ~0.8 mg), the capacitance of the mixture ( $C$ ) would be calculated as,

$$C \cdot m = It / \Delta V = C_c \cdot m_c + C_n \cdot m_n,$$

where  $m = m_c + m_n$  ( $m$ ,  $m_c$  and  $m_n$  is the mass of the mixture, CoO and NiHON, respectively), and  $C_c$ ,  $C_n$  is the capacitance of CoO and NiHON, respectively.

At the current density of 13.33 A/g, even if CoO and NiHON could maintain a same capacitance (as that at lower current density) of 307 F/g and 1200 F/g, then from the above formula,

$$C \cdot 3\text{mg} = 307\text{F/g} \cdot 2.2\text{mg} + 1200\text{F/g} \cdot 0.8\text{mg}$$

$$C = \sim 545 \text{ F/g.}$$

The result is still poorer than the data we get from the hybrid structure, which shows a capacitance of 671.3 F/g at the current density of 13.33 A/g.

### References:

1. W. Xing, S. Z. Qiao, X. Z. Wu, X. L. Gao, J. Zhou, S. P. Zhuo, S. B. Hartono, D. H. Jurcakova, J. Power Sources., 2011.196(8), 4123.
2. X. Y. Lang, A. Hirata, T. Fujita and M. W. Chen, *Nat. Nanotechnol.*, 2011, 6, 232.