

 Open access • Journal Article • DOI:10.1007/S11663-998-0131-X

## Kinetics of carbochlorination of chromium (III) oxide — [Source link](#)

Ndue Kanari, I. Gaballah, B. R. Reddy

**Institutions:** Centre national de la recherche scientifique

**Published on:** 01 Aug 1998 - Metallurgical and Materials Transactions B-process Metallurgy and Materials Processing Science (Springer-Verlag)

**Topics:** Reaction rate, Order of reaction, Reaction mechanism, Chemical reaction and Chromium(III) oxide

Related papers:

- [Kinetics of Chlorination and Carbochlorination of Molybdenum Trioxide](#)
- [Kinetics of chlorination and oxychlorination of chromium \(III\) oxide](#)
- [Chlorination and carbochlorination of magnesium oxide](#)
- [Kinetics of chlorination and carbochlorination of pure tantalum and niobium pentoxides](#)
- [Kinetics of chlorination and carbochlorination of lead sulfate](#)

Share this paper:    

View more about this paper here: <https://typeset.io/papers/kinetics-of-carbochlorination-of-chromium-iii-oxide-158vwp687x>



**HAL**  
open science

## Kinetics of carbochlorination of chromium (III) oxide

Ndue Kanari, B.R. Reddy,, I. Gaballah

► **To cite this version:**

Ndue Kanari, B.R. Reddy,, I. Gaballah. Kinetics of carbochlorination of chromium (III) oxide. Metallurgical and Materials Transactions B, Springer Verlag, 1998, 29 (4), pp. 729-737. 10.1007/s11663-998-0131-x . hal-01508122

**HAL Id: hal-01508122**

**<https://hal.univ-lorraine.fr/hal-01508122>**

Submitted on 5 May 2017

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## **Kinetics of Carbochlorination of Chromium (III) Oxide**

**N. KANARI, B. R. REDDY<sup>a</sup> and I. GABALLAH.**

Mineral Processing and Environmental Engineering team, LEM<sup>b</sup>

Associated to CNRS<sup>c</sup> URA 235, ENSG<sup>d</sup>, INPL<sup>e</sup>, BP 40, 54501 Vandœuvre, France.

Kinetics of the carbochlorination of  $\text{Cr}_2\text{O}_3$  has been studied with  $\text{Cl}_2+\text{CO}$  gas mixtures between 500 °C to 900 °C using thermogravimetric analysis. The apparent activation energy is about 100 kJ/mol. Mathematical fitting of the experimental data suggests that the shrinking sphere model is the most adequate to describe the carbochlorination mechanism of chromium oxide and that is controlled by the chemical reaction.

In the temperature range of 550 °C to 800 °C, the reaction order is about 1.34 and is independent of temperature. Changing the  $\text{Cl}_2+\text{CO}$  content from 15 pct to 100 pct increase the reaction rate and does not affect the reaction mechanism. Similarly, changing the ratio of  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  from 0.125 to 0.857 do not modify the carbochlorination mechanism of  $\text{Cr}_2\text{O}_3$ . In these conditions, the reaction rate passes through a maximum when using a chlorinating gas mixture having a  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  ratio of about 0.5.

---

a. Regional Research Laboratory, Council of Scientific and Industrial Research, Bhubaneswar, 751013, Orissa, India  
b. Laboratoire Environnement et Minéralurgie, rue du Doyen M. Roubault, BP 40, 54501 Vandœuvre Cedex, France  
c. Centre National de la Recherche Scientifique, 3 rue Michel-Ange, 75794 Paris Cedex, France.  
d. Ecole National Supérieure de Géologie, rue du Doyen M. Roubault, BP 40, 54501 Vandœuvre Cedex, France.  
e. Institut National Polytechnique de Lorraine, 2 rue de la Forêt de Haye, 54501 Vandœuvre Cedex, France.

## I. INTRODUCTION

More than 75 pct of the world chromium consumption is used for the production of the ferro-chromium alloys [1]. About 25 pct is used for chemical, refractory and foundry applications. Chromium oxide and its compounds are utilized mainly as pigment, catalyst and as a raw material for the synthesis of chemicals used in the tanning, textile coloring, ...

A survey of literature concerning the chromium oxide and related materials indicate that most of the research work relates to the conversion of oxide to chlorides/or oxychlorides depending on the oxygen partial pressure in Cr-Cl-O system. Kinetics information concerning carbochlorination of  $\text{Cr}_2\text{O}_3$  is limited.

Saeki et al. [2] investigated chlorination of  $\text{Cr}_2\text{O}_3$  by  $\text{Cl}_2$  using samples obtained by heating a hydrated chromium oxide either at 440 °C or 1000 °C. These solids were chlorinated with chlorine to  $\text{CrO}_2\text{Cl}_2$  at 500 °C and 590 °C, respectively. These authors also investigated the chlorination of the same samples of  $\text{Cr}_2\text{O}_3$  by  $\text{Cl}_2+\text{C}$  mixture. The carbochlorination of these solids to  $\text{CrCl}_3$  start at 200 °C and 225 °C, respectively. The conversion extents of  $\text{Cr}_2\text{O}_3$  were 38 and 98 pct at 600 °C and 850 °C, respectively.

Hussein et al. [3] reported the chlorination of pure FeO, MgO,  $\text{Fe}_2\text{O}_3$ ,  $\text{Cr}_2\text{O}_3$  and  $\text{Al}_2\text{O}_3$ , their mixture and synthetically prepared compounds having spinel general formula  $\text{Me}^{2+}\text{Me}_2^{3+}\text{O}_4$ . They concluded that chlorination can be achieved in the presence of carbon for all the oxides. They emphasized that for a reaction time of one hour, temperatures higher than 800 °C, a chlorine flow rate of about 3 L/g/h and three times the stoichiometric amount of carbon are necessary for the chlorination of the above mentioned oxides. However, without carbon the reaction is very slow and proceeds with the formation of oxychlorides. Morozov and Fefelova [4] in their study on chlorination of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2$  in the temperature range of 700 °C to 1000 °C reported the formation of  $\text{Cr}^{+2}$ ,  $\text{Cr}^{+3}$  and  $\text{Cr}^{+4}$  chlorides and the non existence of oxychlorides in this temperature range.

Sano and Belton [5] investigated the chlorination of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2\text{-O}_2\text{-Ar}$  atmosphere using transpiration technique in the temperature range of 627 °C to 977 °C. They observed that the reaction product is gaseous  $\text{CrO}_2\text{Cl}_2$ . Maximum reaction rate was obtained for a  $\text{Cl}_2/\text{O}_2$  molar ratio equal to 4. The formation of chromium oxychloride had been confirmed by Jacobson

et al. [6] using the mass spectrometric observation of chlorinated products issued from the oxychlorination of  $\text{Cr}_2\text{O}_3$  - forming alloys. On the other hand, Kuffa et al. [7] confirmed the formation of  $\text{CrO}_2\text{Cl}_2$  during the oxychlorination of  $\text{Cr}_2\text{O}_3$  briquettes using thermogravimetric analysis 'TGA'.

This paper is a part of a research program concerning the chlorination kinetics of refractory metals oxides such as  $\text{V}_2\text{O}_5$  [8],  $\text{MoO}_3$  [9],  $\text{Nb}_2\text{O}_5$  and  $\text{Ta}_2\text{O}_5$ [10] as well as eventual application to the extraction of these metals from spent catalysts [11] or tin slag [12]. It deals with the study of the carbochlorination kinetics' of chromium (III) oxide with  $\text{Cl}_2+\text{CO}$  and  $\text{Cl}_2+\text{CO}+\text{N}_2$  gas mixtures.

## II. EXPERIMENTAL

### A. Raw Materials

The sample used in this study is  $\text{Cr}_2\text{O}_3$  powder supplied by LABORATOIRES STANDA having a purity higher than 99 pct. Spectra of EPMA - SEM (electron probe microanalysis of the scanning electron microscope) and that of XRD (X-rays diffraction) of the sample indicate only the presence of  $\text{Cr}_2\text{O}_3$  phase (Fig. 1). The specific surface area of the sample was about  $3.8 \text{ m}^2/\text{g}$ . The gases ( $\text{Cl}_2$ ,  $\text{CO}$ ,  $\text{N}_2$ ) used were of high pure quality. Chemicals employed in this study were analytical grade.

### B. Equipment



Chlorination experiments were carried out using TGA including the CAHN D100 microbalance with a direct data acquisition described previously [8]. The XRD was done with a PHILIPS diffractometer equipped with a Co or Cu anti-cathode and a monochromator. The scanning electron microscope used in this study was a CAMBRIDGE STEREO - SCAN 250 equipped with a microprobe PGT-III that permits a qualitative or a semi-qualitative elementary analysis of elements having an atomic number higher than 5. Specific surface area measurements were done using the analyzer Beta 4201 of Beta Scientific Corporation, Albertson, New York.

### C. Experimental procedure

A sample of about 40 mg placed in a boat was introduced into the furnace. The furnace heating rate was maintained at about 7 °C/min for non-isothermal tests. In this case, the sample was heated directly in the chlorinating gas mixture. For isothermal experiments, the sample was heated to the desired temperatures under nitrogen atmosphere. As soon as the furnace attains the experimental temperature, N<sub>2</sub> flow was replaced by the chlorinating gas mixture and maintained during the reaction time. The exhaust gases were purified using NaOH solution before their release to the atmosphere.

## III. THERMODYNAMIC STUDY

The possible carbochlorination reactions and the corresponding metal chlorides that are generated during the reaction of Cr<sub>2</sub>O<sub>3</sub> with Cl<sub>2</sub>+CO gas mixtures are as follow.



The standard Gibbs energy changes of the reactions 1 to 3 as a function of temperature [13] are given in Figure 2. It can be seen that the carbochlorination reactions of chromium oxide are thermodynamically feasible in the explored temperature range. CrCl<sub>2</sub> and CrCl<sub>3</sub> are the probable reaction products at temperatures lower and higher than 650 °C, respectively. The formation of CrCl<sub>4</sub> is the least favored from the thermodynamic point of view.

Figure 3 shows the phase stability diagrams of Cr-O-Cl system at 600 °C and 800 °C. Based on the gases purity, the estimated P<sub>Cl<sub>2</sub></sub> and P<sub>O<sub>2</sub></sub> of the gas mixtures used in this study for these temperatures are indicated by a black and white circles, respectively. This figure indicates that the carbochlorination of Cr<sub>2</sub>O<sub>3</sub>, in our experimental conditions, will only produce CrCl<sub>3</sub>.

## IV. RESULTS AND DISCUSSION

### A. Non-isothermal chlorination of $\text{Cr}_2\text{O}_3$

To define the reactivity of  $\text{Cr}_2\text{O}_3$  with respect to the  $\text{Cl}_2+\text{CO}$  gas mixture, carbochlorination of chromium oxide under continuous rising temperature conditions was carried out up to 900 °C. The total gas flow rate was maintained at 80 L/h. The pct weight loss observed as a function of temperature is shown in Figure 4. It can be seen that the reaction of  $\text{Cl}_2+\text{CO}$  with  $\text{Cr}_2\text{O}_3$  starts at about 500 °C and is complete at about 900 °C. This figure also gives the pct weight loss of  $\text{CrCl}_3$  treated in the same conditions. Clearly, the rate of  $\text{CrCl}_3$  volatilization is higher than that of its formation during the carbochlorination of  $\text{Cr}_2\text{O}_3$  in the explored temperature range. In such case, the measurement of pct weight loss as a function of time will probably represent the reaction rate of the  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$  gas mixture.

### B. Kinetics of the carbochlorination of $\text{Cr}_2\text{O}_3$

#### 1. Effect of gas flow rate

The effect of  $\text{Cl}_2+\text{CO}$  gas velocity on the chlorination reaction rate was studied to determine the conditions where gas starvation and mass transfer limitations could be minimized. As the carbochlorination of chromium oxide is almost complete at 900 °C, tests to define the critical gas flow rate is determined at this temperature (Fig. 4). Figure 5 summarizes the results of reaction rate evolution as a function of total gas flow rate ranging from 7 - 100 cm/ min that corresponds to 8 to 120 L/ h. The effect of gas velocity on reaction rate can be considered negligible beyond 50 cm/ min. A gas flow rate of 80 L/ h eliminate the gas starvation and minimize the mass transfer effects [14].

#### 2. Effect of temperature

A series of isothermal tests was carried out at different temperatures ranging from 500 °C to 900 °C using  $\text{Cl}_2+\text{CO}$  ( $\text{Cl}_2/\text{CO} = 1$ ) and  $\text{Cl}_2+\text{CO}+\text{N}_2$  gas mixtures ( $\text{N}_2/\text{Cl}_2/\text{CO} = 1$ ) at a constant total flow rate of 80 L/ h. Figures 6(a) and 6(b) show the pct weight loss *versus* time curves obtained by the carbochlorination of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$ .

At 500 °C and a reaction time of 4 hours, the weight loss is less than 15 pct. The reaction rate increases steadily with the temperature rise between 500 °C and 900 °C. It reaches 90 pct at 900 °C for a reaction time of about 6 min. The nature of the TG curves for the chlorination of Cr<sub>2</sub>O<sub>3</sub> obtained by using Cl<sub>2</sub>+CO+N<sub>2</sub> or Cl<sub>2</sub>+CO gas mixtures is similar. The only difference is lower reaction rates, for gas mixtures containing N<sub>2</sub>, than those obtained with Cl<sub>2</sub>+CO gas mixture for a given temperature and reaction time. For example, the pct weight loss with Cl<sub>2</sub>+CO at 900 °C and a reaction time of 4 minutes was 66 pct while that for Cl<sub>2</sub>+CO+N<sub>2</sub> gas was 46 pct.

The reaction rate was calculated using the initial linear stage for a reaction extent 'X' (0.05 < X < 0.4). The Arrhenius plot is given in Figure 7. The apparent activation energy is about 100 kJ/mol. Such a value tends to indicate that the carbochlorination mechanism of Cr<sub>2</sub>O<sub>3</sub> powder is controlled by the chemical reaction in the explored temperature range.

To examine this hypothesis, the mathematical formulation of the experimental data was attempted using the following equations [14].

$$1 - (1 - X)^{1/F_p} = kt \quad [4]$$

$$X = kt \quad (\text{For } F_p = 1) \quad [5]$$

$$1 - (1 - X)^{1/2} = kt \quad (\text{For } F_p = 2) \quad [6]$$

$$1 - (1 - X)^{1/3} = kt \quad (\text{For } F_p = 3) \quad [7]$$

where k = constant,

t = chlorination time,

X = extent of reaction (ratio of weight of the reacted fraction to initial weight),

F<sub>p</sub> = particle shape factor (1 for infinite slabs, 2 for long cylinders and 3 for spheres).

Equation 4 is considered to describe a reaction controlled by the chemical reaction in the case of shrinking nonporous particles (with or without a solid porous product) and porous particles with unchanged overall sizes. It also applies for a mechanism affected by pore diffusion in the case of complete gasification of porous solids.

Figure 8 shows the mathematical fitting (using equations 5 to 10) of experimental data of carbochlorination of Cr<sub>2</sub>O<sub>3</sub> with Cl<sub>2</sub>+CO at 700 °C for 0 ≤ X ≤ 0.8. The best mathematical fitting for these experimental data was obtained using equation 7 with a correlation coefficient equal to 1.



Figure 9 shows the mathematical fitting of the experimental data obtained during the carbochlorination of chromium oxide between 550 °C and 900 °C by using equation 7. The average correlation coefficient is 0.998. This supports the hypothesis that the carbochlorination reaction of Cr<sub>2</sub>O<sub>3</sub> particles is controlled by the chemical reaction according to the shrinking sphere model described by equation 7. The similar values of activation energy are reported for the carbochlorination of V<sub>2</sub>O<sub>5</sub><sup>[8]</sup> and Ta<sub>2</sub>O<sub>5</sub><sup>[10]</sup>.

### *3. Comparison between the rate of CrCl<sub>3</sub> formation and volatilization during the isothermal carbochlorination of Cr<sub>2</sub>O<sub>3</sub>*

Figure 10 groups the evolution of the carbochlorination reaction rate of Cr<sub>2</sub>O<sub>3</sub> and that of CrCl<sub>3</sub> volatilization as a function of temperature. It can be noticed that the volatilization rate of CrCl<sub>3</sub> is systematically higher than that of Cr<sub>2</sub>O<sub>3</sub> chlorination in the explored temperature range. This observation agrees well with the results obtained in non-isothermal run (Fig. 4). XRD of the reaction product indicates the presence of chromium trichloride for the whole investigated temperature range. Chromium dichloride had not been detected in reaction products obtained at temperature lower than 650 °C. This is probably due to the presence of chlorine excess in the gas mixture.

### *4. Effect of Cl<sub>2</sub>/(Cl<sub>2</sub>+CO) molar ratio*

The effect of this molar ratio on the reaction rate was studied at 800 °C. The chlorine content in the Cl<sub>2</sub>+CO gas mixture was varied from 0 to 100 pct that corresponds to a Cl<sub>2</sub>/(Cl<sub>2</sub>+CO) ratio of 0 to 1, while the total gas flow rate was kept constant at 80 L/h. Figure 11 groups the evolution of the pct weight loss as a function of time. These curves clearly indicate that the reaction extent is maximum when using a chlorine concentration of about 50 pct in the Cl<sub>2</sub>+CO gas mixture. Increasing or decreasing the chlorine content beyond this value leads to lower reaction extent.

Figure 12 gives the evolution of initial reaction rate ( $0.05 \leq X \leq 0.40$ ) as a function of Cl<sub>2</sub>/(Cl<sub>2</sub>+CO) molar ratio. The reaction rate of Cr<sub>2</sub>O<sub>3</sub> with 100 pct CO is almost equal to zero and rises with increasing the chlorine content in the gas mixture. It reaches a maximum value for

a  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  molar ratio equal to about 0.5. Beyond this ratio, the reaction extent decreases as the chlorine content increases and reaches a minimum value with 100 pct  $\text{Cl}_2$ . The observed maximum reaction rate at  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  molar ratio of 0.5 clearly suggests that the carbochlorination of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$  gas mixture follows equation 2. The XRD and SEM spectra of condensate, obtained from a boat experiment under similar conditions, confirm the presence of  $\text{CrCl}_3$ .

To check the eventual effect of the composition of the chlorinating gas mixture on the reaction mechanism, mathematical formulation of the experimental data was examined. Figure 13 shows the transforms of data of Figure 11 using equation 7. The plots are straight lines with a correlation coefficient close to unity. This observation seems to indicate that the mechanism of carbochlorination of  $\text{Cr}_2\text{O}_3$  remains the same for chlorine contents varied from 12.5 to 85.7 pct in the gas mixture.

#### *5. Effect of $\text{Cl}_2+\text{CO}$ partial pressure*

To determine the effect of diluting the carbochlorinating gas mixture with nitrogen on the reaction rate, a series of experiments was performed at 550 °C, 650 °C and 800 °C with gas mixture having a  $\text{Cl}_2+\text{CO}$  content that varied from 15 pct to 100 pct. During these experiments, the  $\text{Cl}_2/\text{CO}$  molar ratio was kept constant and equal to 1. Figure 14 summarizes the pct weight loss as a function of reaction time for different contents of reactive gases at 550 °C and 800 °C. The results indicate that the reaction rate increases with rise of the partial pressure of  $\text{Cl}_2+\text{CO}$  at any given time and temperature.

Figure 15 gives the evolution of the natural logarithm of the initial reaction rate ( $X = 0.05$  to  $0.40$ ) as a function of the partial pressure of  $\text{Cl}_2+\text{CO}$  at different temperatures. The apparent reaction order ' $n_T$ ' is about 1.34 and is independent of the reaction temperatures between 550 °C and 800 °C. It seems that the carbochlorination mechanism is again independent of the partial pressure of reactive gases in the chlorinating gas mixture. To check this possibility, mathematical formulation of the experimental data was made using equations 5 to 10.

Best results are grouped in Figure 16. The data matches equation 7 well with an average correlation coefficient of 0.999. This confirms that the carbochlorination mechanism of  $\text{Cr}_2\text{O}_3$  follows a chemical controlled reaction.

## V. CONCLUSIONS

The thermodynamic study suggests that the reaction products of the carbochlorination of  $\text{Cr}_2\text{O}_3$  will be  $\text{CrCl}_2$  and  $\text{CrCl}_3$  at temperatures lower and higher than 650 °C. Chromium (III) oxide starts to react with  $\text{Cl}_2+\text{CO}$  gas mixture at about 500 °C generating chromium trichloride. In our experimental conditions, chromium dichloride had not been detected in the reaction product.

During the carbochlorination of  $\text{Cr}_2\text{O}_3$ , the rate of formation of chromium trichloride was systematically lower than its rate of volatilization between 500 °C and 900 °C. Consequently, the experimental data obtained from the TGA can be used for the kinetic study.

The apparent activation energy of the carbochlorination of  $\text{Cr}_2\text{O}_3$  is about 100 kJ/ mole. This value is near to that obtained for the carbochlorination of  $\text{V}_2\text{O}_5$ <sup>[8]</sup> and  $\text{Ta}_2\text{O}_5$ <sup>[10]</sup>. This suggests that the carbochlorination rate of chromium oxide is controlled by the chemical reaction. Mathematical fitting of experimental data indicates that the shrinking sphere model is the most adequate to describe the reaction mechanism. The overall reaction proceeds through the formation of chromium trichloride.

Increasing the  $\text{Cl}_2+\text{CO}$  content in the chlorinating gas mixture from 15 pct to 100 pct does not affect the carbochlorination mechanism of  $\text{Cr}_2\text{O}_3$ . Same conclusion is obtained when varying the  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  ratio from 0.125 to 0.857.

Maximum reaction rate is obtained with a carbochlorinating gas mixture having a  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  ratio of 0.5. The reaction order is about 1.34 with respect to the  $\text{Cl}_2+\text{CO}$  content in the gas mixture. It is independent of temperature between 550 °C and 800 °C.

Results obtained in this study had been extrapolated for upgrading of lean chromite concentrate. This material is essentially composed of spinel having the general formula :  $[(Fe^{2+}, Mg)(Cr, Al, Fe^{3+})_2O_4]$ . Carbochlorination at low temperatures of the chromite concentrate allows the selective removal of iron leading to higher chromium content and Cr/Fe ratio. Such treatment can not be achieved by classical mineral processing methods.

### **ACKNOWLEDGMENTS**

This work was performed in the frame of contract N° BRE2-CT92-0173 thanks to the financial support of the European Union ( DG-XII ). The authors thank Dr. H. L. Schmidt for discussion, suggestion and help. One of the authors (BRR) thanks the CSIR and CNRS for supporting his stay under exchange program India-France.

They also would like to thank Drs. J. C. Mugica (INASMET, San Sebastian, Spain) and M. Coelho (INETI, Lisbon, Portugal) for providing samples and technical discussions. Authors are indebted to E. Allain, A. Bonazebi, M. Djona, S. Ivanaj, N. Menad and N. Mirghaffari for discussions and help on different subjects and to Mrs. C. Tanchel for technical and administrative support.

## REFERENCES

1. Anonymous : Matières premières minérales, Ministère de l'Industrie, des Postes et Télécommunications et du Commerce Extérieur (France), 1995, pp. 59-63.
2. Y. Saeki, R. Matsuzaki and H. Morita : Kogyo Kagaku Zasshi, 1971, Vol. 74 (3), pp. 344-348.
3. M. K. Hussein, H. Winterhager, R. Kammel and K. El-Barawi : Trans.-Inst. Min. Metall., Sect. C, 1974, Vol. 8, pp. C154-C160.
4. I. S. Morozov and G. F. Fefelova : Zh. Prikl. Khim. (Leningrad), 1971, Vol. 44 (5), pp. 1161-1163.
5. N. Sano and G. R. Belton : Met. Trans., 1974, Vol. 5 (10), pp. 2151-2154.
6. N. S. Jacobson, M. J. McNallan and Y. Y. Lee : Metall. Trans. A, 1989, Vol. 20A, pp. 1566-1568.
7. T. Kuffa, N. Ponesky and M. Skrobjan : Thermochemica Acta, 1985, Vol. 92, pp. 201-204.
8. I. Gaballah, M. Djona and E. Allain : Metall Mater. Trans. B, 1995, Vol. 26B, pp. 711-718.
9. M. Djona, E. Allain and I. Gaballah : Metall Mater. Trans. B, 1995, Vol. 26B, pp. 703-710.
10. E. Allain, M. Djona and I. Gaballah : Metall Mater. Trans. B, *in press*.
11. E. Allain, M. Djona and I. Gaballah : Metall Mater. Trans. B, *in press*.
12. I. Gaballah and M. Djona : Metall Mater. Trans. B, Vol. 26 B, 1995, pp. 41-50.
13. A. Roine : In Outokumpu HSC Chemistry for Windows, Version 2.0, Outokumpu Research, Pori, Finland, May 1994.
14. J. Szekely, J. W. Evans and H. Y. Sohn : Gas-Solid Reactions, Academic Press, New York, NY, 1976, pp. 68-70, 73-88, 109-131 and 232-235.

## FIGURE CAPTIONS

- Figure 1 : Results of (a) SEM and (b) XRD analysis of  $\text{Cr}_2\text{O}_3$  sample.
- Figure 2 : Standard free energy change of  $\text{Cr}_2\text{O}_3$  carbochlorination reactions.
- Figure 3 : Phase stability diagram of Cr-O-Cl system at 600 °C and 800 °C.
- Figure 4 : Thermogravimetric analysis of  $\text{Cr}_2\text{O}_3$  in  $\text{Cl}_2+\text{CO}$  gas mixture.
- Figure 5 : Effect of gas flow rate on the chlorination rate of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$ .
- Figure 6 : Comparison of rate of  $\text{CrCl}_3$  volatilization and  $\text{Cr}_2\text{O}_3$  reaction with  $\text{Cl}_2+\text{CO}$ .
- Figure 7 : Isotherms of carbochlorination of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$  gas mixture for (a)  $T \leq 700$  °C and (b)  $T \geq 725$  °C.
- Figure 8 : Arrhenius plot of carbochlorination of  $\text{Cr}_2\text{O}_3$  by  $\text{Cl}_2+\text{CO}$ .
- Figure 9 : Mathematical fitting of carbochlorination data of  $\text{Cr}_2\text{O}_3$  at 700 °C for different model equations.
- Figure 10 : Mathematical fitting of carbochlorination data of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$  for (a)  $T \leq 700$  °C and (b)  $T \geq 725$  °C using equation 7.
- Figure 11 : Isotherms of carbochlorination of  $\text{Cr}_2\text{O}_3$  at 800 °C with  $\text{Cl}_2+\text{CO}$  for (a)  $12.5 \leq \text{Cl}_2 \leq 50.0$  pct and (b)  $55.0 \leq \text{Cl}_2 \leq 100.0$  pct.
- Figure 12 : Effect of  $\text{Cl}_2/(\text{Cl}_2+\text{CO})$  ratio on the  $\text{Cr}_2\text{O}_3$  carbochlorination rate at 800 °C.
- Figure 13 : Mathematical fitting of experimental data of Figure 11.
- Figure 14 : Effect of  $\text{Cl}_2+\text{CO}$  ( $\text{Cl}_2/\text{CO} = 1$ ) partial pressure on  $\text{Cr}_2\text{O}_3$  carbochlorination at (a) 550 °C and (b) 800 °C.
- Figure 15 : Apparent reaction order with respect to  $\text{Cl}_2+\text{CO}$ .
- Figure 16 : Mathematical fitting of the carbochlorination data for different partial pressures of  $\text{Cl}_2+\text{CO}$  at (a) 650 and (b) 800 °C using equation [7].




Fig. 1- Results of (a) SEM and (b) XRD analysis of  $\text{Cr}_2\text{O}_3$  sample.





Fig. 2 - Standard free energy change of  $\text{Cr}_2\text{O}_3$  carbochlorination reactions.



Estimated  $P_{\text{Cl}_2}$  and  $P_{\text{O}_2}$  at 600 (●) and 800 °C (○)

Fig. 3 - Phase stability diagram of Cr-O-Cl system at 600 °C and 800 °C.




Fig. 4 - Thermogravimetric analysis of Cr<sub>2</sub>O<sub>3</sub> in Cl<sub>2</sub>+CO gas mixture.






Fig. 5- Effect of gas flow rate on the chlorination rate of Cr<sub>2</sub>O<sub>3</sub> with Cl<sub>2</sub>+CO.




Fig. 6- Comparison of rate of CrCl<sub>3</sub> volatilization and Cr<sub>2</sub>O<sub>3</sub> reaction with Cl<sub>2</sub>+CO.




Fig. 7- Isotherms of carbochlorination of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$  for (a)  $T \leq 700$  °C and (b)  $T \geq 725$  °C.




Fig. 8- Arrhenius plot of carbochlorination of  $\text{Cr}_2\text{O}_3$  by  $\text{Cl}_2+\text{CO}$ .





Fig. 9- Mathematical fitting of carbochlorination data of  $\text{Cr}_2\text{O}_3$  at  $700\text{ }^\circ\text{C}$  for different model equations.





Fig. 10- Mathematical fitting of carbochlorination data of  $\text{Cr}_2\text{O}_3$  with  $\text{Cl}_2+\text{CO}$  for (a)  $T \leq 700\text{ }^\circ\text{C}$  and (b)  $T \geq 725\text{ }^\circ\text{C}$  using equation 7.




Fig. 11- Isotherms of carbochlorination of Cr<sub>2</sub>O<sub>3</sub> at 800 °C with Cl<sub>2</sub>+CO for (a) 12.5 ≤ Cl<sub>2</sub> ≤ 50.0 pct and (b) 55.0 ≤ Cl<sub>2</sub> ≤ 100.0 pct.




Fig. 12- Effect of Cl<sub>2</sub>/(Cl<sub>2</sub>+CO) ratio on the Cr<sub>2</sub>O<sub>3</sub> carbochlorination rate at 800 °C.





Fig. 13- Mathematical fitting of experimental data of Figure 11.





Fig. 14- Effect of  $\text{Cl}_2+\text{CO}$  ( $\text{Cl}_2/\text{CO} = 1$ ) partial pressure on  $\text{Cr}_2\text{O}_3$  carbochlorination at (a)  $550^\circ\text{C}$  and (b)  $800^\circ\text{C}$ .




Fig. 15- Apparent reaction order with respect to  $\text{Cl}_2+\text{CO}$ .




Fig. 16- Mathematical fitting of the carbochlorination data for different partial pressures of  $\text{Cl}_2+\text{CO}$  at (a) 650 and (b) 800 °C using equation [7].