

Journal section: Oral Surgery
 Publication Types: Research

doi:10.4317/medoral.17462
<http://dx.doi.org/doi:10.4317/medoral.17462>

Mechanical resistance of zirconium implant abutments: A review of the literature

Rocio Velázquez-Cayón ¹, Cristina Vaquero-Aguilar ², Daniel Torres-Lagares ³, Manuel Jiménez-Melendo ⁴, José-Luis Gutiérrez-Pérez ⁵

¹ Research. Faculty of Dentistry. University of Seville

² Research. Department of Physics. University of Seville

³ Professor. Faculty of Dentistry. University of Seville

⁴ Professor. Department of Physics. University of Seville

⁵ Head. University Hospital Virgen del Rocío, Oral and Maxillofacial Surgery Unit, Seville

Correspondence:

Facultad de Odontología
 Universidad de Sevilla
 C/ Avicena s/n - 41009 Sevilla
danieltl@us.es

Velázquez-Cayón R, Vaquero-Aguilar C, Torres-Lagares D, Jiménez-Melendo M, Gutiérrez-Pérez JL. Mechanical resistance of zirconium implant abutments: A review of the literature. Med Oral Patol Oral Cir Bucal. 2012 Mar 1;17 (2):e246-50.
<http://www.medicinaoral.com/medoralfree01/v17i2/medoralv17i2p246.pdf>

Received: 31/12/2010
 Accepted: 16/09/2011

Article Number: 17462 <http://www.medicinaoral.com/>
 © Medicina Oral S. L. C.I.F. B 96689336 - pISSN 1698-4447 - eISSN: 1698-6946
 eMail: medicina@medicinaoral.com
Indexed in:
 Science Citation Index Expanded
 Journal Citation Reports
 Index Medicus, MEDLINE, PubMed
 Scopus, Embase and Emcare
 Índice Médico Español

Abstract

The increase of aesthetic demands, together with the successful outcome of current implants, has renewed interest in the search for new materials with enough mechanical properties and better aesthetic qualities than the materials customarily used in implanto-prosthetic rehabilitation. Among these materials, zirconium has been used in different types of implants, including prosthetic abutments. The aim of the present review is to analyse current scientific evidence supporting the use of this material for the above mentioned purposes.

We carried out the review of the literature published in the last ten years (2000 through 2010) of in vitro trials of dynamic and static loading of zirconium abutments found in the databases of Medline and Cochrane using the key words zirconium abutment, fracture resistance, fracture strength, cyclic loading.

Although we have found a wide variability of values among the different studies, abutments show favourable clinical behaviour for the rehabilitation of single implants in the anterior area. Such variability may be explained by the difficulty to simulate daily mastication under in vitro conditions. The clinical evidence, as found in our study, does not recommend the use of implanto-prosthetic zirconium abutments in the molar area.

Key words: Zirconium abutment, zirconium implant abutment, zirconia abutment, fracture resistance, fracture strength, cyclic loading.

Introduction

Implantology has been one of the greatest odontological achievements in the last century. Once the stage when osteointegration was the only key to success has been overcome, the present challenge is to ensure both the functionality and the aesthetic value of the implant-supported prosthesis.

The advantages of using ceramic components in implantoprosthodontic rehabilitation can be summarized in the possibility to individualize the components, to take full advantage of their light transmission properties, excellent aesthetic qualities with colours resembling those of teeth and their great compatibility with preimplant soft tissues. Nevertheless, there are also disadvantages such as their lesser resistance to fatigue (1).

Nowadays most companies in the sector offer ceramic abutments which may be prefabricated or manufactured and can also be prepared in a dental laboratory either by a technician following the traditional method or with the assistance of computer-based designs. The materials chosen for that purpose are: highly pure alumina (Al₂O₃), TZP ceramics (stabilized tetragonal zirconia) or PSZ ceramics (partially stabilized zirconia). TZP ceramics show superior properties to alumina due to such microstructural differences as density, size of particles (smaller in the case of TZP) and their polymorphic mechanism against flaw propagation. The main reason for such superiority is the yttrium stabilization of the zirconia structure (2).

The production of large components of pure zirconium is not possible. The extensive volume of the transformation between the different stages of the zirconium may be an advantage due to the addition of cubic stabilizing oxides (the most common are yttrium oxide, magnesium and calcium oxide). These oxides can stabilize a relatively weak cubic structure below room temperature. On the other hand, if we add enough amount of stabilizing oxide, and the material is correctly processed, zirconium particles may be stored in a metastable tetragonal form at room temperature. All these materials are known as partially stabilized zirconium ceramics (PSZ). The transformation from the tetragonal to the monoclinic structure may serve to improve the mechanical resistance and fracture tenacity of PSZ ceramics. Used under stress in the area of a flaw, metastable tetragonal particles pass to a stable monoclinic structure, change which is known as martensitic transformation. The extension of the resulting volume is distributed around these particles close to the flaw thus compressing it and delaying its propagation until the stress is increased. This physical phenomenon ensures the reliability of this material for the production of implant-supported abutments (3).

Zirconium oxide, or zirconia, shows similar mechanical properties to metals and its colour resembles that of teeth. Partially yttrium-stabilized zirconia shows the best properties for the purposes under discussion. Zir-

conia was first used with medical purposes in 1969. Helmer and Driskell introduced it as a new material for orthopaedic uses in the Symposium on Use of Ceramics as Surgical Implants. They presented it as a substitute for titanium or alumina prostheses in hip replacement. The first zirconia abutment, Zirabut® (Wohwend Innovative, Zurich, Switzerland) was produced in 1997, although many more were added later (4).

The aim of the present review is to confirm scientific evidence in favour of the resistance of partially yttrium-stabilized zirconia abutments, commonly known simply as zirconia abutments, using dynamic and static loading trials.

Material and Methods

We carried out the review of the literature published during the last ten years (2000-2010) of in vitro trials of dynamic and static loading of zirconium abutments. In order to do so, we used the databases of Medline (Pubmed) and Cochrane. The key words used in the search were: zirconium abutment, zirconium implant abutment, zirconia abutment, fracture resistance, fracture strength, cyclic loading. First of all, we searched zirconium abutment OR zirconium implant abutment OR zirconia abutment and then we looked for fracture resistance OR fracture strength OR cyclic loading. Finally, we combined the keywords of both searches with the operator AND.

In order to complete the search, we carried out a manual examination in the following publications of the articles available on the subject published in the last ten years: Journal of Prosthetic Dentistry, Journal of Oral Rehabilitation, Quintessence International, Journal of Prosthodontics, International Journal of Oral Maxillofacial Implants, International Journal of Prosthodontics.

We examined all the studies including in vitro fracture strength at a constant speed and dynamic loading trials of zirconia abutments used as implantoprosthodontic abutment (with or without comparison with other type of material). We considered both studies in which the implantoprosthodontic system was completely rehabilitated and those in which it was not.

Results

We found 9 articles whose main characteristics are shown in (Table 1).

In one of the trials on zirconia abutments (5) (Wohwend Innovative, Switzerland) a computer controlled universal testing device was used and the load was applied at 30° from the axial axis of the implant-supported system. The implant-abutment system was torqued to 32 N cm. The crown failed in 40% of the cases, the fixing screw in 30% of cases and in the remaining 30% the abutment itself failed. If we leave aside the abutments in which the fixing screw failed, mean fracture-load value was 788.1 N with an interval of 619.5- 1365.6 N. If we consider all the abutments, mean value was 737.6 N.

Table 1. Mechanical trials on zirconium abutments. (NA: not available; CST: constant speed trial).

AUTHORS	TYPE OF ABUTMENT	MEAN FRACTURE FORCE	LOAD APPLICATION AXIS	TYPE OF TRIAL	TORQUE FORCE
Yildirim y cols. 2003 (5)	Wohlrwed Innovative	788 N	30°	CST	32 N.cm
Butz y cols. 2005 (6)	Pilar ZiReal	294 N ± 53 672 N (EVC)	130°	Ciclado (30 N, 1 Hz, 1x10 ⁶ cycles).	32 N.cm
Gehrke y cols. 2006 (8)	Pilar Cercon	403 N (10 ⁵ cycles) 269 N (8x10 ⁵ -5x10 ⁶ cycles)	30°	CST / Cicled (100-250 N, 15 Hz)	20 N.cm
Aramouni y cols. 2008 (7)	Pilar ZiReal	792.2 N ± 122.5	45°	CST	32 N.cm
Kerstein y Radke, 2008 (10)	AAZ / Procera AllZirkon	831 N (AAZ) 740 N (Procera)	40°	CST	NA
Adatia y cols. 2009 (9)	Y-TZP Ceramic Abutment	429 N ± 140	60°	CST	25 N.cm
Kim y cols. 2009 (11)	Procera AllZirkon	480.01N ± 174.46	30°	CST	35 N.cm
Mitsias y cols. 2010 (12)	Y-TZP Ceramic Abutment	690 N (EVC) 400 N (5x10 ⁵ cycles)	30°	CST / Cicled (400N)	NA
Northdurft y cols. 2010 (13)	ZirDesign	233.68 N ± 30.68	NA	CST	NA

Likewise, Butz and cols. (6) in their analysis of 16 abutments Zireal® (Biomet 3i Palm Beach Garden, Florida, US) fixed with gold screws (GoldTite®, Biomet 31 Palm Beach Garden, Florida, US) to 32 N cm and repaired with a Dentitan® crown (Krupp, Essen, Germany), obtained fracture load values within the range 240N-450N, with a mean value of 295 N; 25% of the implants failed as a consequence of abutment fracture, 13% due to fixing screw fracture and the remaining due to the detachment of the crown from the abutment. The same authors observed a fracture load between 180 N and 460 N with a mean value of 325 N, in the case of titanium abutments (GingiHue®, Biomet 3i, Palm Beach Garden, Florida, US) repaired with the same type of crown.

Aramouni and cols. (7) in a recent study on ZiReal® abutments (Biomet 3i, Palm Beach Garden, Florida, US) with porcelain crowns tried at a constant speed of 1mm/min found that the crown failed in 80% of the cases. Such studies show that crown detachment is one of the most common causes of endosseous implant failure due to translation and rotation movements involved in the

abutment-crown interface and the presence of the corresponding adhesive. Thus, applying successive coats of porcelain to cover the abutment seems an effective alternative to solve the problem.

Gehrke and cols. (8) in a report on naked zirconia abutments Cercon® Dentsply/Friadent (Mannheim, Germany) of 4.5 mm in diameter and 18mm in length found a survival rate of up to 106 cycles, 1 Hz at loads of 100 to 450 N. Fracture resistance of these cycled abutments decreased by 60% (up to 270 N) in comparison to non-fatigued abutments. The authors do not explain the origin of the failure.

Adatia and cols. (9) published in 2009 an article on Astra Tech zirconia abutments (Y-TZP®, Sweden) made with different axial reductions (0.5 and 1mm). The authors observed a mean fracture resistance of 429 N±140; 576±120 for the reduction group of 0.5mm and 547±139 in the 1mm group. They concluded that axial reduction does not affect fracture resistance of zirconia abutments in a significant way.

Kerstein and Radke (10) compared two types of zirco-

nia abutments: 29 Procera AllZirkon® abutments (Nobel Biocare, Sweden) and 29 AAZ® abutments (Atlantis®, AstraTech, Sweden) joined to regular platform titanium implants and torqued at 35 N cm. The whole piece was applied increasing loads (beginning at 0 N) until its fracture, with a 40° axis in relation to the axial plan. With a sweeping electron microscope, they analysed the origin of the fracture and its trajectory. Mean fracture force for AAZ® abutments was 831 N and 740 N for AllZirkon® samples.

In both instances, the fracture was due to small defects in their surface resulting from the fabrication process. AAZ® abutments had statistically lower probability of fracture at loads which resembled human mastication. However, both types of abutments failed at loads heavier than those occurring in daily mastication.

Kim and cols. (11) studied an alternative to zirconia abutments obtained through CAD/CAM technique. It is a metal-ceramic abutment containing a biocompatible metal alloy followed by an IPS e.max Press® injection. The authors carried out a trial on cemented crowns (IPS e.max Press®, Ivoclar Vivadent AG, Liechtenstein), and found a mean fracture force of 901.67 N ± 102.05 for the abutment under study and of 480.01 ± 174.46 for the control group, that is the zirconium abutments (Procera AllZirkon®, Nobel Biocare, Sweden).

An in vitro study carried out by Mitsias and cols. (12) compared a zirconium abutment (Astra Tech, Y-TZP®, Sweden) with a titanium abutment, both repaired with metallic crown. The titanium abutment showed significantly better behaviour, both at constant speed (1475 N ± 625 for Ti and 690 N ± 430 for Zr) and during cycled trial. As regards the reliability of both types of abutments, titanium abutments showed a 100% reliability rate whereas zirconium abutments lost reliability as the load was increased up to 400 N.

Northdurft and cols. (13) introduce in their study a new parameter, temperature. They performed a thermocycler trial (105 cycles between 5 and 55°C) of straight and angled zirconium abutments (ZirDesign®, Astra Tech, Sweden) and found a mean fracture force for the former of 233.68 N ± 30.68.

Discussion

The literature so far published on this subject allows us to observe the behaviour of zirconium abutments under loads and pressure resembling daily mastication. We commonly find a wide variability of fracture force values among similar studies. The difficulty to simulate daily mastication resides in the great amount of factors involved in such process which complicate the design of this kind of tests.

As a result, although the occlusal forces involved in mastication are well documented, there is no agreement on mean values. Leaving aside individual anatomic and

physiologic characteristics, maximum occlusal force is reported to be located in the first molar region, with values ranging from 180 to 850 N, decreasing to values between 95 and 250 N in the incisive region (14-16). Considering these data and the fact that, on average, zirconia abutments fracture occurs around 500-540 N, according to the reviewed articles, we could predict a satisfactory aesthetic behaviour of zirconium abutments but we should be cautious with their use in posterior regions.

As regards fatigue trials, a mean load of 50 N during 2.4x10⁵ cycles is considered to represent a year long of mastication. Such data are supported by the agreement observed between clinical and laboratory studies. In this sense, zirconium abutments still show some shortcomings, but we must bear in mind that the lesser the tension on repaired abutments the better their fatigue behaviour and the more satisfactory the results of in vitro studies on abutments without prosthetic crowns.

Current clinical tests show the favourable outcome of zirconium abutments in the incisive region, even in the canine-premolar region, in instances of unitary implant-supported rehabilitations (17-19). Nevertheless, neither our review nor others carried out by different authors, show adequate clinical evidence as regards the use of this type of abutments in the molar region (20).

References

1. Kohal RJ, Att W, Bächle M, Butz F. Ceramic abutments and ceramic oral implants. An update. *Periodontol* 2000. 2008;47:224-43.
2. Piconi C, Maccauro G. Zirconia as a ceramic biomaterial. *Biomaterials*. 1999;20:1-25.
3. Nakamura K, Kanno T, Milleding P, Ortengren U. Zirconia as a dental implant abutment material: a systematic review. *Int J Prosthodont*. 2010;23:299-309.
4. Brodbeck U. The ZiReal post: A new ceramic implant abutment. *J Esthet Restor Dent*. 2003;15:10-24
5. Yildirim M, Fischer H, Marx R, Edelhoff D. In vivo fracture resistance of implant-supported all-ceramic restorations. *J Prosthet Dent*. 2003;90:325-31.
6. Butz F, Heydecke G, Okutan M, Strub JR. Survival rate, fracture strength and failure mode of ceramic implant abutments after chewing simulation. *J Oral Rehabil*. 2005; 32:838-43.
7. Aramouni P, Zebouni E, Tashkandi E, Dib S, Salameh Z, Almas K. Fracture resistance and failure location of zirconium and metallic implant abutments. *J Contemp Dent Pract*. 2008;9:41-8.
8. Gehrke P, Dhom G, Brunner J, Wolf D, Degidi M, Piattelli A. Zirconium implant abutments: fracture strength and influence of cyclic loading on retaining-screw loosening. *Quintessence Int*. 2006;37:19-26.
9. Adatia ND, Bayne SC, Cooper LF, Thompson JY. Fracture resistance of yttria-stabilized zirconia dental implant abutments. *J Prosthodont*. 2009;18:17-22.
10. Kerstein RB, Radke J. A comparison of fabrication precision and mechanical reliability of 2 zirconia implant abutments. *Int J Oral Maxillofac Implants*. 2008;23:1029-36.
11. Kim S, Kim HI, Brewer JD, Monaco EA Jr. Comparison of fracture resistance of pressable metal ceramic custom implant abutments with CAD/CAM commercially fabricated zirconia implant abutments. *J Prosthet Dent*. 2009;101:226-30.
12. Mitsias ME, Silva NR, Pines M, Stappert C, Thompson VP. Reliability and fatigue damage modes of zirconia and titanium abutments. *Int J Prosthodont*. 2010;23:56-9.
13. Northdurft FP, Doppler KE, Erdelt KJ, Knauber AW, Pospeich PR. Influence of artificial aging on the load-bearing capability of straight or

- angulated zirconia abutments in implant/tooth-supported fixed partial dentures. *Int J Oral Maxillofac Implants.* 2010;25:991-8.
14. Haraldson T, Carlsson GE, Ingervall B. Functional state, bite force and postural muscle activity in patients with osseointegrated oral implant bridges. *Acta Odontol Scand.* 1979;37:195-206.
15. Paphangkorakit J, Osborn JW. The effect of pressure on a maximum incisal bite force in man. *Arch Oral Biol.* 1997;42:11-7.
16. De Boever JA, McCall WD Jr, Holden S, Ash MM Jr. Functional occlusal forces: an investigation by telemetry. *J Prosthet Dent.* 1978;40:326-33.
17. Canullo L. Clinical outcome study of customized zirconia abutments for single-implant restorations. *Int J Prosthodont.* 2007;20:489-93.
18. Glauser R, Sailer I, Wohlwend A, Studer S, Schibli M, Schärer P. Experimental zirconia abutments for implant-supported single-tooth restorations in esthetically demanding regions: 4-year results of a prospective clinical study. *Int J Prosthodont.* 2004;17:285-90.
19. Zembic A, Sailer I, Jung RE, Hammerle CH. Randomized-controlled clinical trial of customized zirconia and titanium implant abutments for single-tooth implants in canine and posterior regions: 3-year results. *Clin Oral Implants Res.* 2009;20:802-8.
20. Gomes AL, Montero J. Zirconia implant abutments: a review. *Med Oral Patol Oral Cir Bucal.* 2011;16:e50-5.