

Nanomaterials as Sorbents to Remove Heavy Metal Ions in Wastewater Treatment

Xiangtao Wang¹, Yifei Guo^{1*}, Li Yang¹, Meihua Han¹, Jing Zhao¹ and Xiaoliang Cheng²

¹Institute of Medicinal Plant Development, Chinese Academy of Medical Sciences, Peking Union Medical College, Beijing, P.R. China
²Mailstop 977-180A, Life Sciences Division, Lawrence Berkeley National Lab, Berkeley, USA

Abstract

Wastewater containing heavy metal ions is considered as the serious environmental problem in human society. Adsorption as the widely used method plays an important role in wastewater treatment, which is based on the physical interaction between metal ions and sorbents. With the development of nanotechnology, nanomaterials are used as the sorbents in wastewater treatment; several researches have proved that nanomaterials are the effective sorbents for the removal of heavy metal ions from wastewater due to their unique structure properties. Three kinds of nanomaterials are presented in this paper, including nanocarbon materials, nanometal particles, and polymer-supported nanoparticles. For heavy metal ions, all these nanomaterials show high selectivities and adsorption capacities. Besides, the adsorption isotherm model and adsorption kinetics are introduced briefly to understand the adsorption procedure.

Keywords: Nanomaterials; Adsorption; Heavy metal ions; Wastewater treatment

Introduction

Different contaminants are released to wastewater with the rapid industrialization of human society, including heavy metal ions, organics, bacteria, viruses, and so on, which are serious harmful to human health. Among all water contaminations, heavy metal ions, such as Pb²⁺, Cd²⁺, Zn²⁺, Ni²⁺ and Hg²⁺, have high toxic and non-biodegradable properties, can cause severe health problems in animals and human beings. It is well-known that chronic cadmium toxicity is the inducement of Japan Itai-Itai disease. The harmful effects of Cd also lead a number of acute and chronic disorders, such as renal damage, emphysema, hypertension, testicular atrophy, and skeletal malformation in fetus [1,2]. Wastewater from many industries, including chemical manufacturing, battery manufacturing industries, metallurgical, leather tanning, and mining, contain these heavy metal ions [3]. These wastewater with heavy metal ions are discharged into natural water directly, not only threat the aquatic organisms, but may be enriched by precipitation, adsorption, and harmed human health through the food chain. Thus, the removal of such toxic metal ions from wastewater is becoming a crucial issue.

Heavy metal ions could be eliminated by several traditional techniques [4], including chemical precipitation [5], reverse osmosis [6], electrochemical treatment techniques [7], ion exchange [8], membrane filtration [9], coagulation [10], extraction [11], irradiation [12], and adsorption [13]. Due to its low cost-effective, high efficiency, and simple to operate for removing trace levels of heavy metal ions, adsorption technology [14] is regarded as the most promising one to remove heavy metal ions from effluents among these techniques mentioned above. Several types of materials, such as activated carbons [15], clay minerals [16], chelating materials [17], and chitosan/natural zeolites [18] have been researched to adsorb metal ions from aqueous solutions. Although traditional sorbents could remove heavy metal ions from wastewater, the low sorption capacities and efficiencies limit their application deeply.

To solve these defects of traditional sorbents, nanomaterials are used as the novel ones to remove heavy metal ions in wastewater. Materials with the particle size between 1 nm to 100 nm are defined as nanomaterials. With novel size- and shape-dependent properties,

nanomaterials have been extensively investigated over a decade [19]. In recent years, the development of nanoscience and nanotechnology has shown remarkable potential for the remediation of environmental problems [20,21]. Compared with traditional materials, nanostructure adsorbents have exhibited much higher efficiency and faster rates in water treatment.

Nanomaterials for Adsorption

Used as sorbents for removing heavy metal ions in wastewater, nanomaterials should satisfy the following criterions: 1) The nanosorbents themselves should be nontoxic. 2) The sorbents present relatively high sorption capacities and selectivity to the low concentration of pollutants. 3) The adsorbed pollutant could be removed from the surface of the nano adsorbent easily. 4) The sorbents could be infinitely recycled. So far, a variety of nanomaterials such as carbon nanotubes, carbon based material composites, graphene, nano metal or metal oxides, and polymeric sorbents have been studied in the removal of heavy metal ions from aqueous solutions, and the results indicate that these nanomaterials show high adsorption capacity.

Carbon based nanomaterials

As one of the inorganic materials, carbon based nanomaterials [22] are used widely in the field of removal heavy metals in recent decades, due to its nontoxicity and high sorption capacities. Activated carbon is used firstly as sorbents, but it is difficult to remove heavy metals at ppb levels. Then, with the development of nanotechnology, carbon nanotubes, fullerene, and graphene are synthesized and used as nanosorbents.

***Corresponding author:** Yifei Guo, Institute of Medicinal Plant Development, Chinese Academy of Medical Sciences, Peking Union Medical College, 151 Malianwa North Road, Beijing 100094, P. R. China, E-mail: ffguo@163.com

Received July 16, 2012; Accepted August 20, 2012; Published August 24, 2012

Citation: Wang X, Guo Y, Yang L, Han M, Zhao J, et al. (2012) Nanomaterials as Sorbents to Remove Heavy Metal Ions in Wastewater Treatment. J Environ Anal Toxicol 2:154. doi:10.4172/2161-0525.1000154

Copyright: © 2012 Wang X, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Carbon nanotubes (CNTs) are discovered by Iijima, due to their unique structural, electronic, optoelectronic, semiconductor, mechanical, chemical and physical properties, have been applied widely to remove heavy metals in wastewater treatment. CNTs are used as nanosorbents separately firstly, and show high sorption efficiency of divalent metal ions. Pyrzyńska and Bystrzejewski [23] give the advantages and limitations of heavy metals sorption onto activated carbon, carbon nanotubes, and carbon-encapsulate magnetic nanoparticles, through sorption studies based on Co^{2+} and Cu^{2+} . The results show that carbon nanomaterials have significantly higher sorption efficiency comparing with activated carbons. Meanwhile, Stafiej and Pyrzyńska [24] find solution conditions, including pH and metal ions concentrations, could affect the adsorption characteristics of carbon nanotubes, and the Freundlich adsorption model agree well with their experimental data.

Then, to enhance the sorption capacities, CNTs are modified by oxidation [25,26], combing with other metal ions [27] or metal oxides [28], and coupling with organic compounds [29]. Ball et al. [30] showed that carboxyl-carbon sites are over 20 times more energetic for zinc sorption than unoxidized carbon sites. Salam et al. [29] modified carbon nanotubes with 8-hydroxyquinoline, which are used to remove of Cu^{2+} , Pb^{2+} , Cd^{2+} , and Zn^{2+} . In this paper, adsorption parameters, such as the amount of carbon nanotubes used, temperature, pH, ionic strength, metal ion concentration are studied and optimized. The results show that most of the metals are removed from aqueous solution. The modification of CNTs with 8-hydroxyquinoline enhanced significantly the removal process.

Graphene is another type carbon material as nanosorbent, which is a kind of one or several atomic layered graphites, possesses special two-dimensional structure and good mechanical, thermal properties. Wang et al. [1] synthesized the few-layered graphene oxide nanosheets through the modified Hummers method, this graphene nanosheets are used as sorbents for the removal of Cd^{2+} and Co^{2+} ions from aqueous solution, results indicate that heavy metal ions sorption on nanosheets is dependent on pH and ionic strength, and the abundant oxygen-containing functional groups on the surfaces of graphene oxide nanosheets played an important role on sorption. Kim et al. [31] reported magnetite-graphene adsorbents with a particle size of ~ 10 nm give a high binding capacity for As^{3+} and As^{5+} , and the results indicate that the high binding capacity is due to the increased adsorption sites in the graphene composite.

Nanoparticles from metal or metal oxides

Nanoparticles formed by metal or metal oxides are another inorganic nanomaterials, which are used broadly to remove heavy metal ions in wastewater treatment. Nanosized metals or metal oxides include nanosized silver nanoparticles [32], ferric oxides [33], manganese oxides [34], titanium oxides [35], magnesium oxides [19], copper oxides [36], cerium oxides [37], and so on, all these provide high surface area and specific affinity. Besides, metal oxides possess minimal environmental impact and low solubility and no secondary pollution, have been adopted as sorbents to remove heavy metals.

Hristovski et al. [38] research the feasibility of arsenate removal by aggregated metal oxide nanoparticle media in packed bed columns. Through batch experiments conduct with 16 commercial nanopowders in four water matrices, TiO_2 , Fe_2O_3 , ZrO_2 , and NiO nanopowders are selected out by characterized with fitted Freundlich adsorption isotherm parameters, which exhibit the highest arsenate removal in all water matrices. Cao et al. [39] synthesized the titanate nanoflowers

through a facile hydrothermal treatment of anatase nanopowders in concentration NaOH solution. The nanoflowers have large specific surface area and show availability for the removal of heavy metal ions from water system. Comparative studies exhibit that titanate nanoflowers possess larger adsorption capacity and more rapid kinetics than titanate nanotubes/nanowires. Besides, Titanate nanoflowers showed high selectivity in the removal of highly toxic heavy metal ion Cd^{2+} than less toxic ions Zn^{2+} , Ni^{2+} , which are the potential adsorbents for efficient removal of toxic metal ions. The equilibrium data show the adsorption mechanism fitted well with the Langmuir model, the adsorption kinetics followed the pseudo-second-order model. In addition, nanosized metal or metal oxides can be embedded in supports. Chen et al. [40] synthesized the highly ordered $\text{Mg}(\text{OH})_2$ nanotube arrays inside the pores of porous anodic alumina membranes to form $\text{Mg}(\text{OH})_2/\text{Al}_2\text{O}_3$ composite membranes. And these membranes are used to remove Nickel ions from wastewater with high removal efficiency. Then, $\text{MgO}/\text{NiO}/\text{Al}_2\text{O}_3$ metal-oxides nanostructures are gained after heating the composite membranes, which still present nice performance of Ni^{2+} removal.

Nanosized metal oxides show great removal efficiency of heavy metal in wastewater, owing to their higher surface areas and much more surface active sites than bulk materials. But, it is very difficult to separate them from the wastewater due to their high surface energy and nanosize. So, many researchers turn to design polymer based nanosorbents.

Polymer supported nanosorbents

An efficient sorbent with both high capacity and fast rate adsorption should have the following two main characteristics: functional groups and large surface area [41]. Unfortunately, most current inorganic sorbents rarely have both at the same time, carbon nanomaterials has high surface area, but without adsorbing functional group. On the contrary, organic polymer, polyphenylenediamine, holds a large amount of polyfunctional groups (amino and imino groups) can effectively adsorb heavy metal ions, whereas their small specific area and low adsorption rate limit their application. Therefore, new sorbents with both polyfunctional groups and high surface area are still expected. More recently, the development of hybrid sorbents has opened up the new opportunities of their application in deep removal of heavy metals from water [42,43].

Polymer-layered silicate nanocomposites [44] have attracted both academic and industrial attention because they exhibit dramatic improvement in properties at very low filler contents. Xu et al. [45] synthesized the hybrid polymers from the ring-opening polymerization of pyromellitic acid dianhydride (PMDA) and phenylaminomethyl trimethoxysilane (PAMTMS). This hybrid polymer is used to remove Cu^{2+} and Pb^{2+} , adsorption for Cu^{2+} and Pb^{2+} followed Lagergren second-order kinetic model and Langmuir isotherm model, demonstrating that the adsorption process might be Langmuir monolayer adsorption.

In summary, nanomaterials including traditional inorganic nanoadsorbents and novel polymer supported composites are used to remove the heavy metal ions in wastewater treatment, due to their novel size- and shape-dependent properties, and gain the good to excellent removal efficiency.

Adsorption Isotherm

Adsorption is the process in which heavy metals are adsorbed on the solid surface, and the equilibrium is established when the concentrations of heavy metal adsorbed and in water become constant.

At equilibrium, the relationship between amounts of heavy metal ions adsorbed and in water is called an adsorption isotherm [21]. From these isotherms, several adsorption parameters could be calculated. The most widely used adsorption isotherms are Langmuir model and Freundlich model.

Langmuir model

In this model, adsorption occurs uniformly on the active sites of the adsorbent, and once the active sites are occupied by adsorbates, the adsorption is naturally terminated at this site. The non-linear Langmuir equation is [46,47]:

$$q = \frac{q_{\max} K_L C}{1 + K_L C} \quad (1)$$

where K_L is the equilibrium constant ($L \text{ mg}^{-1}$), q_{\max} is the maximum adsorption capacity (mg g^{-1}) of adsorbent, C is the equilibrium concentration (mg L^{-1}), q is the amount of metals adsorbed at equilibrium (mg g^{-1}).

The linear Langmuir model is given by following equation:

$$\frac{C_e}{q_e} = \frac{C_e}{q_m} + \frac{1}{b q_m} \quad (2)$$

where q_m and b are the saturated monolayer adsorption capacity and the adsorption equilibrium constant. A plot of C_e/q_e versus C_e would result in a straight line. From the slope and intercept, the maximum adsorption capacity and bond energy of adsorbates can be calculated.

Freundlich adsorption isotherm

The Freundlich equation is an empirical model allowing for multilayer adsorption on sorbent. The non-linear form of Freundlich model is [48]:

$$q_e = K_F C_e^n \quad (3)$$

The linear form of Freundlich model can be expressed as:

$$\log q_e = \log K_F + \frac{\log C_e}{n} \quad (4)$$

where q_e is loading of adsorbate on adsorbent at equilibrium (mg g^{-1}); K_F is indicator of sorption capacity ($\text{mg}^{1-n} \text{L}^n \text{g}^{-1}$), n is adsorption energetics and C_e is aqueous concentration of adsorbate at equilibrium (mg L^{-1}).

As the widely used models, the Langmuir model assumes monolayer coverage on sorbent whereas the Freundlich model is an empirical model allowing for multilayer adsorption on sorbent [49]. Besides, there are several different well-known models used to explain the results of adsorption studies, including Tempkin [50], Frenkel-Halsey-Hill [51], Henderson [52], Giles-Smith [53], Dubinin-Radushkevich [54], MT [55], BET [56], BDST [57], Oswin [58], Ferro-Fintan [59], GAB [60], and Peleg [61]. These adsorption models give a representation of the adsorption equilibrium between an adsorbate in solution and the surface of the adsorbent [62].

Adsorption Kinetics Model

In order to determine and interpret the mechanisms of metal adsorption processes and the main parameters governing sorption kinetics, several kinetic models are proposed.

Pseudo-first-order kinetics model

A simple kinetic model suggested for the sorption process in solid/

liquid systems is Lagergren's pseudo-first-order expression, which is given as [63]:

$$\frac{dq_t}{dt} = k_1 (q_e - q_t) \quad (5)$$

Where k_1 is the pseudo-first-order rate constant for the adsorption process (min^{-1}), q_e and q_t are the amounts of metal ions adsorbed per gram of sorbents (mg g^{-1}) at equilibrium and at time t (min), respectively. After integration of this kinetic expression for the initial condition of q_t equal to 0, when time (t) approaches 0, its linear form are obtained:

$$\ln(q_e - q_t) = \ln q_e - k_1 t \quad (6)$$

The plot of $\ln(q_e - q_t)$ vs t gives a straight line, and pseudo-first-order rate constant k_1 can be calculated from the slope of that line.

Pseudo-second-order kinetics model

The kinetic data also can be analyzed by Ho's pseudo-second-order kinetics model. This model is based on the assumption the sorption follows second order chemisorptions, which can be represented in the linear expression as [64]:

$$\frac{t}{q_t} = \frac{1}{k_2 q_e^2} + \frac{t}{q_e} \quad (7)$$

Where k_2 ($\text{g} \cdot \text{mg}^{-1} \cdot \text{min}^{-1}$) is the rate constant of the pseudo-second-order adsorption.

Besides two kinetic models mentioned above, researchers also propose other models, e.g. Elovich equation [65], Weber-Morris diffusion model [66], and so on.

Conclusion

Advances in nanoscale science and engineering are providing new opportunities to develop more cost-effective and environmentally acceptable water treatment technology. Nanomaterials have a number of physicochemical properties that make them particularly attractive for wastewater purification. Recent researches have indicated that nanomaterials as sorbents are useful tools for heavy metal removal, due to their unique structure and surface characteristics. These materials are capable to remove heavy metal ions at low concentration, with high selectivity and adsorption capacity. These properties of nanosorbents make them ideal materials for wastewater treatment technology. To explain the mechanism of adsorption process, adsorption isotherm and adsorption kinetics are concluded in this paper. Although nanosorbents, such as CNTs, nanometal or nanometal oxides, and other organic sorbents, are used successfully in removal heavy metal ions in wastewater, it still remains several problems; wastewater treatment on a large scale is the essential one. Besides, to develop some environment friendly and inexpensive nanomaterials is also the key work. With the nanotechnology developed, the exploitation of new efficient adsorption materials is essential and will continue infinitely, the future of nanomaterials in removal heavy metal ions in wastewater treatment is fairly bright.

References

1. Zhao G, Li J, Ren X, Chen C, Wang X (2011) Few-layered graphene oxide nanosheets as superior sorbents for heavy metal ion pollution management. *Environ Sci Technol* 45: 10454-10462.
2. Moreno-Castilla C, Álvarez-Merino MA, López-Ramón MV, Rivera-Utrilla J (2004) Cadmium ion adsorption on different carbon adsorbents from aqueous solutions. Effect of surface chemistry, pore texture, ionic strength, and dissolved natural organic matter. *Langmuir* 20: 8142-8148.

3. Chen C, Wang X (2006) Adsorption of Ni(II) from aqueous solution using oxidized multiwall carbon nanotubes. *Ind Eng Chem Res* 45: 9144-9149.
4. Fu F, Wang Q (2011) Removal of heavy metal ions from wastewaters: A review. *J Environ Manage* 92: 407-418.
5. Wang LK, Vaccari DA, Li Y, Shammass NK (2005) Chemical Precipitation Physicochemical Treatment Processes. In Wang LK, Hung YT, Shammass NK, Eds. Humana Press 3141-197.
6. Bódalo-Santoyo A, Gómez-Carrasco JL, Gómez-Gómez E, Máximo-Martín F, Hidalgo-Montesinos AM (2003) Application of reverse osmosis to reduce pollutants present in industrial wastewater. *Desalination* 155: 101-108.
7. Walsh FC, Reade GW (1994) Electrochemical techniques for the treatment of dilute metal-ion solutions. *Studies in environmental science* 59: 3-44.
8. Xing Y, Chen X, Wang D (2007) Electrically regenerated ion exchange for removal and recovery of Cr (VI) from wastewater. *Environ Sci Technol* 41: 1439-1443.
9. Ersahin ME, Ozgun H, Dereli RK, Ozturk I, Roest K, et al. (2012) A review on dynamic membrane filtration: Materials, applications and future perspectives. *Bioresour Technol* (in press).
10. Zhang P, Hahn HH, Hoffmann E (2003) Different behavior of iron(III) and aluminum(III) salts to coagulate silica particle suspension. *Acta hydroch hydrob* 31: 145-151.
11. Rykowska I, Wasiak W, Byra J (2008) Extraction of copper ions using silica gel with chemically modified surface. *Chem Pap* 62: 255-259.
12. Batley GE, Farrar YJ (1978) Irradiation techniques for the release of bound heavy metals in natural waters and blood. *Anal Chim Acta* 99: 283-292.
13. Srivastava V, Weng CH, Singh VK, Sharma YC (2011) Adsorption of nickel ions from aqueous solutions by nano alumina: Kinetic, mass transfer, and equilibrium studies. *J Chem Eng Data* 56: 1414-1422.
14. Zamboulis D, Peleka EN, Lazaridis NK, Matis KA (2011) Metal ion separation and recovery from environmental sources using various flotation and sorption techniques. *J Chem Technol Biotechnol* 86: 335-344.
15. Kobya M, Demirbas E, Senturk E, Ince M (2005) Adsorption of heavy metal ions from aqueous solutions by activated carbon prepared from apricot stone. *Bioresour Technol* 96: 1518-1521.
16. Oubagaranadin JUK, Murthy ZVP (2009) Adsorption of divalent lead on a montmorillonite-illite type of clay. *Ind Eng Chem Res* 48: 10627-10636.
17. Sun S, Wang L, Wang A (2006) Adsorption properties of crosslinked carboxymethyl-chitosan resin with Pb(II) as template ions. *J Hazard Mater* 136: 930-937.
18. Wang X, Zheng Y, Wang A (2009) Fast removal of copper ions from aqueous solution by chitosan-g-poly(acrylic acid)/attapulgitite composites. *J Hazard Mater* 168: 970-977.
19. Gao C, Zhang W, Li H, Lang L, Xu Z (2008) Controllable fabrication of mesoporous MgO with various morphologies and their absorption performance for toxic pollutants in water. *Cryst Growth Des* 8: 3785-3790.
20. Lee J, Mahendra S, Alvarez PJJ (2010) Nanomaterials in the construction industry: A review of their applications and environmental health and safety considerations. *ACS Nano* 4: 3580-3590.
21. Ali I (2012) New generation adsorbents for water treatment. *Chem Rev* (in press).
22. Mauter MS, Elimelech M (2008) Environmental applications of carbon-based nanomaterials. *Environ Sci Technol* 42: 5843-5859.
23. Pyrzyńska K, Bystrzejewski M (2010) Comparative study of heavy metal ions sorption onto activated carbon, carbon nanotubes, and carbon-encapsulated magnetic nanoparticles. *Colloids Surf A* 362: 102-109.
24. Stafiej A, Pyrzyńska K (2007) Adsorption of heavy metal ions with carbon nanotubes. *Sep Purif Technol* 58: 49-52.
25. Rao GP, Lu C, Su F (2007) Sorption of divalent metal ions from aqueous solution by carbon nanotubes: A review. *Sep Purif Technol* 58: 224-231.
26. Afzali D, Jamshidi R, Ghaseminezhad S, Afzali Z (2011) Preconcentration procedure trace amounts of palladium using modified multiwalled carbon nanotubes sorbent prior to flame atomic absorption spectrometry. *Arab J Chem* (in press).
27. Gupta VK, Agarwal S, Saleh TA (2011) Synthesis and characterization of alumina-coated carbon nanotubes and their application for lead removal. *J Hazard Mater* 185: 17-23.
28. Zhao X, Jia Q, Song N, Zhou W, Li Y (2010) Adsorption of Pb(II) from an aqueous solution by titanium dioxide/carbon nanotube nanocomposites: Kinetics, thermodynamics, and Isotherms. *J Chem Eng Data* 55: 4428-4433.
29. Kosa SA, Al-Zhrani G, Abdel Salam M (2012) Removal of heavy metals from aqueous solutions by multi-walled carbon nanotubes modified with 8-hydroxyquinoline. *Chem Eng J* 181-182: 159-168.
30. Cho HH, Wepasnick K, Smith BA, Bangash FK, Fairbrother DH, et al. (2009) Sorption of aqueous Zn(II) and Cd(II) by multiwall carbon nanotubes: The relative roles of oxygen-containing functional groups and graphenic carbon. *Langmuir* 26: 967-981.
31. Chandra V, Park J, Chun Y, Lee JW, Hwang IC, et al. (2010) Water-dispersible magnetite-reduced graphene oxide composites for arsenic removal. *ACS Nano* 4: 3979-3986.
32. Fabrega J, Luoma SN, Tyler CR, Galloway TS, Lead JR (2011) Silver nanoparticles: Behaviour and effects in the aquatic environment. *Environ Int* 37: 517-531.
33. Feng L, Cao M, Ma X, Zhu Y, Hu C (2012) Superparamagnetic high-surface-area Fe₃O₄ nanoparticles as adsorbents for arsenic removal. *J Hazard Mater* 217-218: 439-446.
34. Gupta K, Bhattacharya S, Chattopadhyay D, Mukhopadhyay A, Biswas H, et al. (2011) Ceria associated manganese oxide nanoparticles: Synthesis, characterization and arsenic(V) sorption behavior. *Chem Eng J* 172: 219-229.
35. Luo T, Cui J, Hu S, Huang Y, Jing C (2010) Arsenic removal and recovery from copper smelting wastewater using TiO₂. *Environ Sci Technol* 44: 9094-9098.
36. Goswami A, Raul PK, Purkait MK (2011) Arsenic adsorption using copper (II) oxide nanoparticles. *Chem Eng J* (in press).
37. Cao CY, Cui ZM, Chen CQ, Song WG, Cai W (2010) Ceria hollow nanospheres produced by a template-free microwave-assisted hydrothermal method for heavy metal ion removal and catalysis. *J Phys Chem* 114: 9865-9870.
38. Hristovski K, Baumgardner A, Westerhoff P (2007) Selecting metal oxide nanomaterials for arsenic removal in fixed bed columns: From nanopowders to aggregated nanoparticle media. *J Hazard Mater* 147: 265-274.
39. Huang J, Cao Y, Liu Z, Deng Z, Tang F, et al. (2012) Efficient removal of heavy metal ions from water system by titanate nanoflowers. *Chem Eng J* 180: 75-80.
40. Zhang S, Cheng F, Tao Z, Gao F, Chen J (2006) Removal of nickel ions from wastewater by Mg(OH)₂/MgO nanostructures embedded in Al₂O₃ membranes. *J Alloys Compd* 426: 281-285.
41. Huang MR, Huang SJ, Li XG (2011) Facile synthesis of polysulfonated anthraquinone nanosorbents for rapid removal and ultrasensitive fluorescent detection of heavy metal ions. *J Phys Chem C* 115: 5301-5315.
42. Pan B, Pan B, Zhang W, Lv L, Zhang Q, et al. (2009) Development of polymeric and polymer-based hybrid adsorbents for pollutants removal from waters. *Chem Eng J* 151: 19-29.
43. Zhao X, Lv L, Pan B, Zhang W, Zhang S, et al. (2011) Polymer-supported nanocomposites for environmental application: A review. *Chem Eng J* 170: 381-394.
44. Pavlidou S, Papaspyrides CD (2008) A review on polymer-layered silicate nanocomposites. *Progress Polym Sci* 33: 1119-1198.
45. Liu J, Ma Y, Xu T, Shao G (2010) Preparation of zwitterionic hybrid polymer and its application for the removal of heavy metal ions from water. *J Hazard Mater* 178: 1021-1029.
46. Shen W, Chen S, Shi S, Li X, Zhang X, et al. (2009) Adsorption of Cu(II) and Pb(II) onto diethylenetriamine-bacterial cellulose. *Carbohydr Polym* 75: 110-114.
47. Ho YS, Chiu WT, Wang CC (2005) Regression analysis for the sorption isotherms of basic dyes on sugarcane dust. *Bioresour Technol* 96: 1285-1291.
48. Rahmani A, Mousavi HZ, Fazli M (2010) Effect of nanostructure alumina on adsorption of heavy metals. *Desalination* 253: 94-100.
49. Ruparelia JP, Duttagupta SP, Chatterjee AK, Mukherji S (2008) Potential of carbon nanomaterials for removal of heavy metals from water. *Desalination* 232: 145-156.

50. Wang XS, Qin Y (2005) Equilibrium sorption isotherms for of Cu²⁺ on rice bran. *Process Biochem* 40: 677-680.
51. Pierce C (1960) The Frenkel-Halsey-Hill adsorption isotherm and capillary condensation. *J Phys Chem* 64: 1184-1187.
52. Henderson D, Barojas J, Blum L (1983) Anomalous adsorption of ions at an electrode. *J Phys Chem* 87: 4544-4547.
53. Cokelet GR, Hollander FJ, Smith JH (1969) Density and viscosity of mixtures of 1,1,2,2-tetrabromoethane and 1-bromododecane. *J Chem Eng Data* 14: 470-473.
54. Danish M, Hashim R, Mohamad Ibrahim MN, Rafatullah M, Sulaiman O, et al. (2011) Sorption of copper(II) and nickel(II) ions from aqueous solutions using calcium oxide activated date (*Phoenix dactylifera*) stone carbon: Equilibrium, kinetic, and thermodynamic studies. *J Chem Eng Data* 56: 3607-3619.
55. Redhead PA (1996) An empirical isotherm for multilayer physisorption. *Langmuir* 12: 763-767.
56. Onal I, Soyer S, Senkan S (2006) Adsorption of water and ammonia on TiO₂-anatase cluster models. *Surf Sci* 600: 2457-2469.
57. Goel J, Kadirvelu K, Rajagopal C, Kumar Garg V (2005) Removal of lead(II) by adsorption using treated granular activated carbon: Batch and column studies. *J Hazard Mater* 125: 211-220.
58. Saha D, Deng S (2011) Hydrogen adsorption on Pd- and Ru-doped C60 fullerene at an ambient temperature. *Langmuir* 27: 6780-6786.
59. Allegretti F, O'Brien S, Polcik M, Sayago DI, Woodruff DP (2005) Adsorption bond length for H₂O on TiO₂(110): A key parameter for theoretical understanding. *Phys Rev Lett* 95: 226104.
60. Wang Y, Padua GW (2004) Water sorption properties of extruded zein films. *J Agric Food Chem* 52: 3100-3105.
61. Kammoun Bejar A, Boudhrioua Mihoubi N, Kechaou N (2012) Moisture sorption isotherms-experimental and mathematical investigations of orange (*Citrus sinensis*) peel and leaves. *Food Chem* 132: 1728-1735.
62. Arshadi M, Ghiaci M, Gil A (2011) Schiff base ligands immobilized on a nanosized SiO₂-Al₂O₃ mixed oxide as adsorbents for heavy metals. *Ind Eng Chem Res* 50: 13628-13635.
63. Çavuş S, Gürdag Gİ (2009) Noncompetitive removal of heavy metal ions from aqueous solutions by poly[2-(acrylamido)-2-methyl-1-propanesulfonic acid-co-itaconic acid] hydrogel. *Ind Eng Chem Res* 48: 2652-2658.
64. Fan HT, Fan X, Li J, Guo M, Zhang D, et al. (2012) Selective removal of arsenic(V) from aqueous solution using a surface-ion-imprinted amine-functionalized silica gel sorbent. *Ind Eng Chem Res* 51: 5216-5223.
65. Juang RS, Chen ML (1997) Application of the elovich equation to the kinetics of metal sorption with solvent-impregnated resins. *Ind Eng Chem Res* 36: 813-820.
66. Malash GF, El-Khaiary MI (2010) Piecewise linear regression: A statistical method for the analysis of experimental adsorption data by the intraparticle-diffusion models. *Chem Eng J* 163: 256-263.