

REVIEW

Open Access



# PEO based polymer-ceramic hybrid solid electrolytes: a review

Jingnan Feng<sup>1,2</sup>, Li Wang<sup>2</sup>, Yijun Chen<sup>1</sup>, Peiyu Wang<sup>1</sup>, Hanrui Zhang<sup>1</sup> and Xiangming He<sup>2\*</sup> 

## Abstract

Compared with traditional lead-acid batteries, nickel–cadmium batteries and nickel-hydrogen batteries, lithium-ion batteries (LIBs) are much more environmentally friendly and much higher energy density. Besides, LIBs own the characteristics of no memory effect, high charging and discharging rate, long cycle life and high energy conversion rate. Therefore, LIBs have been widely considered as the most promising power source for mobile devices. Commonly used LIBs contain carbonate based liquid electrolytes. Such electrolytes own high ionic conductivity and excellent wetting ability. However, the use of highly flammable and volatile organic solvents in them may lead to problems like leakage, thermo runaway and parasitic interface reactions, which limit their application. Solid polymer electrolytes (SPEs) can solve these problems, while they also bring new challenges such as poor interfacial contact with electrodes and low ionic conductivity at room temperature. Many approaches have been tried to solve these problems. This article is divided into three parts to introduce polyethylene oxide (PEO) based polymer-ceramic hybrid solid electrolyte, which is one of the most efficient way to improve the performance of SPEs. The first part focuses on polymer-lithium salt (LiX) matrices, including their ionic conduction mechanism and impact factors for their ionic conductivity. In the second part, the influence of both active and passive ceramic fillers on SPEs are reviewed. In the third part, composite SPEs' preparation methods, including solvent casting and thermocompression, are introduced and compared. Finally, we propose five key points on how to make composite SPEs with high ionic conductivity for reference.

**Keywords:** Solid electrolyte, Polymer electrolyte, Polyethylene oxide, Ceramic, Nanoparticle

## 1 Introduction

Lithium ion batteries (LIBs) are widely used in phones, computers and other mobile devices owing to their high specific energy, good capability, good cycle performance and environmentally friendly property [1–3]. Although traditional carbonate based liquid electrolytes have high ionic conductivity under normal temperature, the organic solvent contained has the potential danger of leakage and combustion, which may cause severe safety issues. Solid-state electrolytes, both inorganic solid electrolytes and solid polymer electrolytes, can overcome these shortages [4]. The research on solid-state ionic conductors can

trace back to 1834. However, the real threshold of studies on solid-state electrolytes is generally believed to be 1960s when Takahashi et al. [5] found the silver ionic conductivity of  $\text{Ag}_3\text{SI}$  (about  $10^{-2}$  S/cm at ambient temperature). These ceramic materials own excellent ionic conductivity, while they have fatal defects that their rigid and brittle bodies will lead to bad contact with electrodes and bring great difficulties to processing. Therefore, the focus of research gradually shifted from inorganic materials to organic materials which own good flexibility and processability. In 1973, Fenton et al. [6] reported the transport of ions in polyethylene oxide (PEO)-alkali metal salts complexation, which started a new chapter of researches on solid polymer electrolytes (SPEs). After that, Armand et al. [7] reported that the ionic conductivity of such complexations could reach  $10^{-5}$  S/cm in temperature range between 40 and 60 °C, indicating that

\*Correspondence: hexm@tsinghua.edu.cn

<sup>2</sup> Institute of Nuclear and New Energy Technology, Tsinghua University, Beijing 100084, China

Full list of author information is available at the end of the article

SPEs might be used under room temperature. Since then, the research on SPEs has become the most popular part in related fields.

Compared with traditional liquid electrolytes, SPEs can not only alleviate the danger of flammability and possible side reactions with electrodes, but also retain the excellent adhesion and film-forming properties of polymers. Moreover, the solid-state electrolyte membranes are supposed to suppress the growing of lithium dendrite, which can further ensure the safety of the batteries during the charging and discharging process. These characteristics determine that SPEs have a promising future. However, SPEs have not yet reached the practical accessibility due to their huge interfacial resistance and low bulk conductivity ( $10^{-7}$  S/cm) at ambient temperature [8, 9]. To solve these problems, polymer/liquid hybrid [10], polymer/polymer hybrid and polymer/ceramic hybrid were developed [11]. The polymer/liquid hybrid is to form a gel-type polymer electrolyte by adding a small amount of liquid plasticizer, such as ethylene carbonate (EC), propylene carbonate (PC) and dimethyl carbonate (DMC) into the electrolyte. In such hybrid, the liquid phase plays an important role in wetting, reducing the interfacial resistance and directly increasing the ionic conductivity. Nevertheless, such improvement is at the expense of all-solid-state properties of SPEs, which may reduce the mechanical strength of the electrolytes and cause similar problems to liquid electrolytes. The polymer/polymer hybrid is formed by combining different kinds of polymers so that the hybrid can obtain the advantages of each one. As an example, the ionic conductivity of polystyrene (PS)-PEO-PS [12, 13] hybrid system can reach  $2.3 \times 10^{-4}$  S/cm at 60 °C, which is better than the performance of single PEO-based SPEs. But the ionic conductivity is still not high enough for daily use under normal temperature. The polymer/ceramic hybrid is to add inorganic fillers into the electrolytes. These fillers can be divided to two categories due to their own nature. The first are passive fillers for there are no Li ions in themselves and thus they do not directly participate into the transport process of  $\text{Li}^+$ . They can improve the ionic conductivity of SPEs mainly due to the complicated structure of polymer-passive filler interfaces, which results in the suppression of recrystallization of PEO, more free- $\text{Li}^+$  and fast ion transport channels. The fillers in second kind are active, which contain Li ions in their bodies. As a result,  $\text{Li}^+$  can transport through PEO body, PEO-active filler interfaces and active fillers' bodies. The ionic conductivity of the whole SPEs get enhanced in this way. Besides, the mechanical strength can get better by doping with hard ceramic particles [14] and the interfacial stability between electrodes and electrolytes are supposed to be improved mainly due to the water-scavenging effect of


these particles [15–18]. Consequently, polymer-ceramics hybrid become one of the most effective way to improve the performance of SPEs.

## 2 Polymer-LiX matrices

Polymers used in SPEs include polyacrylonitrile (PAN) [19], PS [12, 13], polymethyl methacrylate (PMMA) [20], polyvinylidene fluoride (PVDF) [21], polyvinyl pyrrolidone (PVP) [22], etc. Compared with the other polymers, PEO has many advantages due to its special structure. PEO owns strong electron donating ether oxygen (EO) groups, soft macromolecular backbone, good thermal stability and mechanical properties. As a consequence, PEO has become the most frequently studied polymer base for SPEs. The chemical formula of PEO is  $\text{H}(\text{OCH}_2\text{CH}_2)_n\text{OH}$ , as showed in Fig. 1b. It is water-soluble and in semi-crystalline state at room temperature. Usually, PEO is the name for the polymer with a molecular weight ( $M_n$ ) greater than 20,000. When the molecular weight is less than 20,000, it is called polyethylene glycol (PEG).

In SPEs, both anions and cations participate in the process of ionic conduction. However, due to the mechanism of redox reaction, only the charges carried by  $\text{Li}^+$  are valid. The number of evaluating the contribution of  $\text{Li}^+$  to the whole ionic conductivity is named transference number ( $T_{\text{Li}^+}$ ). This number is normally below 0.5 in SPEs [10]. In the contrary, anions are fixed to the polymer skeleton through covalent bonds in polyelectrolytes. In this way, polyelectrolytes are single ion-conducting electrolytes and their  $T_{\text{Li}^+}$  is close to 1. However, because of the insufficient dissociation of  $\text{Li}^+$ , the ionic conductivity of polyelectrolytes is much lower than that of normal SPEs [23]. So, this article mainly focuses on normal SPEs instead of polyelectrolytes.

The conductive mechanism of PEO-lithium salt (LiX) matrices is shown in Fig. 1a. The whole process can be summarized by the combination and fracture of EO-Li bonds. First, the strong electron donating group EO will complex with the charge carrier  $\text{Li}^+$ . There are about 5 EO to match with 1  $\text{Li}^+$  [24, 25]. Then the conduction of  $\text{Li}^+$  is completed through the segmental motion of PEO molecular chains [26]. In this way,  $\text{Li}^+$  can be transported on a single chain or between different chains. Since the molecular chain movement is restricted to amorphous regions, the transport of  $\text{Li}^+$  in PEO is also limited to these regions, which means the crystallization zone won't exhibit ionic conductivity. Therefore, the ionic conductivity of PEO largely depends on the proportion of amorphous regions. On the other hand, glass transition temperature ( $T_g$ ) is the threshold when segmental motion begins, the lower  $T_g$  is, the higher ionic conductivity PEO will exhibit at room temperature. As a consequence, an




ideal PEO material should satisfy at least two conditions: high amorphous proportion and low  $T_g$ . PEO with low molecular weight meets these requirements, and thus has relatively good ionic conductivity. However, the thermal stability and mechanical strength of SPEs using low molecular weight PEO as polymer backbone are terrible. With the increase of  $M_n$ , the regularity of backbones in PEO goes higher, which leads to the reducing of the proportion of amorphous region, the increasing of  $T_g$  and viscosity. That means the mechanical strength of PEO is increasing while the ionic conductivity is reducing as  $M_n$  goes larger. In other words, PEO with low molecular weight is like liquid, while that with high molecular weight behaves like solid. The frequently used way to improve the performance of PEO include grafting to construct comb-like structure, inserting to make block structure and crosslinking [27–29]. Basically, these three methods are all trying to increase the proportion of amorphous region by destroying the regularity of PEO chains. In this way, the polymer base can not only retain the good mechanical strength of the macromolecule backbones, but also obtain relatively good ionic conductivity and low  $T_g$  from the small molecules [30].

Lithium salts also have a great impact on the whole ionic conductivity of PEO-LiX matrices. Generally used lithium salts include  $\text{LiBF}_4$ ,  $\text{LiAsF}_6$  and  $\text{LiClO}_4$  [24, 31]. Lithium bis(trifluoromethanesulfonyl)imide (LiTFSI), as a new generation of LiX, has particularly excellent performance in SPEs [32]. This is mainly due to its outstanding solubility. The chemical formula of LiTFSI is  $\text{Li}(\text{CF}_3\text{SO}_2)_2\text{N}$ , and its structure is shown in Fig. 1c. The large TFSI<sup>-</sup> anion is delocalized charge and has weak

bond to  $\text{Li}^+$ . Consequently, the dissociation of LiTFSI in SPEs is sufficient and thus more  $\text{Li}^+$  become free from the bondage of anions. These free- $\text{Li}^+$  will then couple with EO to realize the transport in bulk PEO [33–35].

Since  $\text{Li}^+$  transfers in PEO by the segmental motion of molecular chains in amorphous region, the ionic conductivity of SPEs is greatly affected by temperature. As temperature goes higher, the proportion of amorphous region increases continuously, and the total transition of PEO from crystalline to amorphous is completed at melting point ( $T_m$ ), which is directly reflected by the appearance of inflection point of ionic conductivity near  $T_m$ . Besides,  $\text{Li}^+$  moves on the molecular chain by complexing with EO groups. So, the ratio of EO/Li directly affects the binding and the velocity of  $\text{Li}^+$  transport. If EO/Li is too low, the  $\text{Li}^+$  carriers will be not enough in the electrolyte. If EO/Li is too high, the concentration of  $\text{Li}^+$  will be limited. For both situations, the ionic conductivity of PEO-LiX matrices is restricted. Generally, the highest ionic conductivity can be obtained when EO/Li=12–16 [36–39]. Moreover, polymers' end groups can affect the transport of  $\text{Li}^+$  by their different electrochemical properties.

These effects are indicated in Fig. 2a, b. It can be seen from Fig. 2a that as temperature increase, the ionic conductivity of all SPEs with different  $M_n$  does increase. The inflection point of low  $M_n$  systems (PEG 200, PEG 1000) doesn't appear in the range of experimental temperature due to their low  $T_m$ . PEG 9000 system has an inflection point at 322 K, so its  $T_m=322$  K. The inflection point of PEG 35,000 system is at 333 K, indicating that its  $T_m=333$  K. In addition, the ionic conductivity



of low molecular weight PEO system is higher than that of high molecular weight PEO system at the same temperature. It can be found from Fig. 2b that the ionic conductivity of systems with  $-\text{CH}_3$  end group is higher than that of systems with  $-\text{OH}$  end group. This phenomenon is due to the formation of transient cross-linking structure between  $-\text{OH}$  group and ions, which will slow down the transport of  $\text{Li}^+$  [40]. In general,  $-\text{OH}$  is more reactive than  $-\text{CH}_3$  or  $-\text{OCH}_3$ , which results in possible side reaction with electrolytes and poor high-voltage-resistance [41].

### 3 Ceramic fillers

Adding inorganic fillers into SPEs can greatly enhance their performance. On the one hand, it can effectively improve the overall ionic conductivity. On the other hand, it not only maintains the excellent flexibility and ductility of PEO polymer base, but also improves the mechanical strength of the whole body and interfacial stability between electrodes and electrolytes by uniformly dispersed ceramic particles. Therefore, it is an ideal method to improve the performance of SPEs. The cycling performance of systems with typical fillers are shown in

Table 1. Depending on whether the fillers contain  $\text{Li}^+$ , they can be divided into passive fillers and active fillers.

#### 3.1 Passive fillers


Passive fillers refer to ceramic fillers without  $\text{Li}^+$ . So, they are not capable in direct  $\text{Li}^+$  transport. Frequently used passive fillers include  $\text{Al}_2\text{O}_3$  [49, 50],  $\text{SiO}_2$  [51],  $\text{TiO}_2$  [52],  $\text{ZnO}$  [53] and  $\text{ZrO}_2$  [54].

As shown in Fig. 3a, there are two possible transport modes for  $\text{Li}^+$  in PEO-passive filler composites. One is to transport by the segmental motion of PEO molecular chains via PEO body (path 1), and the other is via PEO/passive filler interfaces (path 2). Since fillers can greatly improve the ionic conductivity of SPEs, path 2 is obviously the key reason for such enhancement effect. However, due to the complex interfacial structure between polymer and ceramic fillers, the mechanism of such enhancement effect is still not clear.

In 1991, Capuano et al. [55] studied the effect of  $\gamma\text{-LiAlO}_2$  on PEO- $\text{LiClO}_4$  system, and identified three major functions of inorganic fillers for SPEs: improving the mechanical strength, the ionic conductivity and the stability of the phase interfaces. In 1994, Kumar et al.

**Table 1** Cycling performance of systems with typical fillers

Fillers	Systems	Test condition	With fillers	References
10 wt% $\text{Al}_2\text{O}_3$	$\text{LiFePO}_4\text{-PEO/LiCF}_3\text{SO}_3\text{-Li}$	C/5, 90 °C	125 mAh/g over 50 cycles	[43]
10 wt% $\text{LiAlO}_2$	$\text{LiFePO}_4\text{-PEO/LiTFSI/SN-Li}$	C/10, 60 °C	120 mAh/g over 25 cycles	[44]
20 wt% LAGP	$\text{LiFePO}_4\text{-PEO/LiTFSI-Li}$	1C, 60 °C	108 mAh/g over 50 cycles	[45]
5 wt% LLTO	$\text{LiFePO}_4\text{-PEO/LiTFSI-Li}$	C/2, 60 °C	123 mAh/g over 100 cycles	[46]
10 wt% LLZO	$\text{LiFePO}_4\text{-PEO/LiTFSI-Li}$	C/10, 45 °C	158.7 mAh/g over 80 cycles	[47]
10 wt% LLZTO	$\text{LiFePO}_4\text{-PEO/LiTFSI-Li}$	C/5, 55 °C	139.1 mAh/g over 100 cycles	[48]



**Fig. 3** **a** Two possible paths of  $\text{Li}^+$  transport in PEO-passive fillers composite. **b** Three possible paths of  $\text{Li}^+$  transport in PEO-active fillers composite. **c** Passive fillers' effect of distorting the regularity of PEO, which lead to the inhibition of recrystallization. **d** Lewis acid-base interaction on PEO-ceramic interfaces, including  $\text{Al-X}^-$ ,  $\text{Al-O}$ ,  $\text{O-Li}^+$ ,  $\text{Li}^+-\text{X}^-$ . **e** Long continuous express path of  $\text{Li}^+$  provided by ceramic nanowires compared with discontinuous transport path of  $\text{Li}^+$  provided by ceramic nanoparticles

[56] studied the PEO- $\text{LiBF}_4\text{-Li}_3\text{N}$  system. They thought that the addition of ceramics would destroy the regularity of PEO, thus increased the proportion of amorphous region. The ionic conductivity of SPEs got enhanced in this way. Besides, they proposed that the the increase of


ionic conductivity might be also due to the possible formation of  $\text{Li}^+$  fast transport channels on the polymer/ceramic interfaces. Since the ceramic particles were dispersed uniformly in the system, such express channels would accelerate the transport of  $\text{Li}^+$  in the whole SPEs.

In 1995, Wieczorek et al. [57] pointed out that Lewis acid center of Al atoms on the surface of Al<sub>2</sub>O<sub>3</sub> particles would compete with Lewis acid center of alkali metal salt cations to complex with the Lewis base center of O atoms on the polymer chains. They pointed out that the addition of inorganic fillers would suppress the recrystallization process of molecular chains in PEO, which permanently increased the proportion of amorphous regions in SPEs, and thus improved the ionic conductivity of SPEs at room temperature. Croce et al. [52, 58–60] developed such theories and explained why the ionic conductivity of composite SPEs could still increase with the increase of temperature, while the whole PEO had already been amorphous when the temperature was higher than  $T_m$ . They proposed two hypotheses. The first hypothesis was that Lewis acid groups on the surface of ceramic fillers would compete with Li<sup>+</sup> to complex with O atoms (Lewis basic group) on the polymer chains. Ceramic surface acted as the cross-linking center for PEO segments. In this way, the recrystallization of PEO was suppressed by such structure and the express channels of Li<sup>+</sup> were formed. As described in detail in Fig. 4a, they found that the ionic conductivity of PEO-LiClO<sub>4</sub> matrices doped with Al<sub>2</sub>O<sub>3</sub> would not show sudden change around  $T_m$  and the amorphous to crystalline transition of whole PEO did not appear during the cooling process, which was hugely different from the behavior of ceramic-free SPEs and indicating the inhibition effect on recrystallization. The second hypothesis was that Lewis acid groups on the surface of ceramic particles also competed with

Li<sup>+</sup> to complex with X<sup>-</sup>, which lead to high dissociation order of LiX. These two aspects synergistically increased the concentration of free-Li<sup>+</sup>. Such views were further confirmed by tests. In the PEO-LiClO<sub>4</sub>-10 wt% TiO<sub>2</sub> system [52],  $T_{Li^+}$  can reached 0.6 in the 45–90 °C temperature range while in ceramic-free SPEs, such number was normally 0.2-0.3. As a consequence, when PEO has already transformed into amorphous form, these effects on helping produce more free-Li<sup>+</sup> can still get stronger with the increase of temperature, which results in the slow but continuous increase of ionic conductivity. In 2016, Liu et al. [61] reported a SPE with Y<sub>2</sub>O<sub>3</sub>-doped ZrO<sub>2</sub> (YSZ) nanowires on which many positive-charged oxygen vacancies were located. They found that such vacancies could help the dissociation of LiX. As a result, the ionic conductivity of the composite SPE could reached  $1.07 \times 10^{-5}$  S/cm at 30 °C while filler-free SPE could only reach  $3.62 \times 10^{-7}$  S/cm under the same condition. This experiment also verified the existence of Lewis acid–base interaction on the interfaces.

So far, the mechanism of passive fillers' enhancement effect on SPEs' ionic conductivity can be summarized into two types, which are showed by Fig. 3c, d, respectively.

1. Polymer-ceramic interfaces can permanently increase the proportion of amorphous region and thus increase the ionic conductivity of SPEs at room temperature by inhibiting the recrystallization of PEO.



2. Polymer-ceramic interfaces can help release more free-Li<sup>+</sup> and construct Li<sup>+</sup> express channels through the complicated complexation between Lewis acid center on the surface of ceramics, O atoms (Lewis base center) on the polymer chain and anions (Lewis base center) of LiX.

### 3.2 Active fillers

Active fillers refer to the ceramic fillers which contain Li<sup>+</sup> in their bodies, such as Li<sub>3</sub>N [62, 63], LiAlO<sub>2</sub> [64, 65], Li<sub>1+x</sub>Al<sub>x</sub>Ge<sub>2-x</sub>(PO<sub>4</sub>)<sub>3</sub> (LAGP) [66], Li<sub>1+x</sub>Al<sub>x</sub>Ti<sub>2-x</sub>(PO<sub>4</sub>)<sub>3</sub> (LATP) [67, 68], Li<sub>3x</sub>La<sub>2/3-x</sub>TiO<sub>3</sub> (LLTO) [69], Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub> (LLZO) [70–72], etc. These ceramic materials own high conductivity, good chemical stability, wide electrochemical window and can directly participate into the Li<sup>+</sup> transport process.

Compared with passive fillers, active fillers own stronger enhancement effect on the ionic conductivity of SPEs. This is mainly due to the intrinsic high bulk ionic conductivity of active ceramics. There are several theories to explain this phenomenon [73, 74]:

1. There are a lot of continuous defects in these structures, and the activation energy is low.
2. The ionic conductivity is achieved by concerted hopping of multiple ions instead of single ion.
3. The sublattice is highly disordered and thus the hopping between lattices won't be disturbed.

For these reasons, these materials are also called super ionic conductors. According to the difference of structure, these materials can be roughly divided into six categories [75]: NASICON (Na super ionic conductor)-type [76], LISICON (Lithium super ionic conductor)-type [77], Perovskite-type [78], Garnet-type [79], Li<sub>3</sub>N-type [80] and BPO<sub>4</sub>-type [81]. Table 2 summarizes typical super ionic conductors and their ionic conductivity under room temperature.

In general, the biggest difference is that there is one more fast Li<sup>+</sup> transport path in PEO-active filler composites, compared with the conducting mechanism in PEO-passive filler composites. As showed in Fig. 3b, Li<sup>+</sup> can transport through PEO body (path 1), polymer-ceramic interfaces (path 2) and ceramic fillers' bodies (path 3). In 2016, Zheng et al. [82] confirmed that Li ions were more likely to transport on path 3 by tracking the moving trail of <sup>6</sup>Li<sup>+</sup> in PEO-LiClO<sub>4</sub>-LLZO system, which confirmed that path 3 is exact the key reason to active fillers' better enhancement effect.

**Table 2 Typical super ionic conductors and their conductivity under room temperature**

Categories	Typical example	Ionic conductivity under room temperature	References
NASICON (NaZr <sub>2</sub> (PO <sub>4</sub> ) <sub>3</sub> )-type	LTP (LiTi <sub>2</sub> (PO <sub>4</sub> ) <sub>3</sub> ) LGP (LiGe <sub>2</sub> (PO <sub>4</sub> ) <sub>3</sub> ) LAGP, LATP	10 <sup>-5</sup> –10 <sup>-3</sup> S/cm	[75]
LISICON (Li <sub>2+2x</sub> Zn <sub>1-x</sub> GeO <sub>4</sub> )- type	LZG (Li <sub>1.4</sub> Zn(GeO <sub>4</sub> ) <sub>4</sub> )	10 <sup>-7</sup> S/cm	[77]
Perovskite-type	LLTO	2 × 10 <sup>-5</sup> S/cm	[78]
Garnet-type	LLZO	5.25 × 10 <sup>-5</sup> S/cm	[83, 84]
Li <sub>3</sub> N-type	Li <sub>3</sub> N	10 <sup>-3</sup> S/cm (perpendicular to c axis)	[80]
BPO <sub>4</sub> -type	Li <sub>x</sub> B <sub>1-x/3</sub> PO <sub>4</sub>	10 <sup>-7</sup> –10 <sup>-6</sup> S/cm	[75]

### 3.3 The influence of fillers' concentration, size and shape

Capuano et al. [55] found that the ionic conductivity of SPEs can be improved by small inorganic particles, which can suppress the recrystallization of PEO molecular chains. Furthermore, they pointed out that the concentration of fillers should not be excessive, otherwise it would cause phase discontinuity problem, which led to the negative effect on ionic conductivity. Wang et al. [85–87] studied the PEO-LiClO<sub>4</sub>-LATP system and found that LATP fillers had a maximum concentration of 15 wt%. At this value, the ionic conductivity of the system reached the maximum value of 1.387 × 10<sup>-5</sup> S/cm at 25 °C. As shown in Fig. 4b, when the concentration of inorganic fillers in the system was below this value, the crystallinity of PEO decreased with the increase of filler concentration, and the ionic conductivity increased. Such phenomena can be attributed to the enhancement effect which has been clearly described above. When the concentration was above this value, the crystallinity of PEO increased with the increase of filler concentration, which resulted in the decrease of the ionic conductivity. This may due to the crystallization site effect and molecular interaction between polymer chains, which may lead to lower mobility of Li<sup>+</sup> [88]. As a consequence, the concentration of inorganic fillers is usually restricted to 10-20 wt% of the SPEs in order to get the highest ionic conductivity [89]. Reference concentrations of common inorganic fillers are listed in Table 3.

Li et al. [90] explained the influence of inorganic particles' size on the enhancement effect by molecular dynamics (MD) simulation: lithium salts could not fully dissociate in PEO base to produce free-Li<sup>+</sup>. A considerable number of Li<sup>+</sup> still existed in the form of ion clusters with different sizes. Inorganic fillers could inhibit

**Table 3 Reference concentration of common inorganic fillers**

Fillers	Systems	Concentration of fillers	Maximum ionic conductivity	References
LiAlO <sub>2</sub>	PEO-LiTFSI-15 wt% SN	10 wt%	$1.36 \times 10^{-5}$ S/cm at 30 °C	[64]
LATP	PEO-LiClO <sub>4</sub>	15 wt%	$1.378 \times 10^{-3}$ S/cm at 100 °C and $1.387 \times 10^{-5}$ S/cm at 25 °C	[95]
LLTO	PEO-LiN(SO <sub>2</sub> CF <sub>2</sub> CF <sub>3</sub> ) <sub>2</sub>	20 wt%	$5.0 \times 10^{-4}$ S/cm at room temperature	[87]
LLZO	PEO-LiClO <sub>4</sub>	15 wt%	$9.5 \times 10^{-6}$ S/cm at 20 °C and $1.1 \times 10^{-4}$ S/cm at 40 °C	[96]

the formation of such ion cluster and promote the dissociation of LiX, and thus provided more free-Li<sup>+</sup>. In addition, ceramic fillers' repulsive surface could promote the movement of molecular chains and reduce the viscosity of SPEs [91], then increased the transport velocity of Li<sup>+</sup>. Furthermore, they pointed out that the smaller the inorganic fillers were, the stronger enhance effect they would exhibit due to the increased specific surface area. This view was also confirmed by Zhang et al. [92]. In the experiment, the maximum ionic conductivity of PEO-Li<sub>6.4</sub>La<sub>3</sub>Zr<sub>1.4</sub>Ta<sub>0.6</sub>O<sub>12</sub> (LLZTO) system could increase to  $2.1 \times 10^{-4}$  S/cm at 30 °C when the particle size of LLZTO were decreased to 40 nm. Such maximum ionic conductivity could only reach  $1.3 \times 10^{-5}$  S/cm and  $3.8 \times 10^{-6}$  S/cm when the size of LLZTO were 400 nm and 10 μm [93], respectively.

The shape of fillers also has impact on their enhancement ability. Through the comparative study of PAN-LLTO electrolytes, Liu et al. [69] found that the ionic conductivity of ceramic-free SPEs was  $3.62 \times 10^{-7}$  S/cm at 30 °C, while such number in systems with LLTO particles, systems with disorderly LLTO nanowires and systems with well-aligned LLTO nanowires were  $1.02 \times 10^{-6}$  S/cm,  $5.40 \times 10^{-6}$  S/cm and  $6.05 \times 10^{-5}$  S/cm, respectively. These results indicate the importance of a continuous Li<sup>+</sup> transport pathway [94], which is shown in Fig. 3e. Specifically, if the fillers' surface orientation is close to the ideal transport direction of Li<sup>+</sup>, Li<sup>+</sup> is likely to move quickly without disturbance.

### 3.4 Preparation methods

Widely used preparation methods for composite SPEs include solvent casting [97, 98] and thermocompression [99–101]. Each method has its own advantages. For example, the membrane produced by solvent casting own good flexibility and ductility due to the residual liquid components in the body. Ceramic particles can be dispersed uniformly via the stirring process. For thermocompression, there is no organic solvent involved in the whole process, and the contact between ingredients and the air can be largely avoided. Therefore, the performance of membrane obtained by this method is more stable. Besides, this method is more convenient


and time-saving. So, it is important to adopt appropriate preparation method according to different needs.

Since polymer base and lithium salts normally have good solubility in organic solvent, it is convenient to mix the components of SPEs and then cast with the help of organic solvent. This method is so called solvent casting. The basic procedure of solvent casting is shown in Fig. 5a. First, polymer, lithium salts and fillers are added into organic solvent, which is usually acetonitrile, in a certain proportion. Then, the mixture will be stirred for a long time to make sure that polymer and lithium salts are fully dissolved and inorganic fillers are dispersed uniformly. After that, the ultrasound is used to clear all the bubbles in the vial and make the composition of the mixture more uniform. Later, the colloidal solution will be casted on Teflon overlay and dried in fume hood. Until the organic solvent is totally volatilized, the membrane can be peeled off Teflon and the casting procedure is complete. Usually, the resultant film is transparent by this method.

In thermocompression, there is no organic solvent serving as medium for mixing ingredients, which is the biggest difference from solvent casting. The raw materials are mechanically mixed by ball milling, and the film is directly formed by hot pressing owing to the good flexibility and ductility of polymer. The basic steps of thermocompression are shown in Fig. 5b. First, polymer and inorganic fillers are dried in vacuum at different temperatures, due to the relatively low melting temperature of polymer. Then, sieve the ingredients to get small particles. The small particles are mixed and sealed in polyethylene bottles in a certain proportion. After that, they will be processed by ball milling to get uniform composite powder. Take aluminum foil to pack the powder and place it between two stainless steel plates and use hot press to process the powder to form membrane. After cooling, the homogeneous membrane can be easily peeled off the aluminum foil. As a result, the films obtained by this method are usually semi-transparent.

In general, the inevitable residual liquid in solvent casting can serve as plasticizer to change the overall performance of SPEs. On one hand, the introduction of liquid phase improves the ionic conductivity and ductility of the electrolyte. On the other hand, it sacrifices the strength





and thermal stability because the electrolyte loses the property of all-solid-state. By contrast, the mechanical strength and thermal stability of the membranes produced by thermocompression are higher because this method is solvent-free and can greatly avoid the contact between samples and the air in the process [102].

#### 4 Conclusion

In this paper, the origin and development of SPEs have been described. The influence of  $M_n$ , LiX, temperature, EO/Li and end groups on the ionic conductivity of SPEs is also clarified by analyzing the conductive mechanism of PEO-LiX matrices. Composite SPEs, as one of the most efficient ways to improve the ionic conductivity of the whole electrolyte, is also introduced. Two possible mechanisms of polymer-filler interfaces in PEO-passive filler composites for improving ionic conductivity are clarified. Different from PEO-passive filler composites,  $\text{Li}^+$  can be transported through the ceramic body in polymer-active filler composites. The existence of such express path endows active fillers with stronger enhancement ability. The influence of size, shape and concentration of ceramic fillers on their ability to improve ionic conductivity are also demonstrated. Moreover, two frequently used production methods of SPEs are compared. Five conclusions can provide guidance for the preparation of composite SPEs with better performance:

1. The choice of PEO substrate. Although PEO with low  $M_n$  can get relatively high ionic conductivity, it is more like a liquid than a solid at room temperature, which is contrary to the initial intention of using SPEs. Therefore,  $M_n$  should be relatively large if allowed. Typically, PEO600k is frequently used.
2. The choice of LiX. LiX should own high solubility and high degree of disassociation in PEO, which are necessary for providing enough free- $\text{Li}^+$ . LiTFSI, as a new generation of lithium salt material, can meet above requirements well.
3. The choice of  $\text{Li}^+$  concentration. Generally, when EO/Li = 12–16, the system can obtain the maximum ionic conductivity.
4. The choice of ceramic fillers. Compared with passive fillers, active fillers provide much more  $\text{Li}^+$  express channels in their bodies. Therefore, active fillers are supposed to be the first choice when choosing ceramic additives. Besides, the concentration of ceramic fillers is usually restricted to 10–20 wt% to obtain the highest ionic conductivity. Moreover, the orientation of ceramic fillers is supposed to be close to the ideal  $\text{Li}^+$  transport path between electrodes.
5. The choice of preparation method. Thermocompression method can get rid of organic solvent and avoid contact with the air during the process, which result in more stable productions. Solvent casting method can make the ceramic fillers disperse more uniformly,

and result in more ductile productions. It is necessary to choose different method depending on situations.

### Abbreviations

DMC: Dimethyl carbonate; EC: Ethylene carbonate; EO: Ether oxygen; LIBs: Lithium-ion batteries; LISICON: Lithium super ionic conductor; LiTFSI: Lithium bis(trifluoromethanesulfonyl)imide; LiX: Lithium salt; LAGP:  $\text{Li}_{1+x}\text{Al}_x\text{Ge}_{2-x}(\text{PO}_4)_3$ ; LATP:  $\text{Li}_{1+x}\text{Al}_x\text{Ti}_{2-x}(\text{PO}_4)_3$ ; LLTO:  $\text{Li}_{3-x}\text{La}_{2/3-x}\text{TiO}_3$ ; LLZO:  $\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$ ; LLZTO:  $\text{Li}_6\text{La}_3\text{Zr}_{1.4}\text{Ta}_{0.6}\text{O}_{12}$ ;  $M_n$ : Molecular weight; MD: Molecular dynamics; NASICON: Na super ionic conductor; PEG: Polyethylene glycol; PEGM: Poly(ethylene glycol)methyl ether; PEGDM: Poly(ethylene glycol) dimethyl ether; PS: Polystyrene; PAN: Polyacrylonitrile; PC: Propylene carbonate; PMMA: Polymethyl methacrylate; PVDF: Polyvinylidene fluoride; PVP: Polyvinyl pyrrolidone; PEO: Polyethylene oxide; SPEs: Solid polymer electrolytes;  $T_{1/4}$ : Transference number;  $T_g$ : Glass transition temperature;  $T_m$ : Melting point; YSZ:  $\text{Y}_2\text{O}_3$ -doped  $\text{ZrO}_2$ .

### Acknowledgements

The authors also thank Joint Work Plan for Research Projects under the Clean Vehicles Consortium at U.S. and China—Clean Energy Research Center (CERC-CVC2.0, 2016–2020).

### Authors' contributions

All authors have participated in analyzing data and writing the manuscript. All authors read and approved the final manuscript.

### Funding

This work was funded by the Ministry of Science and Technology of China (No. 2019YFE0100200), the Tsinghua University Initiative Scientific Research Program (No. 2019Z02UTY06) and Tsinghua-Foshan Scientific Research Program (No. 2019THFS0132).

### Availability of data and materials

The test materials and data are available from the corresponding author on reasonable request.

### Competing interests

The authors declare that they have no competing interest.

### Author details

<sup>1</sup> Department of Applied Physics and Applied Mathematics, Columbia University, New York, NY 10027, USA. <sup>2</sup> Institute of Nuclear and New Energy Technology, Tsinghua University, Beijing 100084, China.

Received: 21 October 2020 Accepted: 18 December 2020

Published online: 10 January 2021

### References

- Hou et al., Thermal runaway of Lithium-ion batteries employing  $\text{LiN}(\text{SO}_2\text{F})_2$ -based concentrated electrolytes. *Nat. Commun.* **11**(1), 5100 (2020)
- Zhao, H., et al., Challenges of fast charging for electric vehicles and the role of red phosphorous as anode material: review. *Energies* **12**:20 (2019)
- Guo et al., A polymeric composite protective layer for stable Li metal anodes. *Nano Converg.* **7**(1), 21 (2020)
- Wang et al., Reviewing the current status and development of polymer electrolytes for solid-state lithium batteries. *Energy Storage Mater.* **33**, 188–215 (2020)
- Norby, T., Early history of solid state ionics. *MRS Proc.* **135**:25 (2011)
- Fenton, J.M., Parker, P.V., Wright, Complexes of alkali-metal ions with poly(ethylene oxide). *Polymer* **14**(11), 589–589 (1973)
- Armand, M., et al., Fast ion transport in solids **131**:23 (1979)
- Arya, A.L., Sharma, Polymer electrolytes for lithium ion batteries: a critical study. *Ionics* **23**(3), 497–540 (2017)
- Ngai et al., A review of polymer electrolytes: fundamental, approaches and applications. *Ionics* **22**(8), 1259–1279 (2016)
- Song, Y.Y., Wang, C.C., Wan, Review of gel-type polymer electrolytes for lithium-ion batteries. *J. Power Sources* **77**(2), 183–197 (1999)
- Tan et al., Recent advancements in polymer-based composite electrolytes for rechargeable lithium batteries. *Electrochim. Energy Rev.* **1**(2), 113–138 (2018)
- Devaux et al., Optimization of block copolymer electrolytes for lithium metal batteries. *Chem. Mater.* **27**(13), 4682–4692 (2015)
- Bouchet et al., Charge transport in nanostructured PS-PEO-PS triblock copolymer electrolytes. *Macromolecules* **47**(8), 2659–2665 (2014)
- Weston, B.C.H., Steele, Effects of inert fillers on the mechanical and electrochemical properties of lithium salt poly (ethylene-oxide) polymer electrolytes. *Solid State Ionics* **7**(1), 75–79 (1982)
- Cao et al., Dispersibility of nano- $\text{TiO}_2$  on performance of composite polymer electrolytes for Li-ion batteries. *Electrochim. Acta* **111**, 674–679 (2013)
- Cao et al., In situ prepared nano-crystalline  $\text{TiO}_2$ -poly(methyl methacrylate) hybrid enhanced composite polymer electrolyte for Li-ion batteries. *J. Mater. Chem. A* **1**(19), 5955–5961 (2013)
- He et al., In situ composite of nano  $\text{SiO}_2$ -P(VDF-HFP) porous polymer electrolytes for Li-ion batteries. *Electrochim. Acta* **51**(6), 1069–1075 (2005)
- Li et al., Interface properties between a lithium metal electrode and a poly(ethylene oxide) based composite polymer electrolyte. *J. Power Sources* **94**(2), 201–205 (2001)
- Rahman et al., Fabrication and characterization of a solid polymeric electrolyte of PAN- $\text{TiO}_2$ -LiClO<sub>4</sub>. *J. Appl. Polym. Sci.* **115**(4), 2144–2148 (2010)
- Tan et al., The effects of ceramic fillers on the PMMA-based polymer electrolyte systems. *Ionics* **13**(5), 361–364 (2007)
- Arof et al., Efficiency enhancement by mixed cation effect in dye-sensitized solar cells with a PVdF based gel polymer electrolyte. *Int. J. Hydr. Energy* **39**(6), 2929–2935 (2014)
- Basha et al., Preparation and dielectric properties of PVP-based polymer electrolyte films for solid-state battery application. *Polym. Bull.* **75**(3), 925–945 (2017)
- Takeoka, H., Ohno, E., Tsuchida, Recent advancement of ion-conductive polymers. *Polym. Adv. Technol.* **4**(23), 53–73 (1993)
- Meyer, Polymer electrolytes for lithium-ion batteries. *Adv. Mater.* **10**(6), 439–448 (1998)
- Yao et al., Review on polymer-based composite electrolytes for lithium batteries. *Front Chem* **7**, 522 (2019)
- Xue, D., He, X., Xie, Poly(ethylene oxide)-based electrolytes for lithium-ion batteries. *J. Mater. Chem. A* **3**(38), 19218–19253 (2015)
- Quartarone, P., Mustarelli, A., Magistris, PEO-based composite polymer electrolytes. *Solid State Ionics* **110**(1–2), 1–14 (1998)
- Sadoway, Block and graft copolymer, electrolytes for high-performance, solid-state, lithium batteries. *J. Power Sources* **129**(1), 1–3 (2004)
- Le Nest et al., A new polymer network for ionic conduction. *Electrochim. Acta* **37**(9), 1585–1588 (1992)
- Hu, S., Z. Zhang, and S. Fang, Advanced development of solid polymer electrolytes used in lithium batteries. *Polym. Bull.* **15**: 23 (2001)
- Zhao et al., Advances in ionic conductive polymer electrolytes. *Progress Chem.* **14**(5), 374–383 (2002)
- Geiculescu et al., Solid polymer electrolytes from polyanionic lithium salts based on the LiTFSI anion structure. *J. Electrochem. Soc.* **151**(9), A1363–A1368 (2004)
- Gorecki et al., Physical-properties of solid polymer electrolyte peo(Litfsi) complexes. *J. Phys. Condens. Matter* **7**(34), 6823–6832 (1995)
- Wang et al., Spectroscopic studies on interactions and microstructures in propylene carbonate—LiTFSI electrolytes. *J. Raman Spectrosc.* **32**(11), 900–905 (2001)
- Borodin, G.D., Smith, LiTFSI structure and transport in ethylene carbonate from molecular dynamics simulations. *J. Phys Chem B* **110**(10), 4971–4977 (2006)
- Marzantowicz et al., Influence of crystalline complexes on electrical properties of PEO: LiTFSI electrolyte. *Electrochim. Acta* **53**(4), 1518–1526 (2007)

37. C.D. Robitaille, D. Fauteux, Phase-Diagrams and Conductivity Characterization of Some PEO-Lix Electrolytes. *J. Electrochem. Soc.* **133**(2), 315–325 (1986)
38. M. Marzantowicz et al., Crystalline phases, morphology and conductivity of PEO: LiTFSI electrolytes in the eutectic region. *J. Power Sources* **159**(1), 420–430 (2006)
39. S. Lascaud et al., Phase-diagrams and conductivity behavior of poly(ethylene oxide) molten-salt rubbery electrolytes. *Macromolecules* **27**(25), 7469–7477 (1994)
40. H. Ericson et al., A Raman spectroscopic investigation of methoxyl end capped PPO doped with NaCF<sub>3</sub>SO<sub>3</sub>. *Electrochim. Acta* **43**(10–11), 1401–1405 (1998)
41. X.F. Yang et al., Determining the limiting factor of the electrochemical stability window for PEO-based solid polymer electrolytes: main chain or terminal –OH group? *Energy Environ. Sci.* **13**(5), 1318–1325 (2020)
42. Devaux, D., et al., Mechanism of ion transport in PEO/LiTFSI complexes: Effect of temperature, molecular weight and end groups. *Solid State Ionics* **227**:119–127
43. Zewde, B.W., et al., enhanced lithium battery with polyethylene oxide-based electrolyte containing silane–Al<sub>2</sub>O<sub>3</sub> ceramic filler **6**(8):1400–1405 (2013)
44. Zhang, N., et al., Composite solid electrolyte PEO/SN/LiAlO<sub>2</sub> for a solid-state lithium battery **54**(13):9603–9612 (2019)
45. Y. Zhao et al., A promising PEO/LAGP hybrid electrolyte prepared by a simple method for all-solid-state lithium batteries. **295**, 65–71 (2016)
46. L. Zhu et al., A novel solid PEO/LLTO-nanowires polymer composite electrolyte for solid-state lithium-ion battery. *LLTO* **292**, 718–726 (2018)
47. Wan, Z., et al., Low resistance-integrated all-solid-state battery achieved by Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub> nanowire upgrading polyethylene oxide (PEO) composite electrolyte and PEO cathode binder **29**(1):1805301 (2019)
48. Chen, L., et al., PEO/garnet composite electrolytes for solid-state lithium batteries: from “ceramic-in-polymer” to “polymer-in-ceramic” **46**:176–184 (2018)
49. Y.J. Lim, Y.H. An, N.J. Jo, Polystyrene–Al<sub>2</sub>O<sub>3</sub> composite solid polymer electrolyte for lithium secondary battery. *Nanoscale Res. Lett.* **7**(1), 19 (2012)
50. S.A. Suthanthiraraj, D.J. Sheeba, Structural investigation on PEO-based polymer electrolytes dispersed with Al<sub>2</sub>O<sub>3</sub> nanoparticles. *Ionics* **13**(6), 447–450 (2007)
51. Gondaliya, N., et al. Dielectric and conductivity in silver-poly (ethylene oxide) solid polymer electrolytes dispersed with SiO<sub>2</sub> nanoparticles. *Am. Instit. Phys. Conf. Series.* 2010
52. F. Croce et al., Nanocomposite polymer electrolytes for lithium batteries. *Polymer* **394**(6692), 456–458 (1998)
53. H.M. Xiong et al., Stable polymer electrolytes based on polyether-grafted ZnO nanoparticles for all-solid-state lithium batteries. *J. Mater. Chem.* **16**(14), 1345–1349 (2006)
54. X. Guo, R.Z. Yuan, On the grain-boundaries of ZrO<sub>2</sub>-based solid-electrolyte. *Solid State Ionics* **80**(1–2), 159–166 (1995)
55. F. Capuano, F. Croce, B. Scrosati, Composite polymer electrolytes. *J. Electrochem. Soc.* **138**(7), 1918–1922 (1991)
56. B. Kumar, L.G. Scanlon, Polymer-ceramic composite electrolytes. *J. Power Sources* **52**(2), 261–268 (1994)
57. W. Wieczorek, Z. Florjanczyk, J.R. Stevens, Composite polyether based solid electrolytes. *Electrochim. Acta* **40**(13–14), 2251–2258 (1995)
58. F. Croce et al., Role of the ceramic fillers in enhancing the transport properties of composite polymer electrolytes. *Electrochim. Acta* **46**(16), 2457–2461 (2001)
59. S. Chung et al., Enhancement of ion transport in polymer electrolytes by addition of nanoscale inorganic oxides. **97**, 644–648 (2001)
60. G. Appetecchi et al., Transport and interfacial properties of composite polymer electrolytes. *Electrochim Acta* **45**(8–9), 1481–1490 (2000)
61. W. Liu et al., Improved lithium ionic conductivity in composite polymer electrolytes with oxide-ion conducting nanowires. *ACS Nano* **10**(12), 11407–11413 (2016)
62. J.X. Yang, Y.Z. Jia, Z.X. Yao, Study on the lithium solid electrolytes of Li<sub>3</sub>N–Li<sub>3</sub>Bi–LiCl ternary system—2Li(3)Bi center dot 3LiCl lithium solid electrolyte. *Solid State Ionics* **96**(3–4), 215–218 (1997)
63. Kitahama, K., et al., Synthesis and Nmr-study of solid electrolytes in the system Li<sub>3</sub>N–LiCl. *Solid State Ionics* **3**: 335–339 (1981)
64. N. Zhang et al., Composite solid electrolyte PEO/SN/LiAlO<sub>2</sub> for a solid-state lithium battery. *J. Mater. Sci.* **54**(13), 9603–9612 (2019)
65. I. Villarreal, E. Morales, J.L. Acosta, Ionic conductivity and spectroscopic characterisation of γ-LiAlO<sub>2</sub>-filled polymer electrolytes. *Angew. Makromol. Chem.* **266**(1), 24–29 (1999)
66. Meesala, Y., et al., All-solid-state li-ion battery using Li<sub>1.5</sub>Al<sub>0.5</sub>Ge<sub>1.5</sub>(PO<sub>4</sub>)<sub>3</sub> as electrolyte without polymer interfacial adhesion. *J. Phys. Chem. C* **122**(26): 14383–14389 (2018)
67. Liu, L.H., et al., Li<sub>1.4</sub>Al<sub>0.4</sub>Ti<sub>1.6</sub>(PO<sub>4</sub>)<sub>3</sub> nanoparticle-reinforced solid polymer electrolytes for all-solid-state lithium batteries. *Solid State Ionics* **331**:89–95 (2019)
68. S. Yu et al., Insights into a layered hybrid solid electrolyte and its application in long lifespan high-voltage all-solid-state lithium batteries. *J. Mater. Chem. A* **7**(8), 3882–3894 (2019)
69. W. Liu et al., Enhancing ionic conductivity in composite polymer electrolytes with well-aligned ceramic nanowires. *Nat. Energy* **2**(5), 17035 (2017)
70. A.-N. Wang et al., Mechanical properties of the solid electrolyte Al-substituted Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub> (LLZO) by utilizing micro-pillar indentation splitting test. *J. Eur. Ceram. Soc.* **38**(9), 3201–3209 (2018)
71. J. Li et al., A promising composite solid electrolyte incorporating LLZO into PEO/PVDF matrix for all-solid-state lithium-ion batteries. *Ionics* **26**(3), 1101–1108 (2020)
72. S. Yu et al., Elastic properties of the solid electrolyte Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub> (LLZO). *Chem. Mater.* **28**(1), 197–206 (2016)
73. C.R.A. Catlow, Atomistic mechanisms of ionic transport in fast-ion conductors. *J. Chem. Soc. Faraday Trans.* **86**(8), 1167–1176 (1990)
74. X. He, Y. Zhu, Y. Mo, Origin of fast ion diffusion in super-ionic conductors. *Nat Commun* **8**(1), 15893 (2017)
75. A. Manthiram, X.W. Yu, S.F. Wang, Lithium battery chemistries enabled by solid-state electrolytes. *Nat. Rev. Mater.* **2**(4), 16103 (2017)
76. J.B. Goodenough, H.Y.P. Hong, J.A. Kafalas, Fast Na<sup>+</sup>-ion transport in skeleton structures. *Mater. Res. Bull.* **11**(2), 203–220 (1976)
77. H.Y.P. Hong, Crystal-structure and ionic-conductivity of Li<sub>14</sub>zn(Geo<sub>4</sub>)<sub>4</sub> and other new Li<sup>+</sup> superionic conductors. *Mater. Res. Bull.* **13**(2), 117–124 (1978)
78. Y. Inaguma et al., High ionic-conductivity in lithium lanthanum titanate. *Solid State Commun.* **86**(10), 689–693 (1993)
79. C.A. Geiger et al., Crystal chemistry and stability of “Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub>” garnet: a fast lithium-ion conductor. *Inorg. Chem.* **50**(3), 1089–1097 (2011)
80. Alpen, U., Li<sub>3</sub>N: A promising Li ionic conductor. *J. Solid State Chem.* **29**(3):379–392 (1979)
81. E. Kelder, A new ceramic lithium solid electrolyte for rechargeable swing type batteries. *Solid State Ionics* **85**(1–4), 285–291 (1996)
82. J. Zheng, M.X. Tang, Y.Y. Hu, Lithium ion pathway within Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub>-polyethylene oxide composite electrolytes. *Angewandte Chem Int Edition* **55**(40), 12538–12542 (2016)
83. R.J. Chen et al., Preparation and performance of novel LLTO thin film electrolytes for thin film lithium batteries. *Chin. Sci. Bull.* **57**(32), 4199–4204 (2012)
84. Y.L. Xiong et al., Effects of annealing temperature on structure and optoelectric properties of ion-conducting LLTO thin films prepared by RF magnetron sputtering. *J. Alloy. Compd.* **509**(5), 1910–1914 (2011)
85. Y.J. Wang et al., Conductivity studies of plasticized PEO-Lithium chlorate-FIC filler composite polymer electrolytes. *Mater. Lett.* **59**(24–25), 3021–3026 (2005)
86. Wang, Y.J., et al., Characterization of (PEO)LiClO<sub>4</sub>-Li<sub>1.3</sub>Al<sub>0.3</sub>Ti<sub>1.7</sub>(PO<sub>4</sub>)<sub>3</sub> composite polymer electrolytes with different molecular weights of PEO. *J. Appl. Polym. Sci.* **102**(5):4269–4275 (2006)
87. C. Wang, X.-W. Zhang, A.J. Appleby, Solvent-free composite PEO-ceramic fiber/mat electrolytes for lithium secondary cells. *J. Electrochem. Soc.* **152**(1), A205 (2005)
88. Ji, K.-S., et al., Role of functional nano-sized inorganic fillers in poly(ethylene) oxide-based polymer electrolytes **117**(1–2):124–130 (2003)
89. Z.X. Wang, X.J. Huang, L.Q. Chen, Understanding of effects of nano-Al<sub>2</sub>O<sub>3</sub> particles on ionic conductivity of composite polymer electrolytes. *Electrochim. Solid State Lett.* **6**(11), E40–E44 (2003)
90. Q. Li, H. Ardebili, Atomistic investigation of the nanoparticle size and shape effects on ionic conductivity of solid polymer electrolytes. *Solid State Ionics* **268**, 156–161 (2014)

91. O. Borodin et al., Molecular dynamics study of the influence of solid interfaces on poly(ethylene oxide) structure and dynamics. *Macromolecules* **36**(20), 7873–7883 (2003)
92. J.X. Zhang et al., Flexible and ion-conducting membrane electrolytes for solid-state lithium batteries: dispersion of garnet nanoparticles in insulating polyethylene oxide. *Nano Energy* **28**, 447–454 (2016)
93. C. Hu, Y. Shen, L. Chen, Recent advances in nanostructured composite solid electrolyte. *Curr. Opin. Electrochem.* **22**, 51–57 (2020)
94. J. Yue, S. Xin, Y.-G. Guo, Recent progress and design principles of nanocomposite solid electrolytes. *Curr. Opin. Electrochem.* **22**, 195–202 (2020)
95. Wang, Y.-J., Y. Pan, Li<sub>1.3</sub>Al<sub>0.3</sub>Ti<sub>1.7</sub>(PO<sub>4</sub>)<sub>3</sub> filler effect on (PEO)LiClO<sub>4</sub> solid polymer electrolyte. *J. Polym. Sci. Part B* **43**(6):743–751 (2005)
96. X.Y. Tao et al., Solid-State lithium sulfur batteries operated at 37 degrees C with composites of nanostructured Li<sub>7</sub>La<sub>3</sub>Zr<sub>2</sub>O<sub>12</sub>/carbon foam and polymer. *Nano Lett.* **17**(5), 2967–2972 (2017)
97. B. Kumar, L.G. Scanlon, Polymer-ceramic composite electrolytes: conductivity and thermal history effects. *Solid State Ionics* **124**(3–4), 239–254 (1999)
98. B. Kumar et al., Structural evolution and conductivity of PEO: LiBF<sub>4</sub>-MgO composite electrolytes. *Electrochim. Acta* **46**(10–11), 1515–1521 (2001)
99. Gray, F.M., J.R. MacCallum, C.A. Vincent, Poly(Ethylene Oxide)—LiCl<sub>3</sub>SO<sub>3</sub>—polystyrene electrolyte systems. *Solid State Ionics* **18-9**(part-P1):282–286 (1986)
100. G.B. Appetecchi et al., Hot-pressed, dry, composite, PEO-based electrolyte membranes. *J. Power Sources* **114**(1), 105–112 (2003)
101. Appetecchi, G.B., et al., Hot-pressed, solvent-free, nanocomposite, PEO-based electrolyte membranes II. All solid-state Li/LiFePO<sub>4</sub> polymer batteries. *J. Power Sources* **124**(1):246–253 (2003)
102. J.W. Rhim et al., Effect of the processing methods on the performance of polylactide films: thermocompression versus solvent casting. *J. Appl. Polym. Sci.* **101**(6), 3736–3742 (2006)

### Publisher's Note

Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Submit your manuscript to a SpringerOpen<sup>®</sup> journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

---

Submit your next manuscript at ► [springeropen.com](https://www.springeropen.com)

---