Quantitative equivalence between polymer nanocomposites and thin polymer films

AMITABH BANSAL^{1,2}, HOICHANG YANG^{2,3}, CHUNZHAO LI^{2,4}, KILWON CHO³, BRIAN C. BENICEWICZ^{2,4}, SANAT K. KUMAR^{2,5}* AND LINDA S. SCHADLER^{1,2}*

¹Department of Materials Science and Engineering, Rensselaer Polytechnic Institute, Troy, New York 12180, USA

³Department of Chemical Engineering, Pohang University of Science and Technology, Pohang, Kyungbuk 790-784, Korea

⁴Department of Chemistry and Chemical Biology, Rensselaer Polytechnic Institute, Troy, New York 12180, USA

⁵Department of Chemical and Biological Engineering, Rensselaer Polytechnic Institute, Troy, New York 12180, USA

*e-mail: kumar@rpi.edu; schadl@rpi.edu

Published online: XX Month XXXX; doi:10.1038/nmatXXXX

The thermomechanical responses of polymers, which provide limitations to their practical use, are favourably 12 altered by the addition of trace amounts of a nanofiller. A3 However, the resulting changes in polymer properties Δ4 are poorly understood, primarily due to the non-uniform spatial distribution of nanoparticles. Here we show that the A7 thermomechanical properties of 'polymer nanocomposites' are quantitatively equivalent to the well-documented case of planar polymer films. We quantify this equivalence Δa by drawing a direct analogy between film thickness and A10 an appropriate experimental interparticle spacing. We A11 A12 show that the changes in glass-transition temperature with decreasing interparticle spacing for two filler A13 A14 surface treatments are quantitatively equivalent to the corresponding thin-film data with a non-wetting and A15 a wetting polymer-particle interface, respectively. Our A16 A17 results offer new insights into the role of confinement on the glass transition, and we conclude that the mere A18 presence of regions of modified mobility in the vicinity of A19 the particle surfaces, that is, a simple two-layer model, is A20 insufficient to explain our results. Rather, we conjecture A21 that the glass-transition process requires that the A22 interphase regions surrounding different particles interact. A23

C omputer simulations¹ on the thermomechanical behaviour of polymers with regularly spaced nanoparticles suggest that they should be akin to thin polymer films. This result is found to hold regardless of whether the polymer wets the filler or not. Although this theoretical prediction is apparently well known, it has not been quantitatively verified because experiments typically deal with nanoparticles or nanosilicates, which are nonuniformly distributed in space²⁻¹². We are motivated to quantify experimentally this analogy as it could simplify our understanding of both of these situations, especially polymer nanocomposites, which are of significant practical interest.

Considerable effort has been focused on delineating the role of confinement on the glass transition temperature, $T_{\rm g}$, of thin planar polymer films¹³⁻³²(C. B. Roth and J. R. Dutcher, manuscript in preparation). Two experimental observations are now recognized as being universal: (i) T_g is a function of the film thickness, h; and (ii) the magnitude and sign of the $T_{\rm g}$ shift depends upon polymer– substrate interactions. Polymer films can either be free standing, supported on a substrate or sandwiched between two hard walls. The largest reductions are observed for free-standing films, with the change being twice as large as that found for supported films of the same h (ref. 20). A film properly sandwiched between two impenetrable, wetting walls, on the other hand, shows essentially no change in T_g for any h (ref. 33). These data support the notion that a free surface, or a non-wetting interface between a hard surface and a polymer, is necessary for reductions in T_g (refs 15,16,34). On the basis of this conjecture, surface-layer models that postulate a mobile 'liquid-like' layer have been developed and found to explain the experimental observations of a reduction in T_{g} (ref. 20):

$$T_{\rm g}(h) = T_{\rm g}^{\rm bulk} + \frac{2\xi(T_{\rm g}(h))}{h} (T_{\rm g}^{\rm surf} - T_{\rm g}^{\rm bulk})$$
(1) 30

where T_{g}^{bulk} is the bulk T_{g} and $\xi(T_{g}(h))$ is the thickness of the surface region with a glass transition temperature of T_{e}^{surf} .

Here, we focus on the changes in polymer T_g with increasing filler content in a polymer nanocomposite. For untreated silica surfaces, which are non-wetting to polystyrene (PS), we show that the T_g changes with filler content closely track the results obtained for planar free-standing films. In contrast, for modified silica surfaces that provide intimate surface–polymer

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

31

32

33

34

35

36

37

²Rensselaer Nanotechnology Center, Rensselaer Polytechnic Institute, Troy, New York 12180, USA



Figure 1 SEM images showing fracture surfaces. a, A 15 wt% untreated SiO₂/PS nanocomposite. Nanoparticles reside inside voids indicating dewetting of PS from SiO₂ surfaces. **b**, A 2 wt% SiO₂-g-PS/PS nanocomposite (see the Methods section). The contrast between the filler and matrix is low because the surface is covered by a layer of polymer. Furthermore, in contrast to the untreated surface, the particle surface of the SiO₂-g-PS is well adhered to the PS. The surfaces were prepared by breaking nanocomposite samples under liquid nitrogen.

contact, the changes in T_g with filler content quantitatively follow the trends for capped surfaces. We therefore argue for a quantitative equivalence of the T_g values of thin polymer films and nanocomposites, an analogy we assert will have powerful, potentially far-reaching consequences for our understanding of these closely related situations.

We prepared silica/polystyrene nanocomposites over a broad range of silica loadings and characterized their T_{α} and viscoelastic behaviour (see the Methods section for specific details). Differential scanning calorimetry (DSC), in both heating and cooling modes, 10 gave identical estimates of the $T_{\rm g}$. We first focus on fillers with 11 untreated surfaces. Planar PS thin films are known to dewet from 12 flat SiO_x substrates. Similarly, scanning electron microscope (SEM) 13 images (Fig. 1a) of a fracture surface show cavities around silica 14 nanoparticles that formed during brittle fracture, suggesting that 15 there is imperfect wetting, and hence imperfect bonding, between 16 the polymer and the untreated nanoparticles. Further credence for 17 this assignment comes from X-ray photon correlation spectroscopy 18



Figure 2 The glass-transition behaviour of SiO₂/PS nanocomposites. **a**, Representative DSC traces of SiO₂/PS nanocomposites showing only a single endothermic transition (the T_g) and a distinct reduction in average T_g . **b**, T_g of SiO₂/PS nanocomposites as a function of filler loading. There is some scatter in the data associated with different degrees of aggregation. Samples prepared from MEK and THF show the same trend in depression of T_g but the quantitative difference can be accounted for by variations in particle aggregation.

results, which assert that the particle mobility increases by an 19 order of magnitude at 160 °C when the concentration of filler 20 increases from 2 wt% to 15 wt% silica. On the basis of these 21 findings, we conjecture that there is no polymer inside particle 22 aggregates. (This last issue is further substantiated later.) Consistent 23 with these ideas, and with the literature findings on thin capped 24 films with imperfect polymer-surface bonding²⁵, we find that the 25 nanocomposite T_g decreases with increasing filler content (Fig. 2). 26 Although the inherent errors in our measurements (typically ± 1 K) 27 are relatively large, the overall change in $T_{\rm g}$ over the range of 28 silica compositions studied is much larger, ~ 11 K. This gives us 29 confidence that our trends are robust and well outside experimental 30 error. Note that there is some scatter in the data. For example, 31 the 25 wt% SiO₂ sample shows a higher $T_{\rm g}$ than the 15 wt% and 32 40 wt% samples. We shall discuss this aspect below and establish 33 that it is not a consequence of data scatter but rather due to 34



Figure 3 Representative TEM micrographs of SiO₂/PS nanocomposites at various filler concentrations prepared using MEK. a, 2 wt%. b, 5 wt%. c, 15 wt%. d, An example of measured ligaments for a 5 wt% SiO₂/PS nanocomposite sample. e, Distribution of interparticle spacings measured for four representative concentrations. The plot shows the distribution of 1/h. Note that these distributions are not monotonic with increasing silica content, which is consistent with the results shown in Fig. 1.

differences in the spatial distribution of particles. Qualitatively 1 similar results are obtained regardless of the solvent used to 2 prepare the nanocomposites, that is, methylethylketone (MEK) 3 versus tetrahydrofuran (THF). Such decreases in $T_{\rm g}$ upon addition 4 of nanofillers with a non-wetting interface have been reported 5

previously^{3,9}. However, the analogy between these results and those for thin films have not been quantified so far.

To compare our findings with the literature values of $T_{\rm g}$ on thin films, we characterized the distribution of interparticle spacings (h) from transmission electron microscope (TEM) images for each 10

8

sample (representative examples are shown in Fig. 3a-c). Note that the extent of particle agglomeration increases with increased 2 silica loading. Microtomed samples establish that the particles are 3 uniformly present across the film thickness and that there is no preferential surface segregation of the particles (see Supplementary 5 Information). To quantify the distribution of interparticle spacings we drew lines between pairs of nearest-particle faces, so that each particle was at the centre of a minimally closed polygon (Fig. 3d). This construction, which is similar in spirit to the Voronoi tessalation of space, allows us to identify the maximal 10 11 confinement experienced by each volume of polymer. We further need to account for the fact that the extent of confinement created 12 by two particles changes as we traverse their curved contours. A 13 convenient approximation, which avoids this somewhat ambitious 14 exercise, is to use the minimal value of the face-to-face distance or 15 16 interparticle spacing. We create a probability distribution for this quantity (Fig. 3e) and find that it does not change monotonically 17 with filler content. Rather, the 25 wt% composite has a distribution 18 that falls above the 15 wt% sample. This satisfactorily resolves the 19 trend seen in Fig. 2 where the 25 wt% sample has a smaller $T_{\rm g}$ drop 20 21 than the 15 wt% or the 40 wt% samples.

The most obvious means to complete the analogy between nanocomposites and thin films is to obtain an arithmetic average of the distribution of interparticle spacings, that is, $h^* = \langle h_i \rangle$, where $\langle ... \rangle$ denotes an ensemble average. An equivalent geometric definition is

$$h^{**} = \frac{\text{volume of PS (from TEM)}}{\text{surface area of SiO}_2 (from TEM)}.$$

²⁸ We are motivated to study this second definition as it allows ²⁹ us to study critically the applicability of two-layer models. To ³⁰ elaborate on this point, we note that if each particle/aggregate has a ³¹ layer of thickness ξ with modified T_g associated with it, then the net ³² fraction of material that would be affected would be proportional to

$$\frac{\text{surface area of SiO}_2 \text{ (from TEM)}}{\text{volume of PS (from TEM)}} \equiv \frac{1}{h^{**}}.$$

In the simple case where we consider two planar films with the 34 same surface area but different thicknesses, it follows that $h^{**} = h^*$. 35 Thus, we expect that both h^* and h^{**} should provide equivalent 36 37 descriptions of the nanocomposite data. Figure 4a, which compares thin-film data with the nanocomposite data when h^* and h^{**} 38 are used to characterize the nanocomposites, indeed verifies this 39 assertion, but demonstrates that quantitative agreement is not 40 achieved between the thin films and the nanocomposites on this 41 42 basis. Instead, when h^* or h^{**} are used, the nanocomposite data 43 seem to fall at the right-hand extreme of the thin-film results. 44 We are further persuaded that neither h^* nor h^{**} are accurate descriptors because they predict that the T_{g} of the nanocomposites 45 do not reach the bulk values for h^* (and hence h^{**}) that are as large 46 as 200 nm; in contrast, the thin-film data become dependent on 47 thickness only for films thinner than 100 nm. 48

To make further progress, and as no general theory has been 49 proposed for the depression of $T_{\rm g}$ in confined systems, we utilize 50 the form of equation (1) to describe the h dependence of T_{g} . 51 Thus, we assume that the T_g for each ligament (or the region 52 between two particle aggregates), with thickness h_{i} , is described 53 by a thin film of the same thickness. Following equation (1), we 54 therefore hypothesize that the local distribution of T_{σ} values in the 55 nanocomposites directly reflects the distribution of the function 56 (1/h) (Fig. 3e). It then follows that the mean glass transition 57 temperature of the nanocomposite, $\langle T_g \rangle$, should be quantitatively 58 related to a mean spacing, h^{***} , which is a harmonic mean of 59 the interparticle spacing: $1/h^{***} = \langle 1/h_i \rangle$. The T_g values for the 60 nanocomposites prepared from the two solvents and two different 61



Figure 4 A comparison between the glass-transition responses of PS **nanocomposite and thin PS films. a**, The change in T_{q} of SiO₂/PS and SiO₂-g-PS/PS nanocomposites as a function of average ligament thickness. The x error bar represents a 95% confidence level. Data from the literature on free-standing²⁰ and supported^{14,30} films are shown as open circles: following ref. 20 the thickness for supported films has been multiplied by two to account for the relative surface area of the free surfaces in the two cases. Data are also shown for sandwiched films as open triangles in the case where proper surface-polymer bonding was obtained. The film thicknesses are not shifted in this case. b, The change in T_{a} for SiO₂/PS nanocomposites as a function of h_{z}^{***} and h_{z}^{*} . **c**, The corresponding comparison of the normalized width of the glass-transition process. Please refer to Supplementary Information for DMA results of silica/PS nanocomposites. Open circles represent dielectric data from a variety of frequencies on supported films revealing that frequency had no bearing on the relative width of the relaxation: note that the films had a drop similar to those of supported films²¹. The thickness was therefore multiplied by two to account for the surface effects.

27

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

61

62

63

64

65

66

67

68

69

70

71

72

73

74

75

76

77

78

79



Figure 5 The effect of solvent on the agglomeration of nanoparticles. a,b, TEM images of 15 wt% SiO₂/PS nanocomposites prepared by MEK (a) and THF (b). Although the extents of agglomeration are quite different in the two cases, we note that their T_g shifts can be rationalized by calculating the h_2^{***} values. These results emphasize that particle size is a secondary concern in this context.

PS molecular weights are shown as a function of h^{***} in Fig. 4a. In the legend, the number in parentheses is the molecular weight of the matrix. It is clear that the nanocomposite data as characterized by this h^{***} value fall at the extreme left of the thin film, thus providing an incomplete analogy to the thin films.

At this juncture it is important to realize that, even though we have treated the TEM pictures as being two-dimensional snapshots of the nanocomposite, in fact each TEM slice is a film of thickness \sim 50 nm. The h^{***} values, and also the h^* and h^{**} values, must be modified to include this third dimension. We assume that 10 the centres of the nanoparticles are uniformly distributed in the 11 direction normal to the TEM surfaces, z. The h values that are 12 derived from the TEM pictures must therefore be modified to 13 account for the variation of this z component. For the correction of 14 *h*^{*} we reasonably assume that each *h* is represented by the average 15

$$h_z = \frac{\int \sqrt{h^2 + z^2} dz}{\int dz}$$

the corresponding average h value we denote as h_{a}^{*} .

$$\frac{1}{h_z} = \frac{\int \mathrm{d}z/\sqrt{h^2 + z^2}}{\mathrm{d}z},$$
¹⁹

and the average denoted as h_z^{***} . We do not calculate an analogous value of h_z^{**} , but conjecture that its behaviour tracks that of h_z^{*} . The results of this calculation are shown in Fig. 4b. It is immediately clear that this method of accounting for the thickness of the TEM slices allows h_z^{***} to explain quantitatively the nanocomposite data in the language of the thin films, although h_z^{*} shifts even further to the right-hand extreme of the thin-film data. We therefore conclude that the data from the thin films and the nanocomposites follow the same quantitative trend within experimental uncertainties. Furthermore, although the two solvents MEK and THF yield different extents of aggregation of the nanoparticles and hence different interparticle spacings (Fig. 5), they are found to follow the same relationship, emphasizing its apparent generality. Figure 4c, which compares the normalized width of the glass transition in the two cases, makes this connection even stronger.

A particular concern, which has been addressed previously, is the intercalation of PS into the aggregates. If PS has intercalated into the aggregates, then the reduction of T_{g} for a composite with higher aggregation should be more severe than for a composite with lower aggregation. This is not the case for samples of 15 wt% silica prepared from MEK and THF. The THF samples are much more aggregated (Fig. 5), but show a much smaller $T_{\rm g}$ shift than the MEK samples. More importantly, Fig. 4a shows that data from both the solvents fall on the thin-film curve when the nanocomposite data are quantified in terms of h_{z}^{***} . Similar findings are made when the 15 wt% and 25 wt% silica samples (both cast from MEK) are compared. Thus, we conclude that, even though different solvents and molecular weights yield different extents of agglomeration of nanoparticles in the polymer matrices, and hence different values of the interparticle spacing, the size of the agglomerates does not affect the results obtained. Rather, the dominant physics is embodied in the appropriately averaged interparticle separation, h_z^{***} .

To provide further support for the analogy between nanocomposites and thin films, we performed experiments with SiO₂ nanoparticles that had high-molecular-weight PS grafted from them (called SiO₂-g-PS; see the Methods section). These modified particles provide a wetting interface between the particles and a 250,000 g mol⁻¹ molecular weight PS matrix. This assignment is verified by scanning electron microscopy showing a wetting interface (Fig. 1b) and X-ray photon correlation spectroscopy, which suggests that particle mobility in these cases is unaffected by an increase in particle concentration. $T_{\rm g}$ data from these systems are plotted in Fig. 4a and compared with PS films sandwiched between metal layers. Within experimental error, our hypothesis is supported by the fact that no decrease in T_{g} is observed for wetting interfaces. Note also that the width of the glass-transition process is decreased when compared with the case of the non-wetting films (Fig. 4c).

It is interesting that the nanocomposite results agree with the thin-film data given the curvature of the particles and their inherent surface topography. Although we expect topography to play a minor role for the case of dewetting interfaces, the result for the case of wetting interfaces is less clear. However, we note that T_g is a local property driven by events on the 1–2 nm length scale. Because the particle sizes are ~15 nm and the smallest interparticle spacings are ~25 nm, curvature effects should not play a role here. However, much smaller wetting particles might provide critical information on the role of curvature effects. Similarly, we are not completely surprised that surface roughness (or local curvature effects on the nanometre length scale) plays no role as no such effects have been observed for thin planar films.

Our results provide important new insights into glasstransition behaviour in confined geometries. Our primary 2 conclusion is that generic 'two-layer' models, which have been used 3 to interpret equation (1) in the context of thin-film T_g data, do not embody the physics of these situations¹⁵. To explain this potentially 5 far-reaching conclusion, we begin by accepting the conjecture that there is a local layer of altered polymer mobility surrounding each nanoparticle^{10,15,19}. For the unfunctionalized silica particles this would correspond to a region of enhanced mobility. As discussed above, the volume fraction of polymer with altered mobility is 10 11 proportional to $1/h^*$. However, because neither h^* nor h^*_a explain the nanocomposite data in Fig. 4, we conclude that the mere 12 presence of regions of enhanced mobility, that is, a simple two-13 layer model, is insufficient to explain our results. As a consequence, 14 we are forced to require that the 'liquid-like' regions surrounding 15 different particles interact. We conjecture that such interactions 16 could follow the ideas put forward in ref. 24, where it is suggested 17 that the T_{g} process on heating occurs when mobile domains 18 percolate across the specimen. In the nanocomposites, the smallest 19 interparticle spacings, which would percolate first, would dominate 20 behaviour. In the case of the functionalized particles, we argue 21 that similar interaction effects could continue to apply, except that 22 23 the region in close proximity to the particles has reduced mobility when compared with the bulk. We therefore propose that the glass-24 25 transition process in confined geometries requires the interaction of near-surface regions of altered mobility. 26

METHODS

27

28

29

31

32

33

34

35

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

61

62

63

64

65

66

67

68

69

70

71

72 73

74

75

76

PS samples of two difference average molecular weights, 282,000 g mol⁻¹ (polydisperity, PDI = 1.04) and 92,000 g mol^{-1} (PDI = 1.10), were synthesized using anionic polymerization methods. The silica particles (Nissan Chemicals) with an average diameter of 14 ± 4 nm as measured by TEM, and 20 nm as measured by light scattering, were obtained as 30 wt% suspensions in MEK. These were diluted with MEK, sonicated and mixed with a 10% PS solution in MEK. The resulting solution was further sonicated for 2 min, cast on petri dishes and dried at room temperature. To study the effect of surface modification, SiO₂ nanoparticles were end grafted with PS ($M_w = 160,000 \text{ g mol}^{-1}$, PDI = 1.11, grafting density $\sigma \sim 0.57$ chains nm⁻²). Details of this preparation method can be found in ref. 35. The films were peeled from the petri dish and dried in a vacuum oven (<30 mm Hg) at 373 K for 24 h to remove the residual solvent. Subsequent thermal gravimetric analysis (TGA) showed no evidence of residual solvent. Finally, the dried films were compression moulded into 0.5-mm-thick samples at 443 K. No changes in properties on subsequent annealing were observed, suggesting that these moulded samples are well equilibrated to the best of our abilities. It must be noted here that if the untreated SiO2-PS-MEK solution was allowed to equilibrate in a vial at room temperature, the nanoparticles phase segregated to the bottom. This means that the suspensions that are cast on petri dishes do not represent the equilibrium state and that the dispersion of SiO₂ in PS will evolve over the course of evaporation. This balance will be different for different solvents used (that is, THF versus MEK). However, once the dried composite is formed, its state of dispersion does not change upon moulding or upon further annealing. The dispersions of the grafted particles, on the other hand, are stable for extended periods of time, indicating good compatibility of the grafted silica with PS.

The molecular weight of PS was measured before and after sonication. Gel permeation chromatography showed that the M_w values shifted from 282,000 to 252,000 g mol⁻¹ (named PS (250 K)) and 92,000 to 90,000 g mol⁻¹ (named PS (90 K)) after sonication. However, the sample polydispersity was unchanged. Similar results were found for PS in the nanocomposites (after dissolution). We have used the sonicated polymer solutions to prepare both the control samples and the nanocomposites.

DSC and dynamic mechanical analysis (DMA) were used to characterize the T_g . The T_g of the filled PS was characterized as the mid point of the change in specific heat from a DSC scan or the peak position of the loss modulus from DMA. Both these measures were in quantitative agreement (±1 K). For DSC experiments, the moulded samples were heated to 453 K and soaked for 2 min followed by cooling at 10 K min⁻¹. The reported T_g was from the second heating at a rate of 10 K min⁻¹. Both cooling and heating experiments yielded identical results. Experiments to determine the effect of heating rate are in progress. Furthermore, DSC on unmoulded nanocomposites run up to 453 K revealed only the glass transition endotherm and TGA revealed that the thermal degradation of the PS filled with SiO₂ was identical to that of neat PS. We are therefore confident that no chemical reaction took place between SiO₂ and PS.

DMA (Rheometrics DMTA V) was performed in tensile mode (6 mm (L) × 0.5 mm (T) × 3 mm (W)) with a frequency of 1 Hz. Temperature was ramped from 300 to 453 K at 2 K min⁻¹. A dynamic strain of 0.03% was imposed to measure the dynamic modulus in the linear viscoelastic regime.

TEM (JÕEL 840) was used to quantify the average interparticle spacing between SiO₂ particles in the nanocomposites. The moulded samples were cut to a thickness of ~50 nm using an ultramicrotome system (MTXL, Boeckeler Instruments) and studied by TEM. Negatives were scanned at a resolution of 1,200 d.p.i. giving a pixel/nm ratio of ~1:1 (at 22 K magnification). The edges of the nanoparticles were discernable to the naked eye and interparticle spacings were measured by an image analyser (Scion Image software) using at least 600 independent ligaments. We note that, in each nanocomposite, the sizes of the agglomerates were comparable and in most instances much larger than the film thickness. This rules out any artefacts in the measurement of interparticle spacings arising due to the three-dimensional nature of the SiO₂ dispersion. Furthermore, atomic force microscopy images of samples sectioned through their thickness have revealed a uniform distribution of the nanoparticles in the entire thickness (see Supplementary Information, Fig. S1).

Received 17 December 2004; accepted 16 June 2005; published XX Month XXXX.

References

- Starr, F. W., Schroeder, T. B. & Glotzer, S. C. Effects of a nanoscopic filler on the structure and dynamics of a simulated polymer melt and the relationship to ultrathin films. *Phys. Rev. E* 64, 021802–021806 (2001).
- Tran, T. A., Sald, S. & Grohens, Y. Compared study of cooperativity in PMMA nanocomposites and thin films. *Composites A* 36, 461–465 (2005).
- Becker, C., Krug, H. & Schmidt, H. Tailoring of thermomechanical properties of thermoplastic nanocomposite by surface modification of nanoscale silica particles. *Mater. Res. Soc. Symp. Proc.* 435, 237–242 (1996).
- Tsagaropoulos, G. & Eisenberg, A. Dynamic mechanical study of the factors affecting the two glass transition behavior of filled polymers. Similarities and differences with random ionomers. *Macromolecules* 28, 6067–6077 (1995).
- Bares, J. Glass transition of polymer microphase. *Macromolecules* 8, 244–246 (1975).
 Lipatov, Y. S., Rosovitskii, V. F. & Maslak, Y. V. Glass transition in heterogeneous polymer systems
- with a high degree of phase separation. *Polym. Sci. USSR* 26, 1149–1154 (1984).
 7. Besklubenko, Y. D., Privalko, V. P. & Lipatov, Y. S. Thermodynamics of filled poly(methyl
- methacrylate). Polym. Sci. USSR 20, 1473–1479 (1978).
 Lipatov, Y. S. & Privalko, V. P. Glass transition in filled polymer systems. Polym. Sci. USSR 14,
- Ash, B. J., Siegel, R. W. & Schadler, L. S. Glass-transition temperature behavior of alumina/PMMA
- A. J. B. J. J. G. B. J. N. N. C. S. Hauer, L. S. Ghas-trainstron temperature denavior of alumina/PMMA nanocomposites. J. Polym. Sci. B 42, 4371–4383 (2004).
 (D. Ash, B. J. S. Schaller, L. S. & Siegel, R. W. Glass transition behavior of alumina/polymethylmethacrylate
- I. A. B. B. Schweit, E. S. Woger, R. W. Gaas transition denator of adminiarpolymetrylinethactylar nanocomposites. *Mater. Lett.* 55, 83–87 (2002).
 Krishnamoorti, R., Vaia, R. A. & Giannelis, E. P. Structure and dynamics of polymer-layered silicate
- nanocomposites. Chem. Mater. 8, 1728 (1996). 12. Zax, D. B. et al. Dynamical heterogeneity in nanoconfined poly(styrene) chains. J. Chem. Phys. 112,
- 2945–2951 (2000).
 Dalnoki-Veress, K., Forrest, J. A., Murray, C., Gigault, C. & Dutcher, J. R. Molecular weight dependence of reductions in the glass transition temperature of thin, freely standing polymer films. *Phys. Rev. E* 63, 031801–031810 (2001).
- Keddie, J. L., Jones, R. A. L. & Cory, R. A. Size-dependant depression of the glass transition temperature in polymer films. *Europhys. Lett.* 27, 59–64 (1994).
- Ellison, C. J. & Torkelson, J. M. The distribution of glass-transition temperatures in nanoscopically confined glass formers. *Nature Mater.* 2, 695–700 (2003).
- Ellison, T. J. & Torkelson, J. M. Sensing the glass transition in thin and ultrathin polymer films via fluorescence probes and labels. J. Polym. Sci. B 40, 2745–2758 (2002).
- 17. Forrest, J. A. & Dalnoki-Veress, K. The glass transition in thin polymer films. *Adv. Colloid Interface Sci.* **94**, 167–196 (2001).
- Forrest, J. A., Dalnoki-Veress, K. & Dutcher, J. R. Interface and chain confinement effects on the glass transition temperature of thin polymer films. *Phys. Rev. E* 56, 5705–5716 (1997).
- Forrest, J. A., Dalnoki-Veress, K., Stevens, J. R. & Dutcher, J. R. Effect of free surfaces on the glass transition temperature of thin polymer films. *Phys. Rev. Lett.* 77, 2002–2005 (1996).
- Forrest, J. A. & Mattsson, J. Reductions of the glass transition temperature in thin polymer films: Probing the length scale of cooperative dynamics. *Phys. Rev. E* 61, R53–R56 (2000).
- Fukao, K. & Miyamoto, Y. Glass transitions and dynamics in thin polymer films: Dielectric relaxation of thin films of polystyrene. *Phys. Rev. E* 61, 1743–1754 (2000).
- Fukao, K., Uno, S., Miyamoto, Y., Hoshino, A. & Miyaji, H. Dynamics of α and β processes in thin polymer films: Polyvinyl acetate and polymethyl methacrylate. *Phys. Rev. E* 64, 051807–051811 (2001).
- Fukao, K., Uno, S., Miyamoto, Y., Hoshino, A. & Miyaji, H. Relaxation dynamics in thin supported polymer films. J. Non-Cryst. Solids 307, 517–523 (2002).
- Long, D. & Lequeux, F. Hetrogeneous dynamics at the glass transition in van der Waals liquids, in the bulk and in thin films. *Eur. Phys. J. E* 4, 371–387 (2001).
- Mattsson, J., Forrest, J. A. & Borjesson, L. Quantifying glass transition behavior in ultrathin free-standing polymer films. *Phys. Rev. E* 62, 5187–5200 (2000).
- Mayes, A. M. Glass transition of amorphous polymer surfaces. *Macromolecules* 27, 3114–3115 (1994).
 McCoy, J. D. & Curro, J. G. Conjectures on the glass transition of polymers in confined geometries. *J. Chem. Phys.* 116, 9154–9157 (2002).
- Roth, C. B. & Dutcher, J. R. Glass transition temperature of freely-standing films of atactic poly(methyl methacrylate). *Eur. Phys. J. E* 12, S103–S107 (2003).
- Sills, S. *et al.* Interfacial glass transition profiles in ultrathin, spin cast polymer films. J. Chem. Phys. 120, 5334–5338 (2004).
- Singh, L., Ludovice, P. J. & Henderson, C. L. Influence of molecular weight and film thickness on the glass transition temperature and coefficient of thermal expansion of supported ultrathin polymer films. *Thin Solid Films* 449, 231–241 (2004).
- Starr, F. W. & Glotzer, S. C. Simulations of filled polymers on multiple length scales. *Mater. Res. Soc. Symp. Proc.* 661, KK4.1/1–KK4.1/13 (2001).
- vanZanten, J. H., Wallace, W. E. & Wu, W. -L. Effect of strongly favourable substrate interactions on the thermal properties of ultrathin polymer films. *Phys. Rev. E* 53, R2053–R2056 (1996).
- Sharp, J. S. & Forrest, J. A. Free surfaces cause reductions in the glass transition temperature of thin polystyrene films. *Phys. Rev. Lett.* 91, 235701–235704 (2003).
- Jean, Y. C. et al. Glass transition of polystyrene near the surface studied by slow-positron-annihilation spectroscopy. Phys. Rev. B 56, R8459–R8462 (1997).
- Li, C. & Benicewicz, B. C. Synthesis of well defined polymer brushes grafted onto silica nanoparticles via surface reversible addition-fragmentation chain transfer polymerization. *Macromolecules* 28, 0000 (2005).

Acknowledgements

The authors are grateful to the National Science Foundation for funding this research through a Nanoscale Science and Engineering Center Grant. Additional funding was provided by the NSF Division of Materials Research (S.K.K.), Eastman Kodak (B.C.B., S.K.K. and L.S.S.) and the Office of Naval Research (S.K.K. and L.S.S.). The authors also thank R. Krishnamoorti, S. Granick, S. S. Sternstein, P. Keblinski, J. Forrest, M. T. Takemori and A. Eitan for discussions and comments, W. Kim for gel permeation chromatography experiments, A. Kumar for SEM images and the 2001 Mettler-Toledo Thermal Analysis Educational Grant for DSC and TGA. K.C. would like to thank the Ministry of Science and Technology of Korea (National Research Laboratory Program) for their funding.

Correspondence and requests for materials should be addressed to S.K.K. or L.S.S. Supplementary Information accompanies this paper on www.nature.com/naturematerials

Competing financial interests

The authors declare that they have no competing financial interests.

Page 1

Query 1: Line no. 15

Author: Any update for this reference? Also, as per Nature style, unpublished references other than 'in press' should not be given in the reference list. So this reference has been taken from the list and placed in the text where it is cited. Please check now all citations are correctly given.

Page 2

Query 2: Line no. 1

Author: I have inserted a reference to the Methods section here (in Fig. 1 caption) to clarify terminology, OK?

Query 3: Line no. 19

Author: Please specify the unit 'gm' used in Fig. 2a. If is 'gram' it should be ' g^{-1} '; and if it is 'gram metre' it should be ' g^{-1} m⁻¹'.

Query 4: Line no. 20

Author: Please define the basis of the error bars in Fig. 2b.

Page 4

Query 5: Line no. 3

Author: Please explain the basis of error bars in Fig. 4b.

Query 6: Line no. 17

Author: "it" refers to the interparticle spacing here? If not please clarify.

Query 7: Line no. 29 Author: Two-layer models OK here?

Page 5

Query 8: Line no. 20

Author: Please check the displayed equation here, should the value under the root sign be part of the integral in the numerator and is an integral sign missing in the denominator?

Page 6

Query 9: Line no. 64 Author: Please define *L*, *T* and *W* here.

Query 10: Line no. 71

Author: Does the 'K' here mean 1000; if so it should be written as 22,000 as per Nature style.

Query 11: Line no. 104 Author: Please provide page range for ref. 11.

Query 12: Line no. 155 Author: Please provide page range for ref. 35.