

## Spin-Orbit Coupling and Ion Displacements in Multiferroic $\text{TbMnO}_3$

H. J. Xiang,<sup>1</sup> Su-Huai Wei,<sup>1</sup> M.-H. Whangbo,<sup>2</sup> and Juarez L. F. Da Silva<sup>1</sup>

<sup>1</sup>National Renewable Energy Laboratory, Golden, Colorado 80401, USA

<sup>2</sup>Department of Chemistry, North Carolina State University, Raleigh, North Carolina 27695-8204, USA

(Received 20 March 2008; published 18 July 2008)

The magnetic and ferroelectric (FE) properties of  $\text{TbMnO}_3$  are investigated on the basis of relativistic density functional theory calculations. We show that, due to spin-orbit coupling, the spin-spiral plane of  $\text{TbMnO}_3$  can be either the  $bc$  or  $ab$  plane, but not the  $ac$  plane. As for the mechanism of FE polarization, our work reveals that the “pure electronic” model by Katsura, Nagaosa, and Balatsky is inadequate in predicting the absolute direction of FE polarization. Our work indicates that to determine the magnitude and the absolute direction of FE polarization in spin-spiral states, it is crucial to consider the displacements of the ions from their centrosymmetric positions.

DOI: 10.1103/PhysRevLett.101.037209

PACS numbers: 75.80.+q, 71.20.-b, 75.30.Gw, 77.80.-e

Recent studies on magnetic ferroelectric (FE) materials have shown that electric polarization can be significantly modified by the application of a magnetic field [1–7]. Perovskite  $\text{TbMnO}_3$  with a spin-spiral magnetic order is a prototypical multiferroic compound with a gigantic magnetoelectric effect [2]. Currently, there are two important issues concerning the FE polarization of  $\text{TbMnO}_3$ . One concerns the origin of FE polarization. Model Hamiltonians studies of spin-spiral multiferroic compounds have provided two different pictures. In the Katsura-Nagaosa-Balatsky (KNB) model [5], the hybridization of electronic states induced by spin-orbit coupling (SOC) leads to a FE polarization of the charge density distribution even if the ions are not displaced from their centrosymmetric positions. In contrast, the model study by Sergienko and Dagotto [7] concluded that oxygen ion displacements from their centrosymmetric positions are essential for the FE polarization in multiferroic compounds [8]. When carried out with the ions kept at their centrosymmetric positions, density functional theory (DFT) calculations [9] for the spin-spiral states of  $\text{LiCuVO}_4$  predict FE polarizations that agree reasonably well in magnitude with experiment [10], which is in apparent support of the KNB model [5]. It is, therefore, important to check which model, the KNB or the “ion-displacement” model, is relevant for the FE polarization in  $\text{TbMnO}_3$ . The other issue concerns the spin-spiral plane of  $\text{TbMnO}_3$ . Under a magnetic field, the spin-spiral plane of  $\text{TbMnO}_3$  can be either the  $bc$  plane or the  $ab$  plane, but not the  $ac$  plane. To explain this observation, it is necessary to probe the magnetic anisotropy of the  $\text{Mn}^{3+}$  ion. The magnetic anisotropy of the  $\text{Tb}^{3+}$  ion might be also relevant for the magnetoelectric effect, as suggested by Prokhnenko *et al.* [11].

In this Letter, we investigated these issues on the basis of DFT calculations and found that the consideration of the ion displacements is essential for the FE polarizations in the spin-spiral state of  $\text{TbMnO}_3$ , and the KNB model can be erroneous even for predicting the absolute direction of FE polarization. The absence of the  $ac$  plane spin-spiral in

$\text{TbMnO}_3$  is explained by the magnetic anisotropy of the  $\text{Mn}^{3+}$  ion.

Our calculations were based on DFT plus the on-site repulsion  $U$  method [12] within the generalized gradient approximation [13]. We used  $U_{\text{eff}} = 6.0$  eV on Tb 4*f* states. With other  $U_{\text{eff}}$  values for Tb, similar results were obtained. For Mn 3*d* states, we employed  $U_{\text{eff}} = 2.0$  eV, which leads to the spin exchange interactions between the  $\text{Mn}^{3+}$  ions that are consistent with the observed magnetic structure of  $\text{TbMnO}_3$  (see below). For the calculation of FE polarization, the Berry phase method [14] encoded in the Vienna *ab initio* simulation package (VASP) was employed [15,16], in which the Tb 4*f* electrons were treated as core electrons. For the study of the SOC effect associated with the Tb 4*f* electrons, we used the full-potential augmented plane wave plus local orbital method as implemented in the WIEN2K code [17]. Because of the small value of the spin anisotropy, we employed the convergence threshold of  $10^{-7}$  for electron density. As shown in Fig. 1, the experimental crystal structure [18] of  $\text{TbMnO}_3$  has a distorted




FIG. 1 (color online). Perspective view of the orthorhombic structure of  $\text{TbMnO}_3$ . The large, medium, and small spheres represent the Tb, Mn, and O ions, respectively. The Mn-Mn spin exchange paths  $J_{ab}$ ,  $J_{aa}$ ,  $J_{bb}$ , and  $J_{cc}$  are also indicated. The solid vectors denote the easy axes for the  $\text{Tb}^{3+}$  and  $\text{Mn}^{3+}$  spins.

GdFeO<sub>3</sub>-type orthorhombic perovskite structure with space group Pbnm. In our calculations, the experimental structure was used unless otherwise stated.

The basic electronic structure of TbMnO<sub>3</sub> is shown in Fig. 2 in terms of the density of states (DOS) of the FM state calculated by WIEN2K with the Tb 4*f* states treated as valence states. The system is an insulator with energy gap of about 0.5 eV between the spin-up Mn 3*d* *e<sub>g</sub>* states. The spin-up Tb 4*f* states are all occupied while the spin-down Tb 4*f* states occur at around -2.8 eV with the remaining down-spin Tb 4*f* states above the Fermi level. This feature is consistent with the *f*<sup>8</sup> configuration of the Tb<sup>3+</sup> ion. Partial DOS analysis indicates that the occupied down-spin states have mainly the *f<sub>z(x<sup>2</sup>-y<sup>2</sup>)</sub>* orbital character with a slight contribution from the *f<sub>xy<sub>z</sub></sub>* orbital.

For the spin exchange between Mn<sup>3+</sup> ions, there are four spin exchange paths to consider as shown in Fig. 1: *J<sub>ab</sub>* is the intralayer (*ab* plane) nearest neighbor (NN) exchange interaction, *J<sub>aa</sub>* and *J<sub>bb</sub>* are the intralayer next-nearest neighbor (NNN) exchange interactions along the *a* and *b* directions, respectively, and *J<sub>cc</sub>* is the interlayer NN exchange interaction along the *c* direction. The high-spin Mn<sup>3+</sup> ions have the *t<sub>2g</sub><sup>3</sup>e<sub>g</sub><sup>1</sup>* configuration with the *e<sub>g</sub>* states forming a staggered orbital ordering of the *d<sub>3x<sup>2</sup>-r<sup>2</sup></sub>* and *d<sub>3y<sup>2</sup>-r<sup>2</sup></sub>* states. Such an orbital ordering induces an NN intralayer ferromagnetic (FM) exchange, and an NN interlayer antiferromagnetic (AFM) exchange. The cooperative Jahn-Teller distortion associated with the orbital ordering leads to a large NNN intralayer super-superexchange along the *b* direction [19,20]. Our VASP calculations lead to *J<sub>ab</sub>* = -1.52 meV, *J<sub>aa</sub>* = 0.57 meV, *J<sub>bb</sub>* = 0.85 meV, and *J<sub>cc</sub>* = 0.50 meV. The calculated *J<sub>ab</sub>*, *J<sub>bb</sub>*, and *J<sub>cc</sub>* values are consistent with those expected for TbMnO<sub>3</sub> [19]. *J<sub>aa</sub>* was predicted to be FM by Kimura *et al.* [19], but our calculations show it to be AFM. The classical spin analysis based on the Freiser method [21] predicts that the spin ground state is a spin spiral with the modulation vector **q** = (0, *q<sub>y</sub>*, 0) with *q<sub>y</sub>* =  $\text{acos}(-\frac{J_{ab}}{2J_{bb}})/\pi = 0.15$ . The prediction of a spin-spiral ground state is in agreement with the experimental observation [22], which shows an incommen-




FIG. 2 (color online). Electronic structure obtained for the FM state of TbMnO<sub>3</sub> from the WIEN2K calculations. The total DOS, the Tb 4*f* partial DOS, and the Mn 3*d* partial DOS are shown. The position of the *f<sub>z(x<sup>2</sup>-y<sup>2</sup>)</sub>* state is also indicated.

surate spiral with **q** = (0, 0.27, 0) below 28 K. It is worthwhile to point out that if a smaller *U<sub>eff</sub>* is used *J<sub>bb</sub>* will be stronger, and *J<sub>ab</sub>* be weaker, hence leading to a larger *q<sub>y</sub>*.

To examine the magnetic anisotropy of the high-spin Mn<sup>3+</sup> ion in TbMnO<sub>3</sub>, it is necessary to consider DFT + U calculations with SOC included. TbMnO<sub>3</sub> has four Mn<sup>3+</sup> ions per unit cell. The easy axes of these ions are not collinear but related by symmetry. Since the effect of SOC is largely local in nature, we consider for simplicity only one Mn ion (i.e., Mn1 in Fig. 1) per unit cell by replacing the remaining three Mn<sup>3+</sup> ions with Sc<sup>3+</sup> ions that have no magnetic moment. To remove any possible coupling with the Tb 4*f* moment, we replace the Tb<sup>3+</sup> ions of the unit cell with La<sup>3+</sup> ions that have no magnetic moment. The energy dependence upon the Mn spin direction obtained from DFT + U + SOC calculations is shown in Fig. 3(a) for the cases when the Mn spin lies in the *ab* and *bc* planes. The energy minimum occurs at 60° and 70° for the case when the spin lies in the *ab* and *bc* planes, respectively, and the energy minimum for the *ab* plane is lower than that for *bc* plane by 0.12 meV/Mn.




FIG. 3 (color online). (a) The dependence of energy on the direction of the Mn spin in the *ab* plane or the *bc* plane. (b) The local structure of the distorted MnO<sub>6</sub> octahedron. The numbers give the Mn-O bond lengths in Å. The local coordinate system is also indicated. The right-hand-side diagram illustrates the electron configuration of the Mn<sup>3+</sup> (*d<sup>4</sup>*) ion. The label “SOC” denotes that the largest SOC mixing occurs between the *d<sub>xy</sub>* and *d<sub>x<sup>2</sup>-y<sup>2</sup></sub>* states. (c) The dependence of energy on the direction of Tb spins in the *ab* plane.

The above results can be readily understood by analyzing the effect of the SOC Hamiltonian [23,24]. As shown in Fig. 3(b), each  $\text{MnO}_6$  octahedron of  $\text{TbMnO}_3$  is axially elongated. With one of the two longest Mn-O bonds taken as the local  $z$  axis and neglecting the slight difference between the other four short Mn-O bonds, the  $d$ -block levels of the  $\text{Mn}^{3+}$  ( $d^4$ ) ion are described as shown on the right-hand side of Fig. 3(b), which leads to the electron configuration  $(xz)^1(yz)^1(xy)^1(z^2)^1(x^2 - y^2)^0$ . The SOC Hamiltonian  $\lambda \hat{\mathbf{L}} \cdot \hat{\mathbf{S}}$  leads to an interaction of the empty  $d_{x^2-y^2}$  ( $e_g$ ) state with the other  $d$ -states. The strongest SOC occurs between two  $e_g$  states ( $d_{xy}$  and  $d_{x^2-y^2}$ ) with the maximum energy lowering when the spin lies in the local  $z$  direction [24]. For the Mn1 ion, the  $\theta$  and  $\phi$  angles of the local  $z$  direction in the global coordinate system are  $\theta = 80.2^\circ$  and  $\phi = 60.5^\circ$ , respectively. In good agreement with these values, our SOC analysis based on tight-binding calculations [25] shows that the actual easy axis of Mn1 has  $\theta = 84^\circ$  and  $\phi = 60^\circ$ . Thus the easy axis is close to the  $ab$  plane, and is far from the  $c$  axis. This explains why the energy minimum for the Mn spin lying in the  $ab$  plane has a lower energy than that lying in the  $bc$  plane. In addition, the easy axis is closer to the  $b$  axis than to the  $a$  axis. Our result is consistent with the experimental observation [26] that the sine-wave modulation of the Mn magnetic moment below 40 K has the direction parallel to the  $b$  axis. Since the easy axis of the Mn spin is far from the  $c$  direction, it is expected that the spin-spiral plane of  $\text{TbMnO}_3$  is either the  $ab$  plane or the  $bc$  plane, but not the  $ac$  plane [27]. Experimentally [22], it was found that the Mn moments of  $\text{TbMnO}_3$  form a  $bc$  plane elliptical spiral with  $m_b(\text{Mn}) = 3.9\mu_B > m_c(\text{Mn}) = 2.8\mu_B$ . This can be readily explained by the fact that the easy axis of the Mn spins is close to the  $b$  axis, but far from the  $c$  direction.

The magnetic anisotropy of the  $\text{Tb}^{3+}$  ion in  $\text{TbMnO}_3$  was also calculated in a similar manner; three of the four  $\text{Tb}^{3+}$  ions in a unit cell were replaced by  $\text{La}^{3+}$  ions with all the  $\text{Mn}^{3+}$  ions of a unit cell replaced by  $\text{Sc}^{3+}$  ions. Our DFT + U + SOC calculations show that the Tb spin prefers to lie in the  $ab$  plane since the state for the spin parallel to the  $c$  axis is higher than that for the spin in the  $ab$  plane by at least 0.83 meV/Tb. The energy calculated for Tb1 (as labeled in Fig. 1 as a function of the angle  $\phi$  with  $\theta = 90^\circ$ ) is presented in Fig. 3(c), which reveals that the energy minimum occurs at around  $\phi = 145^\circ$ . The large anisotropy energy is consistent with the Ising behavior of Tb moment [11]. The easy axes of the  $\text{Tb}^{3+}$  ions presented in Fig. 1 show that they lie symmetrically around the  $b$ -axis with the angle  $57^\circ$ . This is in excellent agreement with the observed angle of  $57^\circ$  [26].

The electric polarization of  $\text{TbMnO}_3$  in the spin-spiral state was calculated using the VASP. To reduce the computational task, we considered the  $\mathbf{q} = (0, 1/3, 0)$  state, which we simulated by using a  $1 \times 3 \times 1$  supercell. Using the experimental centrosymmetric structure, the electric polar-

ization from the pure electronic effect was calculated to be  $\mathbf{P} = (0, 0, 0.5) \mu\text{C}/\text{m}^2$  [28–30] for the  $bc$  plane spiral shown in Fig. 4(a). Experimentally, the magnitude of the electric polarization for the  $bc$  plane spiral is about  $600 \mu\text{C}/\text{m}^2$  [31], which is 3 orders of magnitude larger than the value calculated with no geometry relaxation. For the  $ab$  plane spiral shown in Fig. 4(b), the electric polarization is calculated to be  $\mathbf{P} = (-331.0, 0, 0) \mu\text{C}/\text{m}^2$  in the absence of geometry relaxation. The absolute directions of the FE polarizations obtained for the  $bc$  and  $ab$  plane spin-spiral states from DFT calculations without geometry relaxation are opposite to those predicted by the KNB model (Eq. 6 of Ref. [5]). To examine the effect of ion displacements in the spin-spiral states on the FE polarization, we optimized the atom positions of  $\text{TbMnO}_3$  in the  $bc$ - and  $ab$  plane spiral states by performing DFT + U + SOC calculations and calculated the electric polarizations of  $\text{TbMnO}_3$  using the relaxed structures. These calculations lead to  $P_c = -424.0 \mu\text{C}/\text{m}^2$  for the  $bc$  plane spiral, and to  $P_a = 131.2 \mu\text{C}/\text{m}^2$  for the  $ab$  plane spiral. The absolute directions of the FE polarizations are switched for both spin-spiral states under geometry relaxation. The calculated FE polarization for the  $bc$  plane spiral using the relaxed structure is now much closer to the experimental value. Furthermore, the direction of the FE polarization is in agreement with experiment [28–30,32] as well as the KNB model. However, this agreement between the KNB model and experimental values is fortuitous; for  $\text{LiCuVO}_4$  and  $\text{LiCu}_2\text{O}_2$ , which consists of  $\text{CuO}_2$  ribbon chains, the KNB model predicts the wrong absolute direction of the FE polarization for the  $ab$  plane spiral, but the correct absolute direction of the FE polarization for the  $bc$  plane spiral, regardless of whether the unrelaxed or the relaxed crystal structures are employed [9]. The failure of the KNB model could be due to the fact that it was derived




FIG. 4 (color online). The atomic displacements (indicated by solid arrows) of the spin-spiral states after geometry optimization for (a) the  $bc$  plane spiral and (b) the  $ab$  plane spiral. The dashed arrows indicate the directions of the Mn spins in the spiral states. The directions of the electric polarizations are also shown.



for the  $t_{2g}$  systems while the  $e_g$  states are important in  $\text{Mn}^{3+}$  and  $\text{Cu}^{2+}$  systems. Furthermore, we notice that the FE polarization of the  $ab$  plane spiral calculated by using the relaxed structure, now along the  $a$  direction, is smaller in magnitude than that calculated by using the experimental structure. In the case of  $\text{LiCuVO}_4$  and  $\text{LiCu}_2\text{O}_2$ , the geometry relaxation in the spin-spiral states was found to enhance the magnitudes of the FE polarizations without changing their absolute directions [9].

To show how the ion displacements break the centrosymmetry, we present the pattern of the atom displacements with respect to the centrosymmetric structure in Fig. 4. For the  $bc$  plane spiral, the O atoms at the Wyckoff  $4c$  position (i.e., O1) lying in the  $ab$  plane of the Tb atoms almost do not move. The movement of all the O atoms at the Wyckoff  $8d$  position (i.e., O2) close to the  $ab$  plane of the Mn atoms have a component along the  $c$  direction. All the Mn and Tb atoms have a displacement along the  $-c$  direction. The largest displacements along the  $c$  direction (about  $2.4 \times 10^{-4}$  Å) occur at the Mn sites rather than at the O sites. This finding is in contradiction to the assumption introduced in the “ion-displacement” model [7]. Considering that the Born effective charge is positive for the  $\text{Tb}^{3+}$  and  $\text{Mn}^{3+}$  cations, and negative for the  $\text{O}^{2-}$  anion, the total electric polarization is expected to be along the  $-c$  direction, in agreement with the DFT calculation. For the  $ab$  plane spiral, some O atoms have displacements along the  $-a$  direction, but other O atoms have displacements along the  $a$  direction. The sum of the O ion displacements is along the  $-a$  direction. The occurrence of alternating O displacements is consistent with the prediction made by Sergienko and Dagotto [7], and is responsible for the smaller electric polarization when compared with the case of the  $bc$  plane spiral. All the Mn atoms have a displacement along the  $a$  direction. Another unexpected finding is that some Tb atoms have the largest displacements with a large component along the  $b$  or  $-b$  direction and a small component along the  $a$  direction.

In summary, the absence of the  $ac$  plane spin-spiral in  $\text{TbMnO}_3$  is explained by the magnetic anisotropy of the  $\text{Mn}^{3+}$  ion. The calculated easy axis for Tb is in excellent agreement with the experimental result. The consideration of the ion displacements in the spin-spiral states of  $\text{TbMnO}_3$  is essential in determining the magnitude and the absolute direction of the FE polarizations, which is in support of the “ion-displacement” model. Surprisingly, the displacements of the  $\text{Mn}^{3+}$  and  $\text{Tb}^{3+}$  ions are generally greater than those of the  $\text{O}^{2-}$  ions. The KNB model, however, can fail to describe both the magnitude and the absolute direction of FE polarization.

Work at NREL was supported by the U.S. Department of Energy, under Contract No. DE-AC36-99GO10337. The research at NCSU was supported by the Office of Basic Energy Sciences, Division of Materials Sciences, U.S. Department of Energy, under Grant No. DE-FG02-86ER45259. We thank Professor D. Vanderbilt for the

discussion about the definition of positive electric polarization [29,30,32].

- 
- [1] S.-W. Cheong and M. Mostvov, *Nat. Mater.* **6**, 13 (2007).
  - [2] T. Kimura *et al.*, *Nature (London)* **426**, 55 (2003).
  - [3] G. Lawes *et al.*, *Phys. Rev. Lett.* **95**, 087205 (2005).
  - [4] N. Hur *et al.*, *Nature (London)* **429**, 392 (2004).
  - [5] H. Katsura *et al.*, *Phys. Rev. Lett.* **95**, 057205 (2005).
  - [6] M. Mostvov, *Phys. Rev. Lett.* **96**, 067601 (2006).
  - [7] I. A. Sergienko and E. Dagotto, *Phys. Rev. B* **73**, 094434 (2006).
  - [8] S. Picozzi *et al.*, *Phys. Rev. Lett.* **99**, 227201 (2007).
  - [9] H.J. Xiang and M.-H. Whangbo, *Phys. Rev. Lett.* **99**, 257203 (2007). The definition of the positive direction of electric polarization adopted in this work is opposite to the conventional one [28–30].
  - [10] F. Schrettle *et al.*, *Phys. Rev. B* **77**, 144101 (2008).
  - [11] O. Prokhnenko *et al.*, *Phys. Rev. Lett.* **99**, 177206 (2007).
  - [12] A.I. Liechtenstein *et al.*, *Phys. Rev. B* **52**, R5467 (1995).
  - [13] J.P. Perdew *et al.*, *Phys. Rev. Lett.* **77**, 3865 (1996).
  - [14] R.D. King-Smith and D. Vanderbilt, *Phys. Rev. B* **47**, 1651 (1993); R. Resta, *Rev. Mod. Phys.* **66**, 899 (1994).
  - [15] P.E. Blöchl, *Phys. Rev. B* **50**, 17953 (1994); G. Kresse and D. Joubert, *ibid.* **59**, 1758 (1999).
  - [16] G. Kresse and J. Furthmüller, *Comput. Mater. Sci.* **6**, 15 (1996); *Phys. Rev. B* **54**, 11169 (1996).
  - [17] P. Blaha *et al.*, in *WIEN2K, An Augmented Plane Wave Plus Local Orbitals Program for Calculating Crystal Properties*, edited by K. Schwarz (Techn. Universität Wien, Austria, 2001).
  - [18] J. A. Alonso *et al.*, *Inorg. Chem.* **39**, 917 (2000).
  - [19] T. Kimura *et al.*, *Phys. Rev. B* **68**, 060403(R) (2003).
  - [20] S. Picozzi *et al.*, *Phys. Rev. B* **74**, 094402 (2006).
  - [21] M. J. Freiser, *Phys. Rev.* **123**, 2003 (1961).
  - [22] M. Kenzelmann *et al.*, *Phys. Rev. Lett.* **95**, 087206 (2005).
  - [23] H. J. Xiang and M.-H. Whangbo, *Phys. Rev. B* **75**, 052407 (2007).
  - [24] H. J. Xiang *et al.*, *Phys. Rev. Lett.* **100**, 167207 (2008).
  - [25] W. A. Harrison, *Electronic Structure and Properties of Solids* (Freeman, San Francisco, 1980).
  - [26] S. Quezel *et al.*, *Physica (Amsterdam)* **86B+C**, 916 (1977).
  - [27] VASP calculations show that the  $ac$  plane spiral has higher energy by 0.23 meV/Mn than the  $ab$  plane or  $bc$  plane spiral. The energy difference between the  $ab$  plane spiral and  $bc$  plane spiral is within 0.02 meV/Mn. This difference is much smaller than that (0.12 meV/Mn) between the minima on the  $bc$  and  $ab$  plane since in a spiral not all spins lie along the minimum direction.
  - [28] In this work we adopt the conventional definition of the positive direction of electric polarization (i.e., from the negative to the positive charge site).
  - [29] S. Seki *et al.*, *Phys. Rev. Lett.* **100**, 127201 (2008).
  - [30] A. Malashevich and D. Vanderbilt, *Phys. Rev. Lett.*, **101**, 037210 (2008).
  - [31] O. Prokhnenko *et al.*, *Phys. Rev. Lett.* **98**, 057206 (2007).
  - [32] Y. Yamasaki *et al.*, *Phys. Rev. Lett.* **98**, 147204 (2007). The polarization direction of this report is in error. It should have been along the  $-c$  direction [28–30]; *Phys. Rev. Lett.* **100**, 219902(E) (2008).