

Structural relaxation around Cr³⁺ and the red-green color change in the spinel (sensu stricto)-magnesiochromite (MgAl₂O₄-MgCr₂O₄) and gahnite-zincochromite (ZnAl₂O₄-ZnCr₂O₄) solid-solution series

ULF HÅLENIUS,^{1,*} GIOVANNI B. ANDREOZZI,² AND HENRIK SKOGBY¹

¹Department of Mineralogy, Swedish Museum of Natural History, SE-10405 Stockholm, Sweden

²Dipartimento di Scienze della Terra, Sapienza Università di Roma, Piazzale Aldo Moro 5, I-00185 Roma, Italy

ABSTRACT

Optical absorption spectra of flux-grown single crystals in the spinel s.s.-magnesiochromite and gahnite-zincochromite solid solutions were recorded with the aim of exploring variations in local Cr-O bond distance as a function of composition. With increasing Cr contents, the crystals vary in color from pale red to intensely red to dark greenish. These variations are reflected in the optical spectra by the position and intensity of the two spin-allowed electronic *d-d* transitions in six-coordinated Cr³⁺ at ~18 000 (ν_1) and 25 000 cm⁻¹ (ν_2). From the shift of the ν_1 band position, a decrease in crystal field splitting, $10Dq$, for six-coordinated Cr³⁺ with increasing Cr contents is evident in both solid-solution series. Based on published Cr-O bond distances for the CrO₆ polyhedra in magnesiochromite and zincochromite of 1.995 and 1.991 Å, respectively, and applying the ligand field relationships, local Cr-O bond distances in gahnite and spinel with Cr contents at trace levels are determined to be 1.974(2) and 1.960(3) Å, respectively. These local Cr-O distances result in relaxation parameters (ϵ) equal to 0.69(2) and 0.60(3) for Cr-O bonds in the Mg(Al_{1-x}Cr_x)₂O₄ and Zn(Al_{1-x}Cr_x)₂O₄ series, respectively. However, the presently obtained Racah *B* values indicate increasing Cr-O bond covalency with increasing Cr³⁺ contents. This suggests that color changes and accompanying $10Dq$ variations may be due to variations in Cr-O bond covalency along the two solid-solution series, without or with very minor local Cr-O bond distance variation. Consequently, the ϵ values obtained from the present optical absorption spectra should be regarded as minimum values.

Keywords: Crystal synthesis, optical spectroscopy, structural relaxation, spinel, gahnite, Cr³⁺