

## Structure of synthetic Na-birnessite: Evidence for a triclinic one-layer unit cell

BRUNO LANSON,<sup>1,\*</sup> VICTOR A. DRITS,<sup>1,2</sup> QI FENG,<sup>3</sup> AND ALAIN MANCEAU<sup>1</sup>

<sup>1</sup>Environmental Geochemistry Group, LGIT, Maison des Géosciences, BP53, University of Grenoble - CNRS, 38041 Grenoble Cedex 9, France

<sup>2</sup>Geological Institute, Russian Academy of Sciences, 7 Pyzhevsky Street, 109017 Moscow, Russia

<sup>3</sup>Department of Advanced Materials Science, Faculty of Engineering, Kagawa University, 2217-20 Hayashi-cho, Takamatsu, Kagawa, 761-0396, Japan

### ABSTRACT

The structure of a synthetic analogue of Na-birnessite (NaBi) was studied by powder X-ray diffraction (XRD). It is shown that NaBi has a one-layer triclinic structure with sub-cell parameters:  $a_p = 2.9513(4) \text{ \AA}$ ,  $b_p = 2.9547(4) \text{ \AA}$ ,  $c_p = 7.334(1) \text{ \AA}$ ,  $\alpha_p = 78.72(2)^\circ$ ,  $\beta_p = 101.79(1)^\circ$ ,  $\gamma_p = 122.33(1)^\circ$ , and space group  $P\bar{1}$ . This sub-cell is equivalent to the base-centered sub-cell with parameters:  $a = 5.174 \text{ \AA}$ ,  $b = 2.848 \text{ \AA}$ ,  $c = 7.334 \text{ \AA}$ ,  $\alpha = 90.53^\circ$ ,  $\beta = 103.20^\circ$ , and  $\gamma = 90.07^\circ$ . A structure model has been refined using the Rietveld technique. NaBi consists of vacancy-free Mn-bearing octahedral layers whose negative charge arises mostly from the substitution of  $\text{Mn}^{3+}$  for  $\text{Mn}^{4+}$ . The departure from the hexagonal symmetry of layers results from Jahn-Teller distortion of  $\text{Mn}^{3+}$  octahedra, which are elongated along the **a** axis, segregated in  $\text{Mn}^{3+}$ -rich rows parallel to the **b** axis, and separated from each other along the **a** axis by two  $\text{Mn}^{4+}$ -rows. Structural sites of interlayer Na cations and  $\text{H}_2\text{O}$  have been determined as well as their occupancies. The sub-cells of the two NaBi modifications described by Drits et al. (1997) as types I and II likely contain four sites for interlayer species, two of which are occupied by Na and the other two by  $\text{H}_2\text{O}$  molecules. In the two NaBi varieties, these pairs of sites are split along the **c** axis and related by a center of symmetry. This splitting is consistent with the modulated structure of both NaBi types, which arises from the periodic displacement of interlayer species along the **b** axis with a periodicity  $\lambda = 6b$  (Drits et al. 1997).