

The structure of disordered mackinawite

MARIËTTE WOLTERS,^{1,*} SJIERK J. VAN DER GAAST,² AND DAVID RICKARD³

¹Department of Geochemistry, Faculty of Earth Sciences, Utrecht University, Utrecht, The Netherlands

²Royal Netherlands Institute for Sea Research (NIOZ), Texel, The Netherlands

³School of Earth, Ocean, and Planetary Sciences, Cardiff University, Cardiff, Wales, U.K.

ABSTRACT

Synthetic Fe²⁺ monosulfide, FeS_{am}, displays a disordered tetragonal mackinawite structure. It is nanocrystalline, with an average primary particle size equivalent to a crystallite size of 4 nm and a corresponding specific surface area of 350 m²/g. It can be described in terms of a mixture of two end-member phases with different long-range ordering, which we refer to as MkA and MkB. MkA has an average primary particle size of 2.2 × 1.7 nm and lattice parameters $a = b = 4.0 \text{ \AA}$, $c = 6.6 \pm 0.1 \text{ \AA}$. MkB has an average primary particle size of 7.4 × 2.9 nm and lattice parameters $a = b = 3.7 \text{ \AA}$, $c = 5.5 \pm 0.2 \text{ \AA}$. A typical disordered mackinawite precipitate consist of 30% MkA and 70% MkB and the proportion of MkA decreases with age. Lattice expansions relative to crystalline mackinawite ($a = b = 3.7 \text{ \AA}$, $c = 5.0 \text{ \AA}$) may be explained by intercalation of water molecules between the tetrahedral sheets and by lattice relaxation due to small crystallite size.

The formation of two phases of FeS_{am} is consistent with competing pathways involved in its formation from aqueous solution. MkA may be equivalent to sheet-like precipitated aqueous FeS clusters. The reactivity of FeS_{am} is dependent on the proportion of the two end-member phases. These in turn are dependent on the conditions of formation, especially pH, and the age of the precipitate. These observations partly explain the reported differences in FeS_{am} reactivity in experimentation and in the environment. The structural model has implications for the behavior of natural acid volatile sulfides in scavenging elements from solution in natural environments.