#### **Research Article**

**Open Access** 

# Kadir Mercan, Çiğdem Demir, and Ömer Civalek\* Vibration analysis of FG cylindrical shells with power-law index using discrete singular convolution technique

DOI 10.1515/cls-2016-0007 Received Jan 08, 2016; accepted Jan 14, 2016

**Abstract:** In the present manuscript, free vibration response of circular cylindrical shells with functionally graded material (FGM) is investigated. The method of discrete singular convolution (DSC) is used for numerical solution of the related governing equation of motion of FGM cylindrical shell. The constitutive relations are based on the Love's first approximation shell theory. The material properties are graded in the thickness direction according to a volume fraction power law indexes. Frequency values are calculated for different types of boundary conditions, material and geometric parameters. In general, close agreement between the obtained results and those of other researchers has been found.

**Keywords:** Discrete singular convolution; free vibration; functionally graded material; cylindrical shells

### **1** Introduction

Circular cylindrical shells are generally used in different applications compared to the conical, spherical, shells of revolution and toroidal shells because of its simple and advantages geometry. Cylindrical shells are used in many engineering applications such as mechanical, civil and aerospace engineering. Thus, frequencies and mode shapes of such structures are important in the design of systems [1–5]. Many of researchers have spent great - efforts in order to analysis of the circular shells under different effects. As a consequence, a number of analytical and numerical methods have been also studied on the vibration analysis of circular cylindrical shells during the past fifty years [6–26]. By using the functionally graded materials in the structural components, FGM shells are gaining the considerable importance and find plenty of applications in high temperature applications in petro-chemical, civil and aerospace industries [27–30]. Nowadays, FGM based structures and devices such as beams, plates and shells have been widely used in aerospace, mechanical, automobile and civil engineering applications. Understanding of free vibration behavior of these structures is an important task for the successful applications. So, many studies have been made by researchers on this field [31–45].

Recently, the method of discrete singular convolution (DSC) proposed by Wei [46, 47] has been increasingly applied to solve many engineering and sciences problems such as mathematical physics, fluid and solid mechanics [48–52]. By this time, Ritz, Galerkin, finite differences, finite elements method, boundary element methods have widely used for vibration problem of shells. Recent years, the method of differential quadrature (DQ), discrete singular convolution (DSC) and meshless methods have become increasingly popular in the numerical solution of initial and boundary value problems in engineering applications. These methods can yield accurate solutions with relatively much fewer grid points. It has been also successfully employed for different solid and fluid mechanic problems. More recently, a detailed investigated and discussion of the strong formulation and differential quadrature methods has been presented by Tornabene et al [15].

In the present study, free vibration analysis of FGM circular cylindrical shells is performed on the basis of Love's shell theory. The related governing differential equation for vibration with corresponding boundary conditions is derived. Then, the method of DSC is used for numerical solution of the related differential equations. The effects of the power of the material property variation function, boundary conditions and mode numbers on frequency response of FGM shell are investigated. Some comparative results are also presented to show the convergence and accuracy of the results obtained by present DSC method. This is the first instance in which the DSC method has been adopted for free vibration analysis of FGM cylindrical shells.

**(co) BYANCEND** © 2016 K. Mercan et al., published by De Gruyter Open. This work is licensed under the Creative Commons Attribution-NonCommercial-NoDerivs 3.0 License. The article is published with open access at www.degruyter.com.

Kadir Mercan: Akdeniz University, Faculty of Engineering, Civil Engineering Dept., Division of Mechanics Antalya-TURKIYE Çiğdem Demir: Akdeniz University, Faculty of Engineering, Civil Engineering Dept., Division of Mechanics Antalya-TURKIYE \*Corresponding Author: Ömer Civalek: Akdeniz University, Faculty of Engineering, Civil Engineering Dept., Division of Mechanics Antalya-TURKIYE, E-mail: civalek@yahoo.com



Figure 1: Functionally graded circular shells

### 2 Formulations

#### 2.1 Circular shell

Consider a cylindrical shell rotating about its symmetrical and horizontal axis at an angular velocity  $\omega$  as shown in Figure 1. The thickness of the shell and length are denoted by *h* and *L*, respectively. The cylindrical shell is referred to a coordinate system (x,  $\theta$ , z) as shown in Figure 1. The components of the deformation of the cylindrical shell with references to this coordinate system are denoted by u, v, w in the x,  $\theta$  and z directions, respectively.

Based on Love's first approximation theory, the strain components of this vector are defined as linear functions of the normal (thickness) coordinate *z*, namely

$$\varepsilon_{x} = \varepsilon_{1} + z_{\kappa_{1}}, \qquad (1a)$$

$$\varepsilon_{\theta} = \varepsilon_2 + z_{\kappa_2},$$
 (1b)

$$\varepsilon_{x\theta} = \gamma + 2z\tau,$$
 (1c)

where  $\{\varepsilon\}^T = \{\varepsilon_1, \varepsilon_2, \gamma\}$  and  $\{\kappa\}^T = \{\kappa_1, \kappa_2, 2\tau\}$  are respectively the strain and curvature vectors of the reference surface. They are defined by [1]

$$\varepsilon_1 = \frac{\partial u}{\partial x},$$
 (2a)

$$\varepsilon_2 = \frac{1}{R} \left( \frac{\partial v}{\partial \theta} + w \right),$$
 (2b)

$$\gamma = \frac{1}{R} \frac{\partial u}{\partial \theta} + \frac{\partial v}{\partial x}, \qquad (2c)$$

$$\kappa_1 = -\frac{\partial^2 w}{\partial x^2},\tag{3a}$$

$$\kappa_2 = -\frac{1}{R^2} \frac{\partial^2 w}{\partial \theta^2} + \frac{\partial v}{\partial \theta},$$
 (3b)

$$\tau = -\frac{2}{R} \frac{\partial^2 w}{\partial x \partial \theta} + \frac{\partial v}{\partial x}.$$
 (3c)

The force and moment resultants and can be obtained by

$$\left\{\begin{array}{c}N\\M\end{array}\right\} = \left[\begin{array}{c}A&B\\B&D\end{array}\right] \left\{\begin{array}{c}e\\\kappa\end{array}\right\},\tag{4}$$

where  $A_{ij}$ ,  $B_{ij}$  and  $D_{ij}$  are the extensional, coupling and bending stiffnesses and calculated from the following equations:

$$(A_{ij}, B_{ij}, D_{ij}) = \int_{-h/2}^{h/2} Q_{ij}^{*}(1, z, z^{2}) dz, \qquad (5)$$

i = 1, 2 and j = 3+i. For an arbitrarily laminated composite shell, these stiffnesses can be given as [26]

$$(A_{ij}) = \sum_{k=1}^{N_L} Q_{ij}^{(k)} (h_k - h_{k-1}), \qquad (6a)$$

$$(B_{ij}) = \frac{1}{2} \sum_{k=1}^{N_L} Q_{ij}^{(k)} \left( h_k^2 - h_{k-1}^2 \right), \qquad (6b)$$

$$(D_{ij}) = \frac{1}{3} \sum_{k=1}^{N_L} Q_{ij}^{(k)} \left( h_k^3 - h_{k-1}^3 \right).$$
 (6c)

Where  $N_L$  is the number of total layers of the laminated conical shell,  $Q_{ij}^{(k)}$ , the element of the transformed reduced stiffness matrix for the kth layer, and  $h_k$  and  $h_{k-1}$  denote distances from the shell reference surface to the outer and inner surfaces of the kth layer.

The transverse shear force resultants can be given from  $M_x$ ,  $M_\theta$  and  $M_{x\theta}$  by

$$Q_{x} = \frac{1}{R(x)} \frac{\partial}{\partial x} \left[ R(x)M_{x} \right] - \frac{M_{\theta}\sin\alpha}{R(x)} + \frac{1}{R(x)} \frac{\partial M_{x\theta}}{\partial \theta}, \quad (7)$$

$$Q_{\theta} = \frac{1}{R(x)} \frac{\partial}{\partial x} \left[ R(x) M_{x\theta} \right] + \frac{M_{x\theta} \sin \alpha}{R(x)} + \frac{1}{R(x)} \frac{\partial M_{\theta}}{\partial \theta}, \quad (8)$$

where

$$\rho_t(x,\theta) = \frac{1}{h} \int_{-h/2}^{h/2} \rho(x,\theta,z) dz, \qquad (9)$$

where  $\rho$  and  $\rho_t$  are, respectively, the density and density per unit area. Moment resultants and in-surface force can be obtained by

$$N = (N_x, N_\theta, N_{x\theta})^T = \int_{-h/2}^{h/2} (\sigma_x, \sigma_\theta, \sigma_{x\theta})^T dz, \quad (10a)$$

$$M = (M_x, M_\theta, M_{x\theta})^T = \int_{-h/2}^{h/2} (\sigma_x, \sigma_\theta, \sigma_{x\theta})^T z dz, \quad (10b)$$

where the stress vector field  $(\sigma)^T = \{\sigma_x, \sigma_\theta, \sigma_{x\theta}\}$ . The stress vector of the *kth* layer for laminated composite conical shells in which each layer is orthotropic is

$$\{\sigma_k\} = \left[\overline{Q}_{ij}\right] \{\overline{\varepsilon}_k\},\tag{11}$$

where  $\{\overline{\varepsilon}_k\}^T = \{\varepsilon_x, \varepsilon_\theta, \varepsilon_{x\theta}\}$  is the strain vector. For a thin shell, the stresses defined in Equation (11) are given by

$$\left\{ \begin{array}{c} \sigma_{x} \\ \sigma_{\theta} \\ \sigma_{x\theta} \end{array} \right\} = \left[ \begin{array}{c} Q_{11} & Q_{12} & 0 \\ Q_{12} & Q_{22} & 0 \\ 0 & 0 & Q_{66} \end{array} \right] \left\{ \begin{array}{c} \varepsilon_{x} \\ \varepsilon_{\theta} \\ \varepsilon_{\theta x} \end{array} \right\}.$$
(12)

The element of the reduced stiffness are defined as

$$Q_{11} = \frac{E(z)}{1 - v(z)^2}, \quad Q_{12} = \frac{v(z)E(z)}{1 - v^2},$$
 (13a)

$$Q_{22} = \frac{E(z)}{1 - \nu(z)^2}, \quad Q_{66} = \frac{E(z)}{2[1 + \nu(z)]}.$$
 (13b)

Following the Love's first approximation shell theory [31] governing equations for free vibration analysis of cylindrical shells can be given as [16, 17];

$$L_{11}u + L_{12}v + L_{13}w - \rho h \frac{\partial^2 u}{\partial t^2} = 0,$$
 (14a)

$$L_{21}u + L_{22}v + L_{23}w - \rho h \frac{\partial^2 v}{\partial t^2} = 0,$$
 (14b)

$$L_{31}u + L_{32}v + L_{33}w - \rho h \frac{\partial^2 w}{\partial t^2} = 0, \qquad (14c)$$

where

$$L_{11} = A_{11} \frac{\partial^2}{\partial x^2} + \left(\frac{A_{66}}{R^2}\right) \frac{\partial^2}{\partial \theta^2},$$
 (15)

$$L_{12} = \frac{(A_{12} + A_{66})}{R} \frac{\partial^2}{\partial x \partial \theta} + \frac{(B_{12} + 2B_{66})}{R^2} \frac{\partial^2}{\partial x \partial \theta}, \quad (16)$$

$$L_{13} = \frac{A_{12}}{R} \frac{\partial}{\partial x} - \frac{B_{12} + 2B_{66}}{R^2} \frac{\partial^3}{\partial x \partial \theta^2} - B_{11} \frac{\partial^3}{\partial x^3}, \qquad (1)$$

$$L_{21} = \frac{(A_{12} + A_{66})}{R} \frac{\partial^2}{\partial x \partial \theta} + \frac{(B_{12} + 2B_{66})}{R^2} \frac{\partial^2}{\partial x \partial \theta}, \quad (18)$$

$$L_{22} = \left[A_{66} + \frac{3B_{66}}{R} - \frac{2D_{66}}{R^2}\right] \frac{\partial^2}{\partial x^2} + \left[\frac{A_{22}}{R^2} + \frac{2B_{22}}{R^3} + \frac{D_{22}}{R^4}\right] \frac{\partial^2}{\partial \theta^2},$$

$$L_{23} = \left(\frac{A_{22}}{R^2} + \frac{B_{22}}{R^3}\right) \frac{\partial}{\partial \theta} - \left(\frac{B_{22}}{R^3} + \frac{D_{22}}{R^4}\right) \frac{\partial^3}{\partial \theta^3} - (20)$$
$$- \left[\frac{(B_{12} + 2B_{66})}{R} + \frac{(D_{12} + 2D_{66})}{R^2}\right] \frac{\partial^3}{\partial x^2 \partial \theta},$$

$$L_{31} = B_{11} \frac{\partial^3}{\partial x^3} - A_{12} \frac{1}{R} \frac{\partial}{\partial x} + \frac{(B_{12} + 2B_{66})}{R^2} \frac{\partial^3}{\partial x \partial \theta^2}, \quad (21)$$

$$L_{32} = \left[-A_{22}\frac{1}{R^2} + \frac{B_{22}}{R^3}\right]\frac{\partial}{\partial\theta} +$$
(22)

$$+ \left[\frac{B_{22}}{R^3} + \frac{D_{22}}{R^4}\right] \frac{\partial^3}{\partial\theta^3} + \left[\frac{(B_{12} + 2B_{66})}{R} + \frac{(D_{12} + 4D_{66})}{R^2}\right] \frac{\partial^3}{\partial x^2 \partial \theta},$$

$$L_{33} = -A_{22} \frac{1}{R^2} - D_{11} \frac{\partial^4}{\partial x^4} -$$
(23)  
$$- \frac{2D_{12} + 4D_{66}}{R^2} \frac{\partial^4}{\partial x^2 \partial \theta^2} - \frac{D_{22}}{R^4} \frac{\partial^4}{\partial \theta^4} +$$
$$+ \frac{2B_{12}}{R} \frac{\partial^2}{\partial x^2} + \left[\frac{2B_{22}}{R^3}\right] \frac{\partial^2}{\partial \theta^2},$$

where  $A_{ij}$ ,  $B_{ij}$  and  $D_{ij}$  are the tensile, coupling and bending stiffness respectively, and defined above.

#### 2.2 Functionally graded materials

Functionally graded materials are relatively new advanced composite material. After the invitation of the FGM, great deals of research have been made on fabrication and applications of this new material concept. Functionally graded materials are characterized by gradually changed physical properties.

$$p = p_0 \left[ 1 + p_{-1}/T + p_1 T + p_2 T^2 + p_3 T^3 \right], \qquad (24)$$

where  $p_i$  are the coefficients of temperature defined in Kelvin and them are unique to the constituent materials.

$$p = \sum_{j=1}^{k} p_j V_f,$$
(25)

(7) where  $p_j$  and  $V_f$  are the material property and volume fraction of the constituent material j, respectively. The sum of volume fraction is defined as

$$\sum_{k=1}^{l} V_{fl} = 1.$$
 (26)

(19) For an uniform thickness shell, the volume fraction is defined by

$$V_f = \left(\frac{z}{h} + \frac{1}{2}\right)^N.$$
 (27)

The power-law exponent is defined by N. The material properties for two-constituent FGM can be defined as [31]

$$E(z) = (E_1 - E_2) \left(\frac{z}{h} + \frac{1}{2}\right)^N + E_2$$
(28)

$$v(z) = (v_1 - v_2) \left(\frac{z}{h} + \frac{1}{2}\right)^N + v_2$$
(29)

$$\rho(z) = (\rho_1 - \rho_2) \left(\frac{z}{h} + \frac{1}{2}\right)^N + \rho_2$$
(30)

# 3 Discrete Singular Convolution (DSC)

The method of discrete singular convolution (DSC) is based on the principles of the theory of wavelets and the theory of distributions [46]. Discrete singular convolutions algorithm was originally introduced by Wei [47] as a potential numerical method via some regularized kernels. Hilbert and delta transforms are generally used in this approach. Since then, applications of the DSC method to various science and engineering problems have been investigated and their successes have demonstrated the potential of the method as an attractive numerical analysis technique. In this paper, details of the DSC method are not given; interested readers may refer to the works of [46–59]. Consider a distribution, *T* and  $\eta(t)$  as an element of the space of the test function. A singular convolution can be defined by [46]

$$F(t) = (T \star \eta)(t) = \int_{-\infty}^{\infty} T(t-x)\eta(x)dx, \qquad (31)$$

where T(t - x) is a singular kernel. The DSC algorithm can be realized by using many approximation kernels. However, it was shown [53–70] that for many problems, the use of the regularized Shannon kernel (RSK) is very efficient. The RSK is given by [47]

$$\delta_{\Delta,\sigma} \left( x - x_k \right) = \frac{\sin \left[ (\pi/\Delta) \left( x - x_k \right) \right]}{(\pi/\Delta) \left( x - x_k \right)} \exp \left[ -\frac{\left( x - x_k \right)^2}{2\sigma^2} \right]; \quad (32)$$
  
$$\sigma > 0,$$

where  $\Delta = \pi/(N-1)$  is the grid spacing and *N* is the number of grid points. The parameter  $\sigma$  determines the width of the Gaussian envelope and often varies in association with the grid spacing, i.e.,  $\sigma = rh$ . In the DSC method, the function f(x) and its derivatives with respect to the *x* coordinate at a grid point  $x_i$  are approximated by a linear sum of discrete values  $f(x_k)$  in a narrow bandwidth  $[x - x_M, x + x_M]$ . This can be expressed as [48]

$$\frac{d^{n}f(x)}{dx^{n}}\Big|_{x=x_{i}} = f^{(n)}(x) \approx \sum_{k=-M}^{M} \delta^{(n)}_{\Delta,\sigma}(x_{i}-x_{k})f(x_{k}); \quad (33)$$

$$(n=0,1,2,\ldots,),$$

where superscript *n* denotes the *n*th-order derivative with respect to *x*. The displacement terms are taken as

$$u = U(x) \cdot \cos(n\theta) \cdot \cos(\varpi t), \qquad (34a)$$

$$v = V(x) \cdot \sin(n\theta) \cdot \cos(\varpi t),$$
 (34b)

$$w = W(x) \cdot \cos(n\theta) \cdot \cos(\varpi t), \qquad (34c)$$

where  $\varpi$  is referred to as the circular frequency parameter. Substituting Equations (34) into Equations (14), the governing equations can be written as

$$\left[S_{ij}\right]\left\{D\right\} = 0. \tag{35}$$

In this study, the following two boundary conditions are considered. The letters S and C denote simply supported and clamped boundary conditions, respectively. *Simply supported edge (S)* 

$$W = 0, W = 0, N_{\chi} = 0, M_{\chi} = 0.$$
 (36)

Clamped edge (C)

$$U = 0, V = 0, W = 0 \text{ and } \partial W / \partial x = 0.$$
 (37)

DSC form of the boundary conditions can be easily written. For clamped edge, for example, given as

$$U_{i,j} = 0, \ V_{i,j} = 0, \ W_{i,j} = 0 \text{ and }$$
(38)  
$$\sum_{k=-M}^{M} \delta_{\Delta,\sigma}^{(1)}(k\Delta x) W_{i+k,j} = 0.$$

By the DSC rule, the governing equations and the corresponding boundary conditions can be replaced by a system of simultaneously linear algebraic equations in terms of the displacements at all the sampling points. It is noted that for a well-posed problem the number of equations should be identical to the number of unknowns. A treatment commonly used in the open literature [46–70] is applied in this study. By rearranging the DSC form of the governing equations, one has the assembled form of the resulting equations as

$$[[S_{dd}][S_{db}]] \left\{ \begin{array}{c} \{U_d\} \\ \{U_b\} \end{array} \right\} -$$
(39)  
$$-\Omega [[B_{dd}][B_{db}]] \left\{ \begin{array}{c} \{U_d\} \\ \{U_b\} \end{array} \right\} = \{0\},$$

where  $\{U_b\}$  represents the unknown boundary grid points values, whereas,  $\{U_d\}$  represent the domain grid point unknowns. The subscript *b* represents the degree of freedom on the boundary and subscript *d* represents the degree of freedom on the domain. Substituting the DSC rule into the

boundary conditions at the sampling points at two boundary points leads to

$$\left[\left[S_{bd}\right]\left[S_{bb}\right]\right]\left\{\begin{array}{c}\left\{U_{d}\right\}\\\left\{U_{b}\right\}\end{array}\right\} = \{0\}.$$
(40)

After rewriting Equation (40) as  $U_b = -S_{bb}^{-1}S_{bd}U_d$  and then substituting the resulting equation into Equation (39), we obtain

$$SU = \Omega BU,$$
 (41)

in which  $S = S_{dd} - S_{db}S_{bb}^{-1}S_{bd}$ ,  $B = B_{dd} - B_{db}S_{bb}^{-1}S_{bd}$  and U is the displacement vector on the domain. In this study, the numerical results are given by the dimensionless frequency parameter  $\Omega$ , defined as [31]

$$\Omega = R \sqrt{\frac{\rho \left[1 - \upsilon(z)^2\right]}{E(z)}} \varpi.$$
(42)

### **4 Numerical results**

Table 1 lists the material properties for related three materials as T=300 K (room temperature). Three materials are denoted as Material I, Material II, and Material III for Stainless Steel, Zirconia and Nickel, respectively. By using these three materials, six different configurations (Type A, Type B, Type C, Type D, Type E, Type F) of FGM cylindrical shells are possible for inner and outer surfaces as listed in Table 2.

Firstly, a comparative study for vibration analysis of isotropic cylindrical shell and FG shell has been presented. In order to obtain a reasonable convergence for the frequency values, the number of required grid points in related directions of shells in the DSC solution should be determined.

To validate the analysis, obtained frequency values for FGM cylindrical shells are compared with the results given by Loy *et al.* [31] in the literature, as shown in Table 3 for different grid numbers. The comparison shows that the present DSC results agreed well with those in literatures. It is found from the results that, only 13 grid points can yield accurate results for frequency.

Table 4 shows the frequency values of FGM shell for six different cases and different index values. It is shown that the value of volume fraction exponent has less effect on frequency. For some types of materials (Type B, Type C, Type E) frequency values increased with the increasing value of volume fraction exponent. However, the frequencies decrease with p for the other type of material combinations (Type A, Type D, Type F). This situation is de-



**Figure 2:** Variation of natural frequency with length-to-radius ratio of FGM cylindrical shell with SS edges (m=1; R/h=500; Type A)



**Figure 3:** Variation of natural frequency with mode numbers of FGM cylindrical shell with different boundary conditions (m=1; R/h=500; Type A)



Figure 4: Frequency values for different FGM configurations of C-S shell

Matorial Types	Material Constants	Coefficients				
material types		p <sub>0</sub>	р	<b>p</b> <sub>1</sub>	<b>p</b> <sub>2</sub>	<b>p</b> <sub>3</sub>
Material I	υ	0.3262	0	$-2.002 \times 10^{-4}$	$-3.797 \times 10^{-7}$	0
(Stainless Steel)	ho(kg/m <sup>3</sup> )	8166	0	0	0	0
	<b>E(N/m<sup>2</sup>)</b>	$201.04 \times 10^{9}$	0	$3.079 \times 10^{-4}$	$-6.534 \times 10^{-7}$	0
Material II	υ	0.2882	0	$1.133 \times 10^{-4}$	0	0
(Zirconia)	ho (kg/m <sup>3</sup> )	5700	0	0	0	0
	<b>E(N/m<sup>2</sup>)</b>	$244.27 \times 10^{9}$	0	$-0.1371 \times 10^{-4}$	$1.133 \times 10^{-4}$	$-3.681 \times 10^{-10}$
Material III	υ	0.310	0	0	0	0
(Nickel)	ho(kg/m <sup>3</sup> )	8900	0	0	0	0
	$E(N/m^2)$	223.95 × 10 <sup>9</sup>	0	$2.794 \times 10^{-4}$	$-3.998 \times 10^{-9}$	0

Table 1: Material properties of FG materials for circular cylindrical shell

Table 2: Types of FGM circular shell for each layer (surface)

Types of FGM shells	Inner Surface	Outer Surface
Туре А	Nickel	Stainless Steel
Туре В	Stainless Steel	Nickel
Туре С	Stainless Steel	Zirconia
Type D	Zirconia	Stainless Steel
Туре Е	Nickel	Zirconia
Type F	Zirconia	Nickel

pendent on the values of material parameter for two constituent materials configuration for FGM shell. Namely, the ratio of modulus of elasticity and ratio of Poisson's are significant effect on this change (decrease or increases). This phenomenon detailed investigated by Iqbal *et al.* [33]. Natural frequency of FG circular cylindrical shell with different boundary conditions is listed for material D in Table 5. It is shown that the natural frequencies initially decrease gradually and then increase with n. The frequency versus mode numbers trend is very similar to homogenous shell. Also, the frequencies values in C-C boundary conditions are greater than that for C-S and S-S boundary conditions.

Variation of natural frequencies with length-to-radius ratio (L/R) of FGM cylindrical shell with SS (both ends simply supported) edges are depicted in Figure 2 for the value of m=1; R/h=500. The material configuration is the Nickel at the inner surface and stainless steel at the outer surface. It is seen that the frequency values of FGM shells are decreased rapidly with the inceaseing value of the lengthto-radius ratio. Becasue, the stiffness of the shell decrase with the increasing of L/R ratio. Also, the effect of volume fraction index on frequency is very small. The effect of boundary conditions on frequency with mode numbers is **Table 3:** Comparative study of natural frequency of FG circular cylindrical shell with simply supported edges (m=1;h/R=0.002;L/R=20;Type A; p=2)

_							
-	Dof 21	Present DSC results					
	Kel. 51	N=9	N=13	N=15	N=17		
1	13.103	12.9982	13.1088	13.1088	13.1088		
2	4.4435	4.44967	4.45013	4.45013	4.45013		
3	4.1235	4.11034	4.12365	4.12365	4.12365		
4	6.9820	6.98285	6.98271	6.98271	6.98271		
5	11.151	11.1498	11.1516	11.1516	11.1516		
6	16.323	16.3301	16.3241	16.3241	16.3241		
7	22.454	22.4638	22.4550	22.4550	22.4550		
8	29.533	29.6013	29.5346	29.5346	29.5346		
9	37.559	37.5749	37.5602	37.5602	37.5602		

shown in Figure 3. According to the figure, frequency values in C-C boundary condition is greater than that for C-S and S-S type of boundary conditions. With the increase of the mode number, teh frequency value decreases when n< 3. Then the frequency valus increase slowly to a stable value. Frequency values for different FGM configurations of C-S shell is drawn in Figure 4 for p=15; h/R=0.002 and L/R=20 values. For some types of materials (Type B, Type C, Type E) frequency values increased with the increasing value of volume fraction exponent. However, the frequencies decrease with p for the other type of material combinations (Type A, Type D, Type F). This situation is dependent on the values of material parameter for two constituent materials configuration for FGM shell. Namely, the ratio of modulus of elasticity and ratio of Poisson's are significant effect on this change (decrease or increases). This phenomenon detailed investigated by Iqbal et al. [33]. Vari-

	5	FGM types for inner and outer material						
р	П	Туре А	Туре В	Type C	Type D	Type E	Type F	
	1	13.3895	13.0387	14.2828	13.7341	14.0703	13.1821	
0.3	2	4.5301	4.4160	4.8351	4.6601	4.7640	4.4671	
	3	4.2120	6.9392	4.4830	4.3073	4.4150	4.1261	
	1	12.9504	13.4834	13.6185	14.4623	13.003	14.3708	
10	2	4.3896	4.5681	4.6082	4.9076	4.4001	4.8742	
	3	4.0715	4.2369	4.2411	4.5783	4.0458	4.5425	
15	1	12.9334	13.5051	13.5960	14.5004	12.9682	14.4361	
	2	4.3831	4.5755	4.6020	4.9185	4.3904	4.8951	
	3	4.0654	4.2451	4.2431	4.5813	4.0431	4.5562	

Table 4: Frequency values of simply supported (S-S) FGM circular cylindrical shell with different types and modes

**Table 5:** Natural frequencies of FG circular cylindrical shell with different boundary conditions (m=1;h/R=0.002;L/R=20; Type D; p=15)

n	SS	CC	CS
1	14.5012	31.4103	22.2627
2	4.9185	10.6005	7.4646
3	4.5813	6.41363	5.3103
4	7.6503	8.2011	7.9245
5	12.4026	12.5338	5.3087



ation of frequency values with mode number of SS shell for different constituent of material is given in Figure 5 for S-S shell. Frequencies values are firstly decrased (for n=1,2,3) and increasing rapidly with the mode numbers, as similar to the isotropic one.

# **5** Conclusions

By using the efficient numerical method, free vibration analysis of functionally graded cylindrical shells has been investigated. It is possible to say that the method of DSC provides a controllable numerical accuracy by using the suitable bandwidth. This is more important for large scale computations. The implementation of boundary conditions, programming and formulation procedures are found to be straightforward and simple. Being a noniterative method, the method DSC is relatively less computationally intensive. Also the method of DSC gives reasonably accurate values for frequencies. The required computing time is very small. Although not provided here, the **Figure 5:** Variation of frequency values with mode number of SS shell for different types of FGM

method is also produces more accurate results for classical single material shell.

## 6 Acknowledgements

The financial support of the Scientific Research Projects Unit of Akdeniz University is gratefully acknowledged.

## References

 J.N. Reddy, Mechanics of laminated composite plates and shells: theory and analysis. (2<sup>nd</sup> ed.) New York: CRC Press, 2003.

- [2] A.W. Leissa, Vibration of shells, Acoustical Society of America, 1993.
- [3] W. Soedel, Vibrations of shells and plates, Third Edition, CRC Press, 2004.
- [4] F. Tornabene, N. Fantuzzi, Mechanics of laminated composite doubly-curved shell structures, the generalized differential quadrature method and the strong formulation finite element method, Società Editrice Esculapio, 2014.
- [5] Ö. Civalek, Finite element analyses of plates and shells, Elazığ: Fırat University, (in Turkish) 1998.
- [6] A.J.M. Ferreira, R.M.N. Roque, Jorge, E.J. Kansa, Static deformations and vibration analysis of composite and sandwich plates using a layerwise theory and multiquadrics discretizations, Eng. Anal. Bound Elem., 29 (2005), 1104-1114.
- [7] A.J.M. Ferreira, G.E. Fasshauer, Analysis of natural frequencies of composite plates by an RBF-pseudospectral method, Comp.Struct., 79(2) (2007), 202-210.
- [8] A.J.M. Ferreira, Polyharmonic (thin-plate) splines in the analysis of composite plates, Int. J. Mech. Sci., 46 (2004), 1549-1569.
- [9] F. Tornabene, N. Fantuzzi, E. Viola, A.J.M. Ferreira, Radial basis function method applied to doubly-curved laminated composite shells and panels with a General Higher-order Equivalent Single Layer formulation, Compos. Part B: Eng., 55 (2013), 642-659.
- [10] F. Tornabene, N. Fantuzzi, E. Viola, R. C. Batra, Stress and strain recovery for functionally graded free-form and doubly-curved sandwich shells using higher-order equivalent single layer theory, Comp. Struct., 119 (2015), 67-89.
- [11] F. Tornabene, E. Viola, D.J. Inman, 2-D differential quadrature solution for vibration analysis of functionally graded conical, cylindrical shells and annular plate structures, J. Sound Vib., 328 (2009), 259-290.
- [12] S.R. Li, R.C. Batra, Buckling of axially compressed thin cylindrical shells with functionally graded middle layer. Thin-Walled Struct., 44 (2006), 1039-1047.
- [13] E. Viola, F. Tornabene, E. Ferretti, N. Fantuzzi, On static analysis of composite plane state structures via GDQFEM and Cell Method, CMES, 94(2013), 421-458.
- [14] F. Tornabene, N. Fantuzzi, M Bacciocchi, The local GDQ method applied to general higher-order theories of doubly-curved laminated composite shells and panels: the free vibration analysis, Comp. Struct., 116 (2014), 637-660.
- [15] F. Tornabene, N. Fantuzzi, F. Ubertini, E. Viola, Strong formulation finite element method based on differential quadrature: a survey, Appl. Mech. Rev., 67 (2015), 1 – 55.
- [16] Ö. Civalek, A parametric study of the free vibration analysis of rotating laminated cylindrical shells using the method of discrete singular convolution, Thin. Wall. Struct., 45 (2007), 692-698.
- [17] Ö. Civalek, M. Gürses, Free vibration analysis of rotating cylindrical shells using discrete singular convolution technique, Int. J. Press. Vessel. Pip., 86(10) (2009), 677-683.
- [18] Ö. Civalek, Vibration analysis of laminated composite conical shells by the method of discrete singular convolution based on the shear deformation theory, Compos. Part B: Eng., 45(1) (2013), 1001-1009.
- [19] Ö. Civalek, Free vibration analysis of composite conical shells using the discrete singular convolution algorithm, Steel Compos. Struct., 6(4) (2006), 353-366.
- [20] Ö. Civalek, The determination of frequencies of laminated conical shells via the discrete singular convolution method, J. Mech.

Mater. Struct., 1(1) (2006), 163-182.

- [21] Ö. Civalek, Vibration analysis of conical panels using the method of discrete singular convolution, Commun. Numer. Meth. Eng., 24 (2008), 169-181.
- [22] J.C. Zhang, T.Y. Ng, K.M. Liew, Three-dimensional theory of elasticity for free vibration analysis of composite laminates via layerwise differential quadrature modeling, Int. J. Numer. Meth. Eng., 57 (2003), 1819–1844.
- [23] Ö. Civalek, M. Ülker, Harmonic differential quadrature (HDQ) for axisymmetric bending analysis of thin isotropic circular plates, Struc. Eng. Mech., 17(1) (2004), 1-14.
- [24] Ö. Civalek, Geometrically non-linear static and dynamic analysis of plates and shells resting on elastic foundation by the method of polynomial differential quadrature (PDQ), Ph. D. Thesis, Firat University, Elazig, 2004 (in Turkish).
- [25] Ö. Civalek, Nonlinear dynamic response of laminated plates resting on nonlinear elastic foundations by the discrete singular convolution-differential quadrature coupled approaches, Compos. Part B: Eng., 50 (2013), 171-179.
- [26] K.M. Liew, X. Zhao, T.Y. Ng, The element-free kp-Ritz method for vibration of laminated rotating cylindrical panels, Int. J. Struct. Stab. Dyn., 2 (2002), 523–58.
- [27] M. Kouzumi, The concept of FGM. Ceramic Transactions, Functionally Gradient Materials, 34 (1993), 3-10.
- [28] A. Ghosh, Y. Miyamoto, I. Reimanis, J.J. Lannutti, Functionally graded materials: Manufacture, properties and applications, Am. Cer. So., Ceramic Place, Westerville, Ohio (1997).
- [29] V. Birman,L.W. Byrd, Modeling and analysis of functionally graded materials and structures, Appl. Mech. Rev., 160 (2007), 195.216.
- [30] X.D. Zhang, D.Q. Liu, C.C. Ge, Thermal stress analysis of axial symmetry functionally gradient materials under steady temperature field, Journal of Functional Material, 25(1994), 452-455.
- [31] C.T. Loy, K.Y. Lam, J.N. Reddy, Vibration of functionally graded cylindrical shells, Int. J. Mech. Sci., 41 (1999), 309-324.
- [32] P. Malekzadeh, Y. Heydarpour, Free vibration of rotating functionally gradient cylindrical shells in thermal environment, Compos. Struct., 94 (2012), 2971-2981.
- [33] Z. Iqbal, M.N. Naeem, N. Sultana, Vibration characteristics of FGM circular cylindrical shells using wave propagation approach, Acta Mech., 208 (2009),237-248.
- [34] S.C. Pradhan, C.T. Loy, K.Y. Lam, J.N. Reddy, Vibration characteristics of functionally graded cylindrical shells under various boundary conditions, Appl. Acoustics, 61 (2000), 111–124.
- [35] M.M. Najafizadeh, M.R. Isvandzibaei, Vibration of functionally graded cylindrical shells based on higher order shear deformation plate theory with ring support, Acta Mech., 191 (2007), 75-91.
- [36] H. Haddadpour, S. Mahmoudkhani, H.M. Navazi, Free vibration analysis of functionally graded cylindrical shells including thermal effects, Thin-Walled Struct., 45 (2007), 591-599.
- [37] M. N. Naeem, S. H. Arshad, and C. B. Sharma, The Ritz formulation applied to the study of the vibration frequency characteristics of functionally graded circular cylindrical shells, Proc. Inst. Mech. Eng. Part C: J. Mech. Sci., 224 (2010), 43–54.
- [38] S.H. Arshad, M.N. Naeem, N. Sultana, A.G. Shah, Z. Iqbal, Vibration analysis of bi-layered FGM cylindrical shells, Arch. Appl. Mech., 81(3) (2011), 319-343.
- [39] X. Han, G.R. Liu, Z.C. Xi, K.Y. Lam, Characteristics of waves in a functionally graded cylinder, Int. J. Mech. Eng., 53 (2002), 653-

676.

- [40] H. Thai, S. Kim, A review of theories for the modeling and analysis of functionally graded plates and shells, Comp. Struct., 128 (2015), 70-86.
- [41] M. Merazi, L. Hadji, T. Daouadji, A. Tounsi, E. Adda Bedia, A new hyperbolic shear deformation plate theory for static analysis of FGM plate based on neutral surface position, Geomechanics and Engineering, 8(3) (2015), 305-321.
- [42] A. Hamidi, M. Houari, S. Mahmoud, A. Tounsi, A sinusoidal plate theory with 5-unknowns and stretching effect for thermomechanical bending of functionally graded sandwich plates, Steel Comp. Struct., 18(1) (2015), 235-253.
- [43] A.G. Shah, T. Mahmood, M.N. Naeem, Z. Iqbal, S.H. Arshad, Vibrations of functionally graded cylindrical shells based on elastic foundations. Acta Mech., 211 (2010), 293–307.
- [44] Z. Iqbal, M.N. Naeem, N. Sultana, Vibration characteristics of FGM circular cylindrical shells using wave propagation approach, Acta Mech., 208 (3-4) (2009) 237-248.
- [45] A.G. Shah, T. Mahmmod, M.N. Naeem, Vibration of FGM thin cylindrical shells with exponential volume fraction law, Appl. Math. Mech. (English Edition), 30 (5) (2009), 607-615.
- [46] G.W. Wei, A new algorithm for solving some mechanical problems, Comput. Methods Appl. Mech. Eng., 190 (2001), 2017-2030.
- [47] G.W. Wei, Vibration analysis by discrete singular convolution, J. Sound Vib., 244 (2001), 535-553.
- [48] G.W. Wei, Y.C. Zhou, Y. Xiang, A novel approach for the analysis of high-frequency vibrations, J. Sound Vib., 257(2) (2002), 207-246.
- [49] G.W. Wei, Y.C. Zhou, Y. Xiang, Discrete singular convolution and its application to the analysis of plates with internal supports. Part 1: Theory and algorithm, Int. J. Numer. Methods Eng., 55 (2002), 913-946.
- [50] G.W. Wei, Y.C. Zhou, Y. Xiang, The determination of natural frequencies of rectangular plates with mixed boundary conditions by discrete singular convolution, Int. J. Mech. Sci. 43 (2001), 1731-1746.
- [51] Y.C. Zhou, G.W. Wei, DSC analysis of rectangular plates with non-uniform boundary conditions, J. Sound Vib., 255(2) (2002), 203-228.
- [52] Y. Hou, G.W. Wei, Y. Xiang, DSC-Ritz method for the free vibration analysis of Mindlin plates, Int. J. Numer. Meth. Eng., 62 (2005), 262–288.
- [53] C.W. Lim, Z.R. Li, G.W. Wei, DSC-Ritz method for high-mode frequency analysis of thick shallow shells, Int. J. Numer. Methods Eng., 62 (2005), 205-232.
- [54] Ö. Civalek, A four-node discrete singular convolution for geometric transformation and its application to numerical solution of vibration problem of arbitrary straight-sided quadrilateral plates, Appl. Math. Model., 33(1) (2009), 300-314.
- [55] Ö. Civalek, Three-dimensional vibration, buckling and bending analyses of thick rectangular plates based on discrete singular convolution method, Int. J. Mech. Sci., 49 (2007), 752-765.
- [56] Ö. Civalek, M.H. Acar, Discrete singular convolution method for the analysis of Mindlin plates on elastic foundations, Int. J. Press. Vessel. Pip., 84 (2007), 527-535.
- [57] Ö. Civalek, Fundamental frequency of isotropic and orthotropic rectangular plates with linearly varying thickness by discrete singular convolution method, Appl. Math. Model., 33(10) (2009), 3825-3835.

- [58] Ö. Civalek, Free vibration analysis of symmetrically laminated composite plates with first-order shear deformation theory (FSDT) by discrete singular convolution method, Finite Elem. Anal. Des., 44(12-13) (2008), 725-731.
- [59] Ö. Civalek, A.K. Korkmaz, Ç. Demir, Discrete singular convolution approach for buckling analysis of rectangular Kirchhoff plates subjected to compressive loads on two opposite edges, Adv. Eng. Softw., 41 (2010), 557-560.
- [60] Ö. Civalek, Analysis of thick rectangular plates with symmetric cross-ply laminates based on first-order shear deformation theory, J. Compos. Mater. 42 (2008), 2853-2867.
- [61] A. Seçkin, A.S. Sarıgül, Free vibration analysis of symmetrically laminated thin composite plates by using discrete singular convolution (DSC) approach: Algorithm and verification, J. Sound Vib., 315 (2008), 197-211.
- [62] A. Seçkin, Modal and response bound predictions of uncertain rectangular composite plates based on an extreme value model, J. Sound Vib., 332 (2013), 1306–1323.
- [63] L. Xin, Z. Hu, Free vibration of layered magneto-electro-elastic beams by SS-DSC approach, Compos. Struct., 125 (2015), 96–103.
- [64] L. Xin, Z. Hu, Free vibration of simply supported and multilayered magneto-electro-elastic plates, Compos. Struct., 121 (2015), 344-350.
- [65] X. Wang, S. Xu, Free vibration analysis of beams and rectangular plates with free edges by the discrete singular convolution, J. Sound Vib., 329(10) (2010), 1780–1792.
- [66] X. Wang, Y. Wang, S. Xu, DSC analysis of a simply supported anisotropic rectangular plate, Compos. Struct. 94(8) (2012), 2576–2684.
- [67] G. Duan, X. Wang, C. Jin. Free vibration analysis of circular thin plates with stepped thickness by the DSC element method, Thin. Wall. Struct., 85 (2014), 25-33.
- [68] A.K. Baltacioglu, Ö. Civalek, B. Akgöz, F. Demir, Large deflection analysis of laminated composite plates resting on nonlinear elastic foundations by the method of discrete singular convolution, Int. J. Pres. Ves. Pip., 88 (2011), 290-300.
- [69] Ö. Civalek, B. Akgöz, Vibration analysis of micro-scaled sector shaped graphene surrounded by an elastic matrix, Comp. Mater. Sci.,77 (2013), 295-303.
- [70] M. Gürses, Ö. Civalek, A. Korkmaz, H. Ersoy, Free vibration analysis of symmetric laminated skew plates by discrete singular convolution technique based on first-order shear deformation theory, Int. J. Numer. Meth. Eng., 79 (2009), 290-313.